2002

Automation of the Superpave mix design process for the West Virginia Division of Highways

Martin Felix Padula
West Virginia University

Follow this and additional works at: <https://researchrepository.wvu.edu/etd>

Recommended Citation

Padula, Martin Felix, "Automation of the Superpave mix design process for the West Virginia Division of Highways" (2002). *Graduate Theses, Dissertations, and Problem Reports*. 1288.
<https://researchrepository.wvu.edu/etd/1288>

This Thesis is protected by copyright and/or related rights. It has been brought to you by the The Research Repository @ WVU with permission from the rights-holder(s). You are free to use this Thesis in any way that is permitted by the copyright and related rights legislation that applies to your use. For other uses you must obtain permission from the rights-holder(s) directly, unless additional rights are indicated by a Creative Commons license in the record and/ or on the work itself. This Thesis has been accepted for inclusion in WVU Graduate Theses, Dissertations, and Problem Reports collection by an authorized administrator of The Research Repository @ WVU. For more information, please contact researchrepository@mail.wvu.edu.

**AUTOMATION OF THE SUPERPAVE MIX DESIGN PROCESS
FOR THE WEST VIRGINIA DIVISION OF HIGHWAYS**

MARTIN PADULA

*Thesis submitted to the College of Engineering and Mineral Resources at West
Virginia University in partial fulfillment of the requirements for
the degree of*

**Master of Science
In
Civil and Environmental Engineering**

**Dr. John P. Zaniwski, Chair
Dr. Ronald W. Eck,
Mr. Michael Blankenship**

Department of Civil and Environmental Engineering

**Morgantown, West Virginia
2002**

Keywords: Superpave, Asphalt, Steel Slag, Computer Programming

During the fifty years between 1940 and 1990, the nation's bituminous roadways were predominantly designed using either the Marshall or Hveem method. The Superior Performing Asphalt Pavements (Superpave)TM method was later developed to address the issues of increased traffic volumes and heavier loads on the nation's roadways. This new mix design process relies on volumetric calculations and graphs, which are cumbersome to perform by hand. There is no current public domain Superpave software package available which is independent of any commercial laboratory product and available to an asphalt mix designer. A component of this research project consisted of creating a generic Superpave mix design program that can be utilized by anyone, regardless of the laboratory equipment used for testing.

The goal of this research is to create a fully functional software package to automate the entire Superpave mix design process. The program was then used to design asphalt mixes made of steel slag obtained from International Mill Service, Inc. (IMS) as the only aggregate type. Steel slag aggregate offers a cost effective alternative to conventional aggregates used in asphalt mixes. Various mix designs were created, using only steel slag, in an attempt to meet all volumetric requirements. The steel slag mix performance was then evaluated with respect to rutting. These results were compared to mixes created with limestone and other natural aggregates to determine performance of the software and feasibility of slag utilization. After numerous aggregates structures and binder trials, no acceptable mix design could be created comprised of IMS steel slag.

ACKNOWLEDGEMENTS

I would like to thank Dr. John Zaniwski for his unceasing support and assistance throughout the research and thesis writing process. I am grateful that he made me work harder than I ever thought was possible, in the process making me a stronger person and better engineer. Without his guidance and encouragement, I never would have been able to accomplish so much.

I would also like to thank Dr. Ronald Eck and Mr. Michael Blankenship for being on my thesis committee. The time and effort they put into revising and correcting my thesis, while adding helpful comments about improving the text, made the document a much more complete and polished work.

Also deserving of much thanks are my parents, Donald and Ann Padula. Without their constant love and support, my success would never have been possible.

A special thanks goes to Jennifer Morris, fellow graduate student, friend, and constant source of encouragement and strength. She helped me deal with the challenges that each day presented and encouraged me not to give up on my goals.

Keith Lesch, Christian Duvall, Karl Leslie and Vincent Medved also provided expert advice in the computer programming, for their time and energy, I am extremely grateful.

Thanks also goes to Andy Kincell, Carlos Reyes, David Diaz, Sean Rafferty, and Sri Harsha Nallamothe, their help in the West Virginia University Asphalt Laboratory is appreciated.

TABLE OF CONTENTS

ABSTRACT	ii
ACKNOWLEDGEMENTS	iii
TABLE OF CONTENTS	iv
CHAPTER 1 INTRODUCTION	1
1.1 PROBLEM STATEMENT	1
1.2 OBJECTIVES	2
1.3 SCOPE OF WORK AND LIMITATIONS	2
1.4 THESIS OVERVIEW	3
CHAPTER 2 LITERATURE REVIEW	4
2.1 INTRODUCTION	4
2.2 SUPERPAVE MIX DESIGN	5
2.2.1 SUMMARY OF PROCESS	5
2.2.2 MIX COMPOSITION INFORMATION	7
2.2.3 AGGREGATE CONSENSUS PROPERTIES	7
2.2.4 DAS ASPHALT CONTENT ESTIMATING	11
2.2.5 MAXIMUM THEORETICAL SPECIFIC GRAVITY TESTING.....	14
2.2.6 GYRATORY COMPACTOR SAMPLES	16
2.2.7 VOLUMETRIC ANALYSIS.....	20
2.2.8 VOLUMETRIC ANALYSIS ADJUSTMENTS	24
2.2.9 DETERMINING OPTIMUM ASPHALT CONTENT	26
2.2.10 FINAL TESTS TO EVALUATE ACCEPTABILITY	29
2.2.11 ASPHALT PAVEMENT ANALYZER	31
2.2.12 AVAILABLE SUPERPAVE SOFTWARE	32
2.3 STEEL SLAG AS AN HMA AGGREGATE ALTERNATIVE.....	33
2.4 MICROSOFT EXCEL AS A SOFTWARE DEVELOPMENT TOOL.....	35
2.5 SUMMARY	36
CHAPTER 3 RESEARCH METHODOLOGY.....	37
3.1 INTRODUCTION	37
3.2 SPREADSHEET DEVELOPMENT	37
3.3 SPREADSHEET VERIFICATION.....	39
3.4 INTERFACE DEVELOPMENT	39

3.5 PROGRAM VALIDATION	40
3.6 STEEL SLAG RESEARCH	40
CHAPTER 4 PROGRAM STRUCTURE AND VALIDATION.....	41
4.1 SUPERPAVE CALCULATOR STRUCTURE	41
4.1.1 INTRODUCTION	41
4.1.2 MIX DESIGN INFORMATION	42
4.1.3 DESIGN AGGREGATE STRUCTURE DETERMINATION	42
4.1.4 DESIGN AGGREGATE STRUCTURE VOLUMETRICS.....	44
4.1.5 VOLUMETRICS USING FOUR DIFFERENT ASPHALT CONTENTS..	44
4.1.6 FINAL ACCEPTABILITY TESTING.....	45
4.1.7 SAVING AND EXITING.....	45
4.2 SOFTWARE VERIFICATION PROCESSES	45
4.3 PROGRAM FUNCTIONALITY VALIDATION.....	46
4.4 ACCEPTABILITY OF SUPERPAVE CALCULATOR RESULTS	46
4.5 LABORATORY VALIDATION OF SOFTWARE.....	47
CHAPTER 5 MIX DESIGN OF STEEL SLAG ASPHALT	53
5.1 MATERIALS AND PREPARATION	53
5.2 AGGREGATE PROPERTIES.....	53
5.3 INITIAL MIX DESIGN TRIALS USING STEEL SLAG.....	54
5.4 DAS #1.....	55
5.5 DAS #2.....	57
5.6 DAS FROM LITERATURE TO DETERMINE OPTIMUM BINDER PERCENTAGE.....	58
5.7 EVALUATION OF RUT SUSCEPTIBILITY AND CONCLUSIONS	60
CHAPTER 6 CONCLUSIONS/RECOMMENDATIONS.....	61
6.1 CONCLUSIONS.....	61
6.2 RECOMMENDATIONS.....	61
REFERENCES	63
APPENDIX A SCREEN SHOTS FROM SUPERPAVE CALCULATOR.....	66
APPENDIX B SUPERPPAVE CALCULATOR USER'S MANUAL.....	108
APPENDIX C SLAG AGGREGATE EVALUATION LABORATORY RESULTS...	120
VITA	146

LIST OF FIGURES

Figure 2.1 Superpave Mix Design Summary Sheet.....	6
Figure 2.2 Flat/Elongated Test Dimensional Labels.....	10
Figure 2.3 Superpave Gyratory Compactor	17
Figure 2.4 VTM v/s Asphalt Content (Interpolation Graph)	27
Figure 2.5 VMA v/s Asphalt Content (Interpolation Graph).....	27
Figure 2.6 VFA v/s Asphalt Content (Interpolation Graph).....	28
Figure 2.7 %G _{mm,Nini} v/s Asphalt Content (Interpolation Graph).....	28
Figure 2.8 D/b Ratio v/s Asphalt Content (Interpolation Graph)	28
Figure 4.1 Structure of User Interface for Superpave Calculator	43
Figure 4.2 Actual Job Mix Formula Sheet for Superpave Mix Design	51
Figure 5.1 Interpolation of VTM v/s Percent Binder.....	56
Figure 5.2 Interpolation of VMA v/s Percent Binder	56
Figure 5.3 Interpolation of VFA v/s Percent Binder.....	57
Figure A.1 Introduction to Superpave Calculator.....	67
Figure A.2 Superpave Report Information	68
Figure A.3 Superpave Calculator Worksheet Choices	69
Figure A.4 Mix Information Worksheet	70
Figure A.5 Calculated Aggregate Consensus Properties Worksheet.....	71
Figure A.6 Aggregate Data Worksheet.....	72
Figure A.7 Aggregate Gradation Chart.....	73
Figure A.8 Plot of 3 DAS Plotted Together.....	74
Figure A.9 Asphalt Content Estimator for Design Aggregate Structure	75
Figure A.10 Weigh-Out Sheets for Design Aggregate Structure Volumetrics.....	76
Figure A.11 Sample Rice Weigh-Out Sheet, Cumulative Sieve Weights	77
Figure A.12 Sample Rice Weigh-Out Sheet, Individual Sieve Weights	78
Figure A.13 Sample Pill Weigh-Out Sheet, Cumulative Sieve Weights1	79
Figure A.14 Sample Pill Weigh-Out Sheet, Individual Sieve Weights	80
Figure A.15 Data Entry Form for Rice and Pill Tests for Each DAS.....	81
Figure A.16 DAS Pill and Rice Test Analysis Worksheet	82
Figure A.17 Adjusted Volumetrics for Design Aggregate Structures	83
Figure A.18 Percent Binder Estimates for User Defined DAS (If Needed)	84
Figure A.19 Final DAS and Percent Binder Estimate Confirmation.....	85

Figure A.20 Weigh-Out Sheets for Percent Binder Trial Volumetrics.....	86
Figure A.21 Sample Rice Weigh-Out Sheet for Cumulative Sieve Weights	87
Figure A.22 Sample Rice Weigh-Out Sheet for Individual Sieve Weights.....	88
Figure A.23 Sample Pill Weigh-Out Sheet for Cumulative Sieve Weights	89
Figure A.24 Sample Pill Weigh-Out Sheet for Individual Sieve Weights	90
Figure A.25 Final Volumetric Information Entry Worksheet	91
Figure A.26 Percent Binder Trials Volumetric Analysis.....	92
Figure A.27 Graphs of Mix Properties v/s Asphalt Content.....	93
Figure A.28 Chart of Interpolated Final Volumetrics.....	94
Figure A.29 Weigh-Out Sheets for Optimum Asphalt Content Volumetrics.....	95
Figure A.30 Rice Weigh-Out Sheet – Cum. Sieve Weights for Final Volumetrics	96
Figure A.31 Rice Weigh-Out Sheet - Individual Sieve Weights for Final Volumetrics ..	97
Figure A.32 Pill Weigh-Out Sheet - Cumulative Sieve Weights for Final Volumetrics..	98
Figure A.33 Pill Weigh-Out Sheet - Individual Sieve Weights for Final Volumetrics	99
Figure A.34 Volumetric Data Entry Worksheet for Optimum Asphalt Content	100
Figure A.35 Volumetric Data Analysis for Optimum Asphalt Content	101
Figure A.36 Agg. Weigh-Out and Data Entry Worksheets for Tensile Strength Ratio..	102
Figure A.37 Aggregate Weigh-Out Sheet for TSR Pill, Cumulative Sieve Weights	103
Figure A.38 Aggregate Weigh-Out Sheet for TSR Pill, Individual Sieve Weights	104
Figure A.39 Exit Screen for Superpave Calculator	105
Figure A.40 Sample Job Mix Formula Print Out (Produced Using Trial Data).....	106
Figure A.41 Sample Weigh-Out Sheet Print-Out (Using Trial Data).....	107
Figure C.1 Blended Gradation for Trials 1-4 (64% #57 Slag & 36% #10 Slag)	121
Figure C.2 Blended Gradation for Trial 5 (72% #57 Slag & 28% #10 Slag).....	122
Figure C.3 Blended Gradation for Trials 6 & 6.1 (Gradation from Literature).....	123

LIST OF TABLES

Table 2.1 Control Points for Each Nominal Maximum Aggregate Size	8
Table 2.2 WVDOH Superpave Aggregate Consensus Property Requirements 2002	11
Table 2.3 Total Rice Sample Mass for Each Maximum Aggregate Size	15
Table 2.4 Number of Compaction Gyration based on ESAL Data	18
Table 2.5 VMA Tolerances for Each NMAAS	23
Table 2.6 VFA Tolerances for Traffic ESALs.....	23

Table 2.7 %G _{mm,Nini} Tolerances for Traffic ESALs	24
Table 2.8 Gradation Classification	24
Table 2.9 Theoretical Data to Illustrate Mix Properties Interpolation Method	27
Table 2.10 APA Specifications.....	32
Table 4.1 Data Used for Validation of Superpave Calculator	48
Table 4.2 Comparison of Actual and Theoretical DAS Analysis.....	49
Table 4.3 Comparison of Optimum Binder Percentage Analysis and Final Test Results	50
Table 5.1 Dry Sieve Gradation Analysis Results.....	53
Table 5.2 Calculated Steel Slag Specific Gravity and Absorption Values	54
Table 5.3 Trial 1 Volumetric Summary	54
Table 5.4 Trials 2,3 & 4 Volumetric Summary	55
Table 5.5 Trial 5 Volumetric Summary	58
Table 5.6 Steel Slag Gradation from Literature Review.....	59
Table 5.7 Trial 6 Average Volumetric Summary	59
Table 5.8 Average Rut Deformation.....	60
Table C.1 Estimated Binder Percentages from Aggregate Data.....	124
Table C.2 Bulk Specific Gravity and Absorption of ¾” Slag.....	125
Table C.3 Bulk Specific Gravity and Absorption of 1/2” Slag.....	126
Table C.4 Bulk Specific Gravity and Absorption of 3/8” Slag.....	127
Table C.5 Bulk Specific Gravity and Absorption of #4 Slag	128
Table C.6 Summary of Bulk Specific Gravity and Absorption for Coarse Steel Slag ...	129
Table C.7 Fine Steel Slag Aggregate Bulk Specific Gravity and Absorption	130
Table C.8 Trial 1 Volumetric Data	131
Table C.9 Trial 2 Volumetric Data	132
Table C.10 Trial 3 Volumetric Data	133
Table C.11 Trial 4 Volumetric Data	134
Table C.12 Trial 5 Volumetric Data	135
Table C.13 Trial 6 Volumetric Data	136
Table C.14 Trial 6.1 Volumetric Data	137
Table C.15 Trial 1 Pill and Rice Test Data and Calculations	138
Table C.16 Trial 2 Pill and Rice Test Data and Calculations	139
Table C.17 Trial 3 Pill and Rice Test Data and Calculations	140
Table C.18 Trial 4 Pill and Rice Test Data and Calculations	141

Table C.19 Trial 5 Pill and Rice Test Data and Calculations	142
Table C.20 Trial 6 Pill and Rice Test Data and Calculations	143
Table C.21 Trial 6.1 Pill and Rice Test Data and Calculations	144
Table C.22 Rut Testing Results	145

CHAPTER 1 INTRODUCTION

During the fifty years between 1940 and 1990, the nation's bituminous roadways were predominantly designed using either the Marshall or Hveem method. In the mid 1990's, the Superior Performing Asphalt Pavements (Superpave)TM method was developed to address the issues of increased traffic volumes and heavier loads on the nation's roadways. This new mix design process relies on volumetric calculations and graphs, which are cumbersome to perform by hand. Various companies have created Superpave mix design software which directly interfaces with their laboratory equipment. However, there is not a public domain Superpave software package independent of any commercial laboratory product and available to any asphalt mix designer. There is a need for a generic Superpave mix design program that can be utilized by anyone, regardless of the laboratory equipment used for testing.

Steel slag has been used as a Hot Mix Asphalt (HMA) aggregate in many steel producing states since the mid-1960's. Slag has been blended with gravel and crushed stone aggregates to provide a mix with excellent stability and stripping resistance. An investigation of a mix with steel slag as the only aggregate is needed to determine if a mix design for West Virginia roadways is possible.

1.1 PROBLEM STATEMENT

The major benefit of the Superpave mix design procedure is the creation of a superior bituminous pavement that will resist rutting and deformation. The drawback to the process is the intensive and involved nature of the analysis. The entire mix design procedure requires over thirty equations, all of which are interconnected and dependent on the aggregate and binder properties. There is currently no public domain software on the market allowing the mix design process to proceed from aggregate stockpile data to a complete mix design. This lack of Superpave software yields non-uniformity in the mix design submissions, hand calculations and graphs and variability in the mix design format submitted to the highway agency.

Due to the presence of the steel industry in Southwest Pennsylvania and North West Virginia, steel slag has been used in a limited capacity for past Marshall mix

designs. Because of the development of the Superpave mix design process, information on a Superpave mix consisting of only steel slag would be valuable. Since no empirical data is available on mix designs consisting solely of steel slag as the aggregate, research and testing is required.

1.2 OBJECTIVES

The objective of this research was to create a software package that would automate the entire Superpave mix design procedure, then validate the program by creating a mix comprised solely of steel slag aggregate. The goal of the project was to create a “user-friendly” program in Excel that can be used by any mix designer and be easily updated as needed. The program produces printed output in a format compatible with the requirements of the WVDOH. The slag research was intended to determine if a mix design comprising only inexpensive steel slag aggregate was able to meet all necessary criteria and display superior rutting resistance.

1.3 SCOPE OF WORK AND LIMITATIONS

In this research work, software to automate the Superpave mix design method was developed and mixes were created using only locally produced steel slag as the aggregate. The Superpave mix design procedures of the West Virginia Division of Highways (WVDOH) were followed along with the Materials Procedure (MP) dealing with bituminous pavements. The gyratory compactor was used to make the Asphalt Pavement Analyzer (APA) samples to determine the bulk specific gravity and evaluate rut susceptibility.

The Superpave mix design process requires evaluation of aggregate characteristics, including gradations, prior to the determination of binder content. Once the aggregate characteristics are determined, the Superpave analysis process is used to estimate binder contents, then asphalt concrete samples are prepared and tested. The software developed during this research focuses on the Superpave analysis. Therefore, the assumption was made that the designer would complete the aggregate evaluation prior to using the software. The software does not allow for the analysis of aggregate characteristics.

In the mix design process, the user is only allowed to use up to four sources of aggregates per mix design. Generally, it is not feasible for a contractor to use more than four stockpiles in a mix of asphalt concrete, so this should not be a limitation on the application of the program.

The experimental design used for this research work provides a comparison between the mixes created using the software versus those produced by an independent contractor. International Mill Service, Inc. (IMS), located in Weirton, WV provided the steel slag used for the research. The asphalt used was PG 64-22 from Marathon-Ashland. The work was limited to Superpave mixes created in West Virginia and was also limited to laboratory testing. Field evaluation could not be performed since the WVDOH has not constructed any mixes designed using the Superpave Calculator software package.

1.4 THESIS OVERVIEW

This thesis is organized into six chapters and three appendices. After the introductory chapter, Chapter 2 presents a summary of literature review. Superpave mix design procedures are outlined with standard test procedures and required WVDOH specifications. An explanation of the determination of maximum theoretical specific gravity, bulk specific gravity, tensile strength ratio and volumetric calculations are included in the literature review. The method of rut testing with the Asphalt Pavement Analyzer (APA), as specified by the device manufacturer, is also explained. The research methodology and procedures for spreadsheet development and verification, along with interface creation and validation is presented in Chapter 3. Chapter 4 presents the software verification process and structure. Chapter 5 provides an overview of the steel slag mix design and testing. Chapter 6 completes the thesis with the conclusions and recommendations.

Appendix A presents the Superpave Calculator program screen captures along with sample print-outs. The user's manual for the Superpave Calculator comprises Appendix B. Appendix C includes all of the calculated data and computed values throughout the steel slag research and testing.

CHAPTER 2 LITERATURE REVIEW

2.1 INTRODUCTION

The first recorded instance of roads utilizing bituminous pavement techniques dates back to ancient Babylon between 625 and 604 BC. These roadways were nothing more than soil and stone cart paths covered with a layer of tar, or asphalt binder, from a nearby well, called the Fountain of Is, which helped to improve the integrity and useful life of the surface (Baird, 2000). The layer of asphalt waterproofed the roadway, which made it less susceptible to rutting during the muddy times and it also helped to control the dust during the dry periods.

The first roadway paved with bituminous hot mix asphalt (HMA) in the United States was Pennsylvania Avenue in Washington DC in 1876 (Rock Binder's Inc., 2002). A group of army engineers used natural asphalt from Trinidad Lake, located on Island of Trinidad, to pave the road in front of the White House. The surface lasted for 11 years, enduring variable weather conditions and heavy traffic.

By the 1940's, scientists and engineers better understood the nature of HMA paving and the Marshall and Hveem mix design methods were coming into prominence. For the next fifty years, the majority of the roadways built in the United States used one of these two methods, but in the late 1980's, the Strategic Highway Research Program was initiated to develop a better mix design approach. In the mid 1990's, the Superior Performing Asphalt Pavements (Superpave)TM method was developed to address the issues of increased traffic volumes and heavier loads on the nation's roadways. The 2000 Superpave Implementation survey shows that almost every state in the US is at some stage of Superpave implementation (FHWA, 2000). This trend necessitates utilizing modern technology for a streamlined, cost-effective approach to the development of asphalt mix designs.

The Superpave mix design method is described in this chapter. The analytical procedure requires the execution of a series of equations for the volumetric analysis and estimated optimum percent binder. The Microsoft Excel spreadsheet program is well suited for the required analysis and the features implemented during the research are

briefly presented in this chapter. For software verification, research on steel slag as a viable coarse and fine aggregate alternative was explored and numerous design aggregate structures and binder percentages were tried. A brief review of literature concerning steel slag as an HMA aggregate is also included in this chapter.

2.2 SUPERPAVE MIX DESIGN

The Superpave mix design process encompasses a number of tests and procedures which, when properly implemented, provide the information needed to design asphalt concrete. The design process is performed to ensure that seven main objectives are met and the final product meets the criteria for acceptable quality and performance in the following areas (Roberts, et al., 1996):

- Resistance to Permanent Deformation - Pavement should not distort or displace when subjected to traffic
- Fatigue Resistance – Pavement should not crack when subjected to repeated loads
- Resistance to Low Temperature Cracking – Roadways created with the proper binder selection have minimized problems
- Durability – The mix must contain sufficient asphalt cement to ensure an adequate film thickness around the aggregates, which minimizes cement aging during service
- Resistance to Moisture Induced Damage – Proper aggregates must be selected to prevent loss of adhesion between the aggregate surface and the asphalt binder
- Skid Resistance – The mix must be designed to provide sufficient resistance to skidding during normal turning and braking movements
- Workability – The mix must be capable of being placed and compacted with reasonable effort

An outlined structure of the entire mix design process is presented in Figure 2.1. A more in-depth explanation of each step, including the science and assumptions behind the entire mix design procedure, is also included.

2.2.1 SUMMARY OF PROCESS

The entire Superpave mix design process, outlined in Sections 2.2.2 through 2.2.11 is concisely summarized in Figure 2.1, “Superpave Mix Design Steps” from a Superpave Asphalt Mixture Design Workshop (Zaniewski, 2002).

Superpave Mix Design Steps

- Determine design aggregate structure
 - Evaluate stockpiles
 - Test for source properties
 - Test for consensus properties-

<u>Property</u>	<u>Dividing Sieve</u>
Fine aggregate angularity	P 2.36 mm
Sand equivalency	P 4.75 mm
Flat and elongated	R 9.5 mm
Coarse aggregate angularity	R 4.75 mm
 - Gradation
 - Specific gravities, G_{sb} , G_{sa}
 - Determine 3 blends that meet aggregate criteria
 - Gradation – within control points, outside restricted zone
 - Compute blended consensus properties
 - Estimate asphalt content for each blend
 - Make samples, mixing and compacting at temperatures specified by binder supplier
 - Two samples compacted to N_{des}
 - Two G_{mm} samples
 - Compute volumetrics, G_{mm} , G_{mb} , $\%G_{mm}$, VTM, VMA, VFA, D/b, $\%G_{mm,Nini}$
 - Adjust volumetrics for 4% VTM
 - Select best design aggregate structure
- Determine optimum asphalt content
 - Using best design aggregate structure and $P_{b,est}$, compact two samples to N_{des} and two G_{mm} samples at four asphalt contents
 - $P_{b,est} - 0.5\%$
 - $P_{b,est}$
 - $P_{b,est} + 0.5\%$
 - $P_{b,est} + 1.0\%$
 - Compute volumetrics, G_{mm} , G_{mb} , $\%G_{mm}$, VTM, VMA, VFA, D/b, $\%G_{mm,Nini}$
 - Plot volumetrics v/s percent asphalt
 - Select optimum asphalt content at $P_{b,opt}$ – corresponds to 4% VTM and check volumetric criteria
 - Compact two samples at $P_{b,opt}$ and check $\%G_{mm}, N_{max} < 98\%$
- Evaluate moisture sensitivity
 - Compact six samples to 7% air, 95 mm tall
 - Condition three samples
 - Measure split tensile strength of all samples
 - Check TSR > 80%

Figure 2.1 Superpave Mix Design Summary Sheet

2.2.2 MIX COMPOSITION INFORMATION

When the West Virginia Division of Highways (WVDOH) determines that a new roadway is needed, or an existing road needs repaved, a list of mix guidelines is presented to a design laboratory. Mix design details, such as the 20-year design equivalent single axle loads (ESAL's), whether the mix will be a skid design, and the depth from the surface are provided. These are important factors in outlining the limits, tolerances, and controls for the mix design. The ESAL's determine the Fine Aggregate Angularity (FAA), the Flat/Elongated (F/E), and the Sand Equivalency (SE) limits, and also the Voids Filled with Asphalt (VFA) requirements and the needed gyrations for Percent of Theoretical Maximum Specific Gravity ($\%G_{mm,Nmax}$). The temperature range of the region controls the binder grade and specific gravity for the mix design. For example, a PG 64-22 binder is indicative of a geographic area having a seven-day average maximum pavement design temperature of 64°C and a minimum pavement temperature of -22°C. The specific gravity of the binder, while falling between 0.900 and 1.100, is dependent on the binder type and producer and may vary slightly between suppliers. A function of the design layer surface of a bituminous roadway, the Nominal Maximum Aggregate Size (NMAS) also establishes limits and tolerances. The NMAS is defined as, "One sieve size larger than the first sieve to retain more than 10 percent of the material" (Roberts, et al., 1996). From this NMAS designation, the blended gradation control points, as well as the antiquated restricted zone, discussed in Section 2.2.3, are set forth.

2.2.3 AGGREGATE CONSENSUS PROPERTIES

Once the mix composition information is established, the aggregate gradation, source properties, and specific gravity are determined for each stockpile, either by physically testing each aggregate or relying on supplier provided data. The aggregates are blended to create a Design Aggregate Structure (DAS) and then a graph of the blend is analyzed to determine if the control points are violated. Each NMAS has specific control points, which the blend must be between to be considered acceptable. The control points for each NMAS are presented in Table 2.1 (WVDOT, 2000).

Table 2.1 Control Points for Each Nominal Maximum Aggregate Size

[illegible]

In mixes created before 2002, an important requirement to be considered was the restricted zone, which lies along the maximum density line between the intermediate sieve size-either 4.75 or 2.36 mm depending on the NMAS of the mix-and the 0.3 mm sieve. It was believed that blends passing through this zone would lead to excessive rutting or “tender” mixes. Through empirical data over years of testing, it has been determined that a high quality mix can be created that passes through the restricted zone and thus the zone is no longer used to limit aggregate blends (WVDOH, 2000).

Each DAS blend is evaluated for acceptability with respect to fine aggregate angularity, coarse aggregate angularity, flat/elongated ratio, and the sand equivalency test. As required by Superpave, the consensus properties for the design aggregate blends are determined as:

- Coarse Aggregate Angularity (ASTM D 5821) –testing materials retained on 4.75 mm sieve.
- Fine Aggregate angularity (AASHTO T304) – testing materials passing the 2.36 mm sieve.
- Flat & Elongated particles (ASTM D4791) – testing materials retained on 9.5 mm sieve.
- Sand Equivalent (AASHTO T176) –testing materials passing the 4.75 mm sieve.

A stockpile is not considered in the blended consensus property calculation if less than 10% of the stockpile applies to the property standard. For example, if less than 10 percent of a stockpile is retained on the 4.75 mm sieve, the coarse aggregate angularity is not considered for that stockpile.

In West Virginia, a slight modification to the fine aggregate angularity test has been implemented and is specified in MP 401.02.28 as follows in Note 12:

Note 12: “Fine aggregates sizes that are coarse graded and have only a small amount of minus 600 mm (No. 30) material often cannot be individually tested using (the method described in AASHTO T304). Such aggregates must be blended with the other fine aggregates of the mixture to the specified mix design proportions before testing can be conducted.” (WVDOT, 2000)

Equation 2.1 is used for blending the aggregate consensus properties:

$$X = \frac{x_1 P_1 p_1 + x_2 P_2 p_2 + \dots}{P_1 p_1 + P_2 p_2 + \dots} \quad (2.1)$$

where:

X = Blended consensus property;

x_i = Consensus property for stockpile i;

P_i = Percent of stockpile i in the blend; and

p_i = Percent of stockpile i which either passes or is retained on the dividing sieve.

The flat and elongated test follows the general procedures of ASTM D 4791, but is modified for Superpave. Under the Superpave guidelines an aggregate particle coarser than 4.75 mm sieve is flat and elongated if the ratio of the maximum to minimum dimension is greater than 5 (Harman, et al., 1999). Figure 2.2 visually presents the dimensional labels of a typical aggregate, with the length being the maximum dimension and the width as the minimum dimension.

Figure 2.2 Flat/Elongated Test Dimensional Labels

Table 2.2 presents all of the aggregate consensus property requirements as determined by the WVDOT. The values are based solely on the design ESALs and are used when determining if a blended aggregate design structure is acceptable (WVDOT, 2000). These values have changed from the previous DOH specification; Table 2.2 reflects the most recent requirements.

Each of these criteria are tested for the blended design aggregate structures, and any value that falls outside of these tolerances renders that blend unacceptable. In mixes prior to 2002, when the restricted zone was in effect, it was thought that blends that went underneath of the restricted zone provided a better structure. Now, with the restricted zone no longer an issue, the prevailing logic is to create two DAS coarser than and one DAS finer than the maximum density line on a FHWA 0.45 Power Gradation Chart (Harman, et al., 1999). The FHWA 0.45 Power gradation chart is used to define permissible gradations. This chart uses a unique graphing technique to judge the cumulative particle size distribution of a blend. The ordinate (y-axis) of the chart is percent passing. The abscissa (x-axis) is an arithmetic scale of sieve size opening in microns, raised to the 0.45 power (Harman, et al., 1999).

Table 2.2 WVDOH Superpave Aggregate Consensus Property Requirements 2002

Design ESALs (millions)	Coarse Aggregate angularity (%min)*		Fine aggregate angularity (%min)		Sand equivalent	Flat & elongated
	≤100 mm from surface	>100 mm from surface	100 mm from surface	>100 mm from surface	Percent minimum	Percent minimum
<0.3	55/-	-	-	-	40	-
0.3 to <3	75/-	50/-	40	40	40	10
3 to <10	85/80	60/-	45	40	40	10
10 to <20	90/95	80/75	45	40	45	10
10 to <30	95/90	80/75	45	40	45	10
30	100/100	100/100	45	45	50	10

*Percent of one /more than one fractured faces

After the three DAS are determined, trial mixes are created and tested to determine an optimum design aggregate structure, which provides a basis for the remainder of the mix design process.

2.2.4 DAS ASPHALT CONTENT ESTIMATING

Once three blends are created with consensus properties and control points within tolerances, each design aggregate structure's specific gravities are calculated to facilitate an asphalt content (AC) estimation. Two specific gravities are required for calculation of AC, the apparent specific gravity (G_{sa}) and the bulk specific gravity (G_{sb}). By definition, the specific gravity of an aggregate is the ratio of the weight of the unit volume of the

material to the weight of an equal volume of water (Roberts, et al., 1996). The apparent specific gravity includes only the volume of the aggregate particle, while the bulk specific gravity includes the overall volume of the particle, as well as the volume of the pores that become filled with water after a 24-hour soaking. The specific gravities of the blend are calculated using Equation 2.2:

$$G_{sb} = \frac{P_1 + P_2 + \dots + P_n}{\frac{P_1}{G_1} + \frac{P_2}{G_2} + \dots + \frac{P_n}{G_n}} \quad (2.2)$$

where,

G_{sb} = Blended specific gravity of aggregate;

P_n = Percent of aggregate n in the blend; and

G_n = Specific gravity of aggregate n .

The asphalt content estimating process is repeated for each DAS. This repetition is necessary because the blends vary enough that one AC would not produce the required 4.0% air voids necessary for each structure. After the blended G_{sb} and G_{sa} are calculated, the effective specific gravity (G_{se}) is calculated by using an estimated absorption factor (F) of 0.8 and target air voids of 4.0% (Harman, et al., 1999). G_{se} is estimated according to Equation 2.3 (WVDOH, 2000):

$$G_{se} = G_{sb} + F(G_{sa} - G_{sb}) \quad (2.3)$$

where,

G_{se} = Effective specific gravity of aggregate;

G_{sb} = Bulk specific gravity of aggregate;

F = factor for absorption; and

G_{sa} = Apparent specific gravity of aggregate.

The volume of absorbed binder is then calculated according to Equation 2.4

$$V_{ba} = \frac{P_s(1 - V_a)}{\frac{P_b}{G_b} + \frac{P_s}{G_{se}}} \left(\frac{1}{G_{sb}} - \frac{1}{G_{se}} \right) \quad (2.4)$$

where,

V_{ba} = Volume of absorbed binder;

P_s = Percent of aggregate;

V_a = Volume of air voids (4.00%).

P_b = Initial Estimate for asphalt binder content, percent by weight of mix;

G_b = Specific gravity of binder; and

P_s = Percent of aggregate;

G_{se} = Effective specific gravity of aggregate; and

G_{sb} = Bulk specific gravity of aggregate.

The estimated volume of effective binder (V_{be}) is calculated according to Equation 2.5:

$$V_{be} = 0.176 - 0.0675 \log(S_n) \quad (2.5)$$

where,

V_{be} = Volume of effective binder; and

S_n = Nominal maximum sieve size of aggregate blend.

The estimated weight of stone (W_s) is estimated with Equation 2.6 as:

$$W_s = \frac{P_s(1 - V_a)}{\left(\frac{P_b}{G_b} + \frac{P_s}{G_{se}} \right)} \quad (2.6)$$

where,

W_s = Weight of aggregate (g);

P_s = Percent of aggregate;

V_a = Volume of air voids (4.00%);

P_b = Initial Estimate for asphalt binder content, percent by weight of mix;

G_b = Specific gravity of binder; and

G_{se} = Effective specific gravity of aggregate.

Finally, the estimated percent binder can be calculated, combining Equations 2.3 - 2.6 into Equation 2.7:

$$P_{bTrial} = \frac{G_b(V_{be} + V_{ba})}{(G_b(V_{be} + V_{ba})) + W_s} \quad (2.7)$$

where,

P_{bTrial} = Percent (by weight) of binder for the initial trial;

G_b = Specific gravity of binder;

V_{be} = Volume of effective binder.

V_{ba} = Volume of absorbed binder; and

W_s = Weight of aggregate (g).

The value for user defined percent binder (P_b) in Equation 2.4 and P_{bTrial} in Equation 2.7 must be equal, and Equations 2.4-2.7 are iterated until equality is achieved. The asphalt content for each DAS, once determined, is used for two gyratory compaction samples and two maximum theoretical specific gravity tests, then used to calculate an optimum asphalt content.

2.2.5 MAXIMUM THEORETICAL SPECIFIC GRAVITY TESTING

Once three design aggregate structures and their respective estimated percent binders are calculated, they are tested to determine which provides the best aggregate structure. To determine the properties of each DAS, the Rice test is used, in conjunction with the gyratory compactor, to determine the actual percentage of air voids, and the maximum and bulk specific gravities.

The maximum theoretical specific gravity test, developed by James Rice, referred to as the “Rice Test”, is used to determine the maximum specific gravity (G_{mm}) of a sample. G_{mm} is defined as, “The ratio of the weight in air of a unit volume of an uncompacted bituminous paving mixture at a stated temperature to the weight of an equal volume of gas-free distilled water at a stated temperature” (AASHTO T 209-99, 2000). AASHTO standard T209-99 covers the procedures and calculations for determining G_{mm} .

The methodology of this procedure is the same for all samples, but the maximum aggregate size (MAS) of the blend determines the total mass of the sample to be used for testing and is illustrated in Table 2.3. The maximum aggregate size is defined by Superpave as, “One sieve size larger than the nominal maximum aggregate size” (Roberts, et al., 1996).

Table 2.3 Total Rice Sample Mass for Each Maximum Aggregate Size

MAXIMUM AGGREGATE SIZE (mm)	RICE SAMPLE MASS (g)
50	6000
37.5	4000
25	2500
19	2000
12.5	1500
9.5	1000
4.75	500

Once the needed sample mass is determined, the necessary amount of aggregate retained on each sieve size is weighed, and heated at $155 \pm 5^\circ\text{C}$ for a minimum of two hours. An amount of asphalt binder is also heated in the oven until it flows easily and mixing effort is minimal. The aggregate blend and the specified mass of asphalt cement are mixed together until the binder covers the aggregate with an even film thickness. The bituminous mixture is placed back into the oven to cure at $135 \pm 5^\circ\text{C}$ for 2 hours, with stirring every 30 minutes to allow absorption of binder into the aggregates. After the specified reheating time, the sample is removed from the oven and placed on a table, where it is rapidly cooled and the aggregates are separated into individual particles no larger than $\frac{1}{4}$ -inch in diameter. This loose conglomeration of asphalt-covered aggregates is weighed, placed in a bowl, or pycnometer, then covered with water and placed in a vacuum chamber at 15 mm Hg (3.7 ± 0.3 kPa) for 15 ± 2 min. Once all of the trapped gases are removed from the mixture, the sample is suspended in a tank of water and weighed (AASHTO T 209-99, 2000). These masses are then entered into Equation 2.8 and the G_{mm} is obtained.

$$G_{mm} = \frac{A}{A - (B - C)} \quad (2.8)$$

where,

G_{mm} = Maximum theoretical specific gravity;

A = Sample weight (g);

B = Bowl + sample in water weight (g); and

C = Bowl in water (Calibration) weight (g).

Two Rice tests are performed for each DAS and the average is used for further volumetric analysis.

2.2.6 GYRATORY COMPACTOR SAMPLES

For the Superpave mix design process, samples are compacted using the gyratory compactor presented in Figure 2.3. The compacted samples, or “pills” are used to determine the percent air (VTM) and bulk specific gravity (G_{mb}). G_{mb} is defined as, “The ratio of the weight in air of a unit volume of a compacted specimen of HMA (including permeable voids) at a stated temperature to the weight of an equal volume of gas-free distilled water at a stated temperature” (Roberts, et al., 1996).

The bulk specific gravity (G_{mb}) is calculated as:

$$G_{mb} = \frac{A}{B - C} \quad (2.9)$$

where,

G_{mb} = Bulk specific gravity of the pill;

A = Dry weight of pill, (g);

B = Wet weight of saturated surface dry (SSD) pill, (g); and

C = Submerged weight of pill, (g).

$$VTM = \left(1 - \frac{G_{mb}}{G_{mm}} \right) 100 \quad (2.10)$$

where,

VTM = Actual percent of air content of the mix, also known as voids in total mix;

G_{mb} = Bulk specific gravity of the mix; and

G_{mm} = Theoretical maximum specific gravity of the sample.

Figure 2.3 Superpave Gyratory Compactor

When the Strategic Highway Research Program was charged with the development of a superior mix design process, one of the main goals was to develop a laboratory compaction method that can consistently produce specimens representative of in-service pavements. The compactive effort of the gyratory compactor is controlled by three parameters: vertical pressure, angle of compaction, and number of gyrations. The AASHTO provisional standard TP 4-00 covers the compaction of cylindrical specimens of hot-mix asphalt (HMA) using the Superpave gyratory compactor and AASHTO standard T 166-00 outlines the testing methodology of the cylinders. This standard

specifies the compaction criteria of the Superpave gyratory Compactor and states, “The ram shall apply and maintain a pressure of 600 ± 18 kPa perpendicular to the cylindrical axis of the specimen during compaction. The compactor shall tilt the specimen at an angle of $1.25 \pm 0.02^\circ$ and rotate the specimen molds at a rate of 30.0 ± 0.5 gyrations per minute throughout compaction.” (AASHTO T P4, 2000)

Superpave requirements specify that the number of initial, design, and maximum gyrations depend on the traffic ESALs, as presented in Table 2.4 (WVDOT, 2000). The number of gyrations for design, N_d , was selected to produce a density of 4.0% VTM in the mix, which is equivalent to the expected density in the field after construction. An initial compactive effort, N_i , was defined to identify “tender” mixes, which are difficult to compact in the field because the mix lacks the internal friction required to prevent the excessive deformation (Roberts, et al., 1996). The maximum Superpave compactive effort, N_{max} was selected to ensure the material does not over compact under traffic. N_{max} and N_i are a function of N_d :

$$N_i = (N_d)^{0.45} \quad (2.11)$$

$$N_{max} = (N_d)^{1.10} \quad (2.12)$$

where,

N_i = Initial number of gyrations;

N_d = Design number of gyrations; and

N_{max} = maximum number of gyrations.

Table 2.4 Number of Compaction Gyrations based on ESAL Data

ESALs (millions)	N_i	N_d	N_{max}
< 0.3	6	50	75
0.3 < 3	7	75	115
3 < 30	8	100	160
≥ 30	9	125	205

The gyratory compaction samples are created by first determining a total mass and weights retained on each sieve, then weighing the aggregates. The aggregates and

binder must be heated, mixed together, and then cured to allow for binder absorption, stirring every 30 minutes. The aggregate and binder blend is then compacted in a gyratory compactor to a determined number of rotations. In order to determine the proper sample mass for each pill, either the actual G_{mm} , from Equation 2.8, or the theoretical G_{mm} from Equation 2.13 is used. The theoretical volume of a cylinder in Equation 2.14, and the blended aggregate and binder properties are used in Equation 2.15 to estimate a mass that will have 4% air content at 115mm in height. If the maximum theoretical specific gravity test has already been performed, then G_{mm} is calculated according to Equation 2.8, otherwise it can be estimated using Equation 2.13.

$$G_{mm} = \frac{1}{\frac{1-P_b}{G_{se}} + \frac{P_b}{G_b}} \quad (2.13)$$

where,

G_{mm} = Theoretical maximum specific gravity;

P_b = Asphalt content, percent by weight of mix;

G_{se} = Effective specific gravity of aggregate blend; and

G_b = Specific gravity of asphalt cement.

$$V_{pill} = \left[\left(\frac{\pi}{4} d^2 h \right) (1 - V_{surf.}) \right] (1 - V_a) \quad (2.14)$$

where,

V_{pill} = Total volume of the pill, minus all air voids (mm^3);

d = Diameter of gyratory compaction cylinder, 150 mm;

h = Height of gyratory compaction cylinder, 115 mm;

$V_{surf.}$ = Volume of surface voids on the pill; and

V_a = Optimum value of air voids in sample, target is 4.0%.

The volume of surface voids on the pill ($V_{surf.}$) is estimated to be 3.0% from empirical testing conducted in the West Virginia University Asphalt Technology Laboratory.

$$W_{pill} = (V_{cyl})G_{mm} \quad (2.15)$$

where,

W_{pill} = Total theoretical weight of gyratory compactor sample pill (g);

V_{cyl} = Total volume of cylindrical pill, minus all air voids; and

G_{mm} = Theoretical maximum specific gravity.

After the theoretical weight of the pill is calculated, the aggregate is weighed, heated, mixed with the calculated percentage of heated binder, reheated then compacted. The reheated sample is placed into a mold, 150 mm in diameter and 300 mm tall. It is then compacted to a specific number of gyrations, which, theoretically yields a sample exactly 115 mm tall. The compacted pill is removed from the mold and allowed to cool, weighed to within 0.1 g, then submerged in a tank of water for 3 to 5 minutes and weighed to the same tolerance. The wet pill is towel dried to the Saturated Surface Dry (SSD) condition and weighed. These weights are used to calculate the G_{mb} using Equation 2.9, and VTM is computed using Equation 2.10.

Two pills are created for each DAS, and the average G_{mb} , G_{mm} and percent air (VTM) are used for further volumetric analysis.

2.2.7 VOLUMETRIC ANALYSIS

The bulk specific gravity and maximum specific gravity from the tests are used to evaluate the volumetric properties of the mix using Equations 2.16 to 2.24 (Roberts, et al., 1996).

$$\%G_{mm, Ndes} = \frac{G_{mb}}{G_{mm}} \quad (2.16)$$

$$G_{se} = \frac{1 - P_b}{\frac{1}{G_{mm}} - \frac{P_b}{G_b}} \quad (2.17)$$

$$P_{ba} = 100 \left(\frac{G_{se} - G_{sb}}{G_{sb}(G_{se})} G_b \right) \quad (2.18)$$

$$P_{be} = P_b - P_{ba}(1 - P_b) \quad (2.19)$$

$$\frac{d}{B} = \frac{\left(\frac{\%P_{\#200}}{100} \right)}{P_{be}} \quad (2.20)$$

$$\%G_{mm,Nini} = \%G_{mm,Ndes} \frac{h_{des}}{h_{ini}} \quad (2.21)$$

$$VTM = 1 - \frac{G_{mb}}{G_{mm}} \quad (2.22)$$

$$VMA = 100 \left(1 - \frac{G_{mb}(1 - P_b)}{G_{sb}} \right) \quad (2.23)$$

$$VFA = 100 \left(\frac{VMA - VTM}{VMA} \right) \quad (2.24)$$

where,

$\%G_{mm,Ndes}$ = Percent of maximum specific gravity at design number of revolutions;

G_{mb} = Bulk specific gravity;

G_{mm} = Maximum specific gravity;

G_{se} = Effective specific gravity of aggregate;

P_b = Percent binder;

G_b = Specific gravity of the binder;

P_{ba} = Percent binder absorbed;

G_{sb} = Bulk specific gravity of aggregate;

P_{be} = Effective percent binder

$\%P_{\#200}$ = Percent of the aggregate blend passing the #200 sieve;

$\%G_{mm,Nini}$ = Percent of maximum specific gravity at initial number of revolutions;

h_{des} = Height at the design number of revolutions;

h_{ini} = Height at the initial number of revolutions;

VTM = Air voids in compacted mixture;

VMA = Volume of voids in mineral aggregates; and

VFA = Voids filled with asphalt.

For DAS evaluation only, these volumetric properties are used to determine whether the HMA mixture is acceptable. If the VTM is not equal to the target of 4 percent, then it must be mathematically adjusted to 4 percent air and all volumetrics must be adjusted accordingly.

Of all the possible volumetric properties, five have AASHTO tolerances, which must be met (Roberts, et al., 1996):

1. Air Voids in Compacted Mixture (VTM) – The total volume of the small pockets of air between the coated aggregate particles throughout a compacted paving mixture, the target is 4.0%. Tolerance is 3.0% - 5.0%. See Equation 2.22.
2. Volume of Voids in the Mineral Aggregate (VMA) – The volume of intragranular void space between the aggregate particles of a compacted paving mixture that includes the air voids and volume of the asphalt not absorbed into the aggregates. The tolerances on VMA depend on NMAS and are presented in Table 2.5 (Roberts, et al., 1996).

Table 2.5 VMA Tolerances for Each NMAS

NOMINAL MAXIMUM AGGREGATE SIZE (mm)	MINIMUM VMA (%)
37.5	11%
25	12%
19	13%
12.5	14%
9.5	15%

3. Voids filled with Asphalt Cement (VFA) – The percent of the volume of the VMA that is filled with asphalt cement. The tolerances for VFA are dependent on the estimated traffic and are presented in Table 2.6.

Table 2.6 VFA Tolerances for Traffic ESALs

Traffic ESALs (millions)	VFA Percent	
	Minimum	Maximum
< 0.3	70	80
0.3 < 3	65	78
3 < 10	65	75
10 < 30	65	75
≥ 30	65	75

The values in Table 2.5 are the nationally accepted tolerances for VFA percentage. In West Virginia, some slight modifications have been included to prevent troubling issues and are specified in MP 401.02.28 (WVDOT, 2000).

Note 3: “For a 9.5 mm NMAS mixture, the specified VFA range shall be 73% to 76% for design traffic levels ≥ 3 million ESALs.”

Note 4: “For 25 mm NMAS mixture, the specified lower limit of VFA shall be 64% for design traffic levels < 0.3 million ESALS.”

Note 5: “For 37.5 mm NMAS mixtures, the specified lower limit of the VFA range shall be 64% for all design traffic levels.”

4. Percent of Maximum Specific Gravity at the Initial Number of Revolutions ($G_{mm,N_{ini}}$) – Refers to the percent of maximum specific gravity obtained at N_{ini} , which can not be measured, only estimated using the height ratio factors. See Equations 2.16 and 2.21. The criteria for $\%G_{mm,N_{ini}}$ are dependent on the estimated traffic and are presented in Table 2.7.

Table 2.7 %G_{mm,Nini} Tolerances for Traffic ESALs

Traffic ESALs (millions)	Percent of Theoretical Gmm at N _{initial}
< 0.3	≤ 91.5
0.3 < 3	≤ 90.5
3 < 10	≤ 89.0
10 < 30	≤ 89.0
≥ 30	≤ 89.0

5. Dust to Binder Ratio (D/b) – The ratio of the amount of the blended aggregate passing the #200 sieve to the effective binder content of the mix. The value for D/b must be between 0.6-1.2 for coarse graded blends and between 0.8-1.6 for fine graded mixes. According to the Materials Procedure:

“The combined aggregate gradation shall be classified as coarse graded when it passes below the Primary Control Sieve (PCS) control point as defined in Table 2.8. All other gradations shall be classified as fine graded.”

Table 2.8 Gradation Classification

PCS Control Point for Mixture Nominal Maximum Aggregate Size (% Passing)					
Nominal Maximum Aggregate Size	37.5 mm	25.0 mm	19.0 mm	12.5 mm	9.5 mm
Primary Control Sieve	9.5 mm	4.75 mm	4.75 mm	2.36 mm	2.36 mm
PCS Control Point	47	40	47	39	47

2.2.8 VOLUMETRIC ANALYSIS ADJUSTMENTS

In theory, both pills at each DAS would have exactly 4.0% air and the compacted heights would be 115.0 mm, but this is rarely the case; therefore a series of equations are used to adjust the volumetric properties to a target VTM of 4.0%. Equations 2.25-2.30 are used to adjust the values (Harman, et al., 1999).

$$P_{b,est} = P_{b,trial} - (0.4 \times (4.00\% - VTM)) \quad (2.25)$$

$$VMA_{est} = VMA + C \times (4.00\% - VTM) \quad (2.26)$$

$$VFA_{est} = 100 \left(\frac{VMA_{est} - 4.00\%}{VMA_{est}} \right) \quad (2.27)$$

$$\%Gmm_{est,Nini} = \%Gmm_{Nini} - (4.00\% - VTM) \quad (2.28)$$

$$P_{be,est} = -(G_b * P_s) \left(\frac{(G_{se} - G_{sb})}{G_{se}(G_{sb})} \right) + P_{b,est} \quad (2.29)$$

$$\frac{d}{B_{est}} = \frac{\%P_{\#200}}{P_{be,est}} \quad (2.30)$$

where,

$P_{b,est}$ = Estimated percent binder needed to achieve 4.0% air;

$P_{b,trial}$ = Percent binder used in the initial trials;

VTM = Air voids in compacted mixture;

VMA_{est} = Estimated air voids in compacted mixture, from trial volumetric data;

VMA = Volume of voids in mineral aggregates;

C = Correction factor,

If VTM < 4.0%, C = 0.1,

If VTM > 4.0%, C = 0.2;

VFA = Voids filled with asphalt;

VFA_{est} = Estimated voids filled with asphalt, from trial volumetric data;

$\%G_{mm\ est,Nini}$ = Estimated percent of maximum specific gravity at the initial number of revolutions;

$\%G_{mm,Nini}$ = Percent of maximum specific gravity at initial number of revolutions;

$P_{b,est}$ = Estimated percent binder, from trial volumetric data;

P_b = Percent binder;

G_b = Specific gravity of the binder;

P_s = Percent stone;

G_{sb} = Bulk specific gravity;

G_{se} = Effective specific gravity;

P_{be} = Effective percent binder;

D/b_{est} = Estimated dust to binder ratio, from trial volumetric data;

D/b = Dust to binder ratio; and

$\%P_{\#200}$ = Percent of the aggregate blend passing the #200 sieve.

The calculated adjusted volumetric properties are then compared to the acceptable limits presented in Section 2.3.4. The adjusted values are analyzed by the technician, who determines which design aggregate structure presents the best overall possibility for a superior HMA pavement. If no DAS yields a viable option for an acceptable structure, three different DASs are chosen and the Rice test and pill compaction procedures are repeated until a structure is determined. Once the design aggregate structure is found, the next procedures are performed to determine the asphalt content that will produce 4.0% VTM, while meeting all required properties.

2.2.9 DETERMINING OPTIMUM ASPHALT CONTENT

Once the design aggregate structure is selected, the optimum asphalt cement percent must be determined. Two maximum theoretical gravity tests are performed and two gyratory compaction samples are created at four asphalt contents:

- $P_{b,est} - 0.5\%$
- $P_{b,est}$
- $P_{b,est} + 0.5\%$
- $P_{b,est} + 1.0\%$

The laboratory procedures are the same as those outlined in Sections 2.2.3 and 2.2.4, and volumetric properties are calculated as detailed in Section 2.2.5. Table 2.9 presents an example of the computed volumetric properties, including, VTM, VMA, VFA, D/b and $\%G_{mm,Nini}$. Each of these parameters is plotted against percent binder as shown on Figures 2.4 to 2.8. The optimum binder percentage is determined as the percent binder corresponding to 4.0% VTM, as shown on Figure 2.4. This percent binder is used to determine the other volumetric properties and those values are compared with the limits set forth in Section 2.2.5 to determine if the asphalt content and DAS are

acceptable. If the criteria are not satisfied, a new design aggregate structure must be evaluated.

Table 2.9 Theoretical Data to Illustrate Mix Properties Interpolation Method

P_b	4.5%	5.0%	5.5%	6.0%
VTM	6.0%	4.6%	2.9%	1.9%
VMA	15.7%	15.3%	15.2%	15.4%
VFA	61.3%	70.0%	79.0%	85.0%
D/b	1.7	1.5	1.2	1.1
$\%G_{mm,Nini}$	84.5%	86.0%	87.2%	87.9%

Figure 2.4 VTM v/s Asphalt Content (Interpolation Graph)

Figure 2.5 VMA v/s Asphalt Content (Interpolation Graph)

Figure 2.6 VFA v/s Asphalt Content (Interpolation Graph)

Figure 2.7 % $G_{mm,Nini}$ v/s Asphalt Content (Interpolation Graph)

Figure 2.8 D/b Ratio v/s Asphalt Content (Interpolation Graph)

The percent binder at 4.0% VTM, and the corresponding volumetric properties, can be interpolated using Equations 2.31 and 2.32. Although Figures 2.4 to 2.8 show

curved relationships, linear interpolation is adequate for the precision needed for this analysis.

$$P_{b,opt,est} = P_{b,below} - \left[\frac{VTM_{below} - 4.00\%}{VTM_{below} - VTM_{above}} \times (P_{b,below} - P_{b,above}) \right] \quad (2.31)$$

$$X_{opt,est} = X_{below} - \left[\frac{P_{b,below} - P_{b,opt,est}}{P_{b,below} - P_{b,above}} \times (X_{below} - X_{above}) \right] \quad (2.32)$$

where,

$P_{b,opt,est}$ = Interpolated percent binder needed to achieve 4.0% air;

$X_{opt,est}$ = Volumetric property to be adjusted to 4.0% VTM, mathematically;

$P_{b,below}$ = Percent binder which yields a VTM immediately below 4%;

$P_{b,above}$ = Percent binder which yields a VTM immediately above 4%;

VTM_{below} = VTM value at P_b which is immediately below 4%;

VTM_{above} = VTM value at P_b which is immediately above 4%;

X_{below} = Volumetric property at P_b which is immediately below 4%; and

X_{above} = Volumetric property at P_b which is immediately above 4%.

2.2.10 FINAL TESTS TO EVALUATE ACCEPTABILITY

Two more Rice tests and compaction samples are created at the interpolated optimum binder percentage and are prepared in the same manner as presented in Sections 2.2.4 and 2.2.5. The samples are compacted to N_{max} and Equation 2.33 is used to calculate $\%G_{mm,Nmax}$, which is then compared with a maximum value of 98.0% (WVDOT, 2000). The air voids of samples compacted with N_{max} revolutions is required to be at least 2 percent; mixtures with less than 2% VTM are believed to be more susceptible to rutting (Roberts, et al., 1996). The percent $\%G_{mm,Nmax}$ provides an estimate of the ultimate field density, which insures that the mixture does not densify excessively, leading to low in-place voids.

$$\%G_{mm, N_{\max}} = \frac{G_{mb, N_{\max}}}{G_{mm}} \quad (2.33)$$

where,

$\%G_{mm, N_{\max}}$ = Percent of maximum specific gravity at the design number of revolutions (See Table 2.4);

$G_{mb, N_{\max}}$ = Bulk specific gravity of the pill compacted to $N_{\max}$ revolutions; and

G_{mm} = Maximum specific gravity from the Rice test.

Values of $\%G_{mm, N_{\max}}$ that are greater than 98.0% are deemed unacceptable and the mix design process returns to the beginning, where a new DAS is selected and all of the subsequent steps are repeated.

The final test of HMA mix design acceptability is the evaluation of moisture susceptibility. Over a period of time, the effects of moisture on an asphalt roadway can lead to a phenomenon called “stripping”. Stripping produces a loss of strength in the asphalt by weakening the bond between the asphalt cement and the aggregates (Roberts, et al., 1996). This loss of strength can be gradual, as the roadway slowly exhibits signs of rutting, or it can be sudden where the roadway shows signs of distress as the asphalt cement peels off of the aggregates. The moisture sensitivity of the design mixture is evaluated by performing the AASHTO T-283 test on the design aggregate blend at the optimum asphalt content. Modifying Equations 2.14 and 2.15 for 7.0% VTM and h_{des} of 95mm, six compaction samples are prepared, as detailed in Section 2.2.5, and the specimens are compacted. The gyratory compactor is set to a height control mode and the compaction continues until the required height is achieved. Three compacted pills are subjected to partial vacuum saturation, followed by an optional freeze cycle, then a 24-hour conditioning cycle at 60°C; three pills are not conditioned. The unconditioned samples are soaked in a water bath at 60°C for 60 minutes to equilibrate the temperatures. The conditioned and unconditioned specimens are tested to determine indirect tensile strengths. The moisture sensitivity is determined as a ratio of the tensile strengths of the conditioned subset divided by the tensile strengths of the control subset. The minimum acceptable value of tensile strength ratio (TSR) allowable is 80%. If the minimum is not

met, a new design is required which incorporates an antistrip agent. According to MP 401.02.28, “A Division approved antistripping additive, such as hydrated lime conforming to the requirements of AASHTO M303, or a liquid antistripping additive, may be added to the mixture if needed. If such an additive is used, the process is restarted at the DAS selection and all design testing must be conducted with the additive in the mixture (WVDOT, 2000).” The use of AASHTO T-283 is not required to design a Superpave mix, but the West Virginia DOH requires the test to ensure rut resistance (WVDOH, 2000).

2.2.11 ASPHALT PAVEMENT ANALYZER

The evaluation of the mix for rut resistance is not part of the Superpave mix design, but can be used with any design method to evaluate asphalt performance. After a mix design is deemed acceptable by passing all required tests, and meeting all necessary criteria, it can be tested for susceptibility to rutting. Ruts are defined as depressions, which occur in the pavement’s wheel path, caused by traffic compaction or displacement of unstable material. A negligible amount of rutting can be expected to occur on a HMA surface due to the continued densification under traffic after initial compaction during construction. Much of the rutting that occurred before the advent of the Superpave method can be attributed to an improper mix design. Some common mistakes made when designing the HMA mixes include the selection of high asphalt content, use of excessive filler material (material passing #200 sieve), or use of too many rounded particles in aggregates. In recent years, the potential for rutting on the nation’s highways has increased due to higher traffic volumes and the increased use of radial tires that typically exhibit higher inflation pressures (Roberts, et al., 1996). One of the most common types of laboratory equipment that predicts field-rutting potential is the Asphalt Pavement Analyzer (APA). The APA is the commercial version of the Georgia Loaded Wheel Tester (GLWT) and was first manufactured in 1996 by Pavement Technology, Inc. The APA is a multi-functional Loaded Wheel Tester (LWT) that can be used for evaluating rutting, fatigue cracking, and moisture susceptibility of hot and cold asphalt mixes.

The standard method followed to determine rutting susceptibility using APA is developed by APAC Materials Services in an ASTM format. Rutting susceptibility of mixes is assessed by placing cylindrical samples under repetitive wheel loads and measuring the amount of permanent deformation under loading. Six samples at a time can be tested in APA under controlled temperature, and in dry or submerged-in-water conditions. The rut depth is measured after the desired number of cycles (usually 8000) of load application. Table 2.9 shows the test parameters specified in the APAC procedure. After the cycles are completed, the cylinders are removed from the APA and the rut depths are measured relative to the surface of the pill. These rut values are then compared with each other and previous empirical data to determine the rutting potential of the mix when laid on a roadway. If the results show a high tendency towards rutting, the mix may have to be redesigned using a different design aggregate structure to minimize the effects of rutting.

Table 2.10 APA Specifications

Factors	Range specified in APAC procedure
Air void content	7 ± 1 %
Test temperature	Based on average high pavement temperature
Wheel load	100 ± 5 lb
Hose pressure	100 ± 5 psi
Specimen type	Beams, cylinders
Compaction	Rolling, vibratory, and gyratory

2.2.12 AVAILABLE SUPERPAVE SOFTWARE

Equipment vendors, such as Pine Instrument Co., have developed Superpave analysis software that is provided with their equipment (Pine, 1998). The American Association of State Highway and Transportation Officials (AASHTO) contracted the University of Maryland to develop a generic Superpave analysis software package, which was released in 2000. However, this software is not currently supported or marketed by AASHTO (AASHTO, 2002). The literature review during the research failed to locate any public domain software.

2.3 STEEL SLAG AS AN HMA AGGREGATE ALTERNATIVE

It is unknown exactly when steel slags were first used as a roadway construction material, but an ancient Roman road, created with slag, dates back to 200AD (Lee, 1974). Steel slag is a by-product of open-hearth, basic oxygen, and electric arc steel making processes and industrial blast furnaces. Steel slags have been used in highway construction in the United States and Canada since the turn of the century (Ciesielski, 1996). Today, there are many types of slag produced in the United States including ferrous slags, chrome slags and copper slags, of which ferrous slags are most abundant in the north-central West Virginia region. Ferrous slags can further be divided into three subcategories: air-cooled blast furnace slag, expanded blast furnace slag, and granulated blast furnace slag. The region's most abundant slag type is air-cooled blast furnace slag, which is produced by pouring the molten slag into a pit or onto a slag bank until cool, at which time it is removed, crushed and screened (McGannon, 1971).

Steel slag is described as:

Steel slag consists of crushed angular particles with rough irregular surfaces. It is essentially free from flat or elongated pieces and has a rougher surface texture than gravels and crushed stones. It is highly resistant to weathering, as are other types of iron blast furnace slags. Freezing and thawing effects together with sulfate soundness losses are reported to be exceptionally low (Noureldin, 1990).

Several studies have been initiated in recent years to determine the acceptability of using steel slag in hot mix asphalt production. Southern Ontario, Canada began using great amounts of slag in HMA in the early 1970's and considerable data has been collected on the performance of various roadways (Ali, et al., 1992). Steel slag has a high bulk specific gravity when compared with most natural aggregates used in HMA mix designs. Slag specific gravity values typically range from 3.2 to 3.6, while the average specific gravity for natural HMA aggregates is approximately 2.6. The hardness, as measured on Moh's hardness scale for slag is between 6 and 7, compared with limestone's rating of 3 to 4. Los Angeles abrasion testing has shown slag to be extremely resistant to degradation, making it a useful material in a surface course. Steel slag is 100% crushed and angular, with a gradation that usually requires no blending. Mixes made with slag have very high stabilities, satisfactory flows and excellent stripping

resistance. Slag mixes also have good heat retention and compatibility, and, when used as a surface coarse, have good wear and skid resistance (Ali, et al., 1992). HMA mixes made with steel slag also demonstrate longer heat retention after mixing and ease of compaction without “shoving” in front of the roller (Ramirez, 1992). It has been empirically determined that the absorption of steel slag is higher than most natural aggregates, especially among the fine aggregates, which, in one regard, is a disadvantage of this material, but it also beneficially produces lower drying costs (Hanson and Lynn, 1995).

The three main disadvantages in using steel slag as an aggregate include: variation in characteristics, extremely high unit weight, and its expansive nature. The characteristic variations are due to the fact that this material is only a by-product of the steel making process, and quality control is not a priority. Even though gradation and screening properties are fairly consistent, the specific gravity and absorption may greatly differ from plant to plant, or even within the same plant. Since the specific gravity of slag is much greater than natural aggregates, it requires more tonnage to produce a specific volume of an HMA mixture. This extra weight per mixture, combined with weight restrictions on the roadways and tonnage limits on trucks, limits slag mixtures as a viable economical alternative to natural HMA mixtures over great distances. Another drawback to using slag involves its expansive nature, which is due to the hydration of calcium and magnesium oxides. The calcium hydrates rapidly to cause extensive volume changes in a short period of time, while the magnesium oxide hydrates more slowly and may not show signs of expansion for several years (Hegmon and Ryan, 1984). This phenomenon can be controlled by one or any combination of three ways, which include: suitable aging in stockpiles, treatment of aggregates with spent acids, or complete coating of particles with asphalt binder to prevent the intrusion of water (Noureldin, 1990).

If steel slag is to be utilized as an aggregate in hot mix asphalt, quality control should be of paramount importance to insure the most uniform by-product possible. The stockpiles should be small and carefully monitored to ensure uniformity; they should be free of large particles, and they should be allowed to adequately age. Research from the Canadian Technical Asphalt Association suggests these five steps to ensure the quality and uniformity of steel slag stockpiles (Emery, 1984):

1. Avoid contamination by refractories and rubbish in the processing areas.
2. Weather the slag for a minimum of one month before screening.
3. Monitor free lime content.
4. Rescreen any agglomerated or crusted stockpiled slag.
5. Pay special attention to AC content and mix adequately.

It is clearly demonstrated that if the slag producer is within a reasonable distance and the slag piles are properly maintained and cured, HMA production with steel slag is definitely a viable option. It is more complicated to ensure the uniformity and consistency of slag aggregates, but if done properly, a pavement with superior performance and a longer life can be expected.

2.4 MICROSOFT EXCEL AS A SOFTWARE DEVELOPMENT TOOL

Microsoft Excel is a powerful tool for analyzing and presenting information (Jacobson, 1997). It is ideally suited for spreadsheet data entry, computations and graphing technology, making this a powerful tool to use when performing a Superpave mix design. The actual data entry into Excel for a mix design can be confusing, with the formulas in certain cells and the output in others. Using Excel's built-in macro function, this problem is eliminated by allowing the user to enter data only in specified fields. Visual Basic for Applications (VBA) first appeared in Excel in Version 5; the use transformed the approach of user interface with the supporting workbooks. Using VBA, the programmer is able to present the user with electronic forms that only allow data entry in certain text boxes and return calculated values in other specified locations (Masters, 1999). This method of user interface minimizes the user-related error while maximizing efficiency. When a userform is implemented, the program's user has no choice but to enter data in only the provided cells for input, thus eliminating the possibility of erasing an important formula or entering an improper data type into a field. VBA in Excel allows the programmer to create a macro to automate all necessary tasks, which is easily shared among users, and can be modified by authorized personnel at any time. The use of VBA requires the programmer to be familiar with the visual basic programming language, and understand Excel's macro features (Schneider, 1999).

2.5 SUMMARY

The Superpave mix design process presented has been used by the West Virginia Division of Transportation and its contractors for the past five years. The entire Superpave process, including the equations and supporting theory, was detailed in the literature review. An explanation of the laboratory testing procedures for maximum theoretical specific gravity and bulk specific gravity, supported by the departmental specification is also included. Also described was a brief overview of the Asphalt Pavement Analyzer, including the theory behind the development and test methodology. The variations between some national standards and the current WV specifications have also been presented, which provide a wider margin of error in some instances and a tighter standard in others. The criteria for both have been presented here.

The literature review of the steel slag research and its benefits and disadvantages was presented to introduce the concept of using slag as a possible superior alternative to natural aggregates in HMA. A brief introduction to Microsoft Excel and the Visual Basic for Applications macro tool were also included.

CHAPTER 3 RESEARCH METHODOLOGY

3.1 INTRODUCTION

In this research, software was developed to automate the aggregate analysis and Superpave mix design process for West Virginia state specifications. The software was then tested using steel slag as the aggregate for an entire mix design. Mixes were prepared at varying asphalt contents until the target of 4.0% VTM was achieved; the rut susceptibility was then tested and compared with acceptable limits. The software validation was achieved by inputting the mix design parameters from previous WVDOT paving contracts and comparing the actual values with the theoretical program output. The following sections of this chapter explain the software development process and the laboratory-testing program conducted in the Asphalt Technology Laboratory of West Virginia University. A flowchart outline of the Superpave mix design process is presented in Figure 3.1, detailing all of the necessary steps to complete an entire design. This outline was used as a guideline in the development of the spreadsheet and the software. The program screen captures are presented in Appendix A, the Superpave Calculator user's manual comprises Appendix B and the steel slag mix design data is presented in Appendix C.

3.2 SPREADSHEET DEVELOPMENT

All of the necessary equations to perform a complete Superpave mix design are presented in Section 2.2. Throughout the design process, many of these calculations must be repeated numerous times. An Excel spreadsheet, which contained each of these equations, was created to streamline the mix design process. The program was designed so that the data input boxes and output fields were identified and the formula cells were protected. Final results were returned in specific, labeled locations along with an indication of whether the results were within specification limits. After all formulas and charts were built into the workbook, the functionality of the program was tested.

Figure 3.1 Superpave Mix Design Process Flow Chart

3.3 SPREADSHEET VERIFICATION

Several different mixes were created using a developmental spreadsheet to verify the accuracy of the equations and identify any formulas that were entered incorrectly. Numerous mix designs were created in the WVU Asphalt Technology Lab, and the workbook was further refined and programming errors were identified and corrected. This spreadsheet worked very well for development, but was not practical for implementation by others. The cells were not protected and each step of the process was on a different worksheet. An interface was required that would remove any interaction with the formulas and limit the user to inputting data and viewing results.

3.4 INTERFACE DEVELOPMENT

Two different software packages were evaluated to create a functional user interface; Visual Basic 6.0 and Visual Basic for Applications (VBA). The interfaces created with VB 6.0 did not directly link to the Excel workbook and all formulas were built into each user form. The necessity of repeating each of the formulas in every VB 6.0 user form proved that VBA was a much more practical alternative. A series of user interface forms was created in VBA, with designated input boxes and areas identified for calculated results and acceptability. As presented in Chapter 4, the program was created using a “hub-and-spoke” design instead of a linear procedure. The reasoning behind the hub utilization is that at any time during the mix design process, the user may need to return to an earlier page to change inputs, or view calculated results. In a linear program, this process may require cumbersome movement through numerous sheets. The hub design allows the user to always return to the main page and proceed further, eliminating unnecessary steps. The design also allows the computer to only load the necessary user forms, instead of all of them, which optimizes the memory and reduces processing time. Unique user forms are displayed in Appendix A and described in Appendix B. Their structure limits the data entry of the user, allowing only reasonable and appropriate inputs. The formulas are hidden and all supporting worksheets remained active, but unseen to the user. After the user interface development, the program was again tested for formula validity and operational functionality.

3.5 PROGRAM VALIDATION

The newly created “Superpave Calculator”, with user interface forms and supporting Excel workbook, was tested in the WVU Asphalt Technology Laboratory and with previous WVDOT mix designs. A complete validation example is presented in Chapter Four. Various WVU mix designs utilized the software for limestone and steel slag aggregate mixes, comparing the calculated results to the actual values. Throughout the validation procedures, any programming errors were identified and corrected and functionality and ease of use were maximized.

3.6 STEEL SLAG RESEARCH

Based on interest expressed by International Mill Service, Inc. (IMS), the Asphalt Technology Laboratory agreed to develop a Superpave mix design using 100% steel slag as the aggregate. Due to the density and surface characteristics of slag, the testing and mix design process for slags are more complicated than for conventional aggregates. It was during the development of the slag mix design that the prototype Superpave analysis spreadsheet was created. The methodology applied to the development of the steel slag mix design was to:

1. obtain samples from the supplier,
2. perform the aggregate evaluation test to characterize the material, as described in Chapter 2.2.2-2.2.8,
3. perform the analysis prescribed in the Superpave mix design method to determine the optimum asphalt content, as described in Chapter 2.2.9-2.2.10 and
4. test the designed mix with the Asphalt Pavement Analyzer, described in Chapter 2.2.11.

All of the results of the steel slag research comprise Chapter 5 and Appendix C.

CHAPTER 4 PROGRAM STRUCTURE AND VALIDATION

4.1 SUPERPAVE CALCULATOR STRUCTURE

4.1.1 INTRODUCTION

The Superpave Calculator software was developed using a hub-and-spoke form for the entire mix design process, as presented in Figure 4.1. The process begins at the top left of the figure and proceeds clockwise until the Superpave mix design procedure is completed. There are four main components to the software, which are connected to the Main Choices Page at the central hub:

- The steps that are within 9 o'clock and 12 o'clock on Figure 4.1 receive the input about the report criteria and aggregate data.
- The right side of the hub diagram, between 12 o'clock and 4 o'clock is used for the design aggregate structure (DAS) determination. If no acceptable DAS is found after performing the five steps, the process returns to the option at 12 o'clock and the steps are repeated.
- The bottom left portion of the diagram, between 5 o'clock and 7 o'clock is used for calculation of the optimum binder percentage once a DAS has been determined.
- The left side of the hub diagram, between 8 o'clock and 9 o'clock, shows the final tests performed once an optimum binder percentage is determined. Mixes that do not meet the $\%G_{mm,Nmax}$ criteria must be redesigned with a new DAS; those that fail the TSR test require antistrip and the binder percentage calculations are repeated.

The Superpave Calculator can run on any computer that is adequate for Excel 97 or a later version. The process for installing the software is presented in Appendix B. The installation process will create a shortcut button on the Excel toolbar. Clicking on the shortcut button will launch the Superpave Calculator. After launching the application, an option of creating a new mix design or modifying an existing project is presented. If modification is required, a Windows "File Open" box is displayed; the user selects the appropriate existing project and opens it for changes. If a new mix design is to

be created, the user first enters all of the necessary report data into the appropriate input fields, detailing project number, location data and mix designer. Information about the aggregates and binder, including suppliers, location, type and codes is also required.

4.1.2 MIX DESIGN INFORMATION

Once the report information is entered, the user is prompted to enter all necessary mix design information by way of a series of option buttons. Required parameters include: design level, binder type, traffic ESALs, NMAAS and specific gravity of the binder. The designer has the option to enter data about temperatures, Recycled Asphalt Pavement (RAP) used in the process, and any helpful comments. The user is then linked to the main choices page, which acts as the “hub” of the program, and is returned here after each successive step is completed. The aggregate data, including gradation, bulk and apparent specific gravity is then entered into the proper fields. The software is designed with a maximum of four separate aggregates allowed for a mix design. Data on the aggregate consensus properties, including fine aggregate angularity, coarse aggregate angularity, sand equivalency and flat-and-elongated ratio is entered in the next step of the process, which is evaluated for acceptability when creating blends.

4.1.3 DESIGN AGGREGATE STRUCTURE DETERMINATION

If the user knows the percentage of each aggregate that is used to create the blend, it may be entered during aggregate data entry; otherwise a Design Aggregate Structure (DAS) must be determined. The DAS evaluation begins with selection of three different aggregate blends that meet all necessary criteria. Percentages, which must add to 100%, are entered into the appropriate input boxes, and a graph of the blended gradation is viewed for acceptability. An asphalt content for each of these DAS is then estimated automatically, using a series of equations based on aggregate data. The estimated asphalt contents are then used in experimental tests to determine the maximum theoretical specific gravity (G_{mm}) and the bulk specific gravity (G_{sb}) of each DAS.

Structure of User Interface for Superpave Calculator

Figure 4.1 Structure of User Interface for Superpave Calculator

4.1.4 DESIGN AGGREGATE STRUCTURE VOLUMETRICS

The weights and heights from the tests are then entered into the proper fields. The calculated volumetric output is presented on a separate user form, which compares the actual values with the acceptable tolerances. These volumetric values are then mathematically adjusted to 4.0% Voids in the Total Mixture (VTM) and presented for selection of the best aggregate structure. If none of the DASs pass all of the volumetric requirements, the user is returned to the page for the initial step in determining a DAS. The user then needs to select and evaluate three new DASs. Once an acceptable DAS is identified, the optimum asphalt binder percentage is determined.

4.1.5 VOLUMETRICS USING FOUR DIFFERENT ASPHALT CONTENTS

The user has the option of accepting the computer calculated optimum binder percentage, or entering a different asphalt content. After finalizing the asphalt percentage, the software creates weigh-out sheets for preparing samples for the volumetric evaluation. Maximum theoretical specific gravity samples are created at:

- $P_{b,est} - 0.5\%$
- $P_{b,est}$
- $P_{b,est} + 0.5\%$
- $P_{b,est} + 1.0\%$

$P_{b,est}$ is the estimated optimum binder percentage used for volumetric analysis, as determined during the DAS selection process. After the tests at the four binder percentages are completed, the weights are entered into the appropriate fields and the software performs the calculations. A graph of the asphalt content (AC) versus Voids in the Total Mix (VTM) is created and the interpolated AC value that yields 4.0% VTM is determined. This AC is then used to interpolate the values for Voids in the Mineral Aggregate (VMA), Voids Filled with Asphalt (VFA), Percent of G_{mm} at initial number of revolutions ($G_{mm,Nini}$) and the Dust to Binder Ratio (D/b). If all of the interpolated values are within the mix design limits, the final tests to evaluate acceptability are performed. If the mix fails the mix design limits, the DAS evaluation must be repeated. However, due to the Superpave process, there is a low probability of not finding a suitable asphalt content for a DAS that was selected using the prescribed methodology.

4.1.6 FINAL ACCEPTABILITY TESTING

Upon determining the optimum binder percentage, two final tests are performed to validate the mix. Two maximum theoretical specific gravity tests are run and two samples are compacted to the maximum number of revolutions, N_{max} . The volumetric analysis is performed on these results and the $\%G_{mm,Nmax}$ is compared to the maximum value of 98.0%. The Superpave Calculator identifies an acceptable result by turning the field around the computed $\%G_{mm,Nmax}$ green; failure to meet the criteria is indicated by a red field.

If $\%G_{mm,Nmax}$ is within the limits, the program automatically creates weigh-out sheets for six more compaction samples to perform the Tensile Strength Ratio Test. The user compacts the six specimens, conditions three of them and leaves the other three unconditioned. The split tensile test is performed on all six samples and the average of the conditioned values is divided by the average of the unconditioned samples. This ratio must meet a minimum of 80 percent to be within the tolerance; once again the software indicates acceptable values. If all of the test results yield passing values, the user is finished with the Superpave mix design process and may print the results and exit the software.

4.1.7 SAVING AND EXITING

At any point along the design process, the user may exit the program by simply pressing the “Exit” button on the main choices page. Exiting brings up the final screen in the series, allowing the user to exit with, or without, saving. Pressing the “Exit and Save” button opens Windows “Save As” box in which the user names the file and places it in the selected folder. The exit page also contains a button which automatically prints out the “West Virginia Division of Highways Job Mix Formula for Superpave Hot-Mix Asphalt”, form T400 SP, with all necessary items automatically entered. When exiting the software, the program automatically closes the Excel workbook.

4.2 SOFTWARE VERIFICATION PROCESSES

The Superpave Calculator verification process required an independent three-step procedure. Data with known results were entered into all of the data entry boxes. This ensured that each input field was properly linked to the Excel spreadsheet and all

formulas received the correct data. After the functionality of the software was validated, data sets from existing mix designs from the West Virginia Division of Highways were entered into the program and the theoretical outputs were compared to the calculated WVDOH values. Once the theoretical values were determined to be equivalent to the actual results, the software was implemented in the West Virginia University Asphalt Technology Laboratory, and new mix designs were created. This chapter details the three verification processes, including a data comparison summary.

4.3 PROGRAM FUNCTIONALITY VALIDATION

After completion of the data entry forms, *userforms*, and the Excel spreadsheet, extensive testing was then conducted to verify the proper function of the workbook-*userforms* program. Data sets with known results were entered into the input fields where the corresponding links to Excel were verified and the calculations were checked. This step was not designed to confirm the software's accuracy in estimation of theoretical binder percentages or calculate a design aggregate structure. The purpose of the validation of functionality was to ensure that every text input corresponded with the proper Excel worksheet cell and the output values were returned correctly. Software accuracy confirmation was conducted with WVDOH data.

4.4 ACCEPTABILITY OF SUPERPAVE CALCULATOR RESULTS

Upon completion of the Superpave Calculator program, validation of the methodology and calculations was required. Six data sets from previous WVDOH Superpave mix designs were entered into the software. Three of the designs were full processes and three were determination of optimum asphalt content, given the design aggregate structures (DAS). The results were calculated and compared to the actual values obtained. Of the six mix designs that were entered, the results from the least accurate are presented in Tables 4.1 to 4.3. The average estimated binder percentages for the DAS differed by only 6% and all volumetric calculations were exactly equal. The source of the difference was traced to the method used by the contractor for estimating binder content. The Superpave Calculator accurately applies the models while the contractor's method used an approximation. From empirical testing, the six percent difference between the actual and theoretical values would not change the final optimum binder percentage; therefore both methods yield acceptable results. All interpolated

values were consistent with the DOH estimates. The final volumetrics and necessary test results were also exactly equal to the DOH values. All input data sets, estimated results and actual values are presented in the following tables, along with the actual and Superpave Calculator T400 SP summary sheets in Figures 4.2 and 4.3.

4.5 LABORATORY VALIDATION OF SOFTWARE

To further validate the program, the Superpave Calculator was used for developing mix designs in the Asphalt Technology Laboratory. The majority of the lab testing was performed with steel slag as the only aggregate. However, the software was used to evaluate mix designs prepared for other projects in the Asphalt Technology Laboratory that contained limestone and natural sand. All of the data sets and results for the steel slag evaluation are presented in Appendix C. These results are discussed in Chapter 5.

Table 4.1 Data Used for Validation of Superpave Calculator

Report Number:	1349538	Date Accepted:	May 6, 2002													
HMA Type:	9.5 mm (Wearing-I) Skid	HMA Code:	Code													
Producer:	Producer	Plant Location:	Location													
Designed By:	Designer	Design Lab:	Lab													
Plant Type:	Batch	Plant Make:	Make													
Plant Code:	Code	Design ESALs:	3 < 30 Million													
	Source	Code	Agg. Type	Agg. Code												
CA1	Source	Code	#8 Limestone	1135												
FA1	Source	Code	Limestone	1116												
FA2	Source	Code	#9 Limestone	1137												
FA3	Source	Code	Limestone	1116												
Binder	Supplier	Code		1091												
<table border="1" style="margin: auto;"> <tr> <td colspan="2">% Binder in RAP Design</td> <td>None</td> </tr> <tr> <td>Mean Temp. (°F)</td> <td>Min. Temp. (°F)</td> <td>Max. Temp. (°F)</td> </tr> <tr> <td>310</td> <td>285</td> <td>335</td> </tr> <tr> <td>Remarks:</td> <td>None</td> <td></td> </tr> </table>					% Binder in RAP Design		None	Mean Temp. (°F)	Min. Temp. (°F)	Max. Temp. (°F)	310	285	335	Remarks:	None	
% Binder in RAP Design		None														
Mean Temp. (°F)	Min. Temp. (°F)	Max. Temp. (°F)														
310	285	335														
Remarks:	None															
Aggregate Gradations																
	#9 Limestone	L.Sand #1	L. Sand #2	Skid												
Sieve	% Passing	% Passing	% Passing	% Passing												
50.0	100.0	100.0	100.0	100.0												
37.5	100.0	100.0	100.0	100.0												
25.0	100.0	100.0	100.0	100.0												
19.0	100.0	100.0	100.0	100.0												
12.5	100.0	100.0	100.0	100.0												
9.5	100.0	100.0	100.0	94.0												
4.75	75	99.8	100.0	2.8												
2.36	2.5	80.9	75.5	1.6												
1.18	1.5	50.9	43.0	1.5												
0.60	1.4	32.9	23.6	1.4												
0.30	1.3	21.2	12.7	1.3												
0.075	1.2	9.5	6.0	1.1												
Gsb	2.681	2.623	2.652	2.693												
Gsa	2.740	2.749	2.743	2.729												
% of Total Blend																
Blend ID	#9 Limestone	L.Sand #1	L. Sand #2	Skid												
Coarse	14	30	18	38												
Fine	10	46	12	32												
Intermediate	12	38	15	35												

Table 4.2 Comparison of Actual and Theoretical DAS Analysis

Comparison of Actual and Theoretical DAS Analysis								
Actual Initial Percent Binders for 3 DAS (From DOT)			Theoretical Initial Percent Binders for 3 DAS (Using an F-Value of 0.6 for Limestone)			%Difference		
Coarse		5.60%	Coarse		5.83%	4.11%		
Fine		5.60%	Fine		5.93%	5.89%		
Intermediate		5.60%	Intermediate		5.88%	5.00%		
DAS Volumetric Analysis Using an Estimated Binder Percentage of 5.6%								
User Input								
Max. Specific Gravity Data				Bulk Specific Gravity Data				
Sample Weight (g)	Bowl + Sample in Water Weight (g)	Calib. Weight (g)	(All weights in grams, heights in mm)					
			Dry	Wet	SSD	h _{ini}	h _{des}	
DAS #1 (Coarse)	2055.6	2197.3	965.7	4857.6	2821.3	4862.9	133.6	118.5
	2064.2	2202.5	965.7	4888.6	2844.4	4892.2	133.1	118.4
DAS #2 (Fine)	2035.6	2185.3	965.7	4851.9	2820.5	4855.5	131.1	117.0
	2029.9	2181.2	965.7	4859.8	2831.5	4865.4	131.3	117.0
DAS #3 (Interm.)	2015.9	2174.4	965.7	4883.8	2842.1	4887.3	132.4	117.7
	2021.6	2176.9	965.7	4864.0	2829.7	4867.0	132.2	117.5
Volumetric Analysis Summary								
	WVDOT Values			Superpave Calculator Values				
DAS	Av. Gmm	Av. Gmb	Av. % Air	Av. Gmm	Av. Gmb	Av. % Air		
Coarse	2.495	2.384	4.45%	2.495	2.383	4.49%		
Fine	2.494	2.387	4.29%	2.493	2.387	4.25%		
Intermediate	2.496	2.388	4.33%	2.496	2.388	4.33%		
From the Volumetric Data, the <u>Intermediate Blend</u> is Chosen for Further Mix Design Analysis								
Percent Binder	WVDOT Value			Superpave Calculator Value				
	5.70%			5.73%				
Percent Difference			0.53%					

Table 4.3 Comparison of Optimum Binder Percentage Analysis and Final Test Results

User Input											
P _b	Max. Specific Gravity Data			Bulk Specific Gravity Data							
	Sample Weight (g)	Bowl + Sample in Water Weight (g)	Calib. Weight (g)	(All weights in grams, heights in mm)							
				Dry	Wet	SSD	h _{ini}	h _{des}			
	5.2%	2049.3	2197.0	965.7	4916.9	2854.0	4926.0	133.4	119.3		
		2036.9	2191.6	965.7	4887.4	2833.1	4894.7	133.4	118.8		
	5.7%	2055.3	2195.6	965.7	4859.6	2827.5	4863.7	131.6	117.1		
		2061.3	2199.1	965.7	4881.7	2847.3	4884.7	131.7	117.2		
	6.2%	2065.3	2195.3	965.7	4887.0	2861.7	4889.0	130.9	116.3		
		2049.9	2185.3	965.7	4908.1	2874.4	4910.6	131.8	117.0		
	6.7%	2025.9	2165.0	965.7	4852.5	2846.6	4854.7	129.6	115.1		
2036.9		2169.9	965.7	4821.8	2826.6	4823.8	129.0	114.6			
Volumetric Analysis Summary											
P _b		WVDOT Values			Superpave Calculator Values						
5.2%		Av. Gmm	Av. Gmb	Av. % Air	Av. Gmm		Av. Gmb	Av. % Air			
5.7%		2.509	2.372	5.46%	2.508		2.372	5.42%			
5.7%		2.490	2.392	3.94%	2.490		2.391	3.98%			
6.2%		2.470	2.411	2.39%	2.470		2.410	2.43%			
6.7%		2.449	2.415	1.39%	2.449		2.415	1.39%			
Interpolated Optimum Percent Binder											
		WVDOT Value			Superpave Calculator Value						
		5.7%			5.7%						
%G _{mm,Nmax} at Optimum Percent Binder											
P _b	Max. Specific Gravity Data			Bulk Specific Gravity Data							
	Sample Weight (g)	Bowl + Sample in Water Weight (g)	Calib. Weight (g)	(All weights in grams, heights in mm)							
				Dry	Wet	SSD	h _{ini}	h _{des}			
	5.7%	2055.3	2195.6	965.7	4857.4	2857.7	4859.4	131.6	115		
		2061.3	2199.1	965.7	4851.4	2857.1	4853.3	131.2	114.7		
	Tensile Strength Ratio										
			WVDOT Value			Superpave Calculator Value					
			97.5%			97.5%					
			Wet Tensile Strength (kN)			22.5		22.5		20.8	
			Dry Tensile Strength (kN)			23.8		22.6		23.8	
		WVDOT Value			Superpave Calculator Value						
		93.7%			94.0%						

T400 SP
03-00

WEST VIRGINIA DIVISION OF HIGHWAYS JOB MIX FORMULA FOR SUPERPAVE HOT-MIX ASPHALT

Report Number:	1349538	Date Accepted:	May 6, 2002
HMA Type:	9.5 mm (Wearing-I) Skid	HMA Code:	
Producer:		Plant Location:	
Designed By:		Design Lab:	
Plant Type:	Batch	Plant Make:	
Plant Code:		Design ESALs:	3 < 30 Million

MIX COMPOSITION						
Coarse Aggregate Source		Code	Fine Agg. / Mineral Filler Source		Code	
CA ₁			FA ₁			
CA ₂			FA ₂			
CA ₃			FA ₃			
	CA ₁	CA ₂	CA ₃	FA ₁	FA ₂	FA ₃
Agg. Type	#8 Limestone			Limestone	#9 Limestone	Limestone
Agg. Code	1135			1116	1137	1116
% Total Agg.	35			38	15	12
% RAP Total Agg.:		Blended Binder G*/sin delta if > 25% RAP:				
% Binder In RAP Design:		Binder Type:		PG 70-22	Binder Code:	1091
Binder Source:		Binder Source Code:				

Sieve Fraction								Fines / Effective	Tensile	
Sieve Size	Target	Allowable		Sieve Size	Target	Allowable		Asphalt Ratio	Strn. Ratio	
		Min.	Max.			Min.	Max.	1.0	93.7	
2" (50 mm)				#4 (4.75 mm)	63		90	Temperature Range Completed Mixture (°F)		
1.5"(37.5mm)				#8 (2.36 mm)	42	36	48			
1" (25 mm)				#16 (1.18 mm)	26			Desirable	Temp. Range	
3/4" (19 mm)				#30 (600 µm)	16			Mean Temp.	Min.	Max.
1/2"(12.5mm)	100	100	100	#50 (300 µm)	10			310	285	335
3/8" (9.5 mm)	98	90	100	#200 (75 µm)	5	2	10			

JOB MIX FORMULA VALUES					
Job Mix Formula Targets				Job Mix Formula Tolerances	
Specific gravity stone bulk (Gsb): 2.658	Design Property	Accepted Target		Minimum	Maximum
	Asphalt (%)	5.7		5.3	6.1
Maximum	Air Voids (%)	4.0		2.8	5.2
Density (kg/m³)	VMA (%)	15.5		14.5	16.5
2491	VFA (%)	74		73	76
Gyrations @ N _{initial} :	8	Gyrations @ N _{design} :	100	Gyrations @ N _{max} :	160

Remarks:

Figure 4.2 Actual Job Mix Formula Sheet for Superpave Mix Design

1400 SP
03-00

**WEST VIRGINIA DIVISION OF HIGHWAYS
JOB MIX FORMULA FOR SUPERPAVE HOT-MIX ASPHALT**

Report Number:	1349538	Date Accepted:	May 6, 2002
HMA Type:	9.5mm (Wearing-I) Skid	HMA Code:	13967
Producer:	Producer	Plant Location:	Location
Designed By:	Designer	Design Lab:	Lab
Plant Type:	Batch	Plant Make:	Make
Plant Code:	Code	Design ESALs (Millions):	3<30

MIX COMPOSITION						
Coarse Aggregate Source			Code	Fine Agg. / Mineral Filler Source		
CA ₁	Supplier		Code	FA ₁	Supplier	
CA ₂				FA ₂	Supplier	
CA ₃				FA ₃	Supplier	
	CA ₁	CA ₂	CA ₃	FA ₁	FA ₂	MIN. FILL
Aggregate Type	#8 L-Stone			Limestone	#9 L-Stone	Limestone
Aggregate Code	1135			1116	1137	1116
% Total Aggregate	35.0%			38.0%	15.0%	12.0%
% RAP Total Agg:	N/A		Blended Binder G*/sin delta if > 25% RAP:			N/A
% Binder in RAP Design:	N/A		Binder Type:	PG 70-22	Binder Code:	1091
Binder Source:	Binder Supplier				Binder Source Code:	Code

Sieve Fraction								Fines/Effective Asphalt Ratio	Tensile	
Sieve Size	Target	Allowable		Sieve Size	Target	Allowable			Strn. Ratio	
		Min.	Max.			Min.	Max.			
								1.0	94.0	
2" (50mm)				#4 (4.75mm)			80	Temperature Range Completed Mixture (°F)		
1.5" (37.5mm)				#8" (2.36mm)	42.5	30	55			
1" (25mm)				#16 (1.18mm)				Desirable Mean Temp.	Temp. Range	
3/4" (19mm)				#30 (600µm)					Min.	Max.
1/2" (12.5mm)	100	100	100	#50 (300µm)				310	285	335
3/8" (9.5mm)	92.5	85	100	#200 (75µm)	5.5	2	9			

JOB MIX FORMULA VALUES				
Job Mix Formula Targets			Job Mix Formula Tolerances	
Specific gravity stone	Design Property	Accepted Target	Minimum	Maximum
bulk (Gsb): 2.658	Asphalt (%)	5.7	5.3	6.1
Maximum Density	Air Voids (%)	4.0	2.5	5.5
(kg/m ³)	VMA (%)	16.0	15.0	17.0
2490.0	VFA (%)	74.5	73.0	76.0
Gyrations @ N _{initial} :	8	Gyrations @ N _{design} :	100	Gyrations @ N _{max} :
				160

Remarks: This is a re-creation of an existing mix, to test software accuracy

Figure 4.3 Job Mix Formula Sheet for Superpave Mix Design Created by the Software

CHAPTER 5 MIX DESIGN OF STEEL SLAG ASPHALT

5.1 MATERIALS AND PREPARATION

The steel slag aggregates used for the entire research project were obtained from International Mill Service, Inc. (IMS), Weirton WV, and consisted of two types: #57 (coarse) slag and #10 (fine) slag. Blends of the two aggregate types were used in each mix design, then tested for volumetric analysis and rut susceptibility. The asphalt used for each design trial was PG 64-22 obtained from Marathon, Ashland, OH. Processing the aggregates consisted of sieving, washing, and oven drying. The aggregates were separated with a nest of sieves, consisting of: 1", 3/4" 3/8" #4, #8, #16, #30, #50, #200 and pan. The material retained on each sieve and pan was placed into storage bins.

5.2 AGGREGATE PROPERTIES

The sieve analysis of the two steel slag aggregates used in this research is shown in Table 5.1 and a summary of the specific gravities of all aggregates used is presented in Table 5.2. Graphs of each blended gradation are found in Appendix C.

Table 5.1 Dry Sieve Gradation Analysis Results

Sieve No.	Percent Passing (%)		Sieve Size (mm)
	IMS #57 Slag	IMS #10 Slag	
2"	100.0	100.0	50
1.5"	100.0	100.0	37.5
1"	100.0	100.0	25
3/4"	87.9	100.0	19
1/2"	41.0	100.0	12.5
3/8"	13.6	100.0	9.5
#4	4.1	96.0	4.75
#8	4.0	73.9	2.36
#16	0.0	57.6	1.18
#30	0.0	40.3	0.6
#50	0.0	25.4	0.3
#200	0.0	10.6	0.075
Pan	0	0	0

Table 5.2 Calculated Steel Slag Specific Gravity and Absorption Values

	3/4"	1/2"	3/8"	#4	Fines
Bulk Specific Gravity (Oven Dry Basis)	3.367	3.345	3.296	3.206	2.880
Bulk Specific Gravity (Saturated-Surface-Dry Basis)	3.417	3.400	3.363	3.298	3.087
Apparent Specific Gravity	3.543	3.540	3.532	3.531	3.634
Absorption, percent	1.48%	1.65%	2.02%	2.87%	7.21%

5.3 INITIAL MIX DESIGN TRIALS USING STEEL SLAG

After obtaining the required steel slag aggregate from IMS, and performing the necessary preparations, the Superpave Calculator was used to determine the initial asphalt content. Previous research has demonstrated that, for limestone mixes, an absorption value of 0.6-0.8 can be used to perform the necessary binder estimation calculations (Harman, et al., 1999). Since the effect of asphalt cement on the IMS steel slag was unknown, an assumption that the absorption behavior matched limestone was used. The first tests were considered asphalt absorption trials, to further understand the nature of the aggregate in order to more accurately predict an initial asphalt estimate. The first trial aggregate blend consisted of 64% #57 and 36% #10 slag, which is displayed in Figure C.1, and the software estimated a binder percentage of 6.5%. All necessary testing was performed to determine the volumetrics of this mix with the full results presented in Appendix C and a summary in Table 5.3.

Table 5.3 Trial 1 Volumetric Summary

Trial 1 - Volumetrics			
64% #57 Slag & 36% #10 Slag 6.5% AC			
Category	Tolerance	Values	Passing
VTM	~4%	0.27%	NO
VMA	13% min	10.41%	NO
VFA	65%-75%	97.45%	NO
D/B	0.60-1.20	1.09	YES

From the summary in Table 5.3, it is obvious that the main criterion in determining mix acceptability, the Voids in the Total Mix (VTM) value does not approach the required value of 4.0%. This lack of air voids in the mix is indicative of an excessive amount of binder. The binder was reduced by 1.0% for the next trial.

5.4 DAS #1

For the next three trials, the binder percent was adjusted from 6.5% to 5.5%, to 5.0% then to 4.5%, in order to increase the value of VTM to 4.0%. The design aggregate structure from trial one was used for all three trials, with volumetric analysis performed on each blend. The full results of these tests are presented in Appendix C and a summary is shown in Table 5.4.

Table 5.4 Trials 2,3 & 4 Volumetric Summary

64% #57 Slag & 36% #10 Slag							
Category	Tolerance	Trial 2 5.5% AC		Trial 3 5.0% AC		Trial 4 4.5% AC	
		Values	Passing	Values	Passing	Values	Passing
VTM	~4%	1.08%	NO	1.61%	NO	3.57%	YES
VMA	13% min	8.44%	NO	7.52%	NO	7.81%	NO
VFA	65%-75%	87.26%	NO	78.56%	NO	54.29%	NO
D/B	0.60-1.20	1.52	NO	1.91	NO	2.63	NO

This iterative decrease in the binder percentage yielded an acceptable air content, but none of the other criteria were close to being within the tolerances. The binder percentage was approaching the proper value, but the aggregate structure was producing an extremely high dust to binder ratio and low VFA and VMA values. Graphs of the volumetrics for the first design aggregate structures at the three asphalt contents were created, in order to linearly interpolate if a theoretical asphalt content would result in all volumetric criteria being satisfied. These graphs are presented in Figures 5.1-5.3.

Figure 5.1 Interpolation of VTM v/s Percent Binder

Figure 5.2 Interpolation of VMA v/s Percent Binder

Figure 5.3 Interpolation of VFA v/s Percent Binder

From an examination of the three linear interpolations, the binder content for VTM is 4.0%-4.5%, for VMA is >8% and for VFA is 4.5%-5.0%. From these values, it was determined that the minimum VMA value would never be satisfied if the VTM and VFA tolerances were met. Based on this inference, along with the fact that the D/b value was double the highest limit, a decision was made to adjust the design aggregate structure.

5.5 DAS #2

To reduce the D/b value, the aggregate structure was made coarser to reduce the amount of dust in the mix, but the binder percentage was held constant at 4.5%. The new blend consisted of 72% #57 and 28% #10 slag, presented in Figure C.2, which still met all criteria, but was much nearer the lower limits of acceptability. The necessary tests were performed on this new DAS and the volumetrics were calculated. The full results of these tests are presented in Appendix C and a summary is shown in Table 5.5.

Table 5.5 Trial 5 Volumetric Summary

Trial 5 - Volumetrics			
72% #57 Slag & 28% #10 Slag 4.5% AC			
Category	Tolerance	Values	Passing
VTM	~4%	4.84%	YES
VMA	13% min	9.43%	NO
VFA	65%-75%	48.62%	NO
D/B	0.60-1.20	1.88	NO

The increase in the coarse aggregate in the mix reduced the D/b and increased the VTM and VMA percentages, but reduced the VFA. Realizing that the necessary air content was achievable, the challenge was increasing VMA and VFA, while decreasing D/b. The asphalt content would require further reduction to meet the criteria. Another issue arose with all of the binder and aggregate adjustments; there was a noticeable increase in mixing difficulty with the decreasing binder percentages. Mixing a sample with only 4.0% asphalt content would have been nearly impossible, thus a new approach was decided to achieve the optimum air content.

5.6 DAS FROM LITERATURE TO DETERMINE OPTIMUM BINDER PERCENTAGE

A new aggregate structure was needed if the criteria were to be met. After reviewing various articles on steel slag hot mix asphalt design, a possible gradation and binder percentage, used in South Carolina, which yielded 4.2% VTM and acceptable volumetric criteria was selected (Hanson and Lynn, 1995). The aggregates used in the literature had nearly the same specific gravities as the IMS slag and the absorption percentages were comparable. The gradation is presented in Table 5.6

Table 5.6 Steel Slag Gradation from Literature Review

	Percent Passing (%)	
Sieve No.	IMS Slag	Sieve Size (mm)
2"	100.0	50
1.5"	100.0	37.5
1"	100.0	25
3/4"	97.0	19
1/2"	89.4	12.5
3/8"	73.0	9.5
#4	53.0	4.75
#8	37.0	2.36
#16	28.0	1.18
#30	23.0	0.6
#50	17.0	0.3
#200	6.0	0.075
Pan	0	0

Two samples were made using the gradations in Table 5.6. This gradation could not be created by blending the IMS coarse and fine aggregate, but it was evaluated to determine if a slag mix could be found which meets the Superpave criteria. The literature recommended using 7.0% asphalt content with the above gradation. The necessary tests were performed and the volumetrics were calculated. The full results of both tests are presented in Appendix C and a summary of averages is shown in Table 5.7.

Table 5.7 Trial 6 Average Volumetric Summary

Trial 6 - Volumetrics			
Gradation from Literature 7.0% AC			
Category	Tolerance	Values	Passing
VTM	~4%	0.39%	NO
VMA	13% min	16.45%	YES
VFA	65%-75%	97.61%	NO
D/B	0.60-1.20	1.12	YES

After examining the three design aggregate structures and the varying binder percentages tried, a conclusion was reached that a mix design cannot be created using only IMS steel slag as the aggregate. The slag used in the research, although having

similar properties to the slag in the literature review, did not behave in the same manner. It was hypothesized that a reduction in binder percentage would increase the VTM to 4.0%, but decrease the VMA and increase the D/b values. The literature gradation was then abandoned and DAS #2 was again tried, at 4.5% to evaluate rut susceptibility.

5.7 EVALUATION OF RUT SUSCEPTIBILITY AND CONCLUSIONS

Six compaction samples were created with 7.0% VTM and subjected to 8000 wheel passes in the Asphalt Pavement Analyzer (APA). The pavement deformation was then measured and compared with acceptable limits. The full results of the rut testing are presented in Appendix C and a summary is presented in Table 5.8.

Table 5.8 Average Rut Deformation

Criteria	G_{mb}	%Air	Rut Depth (mm)
Averages	2.948	7.22%	7.69

The average rut deformation of 7.69 mm is high when compared to the acceptable high limit of 6.0 mm. The high rut susceptibility, combined with not meeting all four volumetric criteria at any time, make an asphalt mixture created with only IMS steel slag as the aggregate an unfeasible task. An acceptable mix design requires the addition of other aggregate types in order to meet volumetric limits and minimize rutting.

CHAPTER 6 CONCLUSIONS/RECOMMENDATIONS

6.1 CONCLUSIONS

Based on the laboratory effort and computer program creation, the following conclusions were made:

- The Superpave mix design is a complex process, best suited for computer analysis.
- The Superpave Calculator software program is an excellent tool for predicting design aggregate structure initial binder percentages.
- The software streamlines volumetric analysis and combines all necessary charts and graphs along with the limits and restrictions.
- Using the Visual Basic for Applications approach to software development, it is easy to modify and keep the limits and specifications current.
- The software is freely available to anyone and the West Virginia Division of Transportation may use it as needed. It can be accessed either electronically through WVU Asphalt Technology website, [<http://www2.cemr.wvu.edu/~wwwasph/>]
- An automated Superpave mix design process will provide a uniform submittal format and will be able to be transmitted and stored electronically.
- A mix design consisting entirely of IMS steel slag as the aggregate does not meet all necessary volumetric criteria or provide adequate rut resistance.
- A functional IMS steel slag asphalt mix design must include some mineral filler or bag house fines to meet the D/b criteria.

6.2 RECOMMENDATIONS

After developing the Superpave Calculator and performing the mix design research on steel slag, the following recommendations are suggested:

- The software may be utilized for all future mix designs created in the West Virginia University Asphalt Technology Laboratory.
- The Superpave Calculator can be used to demonstrate the mix design steps for a university class or a Superpave workshop.

- After the software is distributed around the state, mix design data may be submitted to the DOH electronically in Excel format.
- Superpave is an evolving technology and it will be necessary to monitor and maintain the Superpave calculator to keep pace with these developments.
- The evaluation of the steel slag aggregate performed during this research did not produce an acceptable Superpave mix design. However, this material, when blended with other aggregates, has been used for Marshall mix designs. Therefore, potential for developing a Superpave mix design exists, but further research is needed.

REFERENCES

- AASHTO T 209-99, “Theoretical Maximum Specific Gravity and Density of Bituminous Paving Mixtures”. *Standard Specifications for Transportation Materials and Methods of Sampling and Testing 28th Edition*, Washington D.C.: AASHTO, 2000.
- AASHTO T P4, “Method for Preparing and Determining the Density of HMA Specimens by Means of the Superpave Gyratory Compactor”. *Standard Specifications for Transportation Materials and Methods of Sampling and Testing 28th Edition*, Washington D.C.: AASHTO, 2000.
- AASHTO, *AASHTO Ware Catalog July 1, 2002- June 30, 2003*.
[\[http://www.aashtoware.org/aashtoware/downloads/catalog_2003.pdf\]](http://www.aashtoware.org/aashtoware/downloads/catalog_2003.pdf)
 Accessed December 3, 2002
- Ali, N.A., Chan, J.S.S, Papagiannakis, T., Theriault, E.G., and Bergan, A.T., “The Use of Steel Slag in Asphaltic Concrete”, *Effects of Aggregates and Mineral Fillers on Asphalt Mixture Performance, ASTM STP 1147*, R. C. Meininger, editor, American Society for Testing and Materials, Philadelphia, PA 1992.
- Baird, R. R. *Ancient Routes*. 2000 [<http://www.ancientroute.com/resource/Asphalt.htm>].
 Accessed Nov. 10, 2002.
- Ciesielski, S. K., *Case Histories of Solid Waste Industrial Slags Used in Hot Mix Asphalt Concrete Pavements*, Villanova University. Villanova, PA 1996.
- Emery, John, “Steel Slag Utilization in Asphalt Mixes”. Canadian Technical Asphalt Association Proceedings. Toronto, Ontario 1984.
- Federal Highway Administration. *Implementation Survey IV, 1999-2000*. July 2000
[\[http://ce.ecn.purdue.edu/~spave/Technical%20Info/Meetings/Imp99-00.htm\]](http://ce.ecn.purdue.edu/~spave/Technical%20Info/Meetings/Imp99-00.htm).
 Accessed Nov. 10, 2002.
- Harman, T., D’Angelo, J., Bukowski, J. *Superpave Asphalt Mixture Design Workshop*. Federal Highway Administration. 1999.
[\[http://www.tfhrc.gov/pavement/asphalt/prodrsrch/mixturedesign/mixdsngn.pdf\]](http://www.tfhrc.gov/pavement/asphalt/prodrsrch/mixturedesign/mixdsngn.pdf).
 Accessed Nov. 10, 2002.

- Hanson, D. I., Lynn, C. R., “Study to Improve Asphalt Mixes in South Carolina”, *Volume 2- A Study of Crushed Slag Aggregates in Hot Mix Asphalt*, National Center for Asphalt Technology, Auburn University, Auburn, AL 1995.
- Hegmon, R.R., Ryan, P.F., “The Polishing Resistance of Selected Slag Aggregates”, Report No. S37. The Pennsylvania State University. University Park, PA 1984.
- Jacobson, R. *Microsoft Excel 97 Visual Basic Step by Step*. Redmond, WA 1997.
- Lee, A.R., *Blast Furnace and Steel Slag*, New York, NY 1974.
- Masters, G. *Visual Basic 6 Complete*. Sybex, San Francisco, CA 1999.
- McGannon, H. E., editor *The Making, Shaping and Treating of Steel*. “Slags in Iron and Steelmaking”, Ninth Ed. United States Steel Corporation. Herbeck and Held: Pittsburgh, PA 1971.
- Noureldin, A.S., “Evaluation of Surface Mixtures of Steel and Slag Asphalt”. Transportation Research Record 1269, National Research Council, Washington, D.C 1990.
- Pine Instrument Company, *AFGC125X Gyratory Compactor Operation Manual*. “Pine-Pave User’s Guide Version 4.00” Grove City, PA. 1998.
- Ramirez, T. L., “Research Project No. 79-012”, *Steel Slag Aggregates in Bituminous Mixtures Final Report*, Commonwealth of Pennsylvania Department of Transportation, Harrisburg, PA. 1992.
- Roberts, F. L., Kandhal, Prithvi, S., Brown, E.Ray, Lee, Dah-Yinn, Kennedy, Thomas W. *Hot Mix Asphalt Materials, Mixture Design and Construction*. NAPA Education Foundation, Lanham, MD. 1996.
- Rock Binder’s Inc., *Asphalt Origins* [<http://www.rockbinders.com/asphalt.html>]. Accessed Nov. 10, 2002.
- Schneider, D. I., *An Introduction to Programming Using Visual Basic 6.0 Fourth Edition*. Prentice Hall, Upper Saddle River, NJ. 1999.
- WVDOT Materials Procedure 401.02.28. *Guide to Designing Hot-Mix Asphalt Using the Superpave Volumetric Design System*. Charleston, WV. 2000.

West Virginia Division of Highways Standard Specifications for Roads and Bridges.

Division 400- Bituminous Mixes, Section 401.4.2 Plant Mix Formula. Charleston, WV. 2000.

Zaniewski, J. P., Superpave Mix Design Workshop West Virginia University, Morgantown, WV. 2002.

APPENDIX A

SCREEN SHOTS FROM SUPERPAVE CALCULATOR

Figure A.1 Introduction to Superpave Calculator

Superpave Report Information

Superpave Calculator -Mix Design Report Information

Report Number:	Trial #1	Date Accepted:	1/1/2003
HMA Type:	WCT-1 (Skid)	HMA Code:	72289
Producer:	WVU Asphalt Lab	Plant Location:	Morgantown, WV
Designed By:	M. Padula	Design Lab:	WVU Asphalt Technology Lab
Plant Type:	Test Size Batch	Plant Make:	Bituma-Gencor
Plant Code:	WVU2002		

	Source:	Source Code:	Agg Type:	Code:
CA 1	International Mill Service, Weirton, WV	S044E	#57 Slag	1186
CA 2	International Mill Service, Weirton, WV	S044E	#10 Slag	1173
FA 1	Martin Marietta, Applegrove, OH	T012B	Limestone Sand	1115
FA 2	Standard Lafarge, Weirton, WV	S044C	Slag Sand	1114
Binder	Asphalt Materials, Inc. Marietta, OH	A0380	Binder Code:	1093

Print Form Choices Page

Figure A.2 Superpave Report Information

Superpave Destination Worksheets

New Mix Design Steps (*Required*)

1. Fill Out Mix Design Information Worksheets Report Info
2. Fill Out Consensus Aggregate Properties Acceptability Worksheet Agg Prop
3. Enter the gradations and Gs of each Agg into the Worksheet (And DAS Percentages if known) Agg

☒ Check to Use the DAS Selection Worksheets

DAS Selection (Optional if already known)

4. Find 3 acceptable DAS, using chart and limits Chart
5. View the three selected Design Aggregate Structures plotted together DAS Chart
6. Initial Asphalt Content Estimating Worksheet for each DAS DAS ACE
7. Do 2 Rice tests and make 2 Pills using each DAS and estimated AC WO Sheets
8. Enter the data from the Rice and Pill Tests into the DAS data entry worksheet DAS Data
9. Analyze the Rice and Pill data for Acceptability DAS Test
10. View Adjusted Volumetrics and Select DAS Pick DAS

Mix Design Steps if DAS and Pb,est are Known

* If using user entered DAS, Estimate Pb Necessary Pb, est

11. Confirm Design Aggregate Structure and Pb, est Confirm
12. Do 2 Rice tests and make 2 Pills at four asphalt contents Pb WO Sheets
13. Enter the data from the Rice and Pill Tests into the Percent Binder data entry worksheet Pb Data
14. Analyze the Rice and Pill data for Acceptability Pb Volumetrics
15. View the Volumetric Graphs and Interpolate to determine if passing criteria Interpol. Plots
16. View the chart of the Interpolated Values to determine if passing volumetric criteria Interpol. Chart
16. Do 2 Rice tests and make 2 Pills at the Optimum AC Opt WO Sheets
17. Enter the data from the Rice and Pill Tests into the Optimum AC data entry worksheet Opt AC Data
18. Check %Gmm, Nmax < 98% Gmm, Nmax Val.
19. Check TSR > 0.8 TSR Test

Exit the Superpave Calculator Exit

Figure A.3 Superpave Calculator Worksheet Choices

Superpave Information Sheet

Superpave Calculator -Mix Composition Information

Skid Design: ☒ Yes ☐ No

Binder Grade: ☐ PG 58-28 ☒ PG 64-22 ☐ PG 70-22 ☐ PG 76-22

Depth from Surface: ☒ ≤ 100 mm ☐ > 100 mm

Traffic ESALs (Millions) ☐ < 0.3 ☐ 0.3 to < 3 ☐ 3 to < 10 ☐ [10 to < 20] ☒ 10 to < 30 ☐ ≥ 30

Mix Type (NMAS) ☐ 37.5 mm ☐ 25 mm ☒ 19 mm ☐ 12.5 mm ☐ 9.5 mm ☐ 4.75 mm

Min. Mix Temperature (°F): Max. Mix Temperature (°F):

Specific Gravity of Binder:

RAP Information (If Necessary)

% RAP Total Agg: Blended Binder G*/sin delta if > 25% RAP:

% Binder in RAP Design:

Print Form

Choices Page

Remarks:

Figure A.4 Mix Information Worksheet

Calculated Aggregate Properties

Superpave Calculator - Calculated Aggregate Consensus Properties Worksheet

User Entered Mix Parameters

ESAL (Millions)	10 < 30	Binder Grade Used	PG 64-22
Depth from Surface	<= 100 mm	Skid Design	Skid Design

	Limits		User Entered Properties (Averages)		Passing? (Yes/No)	
	Minimum Percent with 1 Fractured Face	Minimum Percent with 2 Fractured Faces	Minimum Percent with 1 Fractured Face	Minimum Percent with 2 Fractured Faces	Minimum Percent with 1 Fractured Face	Minimum Percent with 2 Fractured Faces
Coarse Aggregate Angularity(%)	95.0%	90.0%	96.0	93.0	YES	YES
Fine Aggregate Angularity (%)	45.0%		52.0		YES	
Flat and Elongated Test (%)	10.0%		8.0		YES	
Sand Equivalency Test (%)	45.0%		63.0		YES	

Print Form

Choices Page

Figure A.5 Calculated Aggregate Consensus Properties Worksheet

Aggregate Data Worksheet

Superpave Calculator - Aggregate Data Worksheet

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge	
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand	
Sieve Size		Percent Passing				
50 mm	2"	100	100	100	100	
37.5 mm	1.5"	100	100	100	100	
25 mm	1"	100	100	100	100	
19 mm	3/4"	87.5	100	100	100	
12.5mm	1/2"	41.4	100	100	100	
9.5 mm	3/8"	4.3	100	100	100	
4.75 mm	#4	4.1	96.7	100	96	
2.36 mm	#8	0	74.9	75	73.9	
1.18 mm	#16	0	60.6	46	57.6	
0.6 mm	#30	0	41.6	30	40.3	
0.3 mm	#50	0	24.5	18	25.4	
0.075	#200	0	10.6	7.5	10.6	
Pan	Pan	0	0	0	0	
		Combined Totals				
Gsb		3.298	2.880	2.592	2.621	3.061
Gsa		3.516	3.634	2.678	2.717	3.450
Percent		55.00%	35.00%	5.00%	5.00%	100.00%

Print Form

Choices Page

Figure A.6 Aggregate Data Worksheet

Figure A.7 Aggregate Gradation Chart

Figure A.8 Plot of 3 DAS Plotted Together

Asphalt Content Estimator for Design Aggregate Structures

Superpave Calculator - Asphalt Content Estimator for Design Aggregate Structures

DAS #1		DAS #2		DAS #3	
Blended Bulk S.G. (Gsb)	3.078	Blended Bulk S.G. (Gsb)	2.955	Blended Bulk S.G. (Gsb)	3.061
Blended Apparent S.G.(Gsa)	3.446	Blended Apparent S.G.(Gsa)	3.247	Blended Apparent S.G.(Gsa)	3.450
F- (Absorption Adj. Factor)	0.8	F- (Absorption Adj. Factor)	0.8	F- (Absorption Adj. Factor)	0.8
☐ Click Here to Change F Value		☐ Click Here to Change F Value		☐ Click Here to Change F Value	
Effective Specific Gravity (Gse)	3.372	Effective Specific Gravity (Gse)	3.188	Effective Specific Gravity (Gse)	3.373
Percent Stone	93.60%	Percent Stone	93.80%	Percent Stone	93.40%
Volume of Air (Va) ☐ Change Va	4.00%	Volume of Air (Va) ☐ Change Va	4.00%	Volume of Air (Va) ☐ Change Va	4.00%
Specific Gravity of Binder	1.033	Specific Gravity of Binder	1.033	Specific Gravity of Binder	1.033
Volume of Absorbed Binder (Vba)	0.075	Volume of Absorbed Binder (Vba)	0.063	Volume of Absorbed Binder (Vba)	0.079
Nominal Maximum Agg. Size (Sn)	19	Nominal Maximum Agg. Size (Sn)	19	Nominal Maximum Agg. Size (Sn)	19
Volume of Effective Binder (Vbe)	0.090	Volume of Effective Binder (Vbe)	0.090	Volume of Effective Binder (Vbe)	0.090
Estimated Weight of Stone (Ws)	2.510	Estimated Weight of Stone (Ws)	2.411	Estimated Weight of Stone (Ws)	2.495
<input type="button" value="Update Values"/>		<input type="button" value="Update Values"/>		<input type="button" value="Update Values"/>	
Est. Total % Binder (Pb-Total)	6.35%	Est. Total % Binder (Pb-Total)	6.14%	Est. Total % Binder (Pb-Total)	6.54%

Figure A.9 Asphalt Content Estimator for Design Aggregate Structure

Weigh-Out Sheets for Design Aggregate Structure Volumetrics

Aggregate Weigh Out Sheets DAS Volumetric Tests

**Do 2 Rice tests and make 2 Pills using each DAS and estimated AC
(Using Cumulative or Individual Sieve Weigh-Out sheets below)**

DAS#1 Rice Cumulative Wts.	DAS#2 Rice Cumulative Wts.	DAS#3 Rice Cumulative Wts.
DAS#1 Rice Individual Wts.	DAS#2 Rice Individual Wts.	DAS#3 Rice Individual Wts.
DAS#1 Pill Cumulative Wts.	DAS#2 Pill Cumulative Wts.	DAS#3 Pill Cumulative Wts.
DAS#1 Pill Individual Wts.	DAS#2 Pill Individual Wts.	DAS#3 Pill Individual Wts.

Choices Page

Figure A.10 Weigh-Out Sheets for Design Aggregate Structure Volumetrics

Rice Weigh Out Sheet - Cumulative Sieve Weights for DAS #1

Aggregate Weigh Out Sheet for Rice Test for DAS #1 - (Cumulative Sieve Weights)

Total Sample Weight (g) Final Aggregate Total Weight (g)

Percentage of Binder Used (%) Weight of Asphalt Binder (g)

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	1105.1 g	1685.7 g	1779.4 g
37.5 mm	1.5"	0.0 g	1105.1 g	1685.7 g	1779.4 g
25 mm	1"	0.0 g	1105.1 g	1685.7 g	1779.4 g
19 mm	3/4"	138.1 g	1105.1 g	1685.7 g	1779.4 g
12.5mm	1/2"	647.6 g	1105.1 g	1685.7 g	1779.4 g
9.5 mm	3/8"	1057.6 g	1105.1 g	1685.7 g	1779.4 g
4.75 mm	#4	1059.8 g	1124.2 g	1685.7 g	1783.1 g
2.36 mm	#8	1105.1 g	1250.8 g	1709.1 g	1803.8 g
1.18 mm	#16	1105.1 g	1333.8 g	1736.3 g	1819.1 g
0.6 mm	#30	1105.1 g	1444.2 g	1751.3 g	1835.3 g
0.3 mm	#50	1105.1 g	1543.4 g	1762.5 g	1849.2 g
0.075 mm	#200	1105.1 g	1624.2 g	1772.3 g	1863.1 g
Pan	Pan	1105.1 g	1685.7 g	1779.4 g	1873.0 g

Figure A.11 Sample Rice Weigh-Out Sheet, Cumulative Sieve Weights

Rice Weigh Out Sheet - Individual Sieve Weights for DAS #1

Aggregate Weigh Out Sheet for Rice Test for DAS #1 - (Individual Sieve Weights)

Total Sample Weight (g) Final Aggregate Total Weight (g)

Percentage of Binder Used (%) Weight of Asphalt Binder (g)

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	0.0 g	0.0 g	0.0 g
37.5 mm	1.5"	0.0 g	0.0 g	0.0 g	0.0 g
25 mm	1"	0.0 g	0.0 g	0.0 g	0.0 g
19 mm	3/4"	138.1 g	0.0 g	0.0 g	0.0 g
12.5mm	1/2"	509.4 g	0.0 g	0.0 g	0.0 g
9.5 mm	3/8"	410.0 g	0.0 g	0.0 g	0.0 g
4.75 mm	#4	2.2 g	19.2 g	0.0 g	3.7 g
2.36 mm	#8	45.3 g	126.6 g	23.4 g	20.7 g
1.18 mm	#16	0.0 g	83.0 g	27.2 g	15.3 g
0.6 mm	#30	0.0 g	110.3 g	15.0 g	16.2 g
0.3 mm	#50	0.0 g	99.3 g	11.2 g	14.0 g
0.075 mm	#200	0.0 g	80.7 g	9.8 g	13.9 g
Pan	Pan	0.0 g	61.5 g	7.0 g	9.9 g

Figure A.12 Sample Rice Weigh-Out Sheet, Individual Sieve Weights

Pill Weigh Out Sheet - Cumulative Sieve Weights for DAS #1

Aggregate Weigh Out Sheet for Pill for DAS #1 - (Cumulative Sieve Weights)

Estimated Total Sample Weight (g) ☐ Click to change Sample Wt.

Final Aggregate Total Weight (g)

Percentage of Binder Used (%)

Weight of Asphalt Binder (g)

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	3078.2 g	4695.5 g	4956.4 g
37.5 mm	1.5"	0.0 g	3078.2 g	4695.5 g	4956.4 g
25 mm	1"	0.0 g	3078.2 g	4695.5 g	4956.4 g
19 mm	3/4"	384.8 g	3078.2 g	4695.5 g	4956.4 g
12.5mm	1/2"	1803.8 g	3078.2 g	4695.5 g	4956.4 g
9.5 mm	3/8"	2945.8 g	3078.2 g	4695.5 g	4956.4 g
4.75 mm	#4	2952.0 g	3131.6 g	4695.5 g	4966.8 g
2.36 mm	#8	3078.2 g	3484.1 g	4760.8 g	5024.5 g
1.18 mm	#16	3078.2 g	3715.4 g	4836.4 g	5067.0 g
0.6 mm	#30	3078.2 g	4022.7 g	4878.1 g	5112.1 g
0.3 mm	#50	3078.2 g	4299.3 g	4909.4 g	5151.0 g
0.075 mm	#200	3078.2 g	4524.1 g	4936.8 g	5189.6 g
Pan	Pan	3078.2 g	4695.5 g	4956.4 g	5217.3 g

Figure A.13 Sample Pill Weigh-Out Sheet, Cumulative Sieve Weights1

Pill Weigh Out Sheet - Individual Sieve Weights for DAS #1

Aggregate Weigh Out Sheet for Pill for DAS #1 - (Individual Sieve Weights)

Estimated Total Sample Weight (g) ☐ Click to change Sample Wt. Final Aggregate Total Weight (g)

Percentage of Binder Used Weight of Asphalt Binder

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	0.0 g	0.0 g	0.0 g
37.5 mm	1.5"	0.0 g	0.0 g	0.0 g	0.0 g
25 mm	1"	0.0 g	0.0 g	0.0 g	0.0 g
19 mm	3/4"	384.8 g	0.0 g	0.0 g	0.0 g
12.5mm	1/2"	1419.0 g	0.0 g	0.0 g	0.0 g
9.5 mm	3/8"	1142.0 g	0.0 g	0.0 g	0.0 g
4.75 mm	#4	6.2 g	53.4 g	0.0 g	10.4 g
2.36 mm	#8	126.2 g	352.6 g	65.2 g	57.7 g
1.18 mm	#16	0.0 g	231.3 g	75.7 g	42.5 g
0.6 mm	#30	0.0 g	307.3 g	41.7 g	45.1 g
0.3 mm	#50	0.0 g	276.6 g	31.3 g	38.9 g
0.075 mm	#200	0.0 g	224.8 g	27.4 g	38.6 g
Pan	Pan	0.0 g	171.4 g	19.6 g	27.7 g

Figure A.14 Sample Pill Weigh-Out Sheet, Individual Sieve Weights

Data Entry Form for Rice and Pill Tests for Each DAS

Superpave Calculator - DAS Volumetric Information Entry Worksheet

	Rice Test			Pill Test				
	Sample Weight (g)	Bowl + Sample in Water Weight (g)	Bowl in Water (Calibration Weight) (g)	Weight of Dry Pill (g)	Weight of Submerged Pill (g)	Weight of SSD Pill (g)	Hini (mm)	Hdes (mm)
DAS #1	1906.3	2786.1	1511.1	5504.9	3612.5	5507.4	123.9	113.8
	1983.1	2647	1330	5439.9	3568.6	5442.6	122.8	114.3
DAS #2	1978.9	2642.4	1330	5273.2	3428.2	5278.1	121.2	114.6
	1983.5	2823.7	1511.1	5263.3	3383.4	5267.8	119.7	114.3
DAS #3	1924	2605.8	1330	5472.6	3558.5	5481.7	122.3	116.2
	1985.8	2629.7	1330	5403.8	3464.2	5416.9	120.9	115.7

Print Form Choices Page

Figure A.15 Data Entry Form for Rice and Pill Tests for Each DAS

DAS Pill and Rice Test Analysis Worksheet

Superpave Calculator - Design Aggregate Structure Volumetric Analysis

	DAS #1	DAS #2	DAS #3
Gmm	2.998	2.963	2.931
Gmb	2.904	2.822	2.806
% Air	3.15%	4.76%	4.26%
% Gmm, N des	96.85%	95.24%	95.74%
Effective GS (Gse)	3.443	3.375	3.364
% Binder Abs. (Pba)	3.56%	4.34%	3.04%
% Binder Eff. (Pbe)	3.02%	2.06%	3.70%
% Gmm, N ini	89.55%	90.50%	91.29%
VTM	3.15%	4.76%	4.26%
VMA	11.64%	10.38%	14.32%
VFA	72.94%	54.17%	70.27%
Dust to Binder	1.53	2.24	1.25

Necessary Criteria Summary		Acceptable?		
	Tolerance	DAS #1	DAS #2	DAS #3
VTM	3.00%-5.00%	YES	YES	YES
VMA	13% Min.	NO	NO	YES
VFA	65%-75%	YES	NO	YES
d to B	0.80-1.60	YES	NO	YES

Print Form Choices Page

Figure A.16 DAS Pill and Rice Test Analysis Worksheet

Adjusted Volumetrics for Design Aggregate Structures

Superpave Calculator - DAS Adjusted Volumetric Analysis Worksheet (to 4.00% Air)

	DAS #1	DAS #2	DAS #3
Trial Percent Binder	6.35%	6.14%	6.54%
Estimated Percent Binder (to Achieve 4.00% Air)	6.01%	6.44%	6.64%
VTM (From Vol. Data)	3.15%	4.76%	4.26%
VMA Estimate	11.73%	10.23%	14.27%
VFA Estimate	65.89%	60.90%	71.97%
% Gmm, Nini - Estimated	88.70%	91.26%	91.55%
Dust to Binder - Estimated	1.53	2.23	1.25
Estimated Effective Percent Binder (Pbe,est)	3.02%	2.07%	3.70%
Pb, Est - 0.5%	5.51%	5.94%	6.14%
Pb, Estimated	6.01%	6.44%	6.64%
Pb, Est + 0.5%	6.51%	6.94%	7.14%
Pb, Est + 1.0%	7.01%	7.44%	7.64%

Necessary Criteria Summary

	Tolerance	DAS #1	DAS #2	DAS #3
VTM	4.00%	4.00%	4.00%	4.00%
VMA	13% Min.	11.73%	10.23%	14.27%
VFA	65%-75%	65.89%	60.90%	71.97%
%Gmm, Nini	< 89%	88.70%	91.26%	91.55%
d to	0.80-1.60	1.53	2.23	1.25

DAS Selection

Choose Optimum Design Aggregate Structure

☐ DAS #1
 ☐ DAS #2
 ☒ DAS #3

If no DAS is sufficient, then return to the Aggregate Gradation Chart and enter 3 new DAS's

Print Form Choices Page Chart

Figure A.17 Adjusted Volumetrics for Design Aggregate Structures

Percent Binder Estimate for User Defined DAS

Superpave Calculator - Asphalt Content Estimator for User Entered DAS

Blended Bulk S.G. (Gsb)	3.061
Blended Apparent S.G.(Gsa)	3.450
F- (Absorption Adj. Factor)	0.8
☐ Click Here to Change F Value	
Effective Specific Gravity (Gse)	3.373
Percent Stone	93.40%
Volume of Air (Va) ☐ Change Va	4.00%
Percent Binder Initial Value(%)	6.60%
Specific Gravity of Binder	1.033
Volume of Absorbed Binder (Vba)	0.079
Nominal Maximum Agg. Size (Sn)	19
Volume of Effective Binder (Vbe)	8.97%
Estimated Weight of Stone (Ws)	2.495
<input type="button" value="Update Values"/>	
Est. Total % Binder (Pb-Total)	6.54%

Figure A.18 Percent Binder Estimates for User Defined DAS (If Needed)

Final Design Aggregate Structure and Estimated Percent Binder Confirmation

Superpave Calculator - DAS and Percent Binder Confirmation Worksheet

Aggregate Structure Used: **USER DEF**

Aggregate Supplier(s):	IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type :	#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Aggregate Percentages:	55.00%	35.00%	5.00%	5.00%
	Pb, Est - 0.5%	Pb, Estimated	Pb, Est + 0.5%	Pb, Est + 1.0%
Estimated Binder Percentages:	6.04%	6.54%	7.04%	7.54%
User Adjusted Binder Percentages (If necessary):	0	0	0	0

☒ Use Estimated Percent Binder
☐ Use User Adjusted Percent Binder Instead of Estimated Percent Binder

Print Form

Choices Page

Figure A.19 Final DAS and Percent Binder Estimate Confirmation

Weigh-Out Sheets for Percent Binder Trial Volumetrics

Aggregate Weigh Out Sheets for Percent Binder Volumetric Tests

**Do 2 Rice tests and make 2 Pills using the selected DAS at each Percent Binder
(Using Cumulative or Individual Sieve Weigh-Out sheets below)**

Pb-0.5% Rice Cumulative Wts.	Pb-0.5% Rice Individual Wts.	Pb-0.5% Pill Cumulative Wts.	Pb-0.5% Pill Individual Wts.
Pb Rice Cumulative Wts.	Pb Rice Individual Wts.	Pb Pill Cumulative Wts.	Pb Pill Individual Wts.
Pb+0.5% Rice Cumulative Wts.	Pb+0.5% Rice Individual Wts.	Pb+0.5% Pill Cumulative Wts.	Pb+0.5% Pill Individual Wts.
Pb+1.0% Rice Cumulative Wts.	Pb+1.0% Rice Individual Wts.	Pb+1.0% Pill Cumulative Wts.	Pb+1.0% Pill Individual Wts.

Choices Page

Figure A.20 Weigh-Out Sheets for Percent Binder Trial Volumetrics

Rice Weigh Out Sheet - Cumulative Sieve Weights for Pb

Aggregate Weigh Out Sheet for Rice Test for Pb - (Cumulative Sieve Weights)

NMAAS

Total Sample Weight (g)	2000.0	19.0	Final Aggregate Total Weight (g)	1869.2
Percentage of Binder Used (%)	6.54%		Weight of Asphalt Binder (g)	130.8
Percent of Antistrip Added (%)			Weight of Antistrip Added (g)	0.0

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	1028.1 g	1682.3 g	1775.7 g
37.5 mm	1.5"	0.0 g	1028.1 g	1682.3 g	1775.7 g
25 mm	1"	0.0 g	1028.1 g	1682.3 g	1775.7 g
19 mm	3/4"	128.5 g	1028.1 g	1682.3 g	1775.7 g
12.5mm	1/2"	602.4 g	1028.1 g	1682.3 g	1775.7 g
9.5 mm	3/8"	983.9 g	1028.1 g	1682.3 g	1775.7 g
4.75 mm	#4	985.9 g	1049.6 g	1682.3 g	1779.5 g
2.36 mm	#8	1028.1 g	1192.3 g	1705.6 g	1800.1 g
1.18 mm	#16	1028.1 g	1285.8 g	1732.7 g	1815.4 g
0.6 mm	#30	1028.1 g	1410.1 g	1747.7 g	1831.5 g
0.3 mm	#50	1028.1 g	1522.0 g	1758.9 g	1845.5 g
0.075 mm	#200	1028.1 g	1612.9 g	1768.7 g	1859.3 g
Pan	Pan	1028.1 g	1682.3 g	1775.7 g	1869.2 g

Print Form

Weighout Menu

Figure A.21 Sample Rice Weigh-Out Sheet for Cumulative Sieve Weights

Rice Weigh Out Sheet - Individual Sieve Weights for Pb

Aggregate Weigh Out Sheet for Rice Test for Pb- (Individual Sieve Weights)

NMA5

Total Sample Weight (g)	<input type="text" value="2000.0"/>	<input type="text" value="19.0"/>	Final Aggregate Total Weight (g)	<input type="text" value="1869.2"/>
Percentage of Binder Used (%)	<input type="text" value="6.54%"/>		Weight of Asphalt Binder (g)	<input type="text" value="130.8"/>
Percent of Antistrip Added (%)	<input type="text" value=""/>		Weight of Antistrip Added (g)	<input type="text" value="0.0"/>

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	0.0 g	0.0 g	0.0 g
37.5 mm	1.5"	0.0 g	0.0 g	0.0 g	0.0 g
25 mm	1"	0.0 g	0.0 g	0.0 g	0.0 g
19 mm	3/4"	128.5 g	0.0 g	0.0 g	0.0 g
12.5mm	1/2"	473.9 g	0.0 g	0.0 g	0.0 g
9.5 mm	3/8"	381.4 g	0.0 g	0.0 g	0.0 g
4.75 mm	#4	2.1 g	21.6 g	0.0 g	3.7 g
2.36 mm	#8	42.2 g	142.6 g	23.4 g	20.7 g
1.18 mm	#16	0.0 g	93.6 g	27.1 g	15.2 g
0.6 mm	#30	0.0 g	124.3 g	15.0 g	16.2 g
0.3 mm	#50	0.0 g	111.9 g	11.2 g	13.9 g
0.075 mm	#200	0.0 g	90.9 g	9.8 g	13.8 g
Pan	Pan	0.0 g	69.3 g	7.0 g	9.9 g

Figure A.22 Sample Rice Weigh-Out Sheet for Individual Sieve Weights

Pill Weigh Out Sheet - Cumulative Sieve Weights for Pb

Aggregate Weigh Out Sheet for Pill at Pb - (Cumulative Sieve Weights)

Estimated Total Sample Weight (g) ☐ Click to change Sample Wt. Final Aggregate Total Weight (g)

Percentage of Binder Used (%) Weight of Asphalt Binder (g)

Percent of Antistrip Added (%) Weight of Antistrip Added (g)

Compaction Parameters

Nini

Ndes

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	2857.5 g	4675.9 g	4935.7 g
37.5 mm	1.5"	0.0 g	2857.5 g	4675.9 g	4935.7 g
25 mm	1"	0.0 g	2857.5 g	4675.9 g	4935.7 g
19 mm	3/4"	357.2 g	2857.5 g	4675.9 g	4935.7 g
12.5mm	1/2"	1674.5 g	2857.5 g	4675.9 g	4935.7 g
9.5 mm	3/8"	2734.6 g	2857.5 g	4675.9 g	4935.7 g
4.75 mm	#4	2740.3 g	2917.5 g	4675.9 g	4946.1 g
2.36 mm	#8	2857.5 g	3313.9 g	4740.8 g	5003.5 g
1.18 mm	#16	2857.5 g	3573.9 g	4816.2 g	5045.8 g
0.6 mm	#30	2857.5 g	3919.4 g	4857.7 g	5090.8 g
0.3 mm	#50	2857.5 g	4230.4 g	4888.9 g	5129.5 g
0.075 mm	#200	2857.5 g	4483.1 g	4916.2 g	5167.9 g
Pan	Pan	2857.5 g	4675.9 g	4935.7 g	5195.4 g

Figure A.23 Sample Pill Weigh-Out Sheet for Cumulative Sieve Weights

Pill Weigh Out Sheet - Individual Sieve Weights for Pb

Aggregate Weigh Out Sheet for Pill at Pb- (Individual Sieve Weights)

Estimated Total Sample Weight (g) ☐ Click to change Sample Wt. Final Aggregate Total Weight (g)

Percentage of Binder Used (%) Weight of Asphalt Binder (g)

Percent of Antistrip Added (%) Weight of Antistrip Added (g)

Compaction Parameters

Nini

Ndes

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	0.0 g	0.0 g	0.0 g
37.5 mm	1.5"	0.0 g	0.0 g	0.0 g	0.0 g
25 mm	1"	0.0 g	0.0 g	0.0 g	0.0 g
19 mm	3/4"	357.2 g	0.0 g	0.0 g	0.0 g
12.5mm	1/2"	1317.3 g	0.0 g	0.0 g	0.0 g
9.5 mm	3/8"	1060.1 g	0.0 g	0.0 g	0.0 g
4.75 mm	#4	5.7 g	60.0 g	0.0 g	10.4 g
2.36 mm	#8	117.2 g	396.4 g	64.9 g	57.4 g
1.18 mm	#16	0.0 g	260.0 g	75.3 g	42.3 g
0.6 mm	#30	0.0 g	345.5 g	41.6 g	44.9 g
0.3 mm	#50	0.0 g	310.9 g	31.2 g	38.7 g
0.075 mm	#200	0.0 g	252.8 g	27.3 g	38.4 g
Pan	Pan	0.0 g	192.8 g	19.5 g	27.5 g

Figure A.24 Sample Pill Weigh-Out Sheet for Individual Sieve Weights

Final Volumetric Information Entry Worksheet

Superpave Calculator - Final Volumetric Information Entry Worksheet

Percent Binder	Rice Test			Pill Test			Hini (mm)	Hdes (mm)
	Sample Weight (g)	Bowl + Sample in Water Weight (g)	Bowl in Water (Calibration Weight) (g)	Weight of Dry Pill (g)	Weight of Submerged Pill (g)	Weight of SSD Pill (g)		
Pb, est-0.5%	1979.5	2644.1	1330.0	5495.3	3540.3	5501.1	119.8	114.6
6.04%	1952.7	2806.6	1511.1	5477.8	3528.2	5482.5	121.3	115.7
Pb, est	1967.5	2632.3	1330.0	5437.0	3521.2	5441.6	122.1	115.6
6.54%	1928.6	2789.6	1511.1	5428.6	3521.6	5433.2	119.3	114.3
Pb, est+0.5%	1974.3	2633.2	1330.0	5384.1	3508.3	5388.7	120.7	114.1
7.04%	1929.4	2785.0	1511.1	5369.5	3489.7	5374.1	119.3	114.4
Pb, est+1.0%	1939.5	2611.4	1330.0	5332.2	3480.8	5336.7	121.9	113.9
7.54%	1957.3	2797.6	1511.1	5319.5	3467.6	5324.0	121.3	114.6

Print Form Choices Page

Figure A.25 Final Volumetric Information Entry Worksheet

Percent Binder Trials - Volumetrics

Superpave Calculator - Percent Binder Trials Volumetric Analysis

(Pb)

Percent Binder	6.04%	6.54%	7.04%	7.54%
% Gmm, N des	94.27%	95.72%	97.07%	97.85%
Effective GS (Gse)	3.381	3.407	3.422	3.450
% Binder Abs. (Pba)	3.19%	3.43%	3.55%	3.80%
% Binder Eff. (Pbe)	3.04%	3.34%	3.74%	4.03%
VTM	5.73%	4.28%	2.93%	2.15%
VMA	13.97%	13.43%	13.26%	13.34%
VFA	59.01%	68.16%	77.89%	83.84%
% Gmm, N ini	90.05%	91.16%	92.42%	91.93%
Dust to Binder	1.52	1.38	1.24	1.15

Print Form

Choices Page

Figure A.26 Percent Binder Trials Volumetric Analysis

Figure A.27 Graphs of Mix Properties v/s Asphalt Content

Chart of Interpolated Final Volumetrics

Superpave Calculator - Interpolated Optimum AC - Volumetric Analysis

Necessary Criteria Summary	Value	Tolerance	Acceptability
Voids in Total Mix (VTM)	4.00%	3.00%-5.00%	YES
Voids in the Mineral Agg. (VMA)	13.40%	13% Min.	YES
Voids Filled with Asph. (VFA)	70.16%	65%-75%	YES
Dust to Binder Ratio (d to B)	1.35	0.80-1.60	YES

Print Form

Choices Page

Figure A.28 Chart of Interpolated Final Volumetrics

Weigh-Out Sheets for Optimum Asphalt Content Volumetrics

Aggregate Weigh Out Sheets for Optimum Asphalt Content Volumetric Testing

Do 2 Rice tests and make 2 Pills using the selected DAS at the Optimum Percent Binder (Using Cumulative or Individual Sieve Weigh-Out sheets below)

Rice - Cumulative Weights	Pill - Cumulative Weights
Rice - Individual Weights	Pill - Individual Weights

Choices Page

Figure A.29 Weigh-Out Sheets for Optimum Asphalt Content Volumetrics

Rice Weigh Out Sheet - Cumulative Sieve Weights for Final Volumetric Tests

Aggregate Weigh Out Sheet for Rice Test for Final Volumetrics- (Cumulative Sieve Weights)

NMA5

Total Sample Weight (g)	2000.0	19.0	Final Aggregate Total Weight (g)	1869.2
Percentage of Binder Used (%)	6.54%		Weight of Asphalt Binder (g)	130.8
Percent of Antistrip Added (%)			Weight of Antistrip Added (g)	0.0

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	1028.1 g	1682.3 g	1775.7 g
37.5 mm	1.5"	0.0 g	1028.1 g	1682.3 g	1775.7 g
25 mm	1"	0.0 g	1028.1 g	1682.3 g	1775.7 g
19 mm	3/4"	128.5 g	1028.1 g	1682.3 g	1775.7 g
12.5mm	1/2"	602.4 g	1028.1 g	1682.3 g	1775.7 g
9.5 mm	3/8"	983.9 g	1028.1 g	1682.3 g	1775.7 g
4.75 mm	#4	985.9 g	1049.6 g	1682.3 g	1779.5 g
2.36 mm	#8	1028.1 g	1192.3 g	1705.6 g	1800.1 g
1.18 mm	#16	1028.1 g	1285.8 g	1732.7 g	1815.4 g
0.6 mm	#30	1028.1 g	1410.1 g	1747.7 g	1831.5 g
0.3 mm	#50	1028.1 g	1522.0 g	1758.9 g	1845.5 g
0.075 mm	#200	1028.1 g	1612.9 g	1768.7 g	1859.3 g
Pan	Pan	1028.1 g	1682.3 g	1775.7 g	1869.2 g

Print Form

Weighout Menu

Figure A.30 Rice Weigh-Out Sheet – Cum. Sieve Weights for Final Volumetrics

Rice Weigh Out Sheet - Individual Sieve Weights for Final Volumetric Tests

Aggregate Weigh Out Sheet for Rice Test for Final Volumetrics- (Individual Sieve Weights)

NMAA

Total Sample Weight (g)	2000.0	19.0	Final Aggregate Total Weight (g)	1869.2
Percentage of Binder Used (%)	6.54%		Weight of Asphalt Binder (g)	130.8
Percent of Antistrip Added (%)			Weight of Antistrip Added (g)	0.0

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	0.0 g	0.0 g	0.0 g
37.5 mm	1.5"	0.0 g	0.0 g	0.0 g	0.0 g
25 mm	1"	0.0 g	0.0 g	0.0 g	0.0 g
19 mm	3/4"	128.5 g	0.0 g	0.0 g	0.0 g
12.5mm	1/2"	473.9 g	0.0 g	0.0 g	0.0 g
9.5 mm	3/8"	381.4 g	0.0 g	0.0 g	0.0 g
4.75 mm	#4	2.1 g	21.6 g	0.0 g	3.7 g
2.36 mm	#8	42.2 g	142.6 g	23.4 g	20.7 g
1.18 mm	#16	0.0 g	93.6 g	27.1 g	15.2 g
0.6 mm	#30	0.0 g	124.3 g	15.0 g	16.2 g
0.3 mm	#50	0.0 g	111.9 g	11.2 g	13.9 g
0.075 mm	#200	0.0 g	90.9 g	9.8 g	13.8 g
Pan	Pan	0.0 g	69.3 g	7.0 g	9.9 g

Print Form

Weighout Menu

Figure A.31 Rice Weigh-Out Sheet - Individual Sieve Weights for Final Volumetrics

Pill Weigh Out Sheet - Cumulative Sieve Weights for Final Volumetric Tests

Aggregate Weigh Out Sheet for Pill for Final Volumetrics- (Cumulative Sieve Weights)

Estimated Total Sample Weight (g) ☐ Click to change Sample Wt. Final Aggregate Total Weight (g)

Percentage of Binder Used (%) Weight of Asphalt Binder (g)

Percent of Antistrip Added (%) Weight of Antistrip Added (g)

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	2857.5 g	4675.9 g	4935.7 g
37.5 mm	1.5"	0.0 g	2857.5 g	4675.9 g	4935.7 g
25 mm	1"	0.0 g	2857.5 g	4675.9 g	4935.7 g
19 mm	3/4"	357.2 g	2857.5 g	4675.9 g	4935.7 g
12.5mm	1/2"	1674.5 g	2857.5 g	4675.9 g	4935.7 g
9.5 mm	3/8"	2734.6 g	2857.5 g	4675.9 g	4935.7 g
4.75 mm	#4	2740.3 g	2917.5 g	4675.9 g	4946.1 g
2.36 mm	#8	2857.5 g	3313.9 g	4740.8 g	5003.5 g
1.18 mm	#16	2857.5 g	3573.9 g	4816.2 g	5045.8 g
0.6 mm	#30	2857.5 g	3919.4 g	4857.7 g	5090.8 g
0.3 mm	#50	2857.5 g	4230.4 g	4888.9 g	5129.5 g
0.075 mm	#200	2857.5 g	4483.1 g	4916.2 g	5167.9 g
Pan	Pan	2857.5 g	4675.9 g	4935.7 g	5195.4 g

Print Form

Weighout Menu

Compaction Parameters

Nini

Nmax

Figure A.32 Pill Weigh-Out Sheet - Cumulative Sieve Weights for Final Volumetrics

Pill Weigh Out Sheet - Individual Sieve Weights for Final Volumetric Tests

Aggregate Weigh Out Sheet for Pill for Final Volumetrics- (Individual Sieve Weights)

Estimated Total Sample Weight (g) ☐ Click to change Sample Wt. Final Aggregate Total Weight (g)

Percentage of Binder Used (%) Weight of Asphalt Binder (g)

Percent of Antistrip Added (%) Weight of Antistrip Added (g)

Compaction Parameters	Aggregate Supplier		IMS		IMS		Martin Mar.		Std. Lafarge	
	Aggregate Type		#57 Slag		#10 Slag		L-stone Sand		Slag Sand	
	Sieve Size									
Nini <input type="text" value="8"/> Nmax <input type="text" value="160"/>	50 mm	2"	0.0	g	0.0	g	0.0	g	0.0	g
	37.5 mm	1.5"	0.0	g	0.0	g	0.0	g	0.0	g
	25 mm	1"	0.0	g	0.0	g	0.0	g	0.0	g
	19 mm	3/4"	357.2	g	0.0	g	0.0	g	0.0	g
	12.5mm	1/2"	1317.3	g	0.0	g	0.0	g	0.0	g
	9.5 mm	3/8"	1060.1	g	0.0	g	0.0	g	0.0	g
	4.75 mm	#4	5.7	g	60.0	g	0.0	g	10.4	g
	2.36 mm	#8	117.2	g	396.4	g	64.9	g	57.4	g
	1.18 mm	#16	0.0	g	260.0	g	75.3	g	42.3	g
	0.6 mm	#30	0.0	g	345.5	g	41.6	g	44.9	g
	0.3 mm	#50	0.0	g	310.9	g	31.2	g	38.7	g
	0.075 mm	#200	0.0	g	252.8	g	27.3	g	38.4	g
	Pan	Pan	0.0	g	192.8	g	19.5	g	27.5	g

Print Form

Weighout Menu

Figure A.33 Pill Weigh-Out Sheet - Individual Sieve Weights for Final Volumetrics

Volumetric Data Entry Worksheet for Optimum Asphalt Content

Superpave Calculator - Volumetric Information Entry Worksheet for Optimum AC

Percent Binder

6.54%

Rice Test

Sample Weight (g)	Bowl + Sample in Water Weight (g)	Bowl in Water (Calibration Weight) (g)
1964.3	2630.3	1330.0
1926.6	2788.4	1511.1

Pill Test

Weight of Dry Pill (g)	Weight of Submerged Pill (g)	Weight of SSD Pill (g)
5433.9	3525.2	5438.5
5418.6	3520.6	5423.2

Print Form

Choices Page

Figure A.34 Volumetric Data Entry Worksheet for Optimum Asphalt Content

Superpave Worksheet - Checking Gmm,Nmax for Acceptability

Superpave Calculator -Optimum AC -Volumetric Analysis Checking Gmm,Nmax

Optimum Asphalt Content	6.54%		
Gmm (from Rice Data)	2.963		
Gmb (from Pill Data)	2.844	Tolerance	Passing?
%Gmm,Nmax	95.99%	98.00%	YES

Print Form

Choices Page

Figure A.35 Volumetric Data Analysis for Optimum Asphalt Content

TSR Weighout Sheets and Data Entry Worksheets

Aggregate Weigh Out Sheets for TSR Testing

TSR Pill - Cumulative Weights

TSR Pill - Individual Weights

TSR Input

	Sample 1	Sample 2	Sample 3	Average
Wet Tensile Strength	45.3	47.5	44.1	45.6
Dry Tensile Strength	32.8	36.8	35.2	34.9

Tensile Strength Ratio

1.31

Acceptable?

YES

Print Form

Choices Page

Figure A.36 Agg. Weigh-Out and Data Entry Worksheets for Tensile Strength Ratio

Weighout Sheet for TSR Pill (Cumulative Weights)

Aggregate Weigh Out Sheet for TSR Pill - (Cumulative Sieve Weights)

Estimated Total Sample Weight (g) ☐ Click to change Sample Wt. Final Aggregate Total Weight (g)

Percentage of Binder Used (%) Weight of Asphalt Binder (g)

Percent of Antistrip Added (%) Weight of Antistrip Added (g)

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	2857.5 g	4675.9 g	4935.7 g
37.5 mm	1.5"	0.0 g	2857.5 g	4675.9 g	4935.7 g
25 mm	1"	0.0 g	2857.5 g	4675.9 g	4935.7 g
19 mm	3/4"	357.2 g	2857.5 g	4675.9 g	4935.7 g
12.5mm	1/2"	1674.5 g	2857.5 g	4675.9 g	4935.7 g
9.5 mm	3/8"	2734.6 g	2857.5 g	4675.9 g	4935.7 g
4.75 mm	#4	2740.3 g	2917.5 g	4675.9 g	4946.1 g
2.36 mm	#8	2857.5 g	3313.9 g	4740.8 g	5003.5 g
1.18 mm	#16	2857.5 g	3573.9 g	4816.2 g	5045.8 g
0.6 mm	#30	2857.5 g	3919.4 g	4857.7 g	5090.8 g
0.3 mm	#50	2857.5 g	4230.4 g	4888.9 g	5129.5 g
0.075 mm	#200	2857.5 g	4483.1 g	4916.2 g	5167.9 g
Pan	Pan	2857.5 g	4675.9 g	4935.7 g	5195.4 g

Figure A.37 Aggregate Weigh-Out Sheet for TSR Pill, Cumulative Sieve Weights

Weighout Sheet for TSR Pill (Individual Weight)

Aggregate Weigh Out Sheet for TSR Pill - (Individual Sieve Weights)

Estimated Total Sample Weight (g) ☐ Click to change Sample Wt. Final Aggregate Total Weight (g)

Percentage of Binder Used (%) Weight of Asphalt Binder (g)

Percent of Antistrip Added (%) Weight of Antistrip Added (g)

Aggregate Supplier		IMS	IMS	Martin Mar.	Std. Lafarge
Aggregate Type		#57 Slag	#10 Slag	L-stone Sand	Slag Sand
Sieve Size					
50 mm	2"	0.0 g	0.0 g	0.0 g	0.0 g
37.5 mm	1.5"	0.0 g	0.0 g	0.0 g	0.0 g
25 mm	1"	0.0 g	0.0 g	0.0 g	0.0 g
19 mm	3/4"	357.2 g	0.0 g	0.0 g	0.0 g
12.5 mm	1/2"	1317.3 g	0.0 g	0.0 g	0.0 g
9.5 mm	3/8"	1060.1 g	0.0 g	0.0 g	0.0 g
4.75 mm	#4	5.7 g	60.0 g	0.0 g	10.4 g
2.36 mm	#8	117.2 g	396.4 g	64.9 g	57.4 g
1.18 mm	#16	0.0 g	260.0 g	75.3 g	42.3 g
0.6 mm	#30	0.0 g	345.5 g	41.6 g	44.9 g
0.3 mm	#50	0.0 g	310.9 g	31.2 g	38.7 g
0.075 mm	#200	0.0 g	252.8 g	27.3 g	38.4 g
Pan	Pan	0.0 g	192.8 g	19.5 g	27.5 g

Print Form

TSR Main Page

Figure A.38 Aggregate Weigh-Out Sheet for TSR Pill, Individual Sieve Weights

Figure A.39 Exit Screen for Superpave Calculator

T400 SP
03-00

**WEST VIRGINIA DIVISION OF HIGHWAYS
JOB MIX FORMULA FOR SUPERPAVE HOT-MIX ASPHALT**

Report Number:	Trial #1	Date Accepted:	January 1, 2003
HMA Type:	WCT-1 (Skid)	HMA Code:	72289
Producer:	WVU Asphalt Lab	Plant Location:	Morgantown, WV
Designed By:	M. Padula	Design Lab:	WVU Asphalt Technology Lab
Plant Type:	Test Size Batch	Plant Make:	Bituma-Gencor
Plant Code:	WVU2002	Design ESALs (Millions):	10 < 30

MIX COMPOSITION						
Coarse Aggregate Source		Code	Fine Agg. / Mineral Filler Source		Code	
CA ₁	IMS	S044E	FA ₁	Martin Mar.	T012B	
CA ₂	IMS	S044E	FA ₂	Std. Lafarge	S044C	
CA ₃			FA ₃			
	CA ₁	CA ₂	CA ₃	FA ₁	FA ₂	MIN. FILL
Aggregate Type	#57 Slag	#10 Slag		L-stone Sand	Slag Sand	
Aggregate Code	1186	1173		1115	1114	
% Total Aggregate	55.00%	35.00%		5.00%	5.00%	
% RAP Total Agg:	N/A		Blended Binder G*/sin delta if > 25% RAP:			N/A
% Binder in RAP Design:	N/A		Binder Type:	PG 64-22	Binder Code:	1093
Binder Source:	Asphalt Materials, Inc. Marietta, OH			Binder Source Code:		A0380

Sieve Fraction								Fines/Effective Asphalt Ratio	Tensile Strn. Ratio	
Sieve Size	Target	Allowable		Sieve Size	Target	Allowable		1.35	1.31	
		Min.	Max.			Min.	Max.			
2" (50mm)				#4 (4.75mm)				Temperature Range Completed Mixture (°F)		
1.5" (37.5mm)				#8" (2.36mm)	35	20	50			
1" (25mm)	100	100	100	#16 (1.18mm)				Desirable Mean Temp.	Temp. Range	
3/4" (19mm)	95	90	100	#30 (600µm)					Min.	Max.
1/2" (12.5mm)	90		90	#50 (300µm)				305	290	320
3/8" (9.5mm)				#200 (75µm)	5	2	8			

JOB MIX FORMULA VALUES					
Job Mix Formula Targets				Job Mix Formula Tolerances	
Specific gravity stone bulk (Gsb): 3.061	Design Property	Accepted Target		Minimum	Maximum
	Asphalt (%)	6.50%		6.10%	6.90%
Maximum Density (kg/m³) 2962.7	Air Voids (%)	4.0		2.5	5.5
	VMA (%)	14.0		13.0	15.0
	VFA (%)	70.0		65.0	75.0
Gyrations @ N _{initial} :	8	Gyrations @ N _{design} :	100	Gyrations @ N _{max} :	160

Remarks: This is a trial to validate the software and demonstrate its utility

Figure A.40 Sample Job Mix Formula Print Out (Produced Using Trial Data)

(Percent Binder - 0.5%) Rice Weighout Sheet - Individual Weights per Sieve Size				
Report Number:		Trial #1		
HMA Type:		WCT-1 (Skid)		
Producer:		WVU Asphalt Lab		
	Source	Source Code	Type	Code
CA1	IMS	S044E	#57 Slag	1186
CA2	IMS	S044E	#10 Slag	1173
FA1	Martin Mar.	T012B	L-stone Sand	1115
FA2	Std. Lafarge	S044C	Slag Sand	1114
Binder	Asphalt Materials, Inc. Marietta, OH	A0380	PG 64-22	1093

Individual Weights (g)				
Sieve Size	CA1 #57 Slag	CA2 #10 Slag	FA1 L-stone Sand	FA2 Slag Sand
2"	0.0	0.0	0.0	0.0
1.5"	0.0	0.0	0.0	0.0
1"	0.0	0.0	0.0	0.0
3/4"	129.2	0.0	0.0	0.0
1/2"	476.5	0.0	0.0	0.0
3/8"	383.5	0.0	0.0	0.0
#4	2.1	21.7	0.0	3.8
#8	42.4	143.4	23.5	20.8
#16	0.0	94.1	27.2	15.3
#30	0.0	125.0	15.0	16.3
#50	0.0	112.5	11.3	14.0
#200	0.0	91.4	9.9	13.9
Pan	0.0	69.7	7.0	10.0

Total Sample Weight (g):	2000.0
Percent Binder:	6.04%
Aggregate total Wt. (g):	1879.2
Percent of Antistrip:	0.00%
Weight of Antistrip (g):	0.0
Final Agg. total Wt. (g):	1879.2
Wt. Of Asphalt Binder (g):	120.8

Weighed by: _____ Date: _____

Figure A.41 Sample Weigh-Out Sheet Print-Out (Using Trial Data)

APPENDIX B

SUPERPPAVE CALCULATOR USER'S MANUAL

Structure of User Interface for Superpave Calculator

Figure B.1 Structure of User Interface for Superpave Calculator

USER'S MANUAL

Welcome to the West Virginia University Department of Civil and Environmental Engineering Asphalt Technology Program's Superpave Calculator. The program is designed for all levels of asphalt mix design knowledge, from a practicing asphalt contractor to a student in an introductory bituminous pavement course. Each step in the Superpave Calculator mix design process is detailed, from the introduction to the exit page and all necessary processes in between. This manual describes the types of values that should be entered in each data entry text box, ensuring proper performance of the software and minimizing error messages. A screen capture of each user form is included in Appendix A, and may be helpful in identifying proper data types and acceptable values.

Section I Installing the Software Computer.

After obtaining a copy of the Superpave Calculator program, which is about 3.5MB, the user must install it on the host computer, create a shortcut in Microsoft Excel, and link the shortcut for future easy access.

1. Create a new folder on the desktop named "Superpave".
2. Copy the program into the "Superpave" folder.
3. Open the program in Microsoft Excel, enable macros, and right click on the toolbars at the top of the screen.
4. Click "Customize" on the menu, and then select the "New" button.
5. Name the new toolbar "Superpave", click "OK".
6. Select the "Commands" tab and highlight the "Macros" option.
7. Left-click "Custom Menu Item" and drag it onto the newly created "Superpave" toolbar.

8. Right-click this newly created button. In the white field, rename the button “&Superpave”, and at the bottom of the menu select “Assign Macro”.
9. Select the “Superpave” macro and click “OK”.
10. Close the Customize menu and drag the newly created button to the top of the screen and “peg” it in an empty space.

After completing this process, the user only needs to click this “Superpave” button to launch the software.

Section II Running the Superpave Calculator

After completing Step I and installing the software and shortcut onto the host computer, the program is ready to run at the click of the “Superpave” button.

To use the program, launch the software by clicking the newly created “Superpave” button. An introduction screen will appear welcoming the user and identifying the developers, origin, version, and latest update. Two choices are presented: begin a new mix design project or open an existing file. New mix design steps are detailed in Section II; saving and opening files for modification are discussed in Section III. Screen captures of every step in the new mix design process are presented in Appendix A and may be referenced to compare acceptable values. After the “New Project” option is selected, the user is prompted to enter the mix design report information.

1. The Mix Design Report Information sheet is designed in tandem with the WV T400 SP Superpave Mix Design Summary sheet, which is required for each new mix design. All input fields are alphanumeric, created to assist the user throughout the process, but not used in calculations. The input fields for Report Number, HMA Type, Producer, etc. are directly linked to the T400 SP summary sheet and they also help to identify the mix if future modification is necessary. The aggregate data input on the bottom half of the screen is used to later identify gradations on graphs and aggregates for weigh out sheets.

The source field requires data about the company supplying the aggregate, with the location of its city and state. The “Source Code” is a five digit alphanumeric code identifying each supplier and is standard for all designers in West Virginia. The “Aggregate Type” is an identifier of the specific type aggregate used, such as #57 Slag, #8 Limestone, or Natural Sand. “Aggregate Code” is the statewide four digit number code identifying each type of aggregate. The binder information is also entered on this sheet identifying the supplier, with city and state, source code and binder code. After entering all data, the user must go to the “Main Choices” page for further processing.

The “Main Choices” screen is the central hub of the entire program, allowing the user to return after every step, before continuing to the next part of the process. This page is linked to the program exit, which is the only method of quitting the application.

The “Mix Composition Information” page is the next step in the design process. The user inputs the required design parameters, which determine the tolerances and criteria that must be followed. The data for skid design, binder grade, depth from surface, traffic ESALs, NMAAS and the binder specific gravity must be entered. The temperatures, RAP data and remarks field are for report information only. The required data entry includes:

- The skid design field, which identifies if the mix will be used as a skid or base design
- Binder type, the four types used in West Virginia are presented for selection
- The depth from surface is dependent on the skid design selection. If the mix will be used as a skid design, the only option is depth <100mm
- The traffic ESALs ,in millions, identifies the expected volume of roadway traffic
- The Nominal Maximum Aggregate Size (NMAAS), identifying the size of the aggregates to be used for the mix design
- Specific gravity of the binder, which must be 0.900-1.100

All of the required data must be entered, or else the program will return an error message prompting the user to completely fill in all information.

2. The Aggregate Consensus Properties page is designed simply as a tool to determine if laboratory generated aggregate data meets the set requirements. The user inputs the data for Coarse Aggregate Angularity (CAA), Fine Aggregate Angularity (FAA), Flat and Elongated Ratio (FE) and the Sand Equivalency Test (SE). The data are entered as percentages. Information from the Mix Composition page determines the acceptable range of values.
3. The Aggregate Data Worksheet allows the user to enter data on up to four different aggregate gradations. Bulk Specific Gravity (Gsb) and Apparent Specific Gravity (Gsa) for each aggregate type are also required. The data on the percent passing each sieve size for the individual aggregates is entered, with each value being equal or less than the previous passing percentage. If a percentage passing is entered that is greater than the value above, the program returns an error message warning the user of an invalid number that must be changed. The data on Gsb and Gsa is also required for the mix design process with Gsb always less than Gsa, otherwise an error message is displayed. Four different aggregates are not required for a mix design, but all of the necessary information on an aggregate must be completely entered, or an error message warns the user of empty input fields. If the design aggregate structure (DAS) is already known, the percentage of each aggregate to be used for a blend may be entered in the appropriate fields below the specific gravity data. If DAS is not yet determined, the percentages may be left blank.

On the Main Choices page, if the DAS is known, uncheck the “Determine DAS” box and proceed straight to estimating the necessary percent binder, with the button located at the top of the second column. If DAS must be determined, proceed to step four and create three individual DAS.

4. The Aggregate Gradation Chart graphically displays the individual gradations for each aggregate used as well as the blended gradation. Below the plot are presented the restrictions for five control points, which are determined by the NMAS of the blend. Also presented is the overall blended NMAS of the current blend in either a red or green text box. When the aggregates are blended, the program calculates these six necessary values as well as the total blend percentage and returns the results in a colored box. If the box is green, the value is acceptable; if it is red, the limit is violated and the blend is unacceptable. The aggregates are blended so that the control points and the NMAS values are within the tolerances and all indicator boxes turn green. If the DAS is known, this is merely a visual tool to confirm acceptability; if DAS is unknown, then three blends are created and saved, using the “Save as DAS #” buttons. The total percentage must equal 100% to exit this page; otherwise an error message is displayed.
5. The DAS Chart page graphically displays the three determined design aggregate structures plotted on a single graph. There is no user input for this step, only a visual presentation of the three DASs.
6. The Initial Asphalt Content Estimator for each DAS uses a series of equations and limits based upon mix information and aggregate data to estimate the asphalt content for each DAS. This value is intended to only be an initial estimate, not the final value. Subsequent testing is needed for a definitive binder percentage as presented in Steps 7-10. This page automatically calculates the binder percentages on loading. If the absorption adjustment factor (F Value) or the design air content (Va) differ from the preset values, the new data must be entered and the binder percentage must be recalculated using the “Update Values” button. The calculated binder percentages are automatically passed to the weigh out sheets for Step 7.
7. Since two maximum specific gravity tests and two gyratory compaction samples are required for each DAS, the aggregates and binder must be weighed, blended and the tests performed. The weigh out sheets are provided to assist the user in determining the amount of material passing the sieves that

must be weighed for each aggregate. Two formats are presented with this software: individual and cumulative sieve weights, both yielding the same final result. The “Print” button prints a form showing all required weights along with the necessary mix design information at the top of the sheet. No user input is necessary on any of these weigh out forms.

8. The Volumetric Data Entry Worksheet receives all of the weights obtained from the two Rice tests and two gyratory samples for each DAS. The Rice weight inputs are presented on the left of the screen; the pill data is entered on the right. All weights are in grams and must be positive numeric values. For the Rice test, the sample weight must be less than the submerged weight and the submerged weight must be greater than the calibration weight; any violation will return an error message. For the pills, the dry weight must be less than the SSD weight and greater than the submerged weight; an error box is displayed if otherwise. The pill heights, in millimeters, are also entered. The initial height must be greater than the design height, which must be between 110 and 120 mm. An error message is displayed if these criteria are not met. The data entered on this worksheet is used to calculate the volumetric properties presented next in Step 9.
9. The Design Aggregate Structure Volumetric Analysis worksheet requires no user input; it displays all of the required volumetric values compared with the set tolerances. The four necessary criteria are presented in a summary on the right of the screen with acceptable values turning the display boxes green and invalid values turning red. The Voids in the Total Mix (VTM), Voids in the Mineral Aggregate (VMA), Voids Filled with Asphalt (VFA) and dust to binder ratio (D/b) values are presented along with the acceptable tolerances. No user input is necessary for this page, only an observation of the values for a comparison in Step 10.
10. The Design Aggregate Structure Volumetric Analysis Adjusted to 4.0% Air worksheet presents all of the volumetric data mathematically adjusted to 4.0% VTM and presented with the tolerances. Upon examining the necessary criteria summary, with acceptable values presented in green boxes and

unacceptable values in red, the user is required to pick the best DAS to continue with the procedure. If no DAS adjusted volumetric data meets all four criteria, the user is returned to the DAS selection plot and the process is repeated again until a valid structure is found. If a DAS meets all four criteria, it is selected and the user returns to the “Main Choices” page to continue the mix design with more volumetric analysis.

If the DAS is already known, as detailed before, the initial asphalt content is estimated for the future volumetric testing.

11. The DAS and Percent Binder Confirmation worksheet provides a summary of the mix design for the upcoming volumetric analysis procedures. The chosen DAS and calculated initial binder estimate are displayed for user verification. If the binder percentage must be adjusted, the new $P_{b,est}$ can be inputted into the yellow box, which then automatically fills in the other necessary binder percentages. If the original binder percentage is to be used, check the designated box, otherwise check “Enter User Adjusted Value” and input the proper data. These values are passed into the weigh-out sheets for the volumetric analysis.
12. The next process is to make two maximum specific gravity and two gyratory compaction samples at each of four binder percentages. The weigh out sheets are provided to assist the user in weighing the material, the same as in Step 7. These sheets differ from those for DAS analysis because the user has the option of entering the percent of antistrip used for each mix and also entering a different weight for the gyratory compaction samples. When new data is entered, all values are immediately updated to reflect the changes. The sheets for the gyratory compaction samples also indicate the number of revolutions for gyratory compactor to achieve N_{des} . The weigh out sheets are used to create the samples necessary for the volumetric analysis of Step 13.
13. The Volumetric Data Entry Worksheet receives all of the weights obtained from the two Rice tests and two gyratory samples for each binder percentage, the same as in Step 8 for DAS volumetric analysis. The Rice weight inputs

are presented on the left of the screen and the pill data is entered on the right. All weights are in grams and must be positive numeric values. For the Rice test, the sample weight must be less than the submerged weight and the submerged weight must be greater than the calibration weight; any violation will return an error message. For the pills, the dry weight must be less than the SSD weight and greater than the submerged weight; an error box is displayed if otherwise. The pill heights, in millimeters, are also entered. The initial height must be greater than the design height, which must be between 110 and 120 mm. An error message is displayed if these criteria are not met. The data entered on this worksheet is used to calculate the volumetric properties presented next in Step 14.

14. The Percent Binder Trials Volumetric Analysis worksheet requires no user input, it only displays the required volumetric values compared with the set tolerances, the same as in Step 9. The four necessary criteria for only the $P_{b,est}$ are presented in a summary at the bottom of the screen, with acceptable values turning the display boxes green and invalid values turning red. The Voids in the Total Mix (VTM), Voids in the Mineral Aggregate (VMA), Voids Filled with Asphalt (VFA) and dust to binder ratio (D/b) values are presented along with the acceptable tolerances. No user input is necessary for this page, only an observation of the values for the interpolation in Step 15.
15. The Mix Properties versus Asphalt Content worksheet graphically interpolates the binder percentage to 4.0% VTM, then adjusts the other four volumetric properties, VMA, VFA, $\%G_{mm,Nini}$ and D/b to that calculated percent binder. The data is processed mathematically by Excel and then displayed visually for easy interpretation of the results. No user input is needed for this worksheet, only a viewing of the results for acceptability. The numerical results are presented in Step 16 for more precise determination of values.
16. The Interpolated Optimum AC-Volumetric Analysis worksheet is the numerical version of the interpolated results from Step 15. If the display boxes are green, the values are acceptable; red boxes signal an unacceptable

result. No user interaction for this worksheet is allowed; it is only intended to notify the user if any value does not meet the necessary criteria.

17. Once the optimum binder percentage is determined by volumetric interpolation, volumetric analysis to determine $\%G_{mm,N_{max}}$ must be performed at this final asphalt content. Two more Rice tests and gyratory samples must be weighed out and the tests must be run in order to calculate the final volumetric properties. The weigh out sheets are of the same fashion as in step 12, allowing the user to enter the amount of antistripping and change the weight of the compaction sample. The sheets indicate the number of revolutions necessary for N_{max} for the gyratory compaction samples. The data from the samples is entered into the volumetric analysis data entry sheet in Step 18.
18. The Volumetric Information Entry Worksheet for Optimum AC is the same as the data entry worksheet for step 13, except no compaction sample heights are required. The Rice weight inputs are presented on the left of the screen and the pill data is entered on the right. All weights are in grams and must be positive numeric values. For the Rice test, the sample weight must be less than the submerged weight and the submerged weight must be greater than the calibration weight; any violation will return an error message. For the pills, the dry weight must be less than the SSD weight and greater than the submerged weight; an error box is displayed if otherwise. This data is used to determine if the value of $\%G_{mm,N_{max}}$ is acceptable in Step 19.
19. The Optimum AC Volumetric Analysis- Checking $\%G_{mm,N_{max}}$ worksheet uses the values from Step 18 and returns the calculated volumetric analysis for $\%G_{mm,N_{max}}$, which must be less than 98.0%. If the value is acceptable, the display box is green; an unacceptable value will return a red box. If the mix is unacceptable, a new DAS is required and the process begins again at Step 4. The last check of mix design acceptability is the evaluation of moisture susceptibility using the TSR test as detailed in Step 20.
20. The Tensile Strength Ratio (TSR) Test is performed by using the provided weigh out sheets to create six gyratory compaction samples for tensile strength testing. Three conditioned and three unconditioned samples are

tested in the laboratory and their results are entered into the designated input boxes. After all values are inputted, the tensile strength ratio is displayed and the acceptability is noted with a red or green result. If the minimum allowable value for TSR, which is 0.8, is not met, anitstripping is added and the process returns to Step 12 where two more Rice tests and gyratory compaction samples are created at each binder percentage. The process is then continued until an acceptable mix design is found, completing the entire procedure. Once a mix design meets all volumetric criteria and has a $\%G_{mm,Nmax} < 98.0\%$ and a $TSR > 0.8$, the Superpave mix design is completed and the mix is deemed acceptable for use on the roadway.

All of the data, in a one-page summary, may be obtained by clicking the “Exit Superpave Calculator” button on the Main Choices page. At this point of the mix design process, the user has the option of printing the report, returning to the calculator or exiting the software. Printing the report only requires clicking the designated button, as does returning to the Superpave Calculator. The user has two other choices, which involve quitting the program by either saving or not saving the data. Quitting without saving loses all of the calculated data and exits Microsoft Excel, but saving the data involves another step, which is detailed in Section III.

Section III Saving and Opening Mix Design Files

At the introduction page, the user has the option of opening an existing project or starting a new project. If an existing mix design project is to be modified, select the appropriate button, which then displays the “Open” box. Choose the previously saved file for modification and click the “Open” button; the data is now loaded into the program and every step is ready for modification.

To save a mix design upon exiting the Superpave Calculator, choose the “Save and Exit” option. A “Save As” box will appear, prompting the user to give the mix design a unique name. Name the data something other than “Superpave” and click the “Save” button. The mix design data will be saved and the workbook will automatically close.

APPENDIX C

SLAG AGGREGATE EVALUATION LABORATORY RESULTS

Figure C.1 Blended Gradation for Trials 1-4 (64% #57 Slag & 36% #10 Slag)

Figure C.2 Blended Gradation for Trial 5 (72% #57 Slag & 28% #10 Slag)

Figure C.3 Blended Gradation for Trials 6 & 6.1 (Gradation from Literature)

Table C.1 Estimated Binder Percentages from Aggregate Data

Trials 1-4 Estimated Binder Percentage from Aggregate Data	
Effective Gs	
Blended Gs _b	3.134
Blended Gs _a	3.558
F	0.8
Gs _E	
Vol. absorbed binder (asphalt)	
Percent Stone	93.40%
V _a (air)	4.00%
Percent Binder	6.60%
G _b	1.033
V _{ba}	
Est. of Vol of Effective Binder	
Sn (mm)	19
V _{be}	
Est. weight of stone	
W _s	
Percent Binder Estimate	
Pb _{Total}	
	6.56%

Trial 5 Estimated Binder Percentage from Aggregate Data	
Effective Gs	
Blended Gs _b	3.169
Blended Gs _a	3.548
F	0.8
Gs _E	
Vol. absorbed binder (asphalt)	
Percent Stone	93.87%
V _a (air)	4.00%
Percent Binder	6.13%
G _b	1.033
V _{ba}	
Est. of Vol of Effective Binder	
Sn (mm)	19
V _{be}	
Est. weight of stone	
W _s	
Percent Binder Estimate	
Pb _{Total}	
	6.17%

Trial 6 Estimated Binder Percentage from Aggregate Data	
Effective Gs	
Blended Gs _b	3.298
Blended Gs _a	3.516
F	0.8
Gs _E	
Vol. absorbed binder (asphalt)	
Percent Stone	95.15%
V _a (air)	4.00%
Percent Binder	4.85%
G _b	1.033
V _{ba}	
Est. of Vol of Effective Binder	
Sn (mm)	19
V _{be}	
Est. weight of stone	
W _s	
Percent Binder Estimate	
Pb _{Total}	
	4.85%

Table C.2 Bulk Specific Gravity and Absorption of 3/4" Slag

WVU ASPHALT LAB

Bulk Specific Gravity and Absorption Coarse Aggregate

Aggregate	3/4" Steel Slag
Date	March 5-6, 2002
Source	IMS Steel Slag
Tested By	M. Padula, D. Diaz & A. Kincell

(Record masses to 1g)

	A	B
A = Mass of oven-dry sample in air, grams	2497.1	2495.1
B = Mass of saturated-surface-dry sample in air, grams	2532.2	2533.8
C = Mass of saturated sample in water, grams	1793.1	1790.1

		A	B	Average	
Bulk Specific Gravity (Oven Dry Basis)	= $A/(B-C)$ =	3.379	3.355	3.367	
		Acceptable Range		0.038	
		Actual Range		0.024	OK
Bulk Specific Gravity (Saturated-Surface-Dry Basis)	= $B/(B-C)$ =	3.426	3.407	3.417	
		Acceptable Range		0.032	
		Actual Range		0.019	OK
Apparent Specific Gravity	= $A/(A-C)$ =	3.547	3.539	3.543	
		Acceptable Range		0.032	
		Actual Range		0.008	OK
Absorption, percent	= $(B-A)/A \times 100$ =	1.41%	1.55%	1.48%	
		Acceptable Range		0.41%	
		Actual Range		0.15%	OK

Report Specific Gravity to the nearest 0.01**Report Absorption to the nearest 0.1%**

Table C.3 Bulk Specific Gravity and Absorption of 1/2" Slag

WVU ASPHALT LAB

Bulk Specific Gravity and Absorption Coarse Aggregate

Aggregate	<u>1/2" Steel Slag</u>
Date	<u>March 5-6, 2002</u>
Source	<u>IMS Steel Slag</u>
Tested By	<u>M. Padula, D. Diaz & A. Kincell</u>

(Record masses to 1g)

	A	B
A = Mass of oven-dry sample in air, grams	1997.4	1996.9
B = Mass of saturated-surface-dry sample in air, grams	2030.7	2029.6
C = Mass of saturated sample in water, grams	1435.8	1430.3

	A	B	Average	
Bulk Specific Gravity (Oven Dry Basis)	3.358	3.332	3.345	
	Acceptable Range		0.038	
	Actual Range		0.025	OK
Bulk Specific Gravity (Saturated-Surface-Dry Basis)	3.414	3.387	3.400	
	Acceptable Range		0.032	
	Actual Range		0.027	OK
Apparent Specific Gravity	3.557	3.524	3.540	
	Acceptable Range		0.032	
	Actual Range		0.032	OK
Absorption, percent	1.67%	1.64%	1.65%	
	Acceptable Range		0.41%	
	Actual Range		0.03%	OK

Report Specific Gravity to the nearest 0.01**Report Absorption to the nearest 0.1%**

Table C.4 Bulk Specific Gravity and Absorption of 3/8" Slag

WVU ASPHALT LAB

Bulk Specific Gravity and Absorption Coarse Aggregate

Aggregate	3/8" Steel Slag
Date	March 5-6, 2002
Source	IMS Steel Slag
Tested By	M. Padula, D. Diaz & A. Kincell

(Record masses to 1g)

	A	B
A = Mass of oven-dry sample in air, grams	1998.2	1997.6
B = Mass of saturated-surface-dry sample in air, grams	2039.1	2037.6
C = Mass of saturated sample in water, grams	1434.2	1430.3

		A	B	Average	
Bulk Specific Gravity (Oven Dry Basis)	$= A/(B-C) =$	3.303	3.289	3.296	
		Acceptable Range		0.038	
		Actual Range		0.014	OK
Bulk Specific Gravity (Saturated-Surface-Dry Basis)	$= B/(B-C) =$	3.371	3.355	3.363	
		Acceptable Range		0.032	
		Actual Range		0.016	OK
Apparent Specific Gravity	$= A/(A-C) =$	3.543	3.521	3.532	
		Acceptable Range		0.032	
		Actual Range		0.022	OK
Absorption, percent	$= (B-A)/A*100 =$	2.05%	2.00%	2.02%	
		Acceptable Range		0.41%	
		Actual Range		0.04%	OK

Report Specific Gravity to the nearest 0.01

Report Absorption to the nearest 0.1%

Table C.5 Bulk Specific Gravity and Absorption of #4 Slag

WVU ASPHALT LAB

Bulk Specific Gravity and Absorption Coarse Aggregate

Aggregate	#4 Steel Slag
Date	March 5-6, 2002
Source	IMS Steel Slag
Tested By	M. Padula, D. Diaz & A. Kincell

(Record masses to 1g)

	A	B
A = Mass of oven-dry sample in air, grams	1994.6	1992.9
B = Mass of saturated-surface-dry sample in air, grams	2053.4	2048.5
C = Mass of saturated sample in water, grams	1428.2	1429.9

		A	B	Average	
Bulk Specific Gravity (Oven Dry Basis)	$= A/(B-C) =$	3.190	3.222	3.206	
		Acceptable Range		0.038	
		Actual Range		0.031	OK
Bulk Specific Gravity (Saturated-Surface-Dry Basis)	$= B/(B-C) =$	3.284	3.312	3.298	
		Acceptable Range		0.032	
		Actual Range		0.027	OK
Apparent Specific Gravity	$= A/(A-C) =$	3.522	3.540	3.531	
		Acceptable Range		0.032	
		Actual Range		0.018	OK
Absorption, percent	$= (B-A)/A*100 =$	2.95%	2.79%	2.87%	
		Acceptable Range		0.41%	
		Actual Range		0.16%	OK

Report Specific Gravity to the nearest 0.01

Report Absorption to the nearest 0.1%

Table C.6 Summary of Bulk Specific Gravity and Absorption for Coarse Steel Slag

WVU ASPHALT LAB

Bulk Specific Gravity and Absorption Coarse Aggregate

Aggregate	Steel Slag Summary
Date	March 5-6, 2002
Source	IMS Steel Slag
Tested By	M. Padula, D. Diaz & A. Kincell

	3/4"	1/2"	3/8"	#4	Fines
Bulk Specific Gravity (Oven Dry Basis)	3.367	3.345	3.296	3.206	2.880
Bulk Specific Gravity (Saturated-Surface-Dry Basis)	3.417	3.400	3.363	3.298	3.087
Apparent Specific Gravity	3.543	3.540	3.532	3.531	3.634
Absorption, percent	1.48%	1.65%	2.02%	2.87%	7.21%

Table C.7 Fine Steel Slag Aggregate Bulk Specific Gravity and Absorption

WVU ASPHALT LAB

Bulk Specific Gravity and Absorption
Fine Aggregate

Field Sample No.	Steel Slag Fines
Date	March 6-7, 2002
Source	IMS Steel Slag
Tested by	M. Padula, D. Diaz & A. Kincell

(Recorded masses to 0.1g)

	A	B	Average
A = Mass of oven-dry sample in air, grams (a-b)	464.7	468.5	
a = Mass of oven-dry sample and drying pan in air, grams	----		
b = Mass of drying pan, grams	----		
B = Mass of pycnometer filled to calibration mark with distilled water, grams	658.8	679.8	
C = Mass of pycnometer, sample, and water to calibration marks, grams	995.3	1019.7	
D = Mass of saturated-surface-dry sample in air, grams	500.0	500.5	
Bulk Specific Gravity (oven dry basis) = $A/(B+D-C)$ =	2.842	2.917	2.880
Bulk Specific Gravity (saturated-surface-dry basis) = $D/(B+D-C)$ =	3.058	3.116	3.087
Apparent Specific gravity = $A/(B+A-C)$ =	3.625	3.643	3.634
Absorption, percent = $(D-A)/A \times 100$ =	7.60%	6.83%	7.21%

Report Specific Gravities to the nearest 0.001

Report Absorption to the nearest 0.01%

Table C.8 Trial 1 Volumetric Data

Trial 1 - Volumetrics		
64% #57 Slag & 36% #10 Slag		
P _b Used	6.50%	
h _{des}	105.5	
h _{ini}	114.3	
G _{mb}	3.003	
G _{mm}	3.011	
% G _{mm} , N des		
% G _{mm} , N des		99.73%
Effective Specific Gravity (G _{SE})		
G _{SE}		3.473
Percent Binder Absorbed		
P _{ba}		3.22%
Percent Binder Effective		
P _{bE}		3.49%
Dust to Binder Ratio		
D to B		1.09
% G _{mm} , N ini		
% G _{mm} , N ini		92.01%
Voids in Total Mix (VTM)		
VTM		0.27%
Voids in the Mineral Agg. (VMA)		
VMA		10.41%
Voids Filled with Asph. (VFA)		
VFA		97.45%

Trial 1 - Volumetrics		
Adjusted to 4% Air		
64% #57 Slag & 36% #10 Slag		
P _b trial		6.50%
Percent Binder		
P _b est		5.00%
VMA Estimate		
VTM		2.66%
C		0.1
VMA _{est}		10.78%
VFA Estimate		
VFA _{est}		62.89%
% G _{mm} est, Nini		
% G _{mm} est, Nini		88.28%
Dust to Binder Estimate		
D/b _{est}		1.09
Estimated Effective % Binder		
P _{be, est}		3.50%
Percent Binder Trials		
P _{b,est} -0.5%		4.50%
P _{b,est}		5.00%
P _{b,est} +0.5%		5.50%
P _{b,est} +1.0%		6.00%

Superpave Criteria			
Actual Values			
Category	Tolerance	Values	Passing
VTM	~4%	0.27%	NO
VMA	13% min	10.41%	NO
VFA	65%-75%	97.45%	NO
D/B	0.60-1.20	1.09	YES

Superpave Criteria			
Theoretical Values			
Category	Tolerance	Values	Passing
VTM	~4%	4.00%	YES
VMA	13% min	10.78%	NO
VFA	65%-75%	62.89%	NO
D/B	0.60-1.20	1.09	YES

Table C.9 Trial 2 Volumetric Data

Trial 2 - Volumetrics			
64% #57 Slag & 36% #10 Slag			
P _b Used		5.50%	
h _{des}		108.8	
h _{ini}		119.1	
G _{mb}		3.036	
G _{mm}		3.069	
% G _{mm} , N des			
% G _{mm} , N des		98.92%	
Effective Specific Gravity (G _{SE})			
G _{SE}		3.467	
Percent Binder Absorbed			
P _{ba}		3.17%	
Percent Binder Effective			
P _{bE}		2.50%	
Dust to Binder Ratio			
D to B		1.52	
% G _{mm} , N ini			
% G _{mm} , N ini		90.37%	
Voids in Total Mix (VTM)			
VTM		1.08%	
Voids in the Mineral Agg. (VMA)			
VMA		8.44%	
Voids Filled with Asph. (VFA)			
VFA		87.26%	

Trial 2 - Volumetrics			
Adjusted to 4% Air			
64% #57 Slag & 36% #10 Slag			
P _b trial		5.17%	
Percent Binder			
P _b est		4.00%	
VMA Estimate			
VTM		1.08%	
C		0.1	
VMA _{est}			
VMA _{est}		8.73%	
VFA Estimate			
VFA _{est}		54.18%	
% G _{mm} est, Nini			
% G _{mm} est, Nini		87.44%	
Dust to Binder Estimate			
D/b _{est}		1.76	
Estimated Effective % Binder			
P _{be, est}		2.17%	
Percent Binder Trials			
P _{b, est} -0.5%		3.50%	
P _{b, est}		4.00%	
P _{b, est} +0.5%		4.50%	
P _{b, est} +1.0%		5.00%	

Superpave Criteria			
Actual Values			
Category	Tolerance	Values	Passing
VTM	~4%	1.08%	NO
VMA	13% min	8.44%	NO
VFA	65%-75%	87.26%	NO
D/B	0.60-1.20	1.52	NO

Superpave Criteria			
Theoretical Values			
Category	Tolerance	Values	Passing
VTM	~4%	4.00%	YES
VMA	13% min	8.73%	NO
VFA	65%-75%	54.18%	NO
D/B	0.60-1.20	1.76	NO

Table C.10 Trial 3 Volumetric Data

Trial 3 - Volumetrics			
64% #57 Slag & 36% #10 Slag			
P _b Used		5.00%	
h _{des}		112.4	
h _{ini}		123.4	
G _{mb}		3.051	
G _{mm}		3.101	
% G _{mm} , N des			
% G _{mm} , N des		98.39%	
Effective Specific Gravity (G _{SE})			
G _{SE}		3.466	
Percent Binder Absorbed			
P _{ba}		3.17%	
Percent Binder Effective			
P _{bE}		1.99%	
Dust to Binder Ratio			
D to B		1.91	
% G _{mm} , N ini			
% G _{mm} , N ini		89.62%	
Voids in Total Mix (VTM)			
VTM		1.61%	
Voids in the Mineral Agg. (VMA)			
VMA		7.52%	
Voids Filled with Asph. (VFA)			
VFA		78.56%	

Trial 3 - Volumetrics			
Adjusted to 4% Air			
64% #57 Slag & 36% #10 Slag			
P _b trial			5.00%
Percent Binder			
P _b est		4.05%	
VMA Estimate			
VTM		1.62%	
C		0.1	
VMA _{est}		7.76%	
VFA Estimate			
VFA _{est}		48.45%	
% G _{mm} est, Nini			
% G _{mm} est, Nini		87.23%	
Dust to Binder Estimate			
D/b _{est}		1.91	
Estimated Effective %Binder			
P _{be, est}		2.00%	
Percent Binder Trials			
P _{b,est} -0.5%		3.55%	
P _{b,est}		4.05%	
P _{b,est} +0.5%		4.55%	
P _{b,est} +1.0%		5.05%	

Superpave Criteria			
Actual Values			
Category	Tolerance	Values	Passing
VTM	~4%	1.61%	NO
VMA	13% min	7.52%	NO
VFA	65%-75%	78.56%	NO
D/B	0.60-1.20	1.91	NO

Superpave Criteria			
Theoretical Values			
Category	Tolerance	Values	Passing
VTM	~4%	4.00%	YES
VMA	13% min	7.76%	NO
VFA	65%-75%	48.45%	NO
D/B	0.60-1.20	1.91	NO

Table C.11 Trial 4 Volumetric Data

Trial 4 - Volumetrics		
64% #57 Slag & 36% #10 Slag		
P _b Used	4.50%	
h _{des}	115.4	
h _{ini}	124.9	
G _{mb}	3.025	
G _{mm}	3.137	
% G _{mm} , N des		
% G _{mm} , N des		96.43%
Effective Specific Gravity (G _{SE})		
G _{SE}		3.470
Percent Binder Absorbed		
P _{ba}		3.19%
Percent Binder Effective		
P _{bE}		1.45%
Dust to Binder Ratio		
D to B		2.63
% G _{mm} , N ini		
% G _{mm} , N ini		89.10%
Voids in Total Mix (VTM)		
VTM		3.57%
Voids in the Mineral Agg. (VMA)		
VMA		7.81%
Voids Filled with Asph. (VFA)		
VFA		54.29%

Trial 4 - Volumetrics		
Adjusted to 4% Air		
64% #57 Slag & 36% #10 Slag		
P _b trial		4.50%
Percent Binder		
P _b est		4.33%
VMA Estimate		
VTM		3.56%
C		0.1
VMA _{est}		7.85%
VFA Estimate		
VFA _{est}		49.04%
% G _{mm} est, Nini		
% G _{mm} est, Nini		88.66%
Dust to Binder Estimate		
D/b _{est}		2.58
Estimated Effective % Binder		
P _{be, est}		1.48%
Percent Binder Trials		
P _{b,est} -0.5%		3.83%
P _{b,est}		4.33%
P _{b,est} +0.5%		4.83%
P _{b,est} +1.0%		5.33%

Superpave Criteria			
Actual Values			
Category	Tolerance	Values	Passing
VTM	~4%	3.57%	YES
VMA	13% min	7.81%	NO
VFA	65%-75%	54.29%	NO
D/B	0.60-1.20	2.63	NO

Superpave Criteria			
Theoretical Values			
Category	Tolerance	Values	Passing
VTM	~4%	4.00%	YES
VMA	13% min	7.85%	NO
VFA	65%-75%	49.04%	NO
D/B	0.60-1.20	2.58	NO

Table C.12 Trial 5 Volumetric Data

Trial 5 - Volumetrics			
72% #57 Slag & 28% #10 Slag			
P _b Used		4.50%	
h _{des}		115.7	
h _{ini}		125.6	
G _{mb}		3.005	
G _{mm}		3.158	
% G _{mm} , N des			
% G _{mm} , N des		95.16%	
Effective Specific Gravity (G _{SE})			
G _{SE}		3.497	
Percent Binder Absorbed			
P _{ba}		3.06%	
Percent Binder Effective			
P _{bE}		1.58%	
Dust to Binder Ratio			
D to B		1.88	
% G _{mm} , N ini			
% G _{mm} , N ini		87.65%	
Voids in Total Mix (VTM)			
VTM		4.84%	
Voids in the Mineral Agg. (VMA)			
VMA		9.43%	
Voids Filled with Asph. (VFA)			
VFA		48.62%	

Trial 5 - Volumetrics			
Adjusted to 4% Air			
72% #57 Slag & 28% #10 Slag			
P _b trial		4.50%	
Percent Binder			
P _b est		4.84%	
VMA Estimate			
VTM		4.84%	
C		0.1	
VMA _{est}			
VMA _{est}		9.27%	
VFA Estimate			
VFA _{est}		56.85%	
% G _{mm} est, Nini			
% G _{mm} est, Nini		88.46%	
Dust to Binder Estimate			
D/b _{est}		1.62	
Estimated Effective % Binder			
P _{be, est}		1.82%	
Percent Binder Trials			
P _{b, est} -0.5%		4.34%	
P _{b, est}		4.84%	
P _{b, est} +0.5%		5.34%	
P _{b, est} +1.0%		5.84%	

Superpave Criteria			
Actual Values			
Category	Tolerance	Values	Passing
VTM	~4%	4.84%	YES
VMA	13% min	9.43%	NO
VFA	65%-75%	48.62%	NO
D/B	0.60-1.20	1.88	NO

Superpave Criteria			
Theoretical Values			
Category	Tolerance	Values	Passing
VTM	~4%	4.00%	YES
VMA	13% min	9.27%	NO
VFA	65%-75%	56.85%	NO
D/B	0.60-1.20	1.62	NO

Table C.13 Trial 6 Volumetric Data

Trial 6 - Volumetrics			
Agg. Blend from Literature			
P _b Used		7.00%	
h _{des}		115.5	
h _{ini}		120.0	
G _{mb}		2.946	
G _{mm}		2.950	
% G _{mm} , N _{des}			
% G _{mm} , N _{des}		99.86%	
Effective Specific Gravity (G _{SE})			
G _{SE}		3.429	
Percent Binder Absorbed			
P _{ba}		1.20%	
Percent Binder Effective			
P _{bE}		5.88%	
Dust to Binder Ratio			
D to B		1.02	
% G _{mm} , N _{ini}			
% G _{mm} , N _{ini}		96.12%	
Voids in Total Mix (VTM)			
VTM		0.14%	
Voids in the Mineral Agg. (VMA)			
VMA		16.90%	
Voids Filled with Asph. (VFA)			
VFA		99.20%	

Trial 6 - Volumetrics			
Adjusted to 4% Air			
Agg. Blend from Literature			
P _{b trial}			7.00%
Percent Binder			
P _{b est}			5.46%
VMA Estimate			
VTM		1.54%	
C		0.1	
VMA _{est}			17.31%
VFA Estimate			
VFA _{est}			76.89%
% G _{mm est} , N _{ini}			
% G _{mm est} , N _{ini}		92.26%	
Dust to Binder Estimate			
D/b _{est}			1.09
Estimated Effective % Binder			
P _{be, est}			5.50%
Percent Binder Trials			
P _{b,est} -0.5%			4.96%
P _{b,est}			5.49%
P _{b,est} +0.5%			5.96%
P _{b,est} +1.0%			6.46%

Superpave Criteria			
Actual Values			
Category	Tolerance	Values	Passing
VTM	~4%	0.14%	NO
VMA	13% min	16.90%	YES
VFA	65%-75%	99.20%	NO
D/B	0.60-1.20	1.02	YES

Superpave Criteria			
Theoretical Values			
Category	Tolerance	Values	Passing
VTM	~4%	4.00%	YES
VMA	13% min	17.31%	YES
VFA	65%-75%	76.89%	NO
D/B	0.60-1.20	1.09	YES

Table C.14 Trial 6.1 Volumetric Data

Trial 6.1 - Volumetrics (Retrial)			
Agg. Blend from Literature			
P _b Used		6.50%	
h _{des}		115.3	
h _{ini}		122.5	
G _{mb}		2.963	
G _{mm} (Estimated)		2.982	
% G _{mm} , N _{des}			
% G _{mm} , N _{des}		99.36%	
Effective Specific Gravity (G _{SE})			
G _{SE}		3.432	
Percent Binder Absorbed			
P _{ba}		1.23%	
Percent Binder Effective			
P _{bE}		5.35%	
Dust to Binder Ratio			
D to B		1.21	
% G _{mm} , N _{ini}			
% G _{mm} , N _{ini}		93.52%	
Voids in Total Mix (VTM)			
VTM		0.64%	
Voids in the Mineral Agg. (VMA)			
VMA		16.00%	
Voids Filled with Asph. (VFA)			
VFA		96.02%	

Trial 6.1 - Volumetrics (Retrial)			
Adjusted to 4% Air			
Agg. Blend from Literature			
P _b trial			6.50%
Percent Binder			
P _b est		5.15%	
VMA Estimate			
VTM		0.63%	
C		0.1	
VMA _{est}		16.31%	
VFA Estimate			
VFA _{est}		75.48%	
% G _{mm} est, N _{ini}			
% G _{mm} est, N _{ini}		90.16%	
Dust to Binder Estimate			
D/b _{est}		1.19	
Estimated Effective %t Binder			
P _{be, est}		5.03%	
Percent Binder Trials			
P _{b,est} -0.5%		4.65%	
P _{b,est}		5.15%	
P _{b,est} +0.5%		5.65%	
P _{b,est} +1.0%		6.15%	

Superpave Criteria			
Actual Values			
Category	Tolerance	Values	Passing
VTM	~4%	0.64%	NO
VMA	13% min	16.00%	YES
VFA	65%-75%	96.02%	NO
D/B	0.60-1.20	1.21	NO

Superpave Criteria			
Theoretical Values			
Category	Tolerance	Values	Passing
VTM	~4%	4.00%	YES
VMA	13% min	16.31%	YES
VFA	65%-75%	75.48%	NO
D/B	0.60-1.20	1.19	YES

Table C.15 Trial 1 Pill and Rice Test Data and Calculations

Superpave Mix Design Trial #1 Using Only IMS Steel Slag as Aggregate						
Mix Composition:		Asphalt Content 5.50%	#57 slag 64.0%	#10 Slag Sand 36.0%		
Maximum Specific Gravity (Dry-Back Procedure Method) [Rice Test]						
		Sample Number				
		1-A		1-B		
Date Performed		3/14/2002		3/14/2002		
Percent Asphalt Used		6.50%		6.50%		
		Dryback		Dryback		
Sample weight (g) (A)		1983.1		1906.3		
Bowl + Sample in water weight (B)		2647.0		2786.1		
Bowl in water (Calibration weight) (C)		1330.0		1511.1		
Surface Dry Sample weight (D)		1977.2		1910.0		
Maximum Specific Gravity		3.004		3.002		
		Average Gmm	3.003			
Weighing Interval		Wt. Pan + Samp	Wt. Pan + Samp			
	0 Min	2430.3	2366.6			
	15 Min	2426.4	2360.6			
	...	...	...			
	135 Min	2413.4	2346.2			
	150 Min	2413.4	2346.2			
Wt of Pan (g)		425.0	436.2			
Precision Requirements: $ G_{mm1} - G_{mm2} \leq 0.019$						
Number of Operators					1	
Acceptable Precision					YES	
WVU Asphalt Lab Test Results for Gryatory Compaction Sample						
		Average Gmm from Rice Test			3.003	
Pill #	1-A	Dry	Wet	SSD	Gmb	% Air
	Weight	5504.9	3670.4	5507.4	2.997	0.21%
Date	3/27/2002					
Pill #	1-B	Dry	Wet	SSD	Gmb	% Air
	Weight	5439.9	3624.5	5442.6	2.992	0.36%
Date	3/27/2002					
Averages					2.994	0.28%
Precision Requirements: $ G_{mb1} - G_{mb2} \leq 0.019$						
Number of Operators					1	
Acceptable Precision					YES	

Table C.16 Trial 2 Pill and Rice Test Data and Calculations

Superpave Mix Design Trial #2 Using Only IMS Steel Slag as Aggregate				
Mix Composition:	Asphalt Content	#57 slag	#10 Slag Sand	
	5.50%	64.0%	36.0%	
Maximum Specific Gravity (Rice Test)				
	Sample Number			
	2-A		2-B	
Date Performed	3/29/2002		3/29/2002	
Percent Asphalt Used	5.50%		5.50%	
	Non-dryback		Non-dryback	
Sample weight (g) (A)	1947.7		1926.0	
Bowl + Sample in water weight (B)	2643.2		2806.6	
Bowl in water (Calibration weight) (C)	1330.0		1511.1	
Maximum Specific Gravity	3.070		3.055	
	Average Gmm	3.062		
Precision Requirements: $ G_{mm1}-G_{mm2} \leq 0.019$				
Number of Operators 1				
Acceptable Precision YES				

WVU Asphalt Lab Test Results for Gryatory Compaction Sample						
	Average Gmm from Rice Test				3.062	
Pill #	2-A	Dry	Wet	SSD	Gmb	% Air
	Weight	5633.4	3780.1	5638.7	3.031	1.02%
Date	3/29/2002					
Pill #	2-B	Dry	Wet	SSD	Gmb	% Air
	Weight	5623.1	3779.1	5627.7	3.042	0.67%
Date	3/29/2002					
	Averages				3.036	0.84%
Precision Requirements: $ G_{mb1}-G_{mb2} \leq 0.019$						
Number of Operators					1	
Acceptable Precision					YES	

Table C.17 Trial 3 Pill and Rice Test Data and Calculations

Superpave Mix Design Trial #3 Using Only IMS Steel Slag as Aggregate			
Mix Composition:	Asphalt Content 5.00%	#57 slag 64.0%	#10 Slag Sand 36.0%
Maximum Specific Gravity (Rice Test)			
	Sample Number		
	3-A		3-B
Date Performed	4/9/2002		4/9/2002
Percent Asphalt Used	5.00%		5.00%
	Non-dryback		Non-dryback
Sample weight (g) (A)	1981.0		1950.8
Bowl + Sample in water weight (B)	2853.3		2649.3
Bowl in water (Calibration weight) (C)	1511.1		1330.0
Maximum Specific Gravity	3.101		3.089
Average Gmm		3.095	
Precision Requirements: $ G_{mm1}-G_{mm2} \leq 0.019$			
Number of Operators		1	
Acceptable Precision		YES	

WVU Asphalt Lab Test Results for Gryatory Compaction Sample						
Pill #	Average Gmm from Rice Test				3.095	
	3-A	Dry	Wet	SSD	Gmb	% Air
	Weight	5804.9	3907.6	5815.2	3.043	1.68%
	Date	4/9/2002				
Pill #	3-B	Dry	Wet	SSD	Gmb	% Air
	Weight	5732.6	3873.8	5746.5	3.061	1.10%
	Date	4/9/2002				
	Averages				3.052	1.39%
Precision Requirements: $ G_{mb1}-G_{mb2} \leq 0.019$						
Number of Operators					1	
Acceptable Precision					YES	

Table C.18 Trial 4 Pill and Rice Test Data and Calculations

Superpave Mix Design Trial #4 Using Only IMS Steel Slag as Aggregate			
Mix Composition:	Asphalt Content 4.50%	#57 slag 64.0%	#10 Slag Sand 36.0%
Maximum Specific Gravity (Rice Test)			
	Sample Number		
	4-A		4-B
Date Performed	4/16/2002		4/16/2002
Percent Asphalt Used	4.50%		4.50%
	Non-dryback		Non-dryback
Sample weight (g) (A)	1972.4		1965.2
Bowl + Sample in water weight (B)	2855.7		2667.9
Bowl in water (Calibration weight) (C)	1511.1		1330.0
Maximum Specific Gravity	3.142		3.133
Average Gmm		3.137	
Precision Requirements: $ G_{mm1}-G_{mm2} \leq 0.019$			
Number of Operators			1
Acceptable Precision			YES

WVU Asphalt Lab Test Results for Gryatory Compaction Sample						
	Average Gmm from Rice Test				3.137	
Pill #	4A	Dry	Wet	SSD	Gmb	% Air
	Weight	5813.5	3916.6	5834.5	3.031	3.38%
Date	4/16/2002					
Pill #	4B	Dry	Wet	SSD	Gmb	% Air
	Weight	5815.5	3917.3	5843.1	3.020	3.75%
Date	4/16/2002					
	Averages				3.025	3.56%
Precision Requirements: $ G_{mb1}-G_{mb2} \leq 0.019$						
Number of Operators					1	
Acceptable Precision					YES	

Table C.19 Trial 5 Pill and Rice Test Data and Calculations

Superpave Mix Design Trial #5 Using Only IMS Steel Slag as Aggregate																					
Mix Composition:	Asphalt Content 4.50%	#57 slag 72.0%	#10 Slag Sand 28.0%																		
Maximum Specific Gravity (Rice Test)																					
	<table><tr><th colspan="2">Sample Number</th></tr><tr><td>5-A</td><td>5-B</td></tr><tr><td>5/8/2002</td><td>5/8/2002</td></tr><tr><td>4.50%</td><td>4.50%</td></tr><tr><td>Non-dryback</td><td>Non-dryback</td></tr><tr><td>1973.4</td><td>1973.2</td></tr><tr><td>2860.8</td><td>2857.9</td></tr><tr><td>1511.1</td><td>1511.1</td></tr><tr><td>3.164</td><td>3.150</td></tr></table>			Sample Number		5-A	5-B	5/8/2002	5/8/2002	4.50%	4.50%	Non-dryback	Non-dryback	1973.4	1973.2	2860.8	2857.9	1511.1	1511.1	3.164	3.150
Sample Number																					
5-A	5-B																				
5/8/2002	5/8/2002																				
4.50%	4.50%																				
Non-dryback	Non-dryback																				
1973.4	1973.2																				
2860.8	2857.9																				
1511.1	1511.1																				
3.164	3.150																				
Date Performed																					
Percent Asphalt Used																					
Sample weight (g) (A)																					
Bowl + Sample in water weight (B)																					
Bowl in water (Calibration weight) (C)																					
Maximum Specific Gravity																					
	<table><tr><td>Average Gmm</td><td>3.157</td></tr></table>	Average Gmm	3.157																		
Average Gmm	3.157																				
<table><tr><td colspan="2">Precision Requirements: $G_{mm1}-G_{mm2} \leq 0.019$</td></tr><tr><td>Number of Operators</td><td>1</td></tr><tr><td>Acceptable Precision</td><td>YES</td></tr></table>				Precision Requirements: $ G_{mm1}-G_{mm2} \leq 0.019$		Number of Operators	1	Acceptable Precision	YES												
Precision Requirements: $ G_{mm1}-G_{mm2} \leq 0.019$																					
Number of Operators	1																				
Acceptable Precision	YES																				

WVU Asphalt Lab Test Results for Gryatory Compaction Sample						
Pill #	Average Gmm from Rice Test				3.157	
	5A	Dry	Wet	SSD	Gmb	% Air
	Weight	5592.4	3755.8	5627.6	2.988	5.36%
Date	5/8/2002					
Pill #	5B	Dry	Wet	SSD	Gmb	% Air
	Weight	5635.3	3800.8	5665.3	3.022	4.26%
	Date	5/8/2002				
Averages					3.005	4.81%
Precision Requirements: $ G_{mm1} - G_{mm2} \leq 0.019$						
Number of Operators					1	
Acceptable Precision					NO	

Table C.20 Trial 6 Pill and Rice Test Data and Calculations

Superpave Mix Design Trial #6 Using Only IMS Steel Slag as Aggregate (Gradation from Literature)			
Mix Composition:	Asphalt Content 7.00%	Blend Data Note: Blend is comprised of 100% IMS Slag	Gradation from Lit. Review
Maximum Specific Gravity (Rice Test)			
	Sample Number		
	6-A		6-B
Date Performed	6/20/2002		6/20/2002
Percent Asphalt Used	7.00%		7.00%
	Non-dryback		Non-dryback
Sample weight (g) (A)	1981.6		1981.9
Bowl + Sample in water weight (B)	2819.1		2642.0
Bowl in water (Calibration weight) (C)	1511.1		1330.0
Maximum Specific Gravity	2.942		2.959
		Average Gmm	2.950
Precision Requirements: $ G_{mm1}-G_{mm2} \leq 0.019$			
Number of Operators			1
Acceptable Precision			YES

WVU Asphalt Lab Test Results for Gryatory Compaction Sample						
	Average Gmm from Rice Test			2.950		
Pill #	6A1	Dry	Wet	SSD	Gmb	% Air
	Weight	5901.5	3904.8	5907.2	2.947	0.10%
Date	6/26/2002					
Pill #	6A2	Dry	Wet	SSD	Gmb	% Air
	Weight	5896.3	3898.6	5901.4	2.944	0.21%
Date	6/26/2002					
	Averages				2.946	0.15%
Precision Requirements: $ G_{mm1}-G_{mm2} \leq 0.019$						
Number of Operators					1	
Acceptable Precision					YES	

Table C.21 Trial 6.1 Pill and Rice Test Data and Calculations

Superpave Mix Design Trial #6.1 Retrial of Trial 6 (To confirm data)			
Mix Composition:	Asphalt Content 7.00%	Blend Data Note: Blend is comprised of 100% IMS Slag	Gradation from Lit. Review
Maximum Specific Gravity (Rice Test)			
Date Performed	Sample Number		
Percent Asphalt Used			
Sample weight (g) (A)	0.0	0.0	
Bowl + Sample in water weight (B)	0.0	0.0	
Bowl in water (Calibration weight) (C)	0.0	0.0	
Maximum Specific Gravity	0.000	0.000	
Average Gmm		2.982	
Note: G_{mm} value estimated from aggregate data			
Precision Requirements: $ G_{mm1} - G_{mm2} \leq 0.019$			
Number of Operators		N/A	
Acceptable Precision		N/A	

WVU Asphalt Lab Test Results for Gryatory Compaction Sample						
		Average Gmm from Rice Test			2.982	
Pill #	6.1 A1	Dry	Wet	SSD	Gmb	% Air
	Weight	5907.7	3924.7	5915.9	2.967	0.51%
Date	6/28/2002					
Pill #	6.1 A2	Dry	Wet	SSD	Gmb	% Air
	Weight	5929.3	3932.9	5936.4	2.959	0.76%
Date	6/28/2002					
Averages					2.963	0.63%
Precision Requirements: $ G_{mm1} - G_{mm2} \leq 0.019$						
Number of Operators					1	
Acceptable Precision					YES	

Table C.22 Rut Testing Results

WWU Asphalt Lab Test Results for Creation of Samples for Rut Testing

Maximum Specific Gravity (Rice Test)				
	Rut Rice #1		Rut Rice #2	
Date Performed	6/10/2002		6/10/2002	
Percent Asphalt Used	4.50%		4.50%	
	Non-dryback		Non-dryback	
Sample weight (g) (A)	1981.2		1981.7	
Bowl + Sample in water weight (B)	2870.4		2686.5	
Bowl in water (Calibration weight) (C)	1511.1		1330.0	
Maximum Specific Gravity	3.186		3.170	
Average Gmm		3.178		

	Weights (g)				
	Dry	Wet	SSD	Gmb	% Air
	3543.3	2365.8	3570.5	2.941	7.44%
Rut Sample# 1					
	Rut Depths (mm)		7.60	7.74	
	Average Rut Depth (mm)		7.67		
	3564.3	2384.9	3592.4	2.952	7.11%
Rut Sample# 2					
	Rut Depths (mm)		7.92	7.46	
	Average Rut Depth (mm)		7.69		
	3552.2	2387.6	3579.7	2.980	6.23%
Rut Sample# 3					
	Rut Depths (mm)		7.72	7.87	
	Average Rut Depth (mm)		7.80		
	3556.8	2377	3583.4	2.948	7.22%
Rut Sample# 4					
	Rut Depths (mm)		6.24	6.28	
	Average Rut Depth (mm)		6.26		
	3548.5	2370.2	3578.6	2.937	7.59%
Rut Sample# 5					
	Rut Depths (mm)		9.02	9.46	
	Average Rut Depth (mm)		9.24		
	3555.2	2382.2	3594.4	2.933	7.71%
Rut Sample# 6					
	Rut Depths (mm)		7.88	7.04	
	Average Rut Depth (mm)		7.46		
			Gmb	% Air	Rut Depth
Averages			2.948	7.22%	7.69

VITA

Martin Felix Padula was born on November 22, 1977 in Detroit, Michigan, the son of Donald and Ann Padula. In 1983 he moved with his family to Fairmont, West Virginia, where he received his primary and secondary education. After completing his work at East Fairmont High School in 1996, he studied Physics and Business at West Virginia Wesleyan College. He earned a Bachelor of Science degree with honors in Business Administration from WVWC in 2000, with minors in Physics, Mathematics, and Economics. Upon graduation, he enrolled in the B.S. program in Civil Engineering at West Virginia University, completing the degree in May 2002, graduating Magna Cum Laude. After 8 months of intense graduate work, he finished his Master of Science degree from WVU in December 2002. He plans to pursue a career as a professional civil engineer.

Permanent Address: Rt. 4 Box 576B
Fairmont, WV 26554

This thesis was created and typed by Martin Padula.