2015

Asphalt and Concrete Pavement Condition Analysis for the WVDOH

Frank Peter Taverna III

Follow this and additional works at: <https://researchrepository.wvu.edu/etd>

Recommended Citation

Taverna III, Frank Peter, "Asphalt and Concrete Pavement Condition Analysis for the WVDOH" (2015). *Graduate Theses, Dissertations, and Problem Reports*. 6778.
<https://researchrepository.wvu.edu/etd/6778>

This Thesis is protected by copyright and/or related rights. It has been brought to you by the The Research Repository @ WVU with permission from the rights-holder(s). You are free to use this Thesis in any way that is permitted by the copyright and related rights legislation that applies to your use. For other uses you must obtain permission from the rights-holder(s) directly, unless additional rights are indicated by a Creative Commons license in the record and/ or on the work itself. This Thesis has been accepted for inclusion in WVU Graduate Theses, Dissertations, and Problem Reports collection by an authorized administrator of The Research Repository @ WVU. For more information, please contact researchrepository@mail.wvu.edu.

Asphalt and Concrete Pavement Condition Analysis for the WVDOH

Frank Peter Taverna III

Thesis submitted to the College of Engineering and Mineral Resources
at West Virginia University in partial fulfillment of the requirements for
the degree of

Master of Science

In

Civil Engineering

Dr. John P. Zaniewski, Chair

Dr. John Quaranta

Dr. Avinash Unnikrishnan

Department of Civil and Environmental Engineering

Morgantown, West Virginia

March 2015

Key Words: Pavement Surface Rating, PSR, pavement condition, pavement surface distress, pavement type selection,

Abstract

Asphalt and Concrete Pavement Condition Analysis for the WVDOH

Frank Peter Taverna III

The objective of this research was to compare the condition of the asphalt and concrete sections of pavement on a section of US 35 for the West Virginia Division of Highways. In the process of completing this objective, existing procedures for pavement assessment were evaluated and an improved methodology for pavement condition evaluation, in terms of Pavement Surface Rating, PSR, was established. PSR uses observable surface distresses to quantify the condition of a pavement on a 0 to 100 scale. The PSR methodology includes surface distress data collection, a distress identification manual, and a PSR calculation procedure and spreadsheet. This process has been adopted by the WVDOH and is included in the special provision specification for pavements constructed using a warranted agreement.

Data from the WVDOH Pavement Management System, PMS, were used to evaluate pavement condition but ultimately deemed ineffective in a relatively small scale analysis. The methodology used to collect and analyze the PMS data was not compatible with the PSR methodology.

Deflection data gathered with a falling weight deflectometer were used to evaluate and compare the structural condition of the US 35 asphalt and concrete pavement sections. A screening of the deflection data on the concrete sections found the number of observations was an insufficient for meaningful analysis. The deflection data on the asphalt pavement sections were suitable for analysis. Since the WVDOH does not have an analysis methodology for deflection data, the research effort on this project focused on applying existing methodologies used for the analysis of deflection data. Due to the data problems, the analysis of the concrete sections was limited. The analysis of the asphalt sections was able to determine effective structural number for the asphalt sections. The analysis process is complex and several issues should be resolved to improve the ability of the WVDOH to use deflection analysis in a routine manner.

Table of Contents

Chapter 1. Introduction	1
1.1 Background	1
1.2 Objective	4
1.3 Scope and Limitations of Research	4
1.4 Organization of Thesis.....	4
Chapter 2. Literature Review	6
2.1 Pavement Surface Distress Indices and Rating Systems	6
2.1.1 Pavement Condition Index	6
2.1.2 MnDOT Surface Rating.....	12
2.1.3 WVDOH Pavement Surface Rating, PSR	14
2.1.4 West Virginia DOH PMS Pavement Distress Evaluation.....	18
2.2 Deflection Testing and Analysis of Deflection Data	21
2.2.1 Falling Weight Deflectometer and Backcalculation of Layer Moduli	21
2.2.2 MODULUS 6.1.....	27
2.2.3 MODTAG	28
2.2.4 BAKFAA.....	29
2.3 Summary of Literature	30
Chapter 3. Methodology.....	31
3.1 Pavement Surface Rating Data Collection and Analysis Process	31
3.1.1 Data Collection Process for Pavement Surface Rating.....	31
3.1.2 Data Analysis Process for Pavement Surface Rating.....	35
3.2 ARAN Surface Distress Data Collection and Comparison Process	39
3.3 Deflection Testing Data Collection and Analysis Process.....	39
3.3.1 Deflection Data Collection	40

3.3.2	Initial Screening of Deflection Data.....	40
3.3.3	MODULUS 6.1 Deflection Data Analysis Process	40
3.3.4	MODTAG Deflection Data Analysis Process	42
3.3.5	BAKFAA Deflection Data Analysis Process	42
Chapter 4.	Analysis.....	44
4.1	Analysis of Improvements in Pavement Surface Rating Process	44
4.1.1	Initial Analysis of US 35 PSR	44
4.1.2	Refinement of PSR Calculation Procedure	46
4.2	Comparison Analysis of ARAN and Manual Survey Surface Distress Data	51
4.3	Deflection Data Analysis	56
Chapter 5.	Results.....	61
5.1	Pavement Surface Rating	61
5.1.1	US 35 PSR Original 2012 Spec. Calculation.....	61
5.1.2	Comparison and Correlation of PSR and PCI.....	63
5.1.3	Recommended PSR Procedure.....	65
5.1.4	US 35 PSR with Recommended Method	68
5.1.5	US 35 PSR Final Calculation vs. Original 2012 Spec. Calculation.....	78
5.2	Comparison of ARAN and PSR Survey Surface Distress Data.....	84
5.3	Deflection Data Results and Summary.....	88
Chapter 6.	Conclusions and Recommendations	91
6.1	Conclusions	91
6.1.1	Pavement Surface Rating	91
6.1.2	Comparison of ARAN and PSR Survey Surface Distress Data	95
6.1.3	FWD Data Analysis	96
6.2	Recommendations	96
6.2.1	Pavement Surface Rating	96

6.2.2	FWD Data and Analysis	97
	References	98
	Appendix A. WVDOT Distress Identification Manual (for PSR calculation).....	100
A.1	Asphalt Surfaces.....	100
A.1.1	Transverse Cracks – #1.....	100
A.1.2	Edge Cracking – #2	101
A.1.3	Alligator Cracking – #3	101
A.1.4	Block Cracking – #4	102
A.1.5	Longitudinal Cracking – #5	103
A.1.6	Longitudinal Joint Deterioration – #6	103
A.1.7	Lane Edge Cracking/Deterioration – #7	104
A.1.8	Raveling/Weathering – #8	106
A.1.9	Patching – #9.....	106
A.1.10	Rutting – #10.....	106
A.2	Concrete Surfaces	107
A.2.1	Transverse Cracks – #11.....	107
A.2.2	Transverse Joint Spalls – #12	108
A.2.3	Transverse Joint Faults – #13.....	109
A.2.4	Blowups – #14.....	109
A.2.5	Longitudinal Cracking – #15	110
A.2.6	Longitudinal Joint Spalling – #16.....	110
A.2.7	Lane Edge Spalling – #17.....	111
A.2.8	D Cracking – #18.....	112
A.2.9	Scaling – #19	112
A.2.10	Patching – #20.....	113
A.2.11	Popouts – #21	113

Appendix B. Deduct Curve Comparison	114
B.1 Deduct Comparison for Asphalt Surfaces	115
B.2 Deduct Comparison for Concrete Surfaces.....	125
Appendix C. FWD text files.....	137
C.1 US 35 All Northbound Drops .FWD (.R80) File Format	137
C.2 US 35 All Southbound Drops .FWD (.R80) File Format	147

List of Figures

Figure 1: Location of US 35 Section Designated for Research Project.....	1
Figure 2: Example of a Flexible Pavement Condition Survey Data Sheet (ASTM D6433-11, 2011).....	7
Figure 3: Example of Jointed Rigid Pavement Condition Survey Data Sheet (ASTM D6433-11, 2011)	8
Figure 4: Example Deduct Value Curves (ASTM D6433-11, 2011).....	9
Figure 5: Calculation of Corrected PCI Value-Flexible Pavement Example from Figure 2(ASTM D6433-11, 2011)	10
Figure 6: Corrected Deduct Value from Total Deduct Value and number of deducts “q” for HMA (ASTM D6433-11, 2011)	11
Figure 7: Standard PCI Rating Scale (after ASTM D6433-11, 2011)	11
Figure 8: ARAN 9000 (Fugro Roadware Inc., 2012).....	19
Figure 9: WVDOH DYNATEST Falling Weight Deflectometer Trailer on US 35	22
Figure 10: Falling Weight Deflectometer Deflection Basin (Cornell University, 2005).....	23
Figure 11: Averaged graphical representation of temperature gradient within asphalt pavements (Alnouri, 1972)	25
Figure 12: Asphalt Section Surface Distress Survey Diagram Segment	33
Figure 13: Concrete Section Surface Distress Survey Diagram Segment.....	34
Figure 14: Final PCI vs. PSR Correlation for Asphalt Surfaces	63
Figure 15: Final PCI vs. PSR Correlation for Concrete Surfaces.....	64
Figure 16: Combination of PCI vs. PSR Correlations to Compare Asphalt and Concrete.....	64
Figure 17: Combined PCI vs. PSR Correlations for all Pavement Surfaces.....	65
Figure 18: Blank Asphalt Surface Segment PSR Calculator	67
Figure 19: Blank Concrete Surface Segment PSR Calculator.....	68

Figure 20: US 35 Asphalt Northbound Slow Lane Pavement Age vs. PSR	71
Figure 21: US 35 Asphalt Northbound Slow Lane Mile Marker vs. PSR.....	71
Figure 22: US 35 Asphalt Northbound Fast Lane Pavement Age vs. PSR.....	72
Figure 23: US 35 Asphalt Northbound Fast Lane Mile Marker vs. PSR.....	72
Figure 24: US 35 Asphalt Southbound Slow Lane Pavement Age vs. PSR	73
Figure 25: US 35 Asphalt Southbound Slow Lane Mile Marker vs. PSR.....	73
Figure 26: US 35 Asphalt Southbound Fast Lane Pavement Age vs. PSR.....	74
Figure 27: US 35 Asphalt Southbound Fast Lane Mile Marker vs. PSR.....	74
Figure 28: US 35 Concrete Northbound Slow Lane Pavement Age vs. PSR	75
Figure 29: US 35 Concrete Northbound Slow Lane Mile Markers vs. PSR.....	75
Figure 30: US 35 Concrete Northbound Fast Lane Pavement Age vs. PSR	76
Figure 31: US 35 Concrete Northbound Fast Lane Mile Marker vs. PSR	76
Figure 32: US 35 Concrete Southbound Slow Lane Pavement Age vs. PSR.....	77
Figure 33: US 35 Concrete Southbound Slow Lane Mile Marker vs. PSR	77
Figure 34: US 35 Concrete Southbound Fast Lane Pavement Age vs. PSR	78
Figure 35: US 35 Concrete Southbound Fast Lane Mile Marker vs. PSR	78
Figure 36: Asphalt Northbound Slow Lane Survey 5 – 2012 Spec. vs 2015 Spec.	80
Figure 37: Asphalt Northbound Fast Lane Survey 5 - 2012 Spec. vs 2015 Spec.	80
Figure 38: Asphalt Southbound Slow Lane Survey 5 - 2012 Spec. vs 2015 Spec.	81
Figure 39: Asphalt Southbound Fast Lane Survey 5 - 2012 Spec. vs 2015 Spec.	81
Figure 40: Concrete Northbound Slow Lane Survey 5 - 2012 Spec. vs 2015 Spec.....	82
Figure 41: Concrete Northbound Fast Lane Survey 5 - 2012 Spec. vs 2015 Spec.....	83
Figure 42: Concrete Southbound Slow Lane Survey 5 - 2012 Spec. vs 2015 Spec.....	83
Figure 43: Concrete Southbound Fast Lane Survey 5 - 2012 Spec. vs. 2015 Spec.....	84
Figure 44: Structural Cracking Index - Manual Survey Data vs. PMS Data Comparison	85
Figure 45: Environmental Cracking Index - Manual Survey Data vs. PMS Data Comparison	85
Figure 46: Net Cracking Index - Manual Survey Data vs. PMS Data Comparison	86
Figure 47: Rut Depth Index - Manual Survey Data vs. PMS Data Comparison	86
Figure 48: Joint Condition Index - Manual Survey Data vs. PMS Data Comparison	87
Figure 49: Concrete Slab Index - Manual Survey Data vs. PMS Data Comparison	87
Figure 50: Asphalt SN_{eff} Comparison	88
Figure 51: BAKFAA Temperature vs. Surface Modulus.....	89

Figure 52: BAKFAA Temperature vs. Subgrade Modulus.....	89
Figure 53: Graphical Comparison of PCI and 2015 PSR Ranges for Qualitative Descriptors	92
Figure 54: Average PSR Comparison: Asphalt vs. Concrete	93
Figure 55: Asphalt Average PSR Comparison: Fast Lane vs. Slow Lane	94
Figure 56: Concrete Average PSR Comparison: Fast Lane vs. Slow Lane.....	94
Figure 57: Fast Lane Average PSR Comparison: Asphalt vs. Concrete.....	95
Figure 58: Slow Lane Average PSR Comparison: Asphalt vs. Concrete.....	95
Figure 59: Transverse Cracks Low Severity Deduct Curve Comparison.....	115
Figure 60: Transverse Cracks Medium Severity Deduct Curve Comparison.....	116
Figure 61: Transverse Cracks High Severity Deduct Curve Comparison	116
Figure 62: Edge Cracking Low Severity Deduct Curve Comparison	117
Figure 63: Edge Cracking Medium Severity Deduct Curve Comparison	117
Figure 64: Edge Cracking High Severity Deduct Curve Comparison	118
Figure 65: Alligator Cracking Low Severity Deduct Curve Comparison	118
Figure 66: Alligator Cracking Medium Severity Deduct Curve Comparison	119
Figure 67: Alligator Cracking High Severity Deduct Curve Comparison.....	119
Figure 68: Block Cracking Low Severity Deduct Curve Comparison	120
Figure 69: Block Cracking Medium Severity Deduct Curve Comparison	120
Figure 70: Block Cracking High Severity Deduct Curve Comparison.....	121
Figure 71: Longitudinal Cracking Low Severity Deduct Curve Comparison	121
Figure 72: Longitudinal Cracking Medium Severity Deduct Curve Comparison	122
Figure 73: Longitudinal Cracking High Severity Deduct Curve Comparison	122
Figure 74: Raveling/Weathering Deduct Curve Comparison.....	123
Figure 75: Patching Deduct Curve Comparison	124
Figure 76: Rutting Low Severity Deduct Curve Comparison	125
Figure 77: Rutting High Severity Deduct Curve Comparison	125
Figure 78: Transverse Cracks Low Severity Deduct Curve Comparison.....	126
Figure 79: Transverse Cracks Medium Severity Deduct Curve Comparison.....	126
Figure 80: Transverse Cracks High Severity Deduct Curve Comparison	127
Figure 81: Transverse Joint Spalls Low Severity Deduct Curve Comparison	128
Figure 82: Transverse Joint Spalls Medium Severity Deduct Curve Comparison	128
Figure 83: Transverse Joint Spalls High Severity Deduct Curve Comparison.....	129

Figure 84: Faulting Low Severity Deduct Curve Comparison	129
Figure 85: Faulting Medium Severity Deduct Curve Comparison.....	130
Figure 86: Faulting High Severity Deduct Curve Comparison	130
Figure 87: Blowups Deduct Curve Comparison	131
Figure 88: Longitudinal Cracking Low Severity Deduct Curve Comparison	132
Figure 89: Longitudinal Cracking Medium Severity Deduct Curve Comparison	132
Figure 90: Longitudinal Cracking High Severity Deduct Curve Comparison	133
Figure 91: D-Cracking Deduct Curve Comparison.....	134
Figure 92: Scaling Deduct Curve Comparison	135
Figure 93: Patching Deduct Curve Comparison	135
Figure 94: Popouts Deduct Curve Comparison	136

List of Tables

Table 1: List of one-tenth mile test sections by start/end mile post	3
Table 2: HMA Surface Pavement Distress Types and Measurements (Office of Materials and Road Research Pavement Management Unit, 2003).....	12
Table 3: Jointed Concrete Pavement Distress Types and Measurements (Office of Materials and Road Research Pavement Management Unit, 2003).....	13
Table 4: HMA Pavement SR Weight Factors (Office of Materials and Road Research Pavement Management Unit, 2003).....	13
Table 5: Jointed Concrete Pavement SR Weight Factors (Office of Materials and Road Research Pavement Management Unit, 2003)	13
Table 6: Total Weighted Percent or Total Weighted Distress Conversion to SR (Office of Materials and Road Research Pavement Management Unit, 2003).....	14
Table 7: PSR Asphalt Distresses, severity levels, and units (Section 490 Nine Year Pavement Performance Criteria)	15
Table 8: PSR Concrete Distresses, severity levels, and units (Section 490 Nine Year Pavement Performance Criteria, 2012)	16
Table 9: PSR Asphalt Distress Weight Factors (Section 490 Nine Year Pavement Performance Criteria, 2012)	16
Table 10: PSR Concrete Distress Weight Factors (Section 490 Nine Year Pavement Performance Criteria, 2012)	17

Table 11: Example of Incentive Performance Criteria for Bonus and Penalty (Section 490 Nine Year Pavement Performance Criteria, 2012)	18
Table 12: Longitudinal Cracking within NB 12.6-12.7 (HMA Section).....	36
Table 13: Transverse Spalled Joints within NB 9.1-9.2 (PCC Section).....	37
Table 14: Post Survey 3 PSR Calculator for Slow Lane of NB 13.2-13.3 (HMA Section)	38
Table 15: Post Survey 3 PSR Calculator for Slow Lane of NB 9.4-9.5 (PCC Section)	38
Table 16: Summary of WVDOT PMS Distress Data for US 35 Northbound Slow Lane Asphalt Section.....	52
Table 17: Summary of WVDOT PMS Distress Data for US 35 Northbound Slow Lane Concrete Section ..	52
Table 18: WVDOT PMS Legend for Distress Data as provided with Distress Summary	53
Table 19: Variation between PSI calculated from IRI and PSI provided	55
Table 20: Inconsistencies between WVDOT PMS and Section 490, Special Provision distress definition and severities	56
Table 21: Estimated SN_{eff} Summary	57
Table 22: Estimated SN_{eff} Identification of Values Generated using M_R^*	57
Table 23: Summary of Asphalt Section SN_{eff} Values at Each Test Location with Addition of Cut/Fill Information	58
Table 24: Reorganization of Table 23 by Cuts and Fills.....	59
Table 25: BAKFAA Moduli Values for Eligible Concrete Drops	60
Table 26: Initial PSR Calculation for Northbound Asphalt Section	61
Table 27: Initial PSR Calculation for Northbound Concrete Section.....	61
Table 28: Initial PSR Calculation for Southbound Asphalt Section	62
Table 29: Initial PSR Calculation for Southbound Concrete Section.....	62
Table 30: Summary of US 35 Concrete Section PSR	69
Table 31: Summary of US 35 Asphalt Section PSR.....	70
Table 32: Asphalt Northbound Survey 5 - 2012 Spec. vs 2015 Spec.....	79
Table 33: Asphalt Southbound Survey 5 - 2012 Spec. vs 2015 Spec.....	79
Table 34: Concrete Northbound Survey 5 - 2012 Spec. vs 2015 Spec.	82
Table 35: Concrete Southbound - Survey 5 - 2012 Spec. vs 2015 Spec.	82
Table 36: Final Summary of Estimated Asphalt SN_{eff}	88
Table 37: Asphalt and Concrete Average Subgrade Modulus Values.....	90
Table 38: Comparison of PCI and 2015 PSR Ranges for Qualitative Descriptors.....	91

Chapter 1. Introduction

1.1 Background

Slightly over 7 miles of US 35 in Mason County, south of Point Pleasant, West Virginia were paved in October 2010 and were identified as a potential subject for development of a warranty specification and additional research for the West Virginia Department of Transportation Division of Highways. The approximate start and end points of the test section are the two intersections of Kanawha Valley Road and US 35. These are located at mile post 9.0 on the south end and 16.5 on the north end of the test section. This stretch of US 35 is a divided highway with 2 lanes in the northbound and southbound directions. It is a common truck route between Charleston, West Virginia and regions of Ohio. At mile post 12.5, which is the overpass bridging Upper Fivemile Creek and Arlee-Couch Road, there is a border between pavement types. Everything south of this point is portland cement concrete constructed by Kokosing Construction Company. Everything north of this point is asphalt pavement laid by West Virginia Paving and Bizzack Construction Company. Figure 1 identifies the section of US 35 designated for this research project.

Figure 1: Location of US 35 Section Designated for Research Project

Of the 7-plus miles of highway section (northbound and southbound), 16 one-tenth mile sections in both the northbound and southbound directions (32 total) were selected as a representative

sample (shown in Table 1). There are three overpasses and three intersections within the entire section. All overpasses are concrete slab bridges with small sections paved in asphalt approaching and leaving the bridges. Within the concrete test sections, there are two cases where the northbound and southbound test section mile posts do not match. Test sections were shifted to avoid overpasses in these instances. Of the three intersections, none are significant stopping points for any trucks, so essentially all heavy traffic travels the length of the test section. Of the 16 one-tenth mile sections in each direction, nine were paved entirely in asphalt and the remaining seven in concrete. The surface materials, directions, and start/finish mile posts (in order of travel direction) are shown in Table 1.

According to as-built drawings, from surface down, asphalt pavement cross-sections consist of:

- 1.5" Superpave HMA 9.5 mm NMA
- 2.25" Superpave HMA 19 mm NMA
- 9" Superpave HMA 37.5 mm NMA (Two 4.5" lifts)
- 4" open graded free draining base
- Subgrade soil

Per the WVDOT Design Directive manual, the Structural Number of this pavement is approximately 6.7.

From surface down, PCC cross-sections consist of:

- 10" depth concrete slab
- 6" open graded free draining base
- Subgrade soil

Since there are two lanes in each direction of the divided highway, they will be referred to as the fast and slow lane throughout. If one were to be driving on the highway, the fast lane would be to the left of the slow lane. (Right and left lanes were not used as identifiers to eliminate confusion in data collection and analysis where travel direction is not always obvious.) Lanes in all sections are approximately 11.5 feet wide with longitudinal construction joints immediately to the slow lane side of the lane divider line. There is also a longitudinal construction joint between the slow lane and the shoulder in all sections. In the asphalt sections the paving width extends approximately 1.5 feet outside into the shoulder of the fast lane. In the concrete sections there is a longitudinal construction joint immediately outside of the fast lane and an additional slab approximately 1.5 feet wide. Concrete slab lengths are approximately 15 feet. In all one-tenth mile concrete test sections, there are 35 full slabs per lane and one partial slab.

	Southbound	Northbound
Asphalt Sections	16.5-16.4	16.4-16.5
	16.1-16.0	16.0-16.1
	15.5-15.4	15.4-15.5
	15.3-15.2	15.2-15.3
	14.7-14.6	14.6-14.7
	14.5-14.4	14.4-14.5
	13.9-13.8	13.8-13.9
	13.3-13.2	13.2-13.3
Concrete Sections	12.7-12.6	12.6-12.7
	12.35-12.25	12.2-12.3
	11.8-11.7	11.7-11.8
	11.5-11.4	11.4-11.5
	10.9-10.8	10.8-10.9
	10.5-10.4	10.4-10.5
	9.5-9.4	9.4-9.5
	9.3-9.2	9.1-9.2

Table 1: List of one-tenth mile test sections by start/end mile post

Manual surveys were performed in a joint effort by WVDOH employees and WVU graduate student researchers. Within each of the 32 test sections, fast and slow lanes existed which were surveyed simultaneously. The surveys were performed during May 2012, October 2012, April 2013, September 2013, and May 2014. For the remainder of this report, these will be referred to as Surveys 1 through 5 respectively.

During the manual survey the observed distresses were mapped onto data collection forms using the procedures described in Appendix A. These manual surveys generally consisted of teams of 2 to 4 people walking each of the one-tenth mile sections and drawing the observed distresses to scale on sheets of grid paper. The papers from the first survey were saved and used again for each subsequent survey. Additions to observed distresses were made in a different color each time. After each survey, observed distresses were tallied and a Pavement Surface Rating, PSR, was calculated for each section. PSR is a scale for quantifying the condition of a pavement based on observed surface distresses.

Initially, a PSR was computed per the April 19, 2012 version of “West Virginia Department of Transportation Division of Highways Special Provision, Section 490: Nine Year Pavement Performance Criteria.” The purpose of the Special Provision document is to establish definitions and guidelines for performing surveys so PSR can be calculated. The pavement performance criteria described assures the

quality of warranted pavements and protects the Division of Highways from specific distresses. PSR calculation is described in detail in Chapter 2.

In addition to the manual surveys, twice during the pavements life, a falling weight deflectometer (FWD) was used and deflection data were collected within the slow lane of all sections. These FWD tests took place in May 2012 and July 2014. The first was excluded from all analysis due to inconsistencies in sensor labeling, inability to identify location of drops, and excessive amounts of non-decreasing deflections.

Also surface distress data collected by an Automatic Road Analyzer, ARAN, for the northbound slow lane were available from the WVDOT Pavement Management System. These data and their analyses are described in Chapter 2.

1.2 Objective

The objective of this research was to compare asphalt and concrete pavements on US 35. Both pavement distress condition and deflection data were available for this comparison.

1.3 Scope and Limitations of Research

The scope of the research is the section of US 35 between mile posts 9.0 and 16.5. The data available to accomplish this objective were limited to the surface distress data collect for the Pavement Management System, periodic manual surveys, and the deflection data collected with the FWD.

1.4 Organization of Thesis

This thesis is organized into six chapters. Following this introduction, Chapter 2 contains a summary of three relevant pavement surface distress index/rating systems, background to a portion of the WVDOT Pavement Management System, and finally background for the Falling Weight Deflectometer as well as the procedure for backcalculating pavement layer moduli and three relevant computer programs which assist with this. Chapter 3 discusses the research methodologies used to collect data and assess the pavement condition using both surface distress and deflection data. Chapter 4 describes the analysis in detail which led to the results contained within Chapter 5. Finally Chapter 6 discusses the relevant conclusions and a few recommendations which were made based on the findings. Additionally three appendices are included. Appendix A is a complete Distress Identification Manual which was developed to aid this research and will be subsequently used in combination with a specification for calculating Pavement Surface Rating for the WVDOT. Appendix B a comprehensive

analysis of the deduct curves associated with Pavement Condition Index. This analysis was used for the development of the PSR procedure. Appendix C contains the deflection data collected by the Falling Weight Deflectometer and use by the three computer programs to backcalculate pavement layer moduli and other information.

Chapter 2. Literature Review

A wide variety of pavement surface distress survey methods and associated indices are available in the literature. The following literature review is limited to four methods that are directly applicable to this research.

Similarly, the review of deflection measurement and analysis focus on the type of deflection device used by the WVDOH. Three backcalculation analysis methods are reviewed that represent the state of the practice.

2.1 Pavement Surface Distress Indices and Rating Systems

Four methods for quantifying surface distresses were reviewed for the purpose of this research. The first is Pavement Condition Index, PCI, which was developed and influenced by the U.S. Army Corps of Engineers and the Washington State Department of Transportation, WSDOT, in the 1960's and 70's. The second is Surface Rating, SR, a procedure developed by Minnesota Department of Transportation, MnDOT. The next method reviewed is the 2012 Pavement Surface Rating, PSR, developed by the West Virginia Department of Transportation. It was derived from the MnDOT's Surface Rating. The method for computing PSR was refined during this research to meet the specific needs of the WVDOH. The final method is the pavement stress evaluation used for the WVDOH PMS.

2.1.1 Pavement Condition Index

ASTM D6433-11 "Standard Practice for Roads and Parking Lots Pavement Condition Index (PCI) Survey" provides a detailed approach to calculating PCI. This condition index is based on a deduct value system which was developed originally by LeClerc and Marshall for the Washington State Department of Transportation in 1971. Shahin, with his team from the U.S. Army Corps of Engineers Construction Engineering Research Laboratory, further developed PCI for the PAVER system (as cited in Jackson, 2008).

"The PCI is a numerical index, ranging from 0 for a completely failed pavement to 100 for a pavement in perfect condition" (Shahin, 2005). Simply put, a pavement theoretically starts with a PCI of 100. It is then surveyed by trained inspectors and deductions are applied to the PCI based on the findings of the inspectors to determine the overall distress related condition of the pavement.

The distress is converted into a percentage based on the amount of test section affected. For the pavement condition survey, distress types are defined for asphalt and concrete surfaces. Severity

The extent of each distress type and severity combination is tallied by total area affected. This is shown in the Distress Severity, Quantity, and Total column of Figure 2. For example, in the first row, the 1L in column 1 indicates alligator cracking at low severity with a total extent of 13 square feet. For distresses that are measured in linear feet, such as longitudinal or transverse cracking, the width of affected area is assumed to be one foot. The “SKETCH” in Figure 2 shows there are 2500 square feet of surveyed test section. Equation 1 shows the density (%) calculation for this case.

[illegible]

7

Figure 4: Example Deduct Value Curves (ASTM D6433-11, 2011)

The PCI is computed through an iterative analysis of the deduct values for the distress severity combinations. First, the maximum number of combinations that will be considered is computed as:

$$m = 1 + \left(\frac{9}{98}\right) * (100 - \text{MaxDV}) \quad (2)$$

where:

m = the allowable number of deducts including fractions (less than or equal to ten)
MaxDV = the maximum deduct value observed

The value of m is truncated to determine the number of whole deduct values that will be used for the corrected deduct value calculation. For the data in Figure 5, $m = 7.9$ so seven deduct values are transferred from Figure 2 to Figure 4, and arranged in descending order. The eighth and lowest deduct value from Figure 2 is adjusted by the decimal fraction from the m calculation, e.g. the eighth largest deduct value from Figure 2, 5.3, is multiplied by 0.9 to compute the deduct value recorded in Figure 4.

The next step is to determine the corrected deduct value using Figure 6. The value in the Total column of Figure 5 is used on the abscissa of Figure 6, Total Deduct Value. The total number of distresses with Total Deduct greater than 2 is "q" and is used to select the curve on Figure 6 to determine the Corrected Deduct Value on the ordinate of Figure 6.

From there, a sequential approach is used to calculate the Maximum Corrected Deduct Value, Max CDV. In each step, the lowest deduct greater than 2 is reduced to 2, q is reduced by 1, Total is

recalculated, and CDV is determined from Figure 6. This process is repeated until q equals 1. PCI for the test section is calculated by subtracting the Maximum CDV from 100 as shown in Figure 5. In this example, the Maximum CDV occurred on the first step of the analysis. However, depending on the relative magnitude of the Deduct Values this is not always the case.

Figure 7 provides qualitative descriptors for PCI ranges.

$$m = 1 + (9/98)(100 - 25.1) = 7.9 < 8$$

Use highest 7 deducts and 0.9 of eighth deduct.

$$0.9 \times 5.3 = 4.8$$

#	Deduct Values									Total	q	CDV
1	25.1	23.4	17.9	11.2	7.9	7.5	6.9	4.8		104.7	8	51.0
2	25.1	23.4	17.9	11.2	7.9	7.5	6.9	2		101.9	7	50.0
3	25.1	23.4	17.9	11.2	7.9	7.5	2	2		96.0	6	46.0
4	25.1	23.4	17.9	11.2	7.9	2	2	2		90.5	5	47.0
5	25.1	23.4	17.9	11.2	2	2	2	2		84.6	4	48.0
6	25.1	23.4	17.9	2	2	2	2	2		75.4	3	48.0
7	25.1	23.4	2	2	2	2	2	2		59.5	2	44.0
8	25.1	2	2	2	2	2	2	2		38.1	1	38.0
9												
10												

$$\begin{aligned} \text{Max CDV} &= \underline{51} \\ \text{PCI} = 100 - \text{Max CDV} &= \underline{49} \end{aligned}$$

Figure 5: Calculation of Corrected PCI Value-Flexible Pavement Example from Figure 2(ASTM D6433-11, 2011)

Figure 6: Corrected Deduct Value from Total Deduct Value and number of deducts “q” for HMA (ASTM D6433-11, 2011)

Figure 7: Standard PCI Rating Scale (after ASTM D6433-11, 2011)

2.1.2 MnDOT Surface Rating

The distress evaluation and analysis system used by the Minnesota Department of Transportation is simpler than the PCI method. MnDOT uses a unique distress identification manual. The distress types used by MnDOT are a subset of the ones used in PCI. However, the severity definitions differ. Table 2 and Table 3 present the distress type, severity and extent measurement for asphalt and concrete pavements respectively. MNDOT considers severity level for three distress types for asphalt pavements and none for concrete pavements. Distress extent is evaluated by the number of occurrences of each severity level of transverse cracking. All other distresses of asphalt pavements are based on the linear feet of the pavement section that have each of the distresses. The percent of the distressed area is determined by dividing the measured distress by the length of the section.

Depending on the pavement type each of the percents are multiplied by the weight factors in Table 4 and Table 5. The resulting products are summed to produce the Total Weighted Percent which is converted to the Surface Rating, SR, using Table 6.

Distress Type	Severity Levels	How to Measurement
Transverse Cracking	Low, Medium, High	Count
Longitudinal Cracking	Low, Medium, High	Lineal Feet
Longitudinal Joint Deterioration	Low, Medium, High	Lineal Feet
Multiple (block) cracking	None	Lineal Feet
Alligator Cracking	None	Lineal Feet
Rutting	None	Lineal Feet
Raveling & Weathering	None	Lineal Feet
Patching	None	Lineal Feet

With the following exceptions, count only the most severe distress in any lineal foot:

- Medium and High severity transverse cracks, raveling/weathering, patching, longitudinal joint cracking and rutting shall be counted in combination with other deficiencies.
- Low severity transverse cracks shall not be counted in the same foot as multiple or alligator cracking.

Table 2: HMA Surface Pavement Distress Types and Measurements (Office of Materials and Road Research Pavement Management Unit, 2003)

Distress Type	Severity Levels	How to Measurement
Slight Joint Spalling	None	Number of Joints
Severe Joint Spalling	None	Number of Joints
Faulted Joints	None	Number of Joints
Cracked Panels	None	Number of Panels
Broken Panels	None	Number of Panels
Faulted Panels	None	Number of Panels
Overlaid Panels	None	Number of Panels
Patched Panels	None	Number of Panels
D-Cracking	None	Number of Panels
Slight Longitudinal Joint Spalling	None	Number of Panels
Severe Longitudinal Joint Spalling	None	Number of Panels

Table 3: Jointed Concrete Pavement Distress Types and Measurements (Office of Materials and Road Research Pavement Management Unit, 2003)

Distress Type	Severity	Weighting Factor
Transverse Cracking	Low	0.01
	Medium	0.10
	High	0.20
Longitudinal Cracking	Low	0.02
	Medium	0.03
	High	0.04
Longitudinal Joint Deterioration	Low	0.02
	Medium	0.03
	High	0.04
Multiple (block) cracking	-	0.15
Alligator Cracking	-	0.35
Rutting	-	0.15
Raveling & Weathering	-	0.02
Patching	-	0.04

Table 4: HMA Pavement SR Weight Factors (Office of Materials and Road Research Pavement Management Unit, 2003)

Distress Type	Severity	Weighting Factor
Transverse Joint Spalling	Low	0.10
	High	0.20
Longitudinal Joint Spalling	Low	0.10
	High	0.20
Cracked Panels	-	0.07
Broken Panels	-	0.07
Faulted Joints	-	0.10
Faulted Panels	-	0.07
100% Overlaid Panels		0.00
Patched Panels		0.14
D-Cracking		0.10

Table 5: Jointed Concrete Pavement SR Weight Factors (Office of Materials and Road Research Pavement Management Unit, 2003)

Table 6 is then used to determine the Surface Rating from the Total Weighted Percent. SR is on a 0 – 4 scale where 0 represents the worst pavement possible and 4 represents the best pavement possible.

Total Weighted Percent	SR
0	4.0
1	3.8
2	3.6
3	3.4
4	3.2
5	3.0
6	2.9
7	2.8
8	2.7
9	2.6
10	2.5
11	2.4
12	2.3
13	2.2
14	2.1
15	2.0
16 – 17	1.9
18	1.8
19 – 20	1.7
21	1.6
22 – 23	1.5
24	1.4
25 – 26	1.3
27	1.2
28 – 29	1.1
30 – 33	1.0
34 – 40	0.9
41 – 47	0.8
48 – 54	0.7
55 – 61	0.6
62 – 68	0.5
69 – 75	0.4
76 - 82	0.3
83 – 89	0.2
90 – 96	0.1
97 – 100	0.0

Table 6: Total Weighted Percent or Total Weighted Distress Conversion to SR (Office of Materials and Road Research Pavement Management Unit, 2003)

2.1.3 WVDOT Pavement Surface Rating, PSR

Pavement Surface Rating, PSR, is an Index developed by Tom Medvick for the West Virginia Division of Highways. This intention was to emulate the simplicity of MnDOT’s SR system and the technical accuracy of the PCI’s system while also considering the pavement types and distresses most pertinent to West Virginia’s highways. The method for evaluation is included in “West Virginia Department of Transportation Division of Highways Special Provision, Section 490: Nine Year Pavement

Performance Criteria,” April 2012. The pavement condition survey and analysis methodology in this special provision represented the WVDOT’s initial development of a detailed manual condition survey methodology and served as the foundation of the condition assessment methodologies developed in this research.

Similarly to MnDOT’s SR, specific distresses for both concrete and asphalt surfaces are measured and recorded. The distresses, associated severity levels, and associated units of measurement are included in Table 7 and Table 8. The definitions for these distresses and their severity levels are based from the “Distress Identification Manual for the Long-Term Pavement Performance (LTPP) Program,” June 2003. The primary differences are that the LTPP manual defines severity levels for raveling/weathering, patching, scaling, and D-cracking, which are not included in the WVDOT Section 490. Section 490 included “Localized Distress” and “Faulted Panels”, however, there was no explicit definition of these distresses in either Section 490 or the LTPP manual.

As in MnDOT’s SR, each distress-severities combination has an associated weight factor which is shown in Table 9 and Table 10.

Distress Type	Severity Levels	How to Measure
Transverse Cracking	Low, Medium, High	Count
Longitudinal Cracking	Low, Medium, High	Lineal Feet
Longitudinal Joint Deterioration	Low, Medium, High	Lineal Feet
Block Cracking	Low, Medium High	Lineal Feet
Alligator Cracking	Low, Medium High	Lineal Feet
Rutting	¼” to ½” and greater than ½”	Lineal Feet
Raveling & Weathering	None	Lineal Feet
Patching	None	Lineal Feet

With the following exceptions, count only the most severe distress in any lineal foot:

- Medium and High severity transverse cracks, raveling/weathering, patching, longitudinal joint cracking and rutting shall be counted in combination with other deficiencies.
- Low severity transverse cracks shall not be counted in the same foot as block or alligator cracking.

Table 7: PSR Asphalt Distresses, severity levels, and units (Section 490 Nine Year Pavement Performance Criteria)

Distress Type	Severity Levels	How to Measure
Transverse Joint Spalling	Low, Medium, High	Number of Joints
Faulted Joints	Low, Medium, High	Number of Joints
Corner Breaks	Low and High	Number of Panels
Faulted Panels (Transverse Crack)	None	Number of Panels
Patched Panels	None	Number of Panels
D-Cracking	None	Number of Panels
Longitudinal Joint Spalling	Low, Medium, High	Number of Panels
Localized Distress	None	Number of Panels
Transverse Cracks	Low, Medium, High	Number of Panels
Longitudinal Cracks	Low, Medium, High	Number of Panels
Scaling	None	Lineal Feet

Table 8: PSR Concrete Distresses, severity levels, and units (Section 490 Nine Year Pavement Performance Criteria, 2012)

Distress Type	Severity	Weight Factor
Transverse Cracking	Low	0.01
	Medium	0.10
	High	0.20
Longitudinal Cracking	Low	0.02
	Medium	0.03
	High	0.04
Longitudinal Joint Deterioration	Low	0.04
	Medium	0.05
	High	0.06
Block Cracking	Low	0.05
	Medium	0.10
	High	0.15
Alligator Cracking	Low	0.15
	Medium	0.25
	High	0.35
Rutting (greater than ¼ inch up to ½ inch)		0.07
Rutting (greater than ½ inch)	-	0.15
Raveling & Weathering	-	0.02
Patching	-	0.04

Table 9: PSR Asphalt Distress Weight Factors (Section 490 Nine Year Pavement Performance Criteria, 2012)

Distress Type	Severity	Weight Factor
Transverse Cracking	Low	0.10
	Medium	0.18
	High	0.25
Longitudinal Cracking	Low	0.10
	Medium	0.18
	High	0.25
Transverse Joint Spalling	Low	0.06
	Medium	0.10
	High	0.22
Longitudinal Joint Spalling	Low	0.06
	Medium	0.10
	High	0.22
Faulted Joints	Low	0.15
	Medium	0.20
	High	0.25
Corner Breaks	Low	0.04
	High	0.15
Faulted Panels	-	0.15
Localized Distress	-	0.40
D-cracking	-	0.10
Scaling	-	0.02
Patched Panels	-	0.14

Table 10: PSR Concrete Distress Weight Factors (Section 490 Nine Year Pavement Performance Criteria, 2012)

For asphalt surfaces, all distress lengths are totaled for each 1/10th mile test section and density percentages are calculated by dividing each total by 528 feet and then multiplying by 100. This holds true for all distresses with the exception of transverse cracking which is counted by number as opposed to length. In this case, the number of cracks in the section is simply multiplied by two to calculate density (for up to 50 cracks so density percentage does not surpass 100).

For jointed concrete test sections, the amount of slabs within the 1/10th mile test section is noted and distress density percentage is calculated based on the amount of affected slabs within the test section. The exceptions here being transverse joint faulting and spalling which are measured in amount of joints affected, and scaling which is measure in linear feet.

The density of each distress is multiplied by the corresponding weight factor and the subsequent weighted distresses are totaled to compute a Total Weighted Distress, TWD. PSR is a function of TWD calculated using Equation 3.

$$PSR = 25 * [e^{1.386 - (0.045 * TWD)}] \quad (3)$$

PSR is evaluated on a 0-100 scale where 100 is a perfect pavement and PSR decreases as distress increases. Additionally, the special provision includes thresholds for bonus and penalty to contractors based on PSR, bid price, and pavement age. An example of the criteria for bonuses and penalties is shown in Table 11. This example assumes a road paved in 2011. The dates and bonus/penalty amounts vary between contracts.

Year	PSR Criteria for Bonus	Bonus	PSR Criteria for corrective action	Penalty for no corrective action
One Oct. 31, 2012	98	\$10,000	<95	\$20,000
Two Oct. 31, 2013	95	\$10,000	<92	\$20,000
Three Oct. 31, 2014	93	\$ 25,000	<90	\$ 50,000
Four Oct. 31, 2015	90	\$ 25,000	<85	\$ 50,000
Five Oct. 31, 2016	90	\$40,000	<85	\$ 80,000
Six Oct. 31, 2017	90	\$40,000	<85	\$ 80,000
Seven Oct. 31, 2018	85	\$80,000	<80	\$ 160,000
Eight Oct. 31, 2019	85	\$80,000	<80	\$ 160,000
Nine Oct. 31, 2020	85	\$140,000	<80	\$ 280,000

Table 11: Example of Incentive Performance Criteria for Bonus and Penalty (Section 490 Nine Year Pavement Performance Criteria, 2012)

Several individual distress thresholds for immediate corrective action are also included in the special provision. For example, if any individual rutting measurement in an HMA or any individual transverse joint faulting measurement in a PCC section exceeds ½ inch, an immediate investigation will be prompted and corrective action may be required. Lastly, the warranty includes criteria for surface friction and roughness but these have no effect on PSR calculation.

2.1.4 West Virginia DOH PMS Pavement Distress Evaluation

The WVDOH uses Deithton Infrastructure Management Systems, dTIMS, software to support its pavement management system, PMS. The pavement condition data that populates the PMS were

collected with an Automatic Road Analyzer, ARAN, through a contract with Fugro Roadware. The state uses International Roughness Index, IRI, data and pavement surface condition measures for the evaluation of the state's system and the development of the State Transportation Improvement Program, STIP.

The ARAN (shown in Figure 8) "is an advanced pavement data collection vehicle equipped with precision survey systems and software. It is capable of completing any roadway data collection task" (Fugro Roadware Inc., 2012).

Figure 8: ARAN 9000 (Fugro Roadware Inc., 2012)

IRI and the pavement surface condition measures, specifically requested by the WVDOH from this vehicle, are used to calculate Composite Condition Index which is then used to make the most efficient pavement rehabilitation decisions for West Virginia.

Composite Condition Index, CCI, is a pavement condition indicator for rigid or flexible pavements developed by Naveed Sami in 1997 for the WVDOH. CCI is a 0-5 scale where 5 represents perfect pavement and 2.5 is the trigger point for investigation and appropriate treatment. CCI is a function of multiple other indices that represent roughness and different distresses of the pavement.

All distress types used in the indices are included in the LTPP distress identification manual and the specific distress definitions “generally follow LTPP definitions” (Sami, 1997). All distresses are evaluated as low, medium, and high severity, however the thresholds for the severity levels are slightly different from the values specified in the LTPP manual.

Currently the WVDOH contracts with Fugro Roadware Inc. to survey pavements with the ARAN and reduce the ARAN information to distress measurements using a combination of automated distress identification programs and human reviewing of the imaging.

For flexible pavements, CCI is a function of Rut Depth Index, RDI, Structural Cracking Index, SCI, Environmental Cracking Index, ECI, and Present Serviceability Index, PSI. PSI is calculated using Equation 4 which is a function of IRI. RDI is calculated using Equation 5 which is a function of the average Rut Depth in inches of the test section. SCI is calculated using Equation 6 which is a function of the extent (percent of area affected) of low, medium, and high severity Alligator Cracking (AL, AM, AH respectively) and low, medium, and high severity Longitudinal Cracking (LL, LM, LH respectively). ECI is calculated using Equation 7 which is a function of the extent (percent of area affected) of low, medium, and high severity Transverse Cracking (TL, TM, TH respectively) and low, medium, and high severity Block Cracking (BL, BM, BH respectively). CCI simply equals the lowest value of PSI, RDI, SCI, and ECI for a given test section.

$$PSI = 5 * e^{-0.0041 * IRI} \quad (4)$$

$$RDI = 5 - 6.65 * RD^{1.41} \quad (5)$$

$$SCI = 5 - 0.21 * AL^{0.67} - 0.24 * AM^{0.69} - 0.40 * AH^{0.80} - 0.28 * LL^{0.73} - 0.32 * LM^{0.75} - 0.60 * LH^{0.89} \quad (6)$$

$$ECI = 5 - 0.32 * TL^{0.75} - 0.40 * TM^{0.80} - 0.60 * TH^{0.89} - 0.24 * BL^{0.69} - 0.28 * BM^{0.73} - 0.40 * BH^{0.80} \quad (7)$$

For rigid pavements, CCI is a function of Joint Condition Index, JCI, and Concrete Slab Index, CSI, and Present Serviceability Index, PSI. PSI is measured using Equation 4 as it is in the case of asphalt pavements. JCI is calculated using Equation 8 which is a function of the extent (percent of slabs affected) of low, medium, and high severity Faulting (FL, FM, FH respectively) and Distressed Joints, DJ.

In this case Distressed Joints are joints with faulting at any severity level. CSI is calculated using Equation 9 which is a function of the extent (percent of slabs affected) of low, medium, and high severity Transverse Cracking (TL, TM, TH respectively) and low, medium, and high severity Transverse & Longitudinal Cracking (SL, SM, SH respectively). Transverse & Longitudinal Cracking represents any slabs affected by either transverse or longitudinal cracks (or both). CCI simply equals the lowest value of PSI, JCI, and CSI for a given test section.

$$JCI = 5 - 0.13 * FL^{0.56} - 0.16 * FM^{0.60} - 0.17 * FH^{0.62} - 0.13 * DJ^{0.56} \quad (8)$$

$$CSI = 5 - 0.13 * TL^{0.75} - 0.17 * TM^{0.80} - 0.20 * TH^{0.89} - 0.20 * SL^{0.69} - 0.28 * SM^{0.73} - 0.40 * SH^{0.80} \quad (9)$$

2.2 Deflection Testing and Analysis of Deflection Data

Falling Weight Deflectometer, FWD, data were collected twice during the evaluation period. Typically these data are used for estimating the modulus of elasticity of pavement layers (Gucunski et al., 2009). The WVDOH does not have standard practice for analyzing FWD data. The following describes three backcalculation methodologies for analyzing FWD data.

2.2.1 Falling Weight Deflectometer and Backcalculation of Layer Moduli

The Falling Weight Deflectometer, FWD, is an instrument that simulates the deflection of pavement caused by a truck driving over its surface. It is the most commonly accepted form of non-destructive testing for evaluating structural condition of pavements. Throughout the country, the majority of FWD's owned by state highway agencies are manufactured by DYNATEST (Alavi et al., 2008).

The FWD applies an impulse load generated by dropping a mass from a specified height onto a circular load plate with a diameter of 300 mm. The DYNATEST Model 8000 FWD has the ability to drop a weight ranging from 110 to 770 lbs from a height of 0.8 to 15 inches to generate a peak force ranging from 1500 to 27,000 lbs. Although the mass which is dropped can be changed, it is recommended that the load applied to the pavement be adjusted by changing the height of the drop (Gucunski et al., 2009). The LTPP protocol specifies four drops at four load levels at each test location on flexible pavements (Schmalzer, 2006). The target load levels and acceptable ranges are:

- 6.0 kips (5.4 to 6.6)
- 9.0 kips (8.1 to 9.9)

- 12.0 kips (10.8 to 13.2)
- 16.0 kips (14.4 to 17.6)

According to the LTPP Manual for Falling Weight Deflectometer Measurements, FWD testing on rigid pavements does not require the 6.0 kip load level.

An array of sensors (also called geophones) measures maximum deflections in mils (1/1000 inches) at certain distances from the plate's center. The entire instrument, including load plate, weights, and geophones, is usually contained within a trailer and pulled by a truck or van. The mass being dropped must be selected before testing and cannot be changed during testing. Otherwise, the procedure is operated completely from a laptop within the vehicle. Figure 9 shows an example of a DYNATEST FWD and the van towing it.

Figure 9: WVDOH DYNATEST Falling Weight Deflectometer Trailer on US 35

The LTPP Manual for Falling Weight Deflectometer Measurements outlines several test plans for various pavement types and the experiment designations of FWD tests. Testing structural properties of pavement materials is included within the General Pavement Studies test plan. For flexible pavements, the LTPP requires tests performed every 25 feet mid-lane and in the outer wheel path within a test section. For rigid pavements, the LTPP requires test performed in the following locations on 20 continuous slabs:

- Mid-Slab (transversely), Mid Panel (longitudinally)
- Slab outer edge, Mid-Panel (longitudinally)

- Slab corner

In all cases, the sensors radiate from the center of the load plate parallel to the pavement centerline. The sensor spacing however, can be configured by the user. The DYNATEST Model 8000 FWD can accommodate sensors up to 8 feet (96 inches) from the center of the loading plate. Typical sensor arrangements typically include 7 or 9 sensors with spacing relative to the center of the load, of:

- -12, 0, 8, 12, 18, 24, 36, 48, and 60 inches
- 0, 8, 12, 18, 24, 36, and 60 inches
- -12, 0, 12, 18, 24, 36, and 60 inches
- 0, 12, 24, 36, 48, 60, and 72 inches

Typically, sensors in the negative direction are only used for load transfer across joints of jointed concrete pavements and across cracks in pavement to check crack propagation. (Gucunski et al., 2009) The LTPP requires that all nine sensor FWDs use the first spacing in the previous list. Seven sensor FWDs are required to use the second spacing on flexible pavements and the third spacing is for rigid pavements. Many other sensor spacing combinations have been suggested which sometimes include a sensor at 72 inches. In any case, a deflection basin is formed that should have a maximum deflection at the sensor centered under the load (0 inches) and deflections will decrease as the distance from the load plate increases. An exaggerated basin example is shown in Figure 10.

Figure 10: Falling Weight Deflectometer Deflection Basin (Cornell University, 2005)

From these measured deflections, stiffness related physical properties of the pavement can be estimated. “One of the more common analysis methods of the deflection data is to backcalculate material response properties for each structural layer within the pavement structure. The specific layer property determined from the peak deflection basin is Young’s modulus, determined by an elastic layer based backcalculation program” (Killingsworth and Von Quintus, 1997). “For rehabilitation design processes, the Mechanistic-Empirical Pavement Design Guide, MEPDG, relies heavily on the material stiffness back calculated from the deflection measurements taken from existing pavements” (Gucunski et al., 2009). Many linear elastic layer theory programs exist that will solve for a deflection basin using known layer thicknesses and applied loads while iteratively varying moduli inputs until the error between the predicted and measured deflections is a minimum. Although this process is widely used, there are many problems that can arise. Upon testing several backcalculation programs for this purpose, Killingsworth and Von Quintus (1997) concluded that, “There is no unique solution for a particular deflection basin; engineering judgment must be used in determining reasonable solutions. Most programs based on elastic layer theory can be used to find a combination of layer moduli with an error term less than 2.0 percent per sensor. However, these layer moduli can be consistently and significantly different between these programs, which prevent the combination and random use of different programs.” In order to better understand these inevitable errors the LTPP Manual for FWD Measurements additionally requires notes be taken by field engineers regarding pavement surface distresses at test locations. “There are limitations to accurate prediction of the layers’ moduli in the areas with longitudinal or transverse cracking, since these cracks disturb the assumption of the layers extending to infinity” (Norouzi, 2013).

For flexible pavements, the estimated modulus values are dependent on the pavement temperature. For instance asphalt moduli can range from over 5,000 ksi at low temperatures to below 100 ksi at high temperatures. Additionally, temperature gradients will occur within pavements as air temperature and sun exposure change. A study on air temperature and resulting in situ pavement temperatures was conducted by Alnouri (1972). The averaged results (independent of solar radiation) are summarized in Figure 11. The left portion of Figure 11 shows daily high air temperature and the maximum average temperature of the pavement through its depth. The right portion of Figure 11 shows when the maximum temperature could be expected at select depths relative to an assumed air temperature daily fluctuation.

Figure 11: Averaged graphical representation of temperature gradient within asphalt pavements (Alnouri, 1972)

Pavement depth, aggregate, percent binder, air voids, etc, will affect the actual temperature of a pavement. The LTPP requires drilling and probing pavements at 5 depths to determine subsurface temperatures when obtaining FWD data. Most backcalculation programs have inputs for temperature when analyzing flexible pavements so a temperature correction can take place. A common temperature gradient prediction equation is the LTPP BELLS2 model originally presented by Lukanen et al. (2000). The model, as shown in Equation 10, requires inputs of a surface temperature, time of day, average air temperature from the previous day, and a distance below the surface for temperature to be calculated.

$$T_d = 2.78 + 0.912 * IR + \{\log(d) - 1.25\} * \{-0.428 * IR + 0.553 * (1 - day) + 2.63 * \sin(hr_{18} - 15.5)\} + 0.027 * IR * \sin(hr_{18} - 13.5) \quad (10)$$

Where:

T_d = Pavement temperature at depth d , ($^{\circ}\text{C}$)

IR = Pavement surface temperature, ($^{\circ}\text{C}$)

d = depth at which material temperature is to be predicted, (mm)

1-day = Average air temperature the day before testing, ($^{\circ}\text{C}$)

hr_{18} = Time of day in a 24-hr clock system, but calculated using an 18-hr asphalt concrete temperature rise and fall time cycle where all times from 0500 to 1100 should be entered as either 5:00 AM or 11:00 AM and minutes should be converted to decimal form

Regardless of the program selected, the result of the backcalculation process will be moduli values which quantify stiffness for layers defined in the pavement structure. For asphalt or concrete layers this is modulus of elasticity. For unbound materials such as free draining base or subgrade soil,

the resilient modulus is determined which is an estimate of modulus of elasticity independent of confining pressures, and moisture related properties which often cannot be known. The estimated resilient modulus of the subgrade soil is directly used in the determination of a pavement's current structural condition and remaining life.

A pavement's current structural condition can be quantified by effective structural number, SN_{eff} , for flexible pavements and effective slab thickness, D , for rigid pavements. A process for using FWD results to determine both is described in AASHTO 93 Pavement Design Guide. Appendix L of the design guide contains a procedure specifically for using FWD results to calculate effective structural number. "The SN_{eff} determination uses a model based on stiffness theory and a two-layer pavement structure. The stiffness of the constructed material, regardless of its constituent components, is represented by the term E_p , which is an average elastic modulus for all the material above the subgrade" (Pologruto, 2007). This process is summarized in Equation 11 and 12. In Equation 12, M_R of the subgrade must be independently determined by backcalculation before E_p may be solved from the remainder of the FWD outputs.

$$SN_{eff} = 0.0045D \sqrt[3]{E_p} \quad (11)$$

$$d_0 = 1.5 * p * a * \left(\frac{1}{\sqrt{1 + \left(\frac{D}{a} \sqrt[3]{\frac{E_p}{M_R}} \right)^2}} + \frac{\left(1 - \frac{1}{\sqrt{1 + \frac{D^2}{a^2}}} \right)}{E_p} \right) \quad (12)$$

Where:

SN_{eff} = effective structural number

D = total thickness of pavement structure resting on subgrade (in)

E_p = effective modulus for total pavement structure (lb/in²)

d_0 = centerline deflection measured by the FWD (in)

p = loading plate pressure applied by the FWD (lb/in²)

a = loading plate radius (in)

M_R = subgrade resilient modulus (lb/in²)

Interestingly, a vast amount of research suggests subgrade resilient modulus as determined by FWD backcalculation will differ from the modulus of the same soil sample determined through triaxial testing in a lab. Based on experimental observation, the AASHTO 93 pavement design guide recommends a correction factor up to 0.33 and 0.25 for subgrade resilient modulus below flexible and rigid pavements respectively to obtain modulus values suitable for design. A 1999 report which mechanistically analyzed FWD data using a finite element method approach concluded that “the correction factors reached in [the] study agree closely with the AASHTO experience-based correction factors” (Shoukry and William, 1999). In a conversation with Trenton Clark (Clark, 2014), Director of Engineering at Virginia Asphalt Association, it was confirmed that many state highway agencies employ policies based on this knowledge. Virginia Department of Transportation uses a “rule of thumb” that backcalculated subgrade resilient moduli should be divided by 3 before being recorded as the “analysis” modulus of the soil. Additionally for VDOT, if that value after being divided by 3 is still over 10,000 psi, it should be recorded as 10,000 psi.

2.2.2 MODULUS 6.1

MODULUS was developed in the early 1990’s by the Texas Transportation Institute, TTI to process FWD data for the Texas Department of Transportation, TxDOT. In 1993, a study was performed by the Strategic Highway Research Program, SHRP, which reviewed 17 moduli backcalculation programs and compared the three best. The study concluded that MODULUS was superior to the rest in terms of repeatability, reasonableness of results, deflection matching errors, ability to match assumed moduli from simulated deflection basins, and versatility (PCS/Law Engineering, 1993). A 1999 study which compared several backcalculation programs concluded that MODULUS 5.0 rendered the most consistent moduli outputs and was the most user friendly when compared to its contemporaries (William, 1999).

MODULUS 6.1 was updated in September 2013. However, the most recent user manual available is specifically for its predecessor MODULUS 6. Most features and interfaces remained unchanged.

Since its development, MODULUS has used the multi-layer elastic theory forward calculation subroutine known as WESLEA. WESLEA, like all multi-layer elastic theory programs, is based on Burmister’s original theory which assumes that all materials within the pavement structure are homogeneous, isotropic, and linearly elastic. This subroutine is used to develop a database of potential

deflection bases for a given pavement structure due to a specified load (William and Shoukry, 1999). “A pattern search technique is then used to determine the set of layer moduli that best fits the measured basin.” (PCS/Law Engineering, 1993) MODULUS’s pattern search algorithm and interpolation scheme makes it much faster than other iterative forward calculating programs (Lytton and Germann, 1989). “Because the program does not use a forward calculation scheme in the iterative process, it is particularly suited for the analysis of large numbers of deflection basins measured on pavement with the same structure.” (PCS/Law Engineering, 1993) Like any other moduli backcalculation technique, the program cannot guarantee that given deflection basins are generated by unique parameters. Engineering judgment entering seed moduli and ranges for layers is required to keep error to a minimum.

MODULUS 6.1 can import falling weight deflectometer data files in Dynatest Edition 9, 10, and 20 (.FWD, .R80, or .R32) formats. This version of the program is specifically for analyzing asphalt pavements. The program will automatically make adjustments to the seed moduli range of asphalt layers depending on the asphalt temperature input. All layers defined require inputs Poisson’s ratio as well as maximum and minimum moduli values except for subgrade modulus which only requires a most probable value. The program also provides a guide for suggested inputs based on layer material and condition. The user has the option to select a drop within the FWD drop sequence and analysis is performed on that drop for all stations within the FWD file. The program screens deflection data for drops with non-decreasing deflections or otherwise irregular deflection basins and give the user the option to exclude those drops. MODULUS will output backcalculated moduli values for all defined layers, a depth to bedrock and provide an absolute error per sensor as a measure of confidence. A remaining life analysis may also be performed which will output a pavements expected remaining life in years and each layers current condition on an ordinal scale if traffic data were input.

2.2.3 MODTAG

MODTAG was developed cooperatively by Cornell University and the Virginia Department of Transportation. It is a combination of programs otherwise known as TAG and MODCOMP. TAG (Test and Guess) is based on AASHTO 1993 equations and was developed by the Virginia Department of Transportation, VDOT. MODCOMP (Modulus Computation), which was developed by Cornell University, is a multi-layer elastic analysis program. MODTAG requires inputs of layer thicknesses, Poisson’s ratios, and seed moduli (as opposed to acceptable moduli ranges) for all layers. Within MODTAG, MODCOMP uses the forward moduli calculating subroutine CHEVLAY to compute surface deflections based on the

inputs. The program iteratively changes the seed moduli until a deflection basin is established that resembles the observed basin within a given tolerance.

The 1999 study by William comparing MODCOMP3, MODULUS 5.0, and EVERCALC 4.0, concluded that MODCOMP3 “resulted in moduli values which seemed to be reasonable and within the material range. However, the resulting modulus value of the concrete layer in the rigid pavement section seemed to be high compared with those resulting from the other two programs.” The study also stated that MODCOMP3 was “the most user-sensitive and required more engineering judgment.”

According to the MODTAG user manual, “The main objective of MODTAG is to provide the engineer the ability to analyze raw deflection data and to use the results in the pavement rehabilitation design process.” The MODTAG user manual also suggests using several methods when analyzing raw FWD data and comparing to one another before any decisions are made. Additionally this information should be used in combination with visual inspection, laboratory testing, and engineering judgment to be most useful.

The program can import falling weight deflectometer data files in Dynatest Edition 20 (.FWD or .R80), Dynatest Edition 25 (.F25), or AASHTO PDDX file formats. Unlike some other FWD analysis programs, MODTAG can only analyze files that represent test sections with identical weight drop sequences at each station. If for any reason a drop load level or a single drop were excluded from any station, MODTAG cannot analyze that file. Additionally outputs are recorded as averages of all drops within a load level at a certain station.

Once a file is imported, number of load levels and drops per load level are input by the user. MODTAG has the ability to perform backcalculation on rigid or flexible pavements provided the user defines any layers as such. A single seed moduli value is required for all layers. MODTAG uses the BELLS3 temperature correction model which uses FWD temperature data and a user input for the average air temperature for the previous day. The user also has the option to directly input the pavement temperature instead. Within the flexible pavement analysis, the program has the ability to output estimated subgrade modulus, effective structural number, and ESAL’s until failure.

2.2.4 BAKFAA

BAKFAA is a layer moduli backcalculation program created by the Federal Aviation Administration. This program is available as a free download on several websites including faa.gov. This program uses the LEAF linear elastic analysis program. Layers are defined and seed moduli are

iteratively changed until a calculated deflection basin matches the observed one within a tolerance. This program is far simpler than the previous two mentioned as all user inputs are included in one window. A single deflection basin can be automatically or manually input along with the layer properties: seed modulus, Poisson's Ratio, and thickness. Unlike the other programs, once an observed deflection basin and pavement structure is input and the program is initiated. The user can watch the moduli values change as the iterations are tallied. Additionally, a plot of the calculated deflection basin is shown as it converges toward the observed basin.

2.3 Summary of Literature

PSR as defined in the April 2012 version the WVDOT Special Provision Section 490 was used as a foundation for evaluation and comparison of the condition of the pavements within US 35. With a comprehensive understanding of this method and the history of its development, improvements to the accuracy and repeatability of the PSR calculation process will be made if necessary. A comparison to PCI will be the most relevant and informative analysis of PSR.

While many backcalculation programs are available in the literature, three programs that have been found by previous researchers to provide the "most reasonable" results were reviewed. Since the literature does not support the selection of one of these programs, all three were applied during this research.

Chapter 3. Methodology

This chapter describes the initial process used for the collection and analysis of the pavement distress data for both the manual condition survey and the automated survey performed for the pavement management system. This is followed by a description of the methodology for analyzing the FWD data.

3.1 Pavement Surface Rating Data Collection and Analysis Process

The following section is separated into two parts. The first covers the 2012 Special Provision, Section 490 method used for pavement surface distress data collection. The second covers the process that was used to calculate Pavement Surface Rating. The purpose of these sections is mainly to establish a starting point for revisions made to the process.

3.1.1 Data Collection Process for Pavement Surface Rating

For each 1/10th mile test section a folder exists containing the distress survey diagrams for the test section. Each sheet contains two grid delineated segments representing a fast and slow lane. For asphalt sections, each diagram contains 50 feet of length per lane. Concrete section diagrams contain 60 feet (approximately 4 slab lengths) per lane. Figure 12 and Figure 13 are examples of blank diagram sheets for asphalt and concrete sections. Each diagram sheet was marked with a start and end station to identify the sequence in the sections.

Surface distress surveys were conducted by a mixed group of WVDOH employees and West Virginia University graduate students. Groups of 2 to 4 people walked the length of each segment with a measuring wheel and recorded observable surface distresses on the diagrams to scale and in the location observed. The WVDOH provided traffic control to close the slow lane during the data collection. The distresses recorded for asphalt sections were:

- Transverse Cracking
- Longitudinal Cracking
- Longitudinal Joint Deterioration
- Block Cracking
- Alligator Cracking
- Rutting
- Raveling and Weathering
- Patching

The distresses recorded for concrete sections were:

- Transverse Joint Spalling
- Faulted Joints
- Corner Breaks
- Faulted Panels
- Patched Panels
- D-Cracking
- Longitudinal Joint Spalling
- Localized Distress
- Transverse Cracks
- Longitudinal Cracks
- Scaling

For rutting measurements, a five foot straight edge was placed over the wheel path and a maximum distance between the bottom of the straight edge and the road surface was recorded. This was done in five locations throughout each asphalt section and in both directions at approximately foot marker 64, 164, 264, 364, and 464. All other distresses were identifiable and observable with by eye. Most of these distresses include severity thresholds which require the surveyors to additionally identify specific features of the distress. Rulers were used to determine the width of a crack or any other small measurement. Definitions for each distress and severity are contained within the April 19, 2012 version of “West Virginia Department of Transportation Division of Highways Special Provision, Section 490: Nine Year Pavement Performance Criteria.” In many cases this document defers definition to the “Distress Identification Manual for the Long Term Pavement Performance Program”.

Distress diagram forms include examples for the method of recording some normal distresses. Adherence to these symbols was to be maintained and in every case the symbols should be accompanied by a label for the observed severity when applicable.

The same diagrams were used for each survey date but a different colored pen or pencil was used to for the different survey dates. This allowed a way for distress progression to be tracked. If unusual discrepancies between surveys occurred, such as the disappearance of a previously noted distress, notes would be made, but under no circumstance were previous surveys altered. The analysis of the data was performed under the assumption that all distress data were accurate at the time of observation.

3.1.2 Data Analysis Process for Pavement Surface Rating

The first analysis of surveyed surface distress data occurred in July of 2013. At this point three surveys had been completed. US 35 was surveyed during May 2012 (Survey 1), October 2012 (Survey 2), and April 2013 (Survey 3). PSR was to be initially calculated as defined in the April 19, 2012 version of “West Virginia Department of Transportation Division of Highways Special Provision, Section 490: Nine Year Pavement Performance Criteria.” This process is described in detail within the WVDOH Section of Surface Distress Ratings in the Literature Review chapter.

Over the course of the research, an Excel file was used to record the observed distresses and calculate PSR. This file includes spreadsheets for pavement type and direction (northbound asphalt, southbound asphalt, northbound concrete, and southbound concrete sections). Each of these spreadsheets consists of a matrix of individual tables which correspond to relevant distress types labeled across the top and the applicable test sections labeled on the left. Thus there is a table which corresponds to every combination of test section and distress type relevant to the calculation of PSR within US 35. Each distress type is divided into columns first by severity level as specified for each distress. The severities are then divided by survey number and then finally separated into fast and slow lane columns. The rows correspond to station numbers within the test section. Additionally, each table includes a section summary which provides totals from each column. Table 12 and Table 13 are examples of these individual tables from within the Excel file.

For each test section, the data from the summary sections were combined into PSR calculation tables within the Excel spreadsheet. PSR values were calculated separately for Fast and Slow Lanes within each of the 32 test sections for each survey. Examples of a PSR calculation table for one lane of an asphalt and concrete section are presented in Table 14 and Table 15 respectively

Any concerns regarding categorization, definition, and weighting of distresses that arose during this process were noted. Assumptions pertaining to the interpretation of survey diagrams and vague areas within the Special Provision, Section 490 spec were also noted along the way. Table 14 and Table 15 show an interim set of weight factors for each distress/severity level. The weight factors were extensively evaluated during the research as part of the iterative process for establishing the WVDOH PSR calculation methodology.

Mile Marker		Longitudinal Cracking																													
		Low Sev. Crack Length (linear feet)										Mod. Sev. Crack Length (linear feet)										High Sev. Crack Length (linear feet)									
		1		2		3		4		5		1		2		3		4		5		1		2		3		4		5	
		SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL
12.6 - 12.7	0+00 - 0+50	4	0	4	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	0+50 - 1+00	6	0	6	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	1+00 - 1+50	16	0	16	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	1+50 - 2+00	0	0	0	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	2+00 - 2+50	20	0	20	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	2+50 - 3+00	40	0	40	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	3+00 - 3+50	22	0	22	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	3+50 - 4+00	0	0	0	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	4+00 - 4+50	0	0	0	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	4+50 - 5+00	0	0	0	0	50	0					0	0	0	0	0	0					0	0	0	0	0	0				
	5+00 - 5+28	0	0	0	0	28	0					0	0	0	0	0	0					0	0	0	0	0	0				
	Total(max):	108	0	108	0	528	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0
Section Summary	Length (ft)	Survey #1			Survey #2			Survey #3			Survey #4			Survey #5																	
	Severity	SL	FL	Total	SL	FL	Total	SL	FL	Total	SL	FL	Total	SL	FL	Total	SL	FL	Total												
	Low	108	0	108	108	0	108	528	0	528																					
	Moderate	0	0	0	0	0	0	0	0	0																					
	High	0	0	0	0	0	0	0	0	0																					
		108	0	108	108	0	108	528	0	528																					

Table 12: Longitudinal Cracking within NB 12.6-12.7 (HMA Section)

Mile Marker		Transverse Joint Spalling																																			
		Low Sev. Spalled Joints (number)										Mod Sev. Spalled Joints (number)										High Sev. Spalled Joints (number)															
		1		2		3		4		5		1		2		3		4		5		1		2		3		4		5							
		SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL	SL	FL				
9.1 - 9.2	0+00 - 0+15	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0										
	0+15 - 0+30	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0										
	0+30 - 0+45	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0										
	0+45 - 0+60	0	0	0	0	0	0	1					0	0	0	0	0	0					0	0	0	0	0	0									
	0+60 - 0+75	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	0+75 - 0+90	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	0+90 - 1+05	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	1+05 - 1+20	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	1+20 - 1+35	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	1+35 - 1+50	0	0	1	0	1	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	1+50 - 1+65	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	1+65 - 1+80	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	1+80 - 1+95	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	1+95 - 2+10	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	2+10 - 2+25	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	2+25 - 2+40	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	2+40 - 2+55	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	2+55 - 2+70	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	2+70 - 2+85	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	2+85 - 3+00	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	3+00 - 3+15	0	0	1	0	1	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	3+15 - 3+30	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	3+30 - 3+45	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	3+45 - 3+60	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	3+60 - 3+75	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	3+75 - 3+90	1	0	1	0	1	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	3+90 - 4+05	1	0	1	0	1	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	4+05 - 4+20	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	4+20 - 4+35	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	4+35 - 4+50	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	4+50 - 4+65	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	4+65 - 4+80	0	0	1	0	1	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	4+80 - 4+95	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	4+95 - 5+10	1	0	1	0	1	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	5+10 - 5+28	0	0	0	0	0	0	0					0	0	0	0	0	0					0	0	0	0	0	0									
	Total:	3	0	6	0	6	1	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0			
Section Summary																																					
	Amount (#)	Survey #1			Survey #2			Survey #3			Survey #4			Survey #5																							
	Severity	SL	FL	Total	SL	FL	Total	SL	FL	Total	SL	FL	Total	SL	FL	Total	SL	FL	Total	SL	FL	Total															
	Low	3	0	3	6	0	6	6	1	7																											
	Moderate	0	0	0	0	0	0	0	0	0																											
	High	0	0	0	0	0	0	0	0	0																											
		3	0	3	6	0	6	6	1	7																											

Table 13: Transverse Spalled Joints within NB 9.1-9.2 (PCC Section)

Slow Lane Survey 3								
PSR Distresses	Severity	Weighting Factor	How to Measure (S.P.)	Number	Length	Percent	Individual Weighted Distress	
Transverse Cracking	Low	0.01	Count	0	-	0.00	0.00	
	Medium	0.10	Count	0	-	0.00	0.00	
	High	0.20	Count	0	-	0.00	0.00	
Longitudinal Cracking	Low	0.02	Linear Feet	-	0	0.00	0.00	
	Medium	0.03	Linear Feet	-	0	0.00	0.00	
	High	0.04	Linear Feet	-	0	0.00	0.00	
Longitudinal Joint Deterioration	Low	0.04	Linear Feet	-	316	59.85	2.39	
	Medium	0.05	Linear Feet	-	0	0.00	0.00	
	High	0.06	Linear Feet	-	0	0.00	0.00	
Block Cracking	Low	0.05	Linear Feet	-	0	0.00	0.00	
	Medium	0.10	Linear Feet	-	0	0.00	0.00	
	High	0.15	Linear Feet	-	0	0.00	0.00	
Alligator/Fatigue Cracking	Low	0.15	Linear Feet	-	0	0.00	0.00	
	Medium	0.25	Linear Feet	-	0	0.00	0.00	
	High	0.35	Linear Feet	-	0	0.00	0.00	
Rutting	Low	0.04	Linear Feet	-	0	0.00	0.00	
	High	0.15	Linear Feet	-	0	0.00	0.00	
Raveling/Weathering	None	0.02	Linear Feet	-	528	100.00	2.00	
Patching	None	0.04	Linear Feet	-	0	0.00	0.00	
							4.39	TWD
							82.0	PSR

Table 14: Post Survey 3 PSR Calculator for Slow Lane of NB 13.2-13.3 (HMA Section)

Slow Lane Survey 3								
PSR Distresses	Severity	Weighting Factor	How to Measure (S.P.)	Number of Joints	Number of Panels	Length	Percent	Individual Weighted Distress
Transverse Joint Spalling	Low	0.15	Number of Joints	21	-	-	60.00	9.00
	Medium	0.20	Number of Joints	0	-	-	0.00	0.00
	High	0.25	Number of Joints	0	-	-	0.00	0.00
Faulted Joints	Low	0.15	Number of Joints	0	-	-	0.00	0.00
	Medium	0.20	Number of Joints	0	-	-	0.00	0.00
	High	0.25	Number of Joints	0	-	-	0.00	0.00
Corner Breaks	Low	0.14	Number of Panels	-	0	-	0.00	0.00
	High	0.25	Number of Panels	-	0	-	0.00	0.00
Faulted Panels (Transverse Crack)	None	0.15	Number of Panels	-	0	-	0.00	0.00
Patched Panels	None	0.14	Number of Panels	-	0	-	0.00	0.00
Longitudinal Joint Spalling	Low	0.15	Number of Panels	-	0	-	0.00	0.00
	Medium	0.20	Number of Panels	-	0	-	0.00	0.00
	High	0.25	Number of Panels	-	0	-	0.00	0.00
Localized Distress	None	0.40	Number of Panels	-	0	-	0.00	0.00
Transverse Cracks	Low	0.10	Number of Panels	-	0	-	0.00	0.00
	Medium	0.18	Number of Panels	-	0	-	0.00	0.00
	High	0.25	Number of Panels	-	0	-	0.00	0.00
Longitudinal Cracks	Low	0.10	Number of Panels	-	2	-	5.71	0.57
	Medium	0.18	Number of Panels	-	0	-	0.00	0.00
	High	0.25	Number of Panels	-	0	-	0.00	0.00
Pop Outs	None	0.04	Number of Panels	-	0	-	0.00	0.00
Scaling	None	0.02	Linear Feet	-	-	0	0.00	0.00
								9.57
								65.0

Table 15: Post Survey 3 PSR Calculator for Slow Lane of NB 9.4-9.5 (PCC Section)

3.2 ARAN Surface Distress Data Collection and Comparison Process

The ARAN recorded surface distresses for the state's pavement management system in the fall of 2012 between Survey 2 and 3. The ARAN data provides another form of surface distress data which could be beneficial to the analysis of the manually surveyed data.

A comparison was conducted to determine the feasibility of replicating indices outlined within the Composite Condition Index using manually surveyed distresses and the CCI calculation model. This was a quick investigation into the consistency between ARAN and human recorded surface distresses for US 35. Inconsistencies between distress and severity definitions were noted and additional assumptions and concerns would be identified from this comparison.

After all assumptions, concerns, and inconsistencies were addressed, distress data from the northbound slow lane in Survey 1, 2, and 3 were applied to the equations for each of the indices within the PMS document. All three calculated indices were compared graphically to the index value provided by the WVDOH PMS.

The above analysis provides a comparison of the PMS statistics computed with the manual survey to the indices in the PMS database. It was not possible to reverse this process to compute PSR from the data in the PMS database. The distress types, extent and severity in the PMS database are not compatible with the calculation of PSR.

3.3 Deflection Testing Data Collection and Analysis Process

In July of 2014, FWD deflection data were collected for US 35 in both northbound and southbound slow lanes of asphalt and concrete sections. The West Virginia Division of Highways does not currently rely on FWD deflection data for managing or designing its pavements, so a goal of this research was to investigate the potential for doing so in the future. Hence, no LTPP, ASTM, or other FWD procedure was explicitly followed with regards to location and frequency of FWD tests.

This section has five parts. The first describes the process by which deflection tests were performed. The second section describes the initial screening of the FWD data. The following three, describe the method by which three different computer programs were used to analyze the data collected. The three programs, which are described in the Literature Review, are MODULUS 6.1, MODTAG, and BAKFAA.

3.3.1 Deflection Data Collection

At each test location, three drops were performed at four target load levels (6, 9, 12, and 16 kips). The sensors were placed at -12, 0, 8, 12, 18, 24, 36, 48, and 60 inches from the center of the load. The -12 and 8 inch sensor were not used for analysis.

All FWD tests were performed at the transverse center of the slow lane of each direction. For the asphalt sections, FWD tests were performed approximately at the beginning and end of each section, resulting in 36 test locations. On concrete sections the FWD tests were performed at approximately the longitudinal center of the first and last whole slab of each section resulting in 28 test locations.

3.3.2 Initial Screening of Deflection Data

Due to the stiffness of concrete pavement it is recommended that only drops within a 16 kip load level be analyzed. Smaller load levels do not generate large enough deflections to analyze the structural capacity. Additionally, per the LTPP protocol, deflection data should be collected at the longitudinal center of the slab $\pm 10\%$ of the slab length. Using these criteria, 12 of the 28 test locations were eliminated from the analysis. The data was then checked to ensure the measured deflections consistently decreased with an increase in distance from the load center. These criteria eliminated 15 drops of the remaining eligible 48 drops (16 acceptable test locations with 3 acceptable drop loads). The screening process left 33 deflection tests for backcalculation analysis within the concrete section.

The longitudinal location criteria and load level criteria do not apply to asphalt pavements. The decreasing deflection screening was applied to the asphalt section. All of the deflection basins exhibited deflections which decreased as distance from the center of the load increased.

3.3.3 MODULUS 6.1 Deflection Data Analysis Process

The MODULUS 6.1 program is limited to the analysis of asphalt pavements. Two separate files for US 35 north and southbound asphalt sections were imported into MODULUS 6.1. Both files included all 12 drops at the 36 asphalt test locations. Backcalculation analyses were performed using each file, one assuming a three layer pavement structure, the other assuming two layers. An average temperature of 87°F was used; the surface temperature of the pavement varied significantly between morning and afternoon measurements. This temperature effectively restricts asphalt layer moduli to a range of 120 to 660 ksi.

The three layer system had a “Surface” asphalt layer of 12.75 inches and Poisson’s Ratio of 0.40 followed by, a “Base” layer consisting of “Other Material” of four inch thickness with moduli range of 10 to 150 ksi and Poisson’s Ratio of 0.35, followed by a semi-infinite “Subgrade” layer consisting of “Other Material” with a seed modulus of 10 ksi and Poisson’s Ratio of 0.40. After running the backcalculation, MODULUS 6.1 provided outputs for each individual deflection basin. Moduli values for each of the three layers, an estimated depth to bedrock, and an absolute error per sensor were recorded for all 432 instances.

From there, the VDOT subgrade modulus “rule-of-thumb” was applied and two different sets of data were generated. The first was the program output subgrade modulus, M_R , and the second divided the M_R by three and capped it at 10 ksi. This will be referred to as M_{R*} . For both M_R data sets, an effective modulus for total pavement structure, E_p , was then calculated as described in the literature review. This required a Microsoft Excel Macro to simultaneously Goal Seek the 432 unique instances in both subgrade modulus sets. After that, the AASHTO 93 effective structural number equation described in the literature review provided an effective structural number, SN_{eff} , for all 864 data sets and the AASHTO 1993 flexible pavement structural design equation was used to calculate an amount of equivalent single axle loads, ESAL, until failure (also known as W_{18}) for each case. All of these outputs could be averaged per the 36 test locations to compare to each other, or averaged further in the north and southbound sections entirely which correspond to morning and afternoon testing. This could provide information as to the effects of using a single average pavement temperature for the entire days testing.

The two layer system had a surface layer of 16.75 inches with a Poisson’s Ratio of 0.40 on a semi-infinite subgrade layer consisting of “Other Material” with a seed modulus of 10 ksi and Poisson’s Ratio of 0.40. The same outputs were provided as in the three layer system, but this time the surface layer moduli could be considered the E_p . Additionally two more variations of E_p were calculated as in the three layer system. In these cases, the specified equation in combination with the Excel Macro and Goal Seek function provide E_p values for the provided M_R and the VDOT “rule-of-thumb” M_{R*} . All other calculations were performed as in the three layer system and thus three more sets of SN_{eff} and W_{18} were rendered.

Thus a total of five variations of SN_{eff} were computed for every FWD drop on the asphalt sections:

- SN_{eff} as a function of E_p as a function of M_R from a 3 layer MODULUS 6.1 backcalculation
- SN_{eff} as a function of E_p as a function of M_{R^*} from a 3 layer MODULUS 6.1 backcalculation
- SN_{eff} as a function of E_p from a 2 layer MODULUS 6.1 backcalculation (E_p output by MODULUS 6.1)
- SN_{eff} as a function of E_p and M_R from a 2 layer MODULUS 6.1 backcalculation
- SN_{eff} as a function of E_p and M_{R^*} from a 2 layer MODULUS 6.1 backcalculation

3.3.4 MODTAG Deflection Data Analysis Process

As in the MODULUS 6.1 analysis, the files for US 35 were imported into MODTAG. A three layer backcalculation was performed using each file. All layer inputs were the same as in MODULUS 6.1 with the exception that MODTAG uses seed moduli values rather than ranges. These were input as 400 and 75 ksi for the surface and base layers. The built in temperature correction was overridden and the pavement was set to a uniform temperature of 87°F to make the results comparable to the MODULUS 6.1 outputs.

MODTAG output M_R , SN_{eff} , and W_{18} for each load level of each test location. These outputs were averaged values of the three drops at each load level. In the asphalt section, a total of 144 sets of deflection data were available from the 36 test locations. As with MODULUS 6.1, M_{R^*} was included in the analysis. The same general analysis processes were used to develop three different SN_{eff} values for the pavement which could be defined as:

- SN_{eff} as provided by 3 layer MODTAG backcalculation
- SN_{eff} as a function of E_p and M_R from a 3 layer MODTAG backcalculation
- SN_{eff} as a function of E_p and M_{R^*} from a 3 layer MODTAG backcalculation

MODTAG was not used for the analysis of the concrete pavements as MODTAG treats the three replicate drops as a single test result and none of the data sets had all three drops pass the screening process.

3.3.5 BAKFAA Deflection Data Analysis Process

BAKFAA was used to perform analysis on both asphalt and concrete FWD data. Although BAKFAA is not necessarily designed specifically for rigid pavement backcalculations, the linear elastic analysis subroutine for estimating layer moduli is applicable to rigid pavements provided appropriate seed moduli are used. In the three layer asphalt backcalculation, the same inputs from MODTAG were

used in BAKFAA, with the addition of interface coefficients of 1.0 (assuming complete bondage between layers), and the exclusion of any temperature input because BAKFAA performs no temperature correction. BAKFAA also included a semi-infinite bedrock layer which required inputs for modulus and depth. These would not be recalculated by the program so values of 500 ksi and 200 inches from pavement surface were used. The depth to bedrock was estimated at 200 for the sake of reasonable comparison to MODULUS 6.1 and MODTAG which previously estimated average depth to hard bottom of 239 and 188 inches respectively. Deflection data from the third replicate of the 16 kip load level at each asphalt test location was manually input into BACKFAA which provided backcalculated moduli values for all three layers. In all, 36 sets of layer moduli were output. As with the previous programs, M_R and M_{R^*} would be used to generate two sets of SN_{eff} for each deflection test.

The same input process was used for 33 concrete drops. The exception being surface and base layers had depths of 10 and 6 inches respectively and the surface layer had seed modulus and Poisson's ratio inputs of 4000 ksi and 0.15 respectively. The only results produced with this analysis were estimates of M_R for some of the concrete sections. These were compared to the M_R results for the asphalt sections.

Chapter 4. Analysis

4.1 Analysis of Improvements in Pavement Surface Rating Process

The improvement of the PSR calculation process was iterative and continuously evolving. This section documents the problems and solutions encountered throughout as comprehensively as possible. It is separated into two parts. The first outlines the initial analysis done after the third survey was completed in July of 2013. The problems discussed there are generally concerning definitions of distresses. Eliminating vagueness and establishing rules for collecting distress data were critical to progressing with improvements. The second part deals with the improvement of PSR in terms of correlation to PCI while also fixing any unresolved flaws in the logic and organization of the process.

4.1.1 Initial Analysis of US 35 PSR

The first analysis of manually surveyed surface distress data occurred after the third survey in July of 2013. PSR was calculated based on the April 2012 version of “West Virginia Department of Transportation Division of Highways Special Provision, Section 490: Nine Year Pavement Performance Criteria”. The method of calculating PSR would be slightly modified by the time of the fifth survey in May of 2014 and completely overhauled after that point. The Initial PSR calculations for US 35 are now obsolete and are only included to mark the progression of changes that were made. A comparison of fifth survey PSR’s using the initial and final calculation methods are prevented later.

Assumptions made during the initial collection of distress data and calculation of PSR for asphalt sections include:

- Only Transverse Cracking, Longitudinal Cracking, Joint Deterioration, Block Cracking, Alligator (Fatigue) Cracking, Rutting, Raveling/Weathering, and Patching are currently factored into PSR.
- Bleeding and Potholes and any other distresses noticed are marked on the surveys but are not factored into PSR.
- Cracking noted at joints is counted as both Longitudinal Cracking and Joint Deterioration
- Joints labeled “LS ravel/deterioration”, “slight ravel/deterioration”, “Slight raveling at center joint” are quantified as joint deterioration, not longitudinal cracking.
- Joints labeled “LS JT”, “LS paint stripe” are considered both Longitudinal Cracking and Joint Deterioration.
- The center joint is included in the slow lane as it is located a few inches to the slow lane side of the lane divider for the vast majority of the asphalt section of US 35.
- Any cracks with unlabeled severity are considered Low Severity.

- When the first page of a sections survey is labeled “raveling 100%”, “100% raveled”, “slight raveling/deterioration”, “LS raveling throughout”, “generally open/raveled”, “opened slightly center mat”, “generally slightly open texture”, “center raveling full length”, etc. without specifically referring to a joint, it means entire length is raveled/weathered.
- Cases where a distress is noted on a survey and then crossed out on the following survey, the distress is still included in the original survey.
- Pencil lines indicate first survey, red ink indicates second survey, blue ink indicates third survey except on mile marker 15.5-15.6 where the first survey is recorded in blue ink, and the third was recorded in pencil (excluding the rutting recordings which were done in the correct color).
- Average Rutting Depth was determined by averaging all values recorded in both wheel paths within the same lane.

Below is the list of necessary assumptions made during the initial collection of distress data and calculation of PSR for concrete sections:

- Only Transverse Joint Spalling, Faulted Joints (longitudinal and transverse), Corner Breaks, (Faulted Panels, Patched Panels, Longitudinal Joint Spalling, Localized Distress, Transverse Cracking, Longitudinal Cracking, and Scaling are currently factored into PSR.
- Pop outs and any other distresses noticed are marked on the surveys but are not factored into PSR calculation. (This was assumed the time of the third survey data collection but was changed before the first data analysis occurred.)
- The center joint is included in the slow lane as it is located a few inches to the slow lane side of the lane divider for the vast majority of the concrete section of US 35.
- Any unlabeled cracks are considered Low Severity.
- All unlabeled spalling as well as spalling labeled “beginning spalling” are counted as Low Severity.
- For Transverse Joint distresses, the slab that begins with that joint (from left to right on the surveys) is the slab where the distress is recorded.
- Vaguely labeled spalling widths such as “W:4”, are recorded using discretion of drawing and assumed meaning.
- Corner Breaks are determined based on the size requirements and the apparent size drawn on surveys.
- Moderate and High Severity Corner Breaks fall under the High severity distress weight.
- Hairline shrinkage cracks which do not propagate far into a slab that are perpendicular to transverse joints and near slab edges may be recorded on diagrams but are not counted as longitudinal cracks.

Below is a list of additional concerns regarding the survey procedure, the data which were collected, and the process for calculating PSR:

- Surveys for PCC Northbound lanes between mile marker 11.7 and 11.8 have many discrepancies between the 3 surveys.
- PSR per “West Virginia Department of Transportation Division of Highways Special Provision” does not currently include pop outs or several other distresses included in the LTPP distress identification manual. (This was true at the time of the third survey but was changed before the initial analysis of the data.)
- The parameters for all cracks in both pavement types are very specific especially in the differences between severity levels. This can lead to distress being classified differently between two surveys depending on the ability of the surveyor to identify if an observation was above or below the threshold.
- No parameters are included for severities of joint faulting for PCC jointed pavements anywhere in the Section 490, S.P. document or in LTPP however there are 3 severities included in the PSR calculation.
- The difference between Longitudinal Cracking and Alligator Cracking within the Longitudinal Cracking definition in the Section 490, S.P. document is very vague.
- Because there are technically two longitudinal joints in the slow lanes of both pavements, distresses involving longitudinal joints can have up to 200% distress in the PSR calculation which seems strange but is shown as acceptable in an example in the Section 490, S.P. document.
- The Section 490, S.P. document gives only two Severity distress weight values for Corner Breaks. It defaults to the LTPP parameters for these severities; however, LTPP defines Corner Breaks as having 3 severities.
- The surveys are conducted by several different people within each survey and within each 1/10th mile section. Discrepancies pertaining to labeling and nomenclature on the surveys are evident.
- This entire process relies on the dependability and training of the surveyors. If surveys are incorrect, PSR will be incorrect.

4.1.2 Refinement of PSR Calculation Procedure

An iterative process of changing weight factors was initially used in the recalibration of the PSR calculator. This was guided mostly by judgment of senior engineers from the DOH and advisors. As the 4th and 5th surveys were conducted in September 2013 and May 2014, more distresses began to emerge and noticeable progressions in certain distresses also became evident. As the road aged and distresses increased, the observed test section Total Weighted Distress values increased, and calculated PSR values decreased, and the effects of the applied weight factors became more evident.

Several variations to weight factors were made so PSR converged toward values which reflected the distresses across US 35. With each variation, additional distress combinations were considered because the road still was relatively young and did not display a wide enough variation of distresses. Several changes to distress definitions, additions of distresses, and combinations of other distresses were made to remedy concerns within the process.

PSR values which were representative of the deterioration of the pavement condition had been reached and the effect of distresses on calculated PSR was intuitively understood but the process was still subjective and imprecise. A more definite and unarguable approach was desired so the roots of the PSR calculation process were revisited. PCI as developed by the U.S. Army Corps of Engineers and describe in ASTM D6433-11 “Standard Practice for Roads and Parking Lots Pavement Condition Index (PCI) Survey” is still one of the most developed and accepted pavement rating systems. PCI had a major influence on the development of WVDOH’s PSR. Because PCI is so well defined and serves the same purpose as PSR, an attempt to directly correlate PSR to PCI was made.

In order to accomplish this, a complete understanding of the PCI calculation process is necessary. The process is summarized within the U.S. Army Corps of Engineers Pavement Condition Index section of Chapter 2. To accurately correlate PSR and PCI, the distress weight factor for PSR must reflect the distress deduct curve for that distress. Several aspects must be considered here due to the differences in the two processes and the goal of WVDOH in creating a process simpler than that used for PCI.

1. PSR uses a single distress weight factor which can be multiplied by a distress extent. This weight factor assumes there is a linear relationship between the extent of a distress and the effect on the pavement condition. PCI uses a deduct curve for all distresses where the distress weight is dependent on the extent. This relationship is not linear and in nearly all cases displays a logarithmic trend where the change in deduct lessens as extent increases toward 100%. Because of this difference, PSR cannot possibly perfectly match a PCI curve.
2. In many cases PSR uses linear measurements or a counted amount to quantify a distress and determine an extent. PCI uses a percent area affected to determine extent in nearly all cases. PSR works under the assumption that a distress extent of 100% is possible. That is to say, a longitudinal joint within an asphalt section which expresses low severity deteriorated for 528 feet within a 1/10th mile section would justify a recording of 100% low severity joint deterioration toward a PSR calculation. The same section when analyzed with PCI would qualify as approximately 8% low severity joint deterioration (if the lane width is 12 feet). Within PCI many distresses simply cannot reach an extent of 100%. For example, by PCI’s definition, 100% longitudinal cracking would mean a longitudinal crack is present within each foot of lane width for the length of the test section. At this point, this distress would likely not be considered longitudinal cracking. This requires a case by case comparison when attempting to correlate each individual distress.

3. In both PCI and PSR, some distress combinations are not possible. For instance, in either case, a theoretical asphalt section with 50% Block Cracking cannot possibly also have 75% Longitudinal Cracking because regardless how these distresses are mapped on a section, there would be overlap and by definition Block Cracking would override Longitudinal Cracking. For this reason, if a comprehensive correlation of PCI and PSR can be accomplished, theoretical distress combinations must be derived from an observable scenario before PCI or PSR is calculated. It would be erroneous to calculate each across the array of mathematically possible distress extents. The practical range of distresses requires understanding of each system as well as experience in observing surface distresses.
4. PCI requires a correction factor after combining all distresses. This reduces the total deduct based on the total amount of observed distresses. The idea here is that there is a type of diminishing return occurring. As the amount of different distresses increase, the effect of each individual one is reduced. Similar to point #1 above, PSR assumes a linear relationship and in this case has no reduction procedure. Where PCI's combination of distresses will express a logarithmic trend again, PSR will have to attempt to linearly approximate the curve.
5. There is a concern that within the PCI calculation method, Jointed Plain Concrete Pavement (JPCP) sections can only be optimally modeled with PCI if there are exactly 20 slabs. An attempt to normalize the PSR to any reasonable amount of slabs within 1/10th of a mile must be made.
6. When making changes to PSR, maintaining a balance of accuracy in modeling pavement condition and simplicity as compared to PCI is critical. The main reason for developing PSR is that PCI requires too many calculations and references to graphs and charts. Approximating PCI's accuracy while reducing the effort to reach it is the goal.
7. It should also be stressed that the goal is not to have any given distress scenario result in identical values for PSR and PCI. The goal is to develop a PSR scale that contains a correlation to PCI but not necessarily at a 1:1 ratio. If the ranges for the qualitative condition expressions need to be adjusted they can be.
8. Additionally, the goal here is to create a scale that can compare asphalt and concrete sections. PCI claims that their pavement condition scale is the same for both asphalt and concrete surfaces. This is to say that a PCI of 75 represents the same quality road surface regardless of pavement type. So if there is a correlation between PSR and PCI, there should be a goal of mirroring that correlation between asphalt and concrete sections.

9. Another goal is to adapt the asphalt PSR calculator to account for composite pavements. This would make the PSR calculation method dependant on the pavement surface material. Although composite pavements are technically classified as rigid pavements, the surface distresses observable would still tend more toward flexible asphalt pavement distresses. However definition changes are necessitated to accommodate this goal.

To incorporate all of these concerns while converging on an acceptable PSR calculation model, first a case by case comparison of PCI deduct curves and PSR weight factors was made. Because both PSR and PCI are based on 0 – 100 scales, PSR weighted distresses can be converted into deduct values which would be comparable to PCI deduct values. For each severity of each distress, the original PSR weighted distress was entered alone into the Total Weighted Distress, TWD, calculation formula at several extent values within the 0 – 100% range.

PCI's deduct value curves for asphalt distresses show extent on a logarithmic scale and concrete distresses on a linear scale. This is because the extent of asphalt distresses is mostly measured on an area affected basis and the extent of concrete distresses is measured on an amount of slabs or joints affected. If 50% or 100% of joints within a concrete section shows spalling at some severity, then the extent would be 50% or 100% respectively. The resulting distress between these two scenarios would be noticeably different, so it is important that concrete distresses measure on a slab/joint affected basis be considered on a 0 – 100% extent range. This is contrary to say, Alligator/Fatigue Cracking on an asphalt surface, where the difference between 5 and 10% affected area may very well be more noticeable than the difference between 70 and 100%. For this reason the array of extent values input into TWD calculations was dependent on the scale used by PCI. For logarithmic scales, the list of extents used to calculate TWD was: .1, .2, .5, 1, 2, 5, 10, 20, 50, and 100%. For standard scales, the list of extents used to calculate TWD was: 0, 5, 10, 15, 20, 30, 50, 70, and 100%. This process successfully converted individual PSR weight factors in deduct curves that could be compared to PCI deduct curves. Each of these extent values were entered into their corresponding deduct curves to find their deduct value. These were entered into Excel files for analyses.

From there, each severity of each distress was carefully examined. The generated deduct curves for PSR TWD deducts for each case was iteratively modified until the curve agreed with the PCI deduct curve. Again, this agreement does not mean that the PCI and PSR deduct values were identical for each input extent. Each case had to be customized to account for differences in distress definitions and extent calculation methods. Additionally, PCI's deduct value correction factor had to be accounted for.

The modification of the PSR deduct curve was accomplished by changing the PSR weight factor associated with each distress. The curve was updated automatically as the new weight factor and the array of extent percentages were used to recalculate the Total Weighted Distress within the Excel file.

A comprehensive analysis of the influences on each weight factor's final value is included in Appendix B. Each severity of each distress for both pavement types includes a list of factors which resulted in the final weight factor. A graphical comparison of PSR weight factor and PCI deduct curve is provided for each relevant distress type/severity combination.

After an examination of each deduct curve individually, the practicality of the combination of distresses had to be verified. To start, a few asphalt and concrete sections from US 35's fifth survey were sampled. PSR for these sections was calculated with the new distress weight factors. Then PCI was computed for each. Only a few US 35 sections were used because the combination and variation of distress types and amounts was fairly limited. From there, hypothetical sections were developed that encompassed each distress type and severity as a primary distress within a section. These hypothetical test sections used logical and realistic combinations of supporting distresses in some cases. Each time, the hypothetical section scenario was developed, and PSR and PCI were calculated. Often, these scenarios were based on interesting pavement distress types and combinations observed by engineers at WVDOT.

A PCI vs. PSR correlation for 77 unique hypothetical section scenarios was developed. Of these, 39 were asphalt surface sections and 38 were concrete surface sections. Regression lines were generated for the PCI vs. PSR correlations of both surface types. A comparison of these regression lines provided a means to determining consistency between PSR values of asphalt versus concrete.

One more series of alterations to PSR weight factors was then made. For both correlation graphs, groups of outliers were identified based on the common distress within them that was affecting the best fit line. As slight corrections were made to the weight factors, PSR of these groupings converged toward the rest of the test points. As the envelopes of both correlations began to tighten and the best fit lines began to converge toward each other, the weight factors were reviewed to ensure that they were still logically sound and satisfied all other concerns mentioned previously. This process repeated until all concerns were satisfied and a panel of engineers from the WVDOT approved the result.

4.2 Comparison Analysis of ARAN and Manual Survey Surface Distress Data

As stated within Chapter 3, an attempt at replicating the indices associated with CCI (outlined in Chapter 2) was made using the surface distress data collected during the first three manual surveys. This was to be compared to the data collected by an ARAN and analyzed by the PMS dTIMS software by the WVDOH.

Distress data were observed within the slow lane of the northbound section of US 35 by the ARAN in a Fall 2012 survey. Data were provided for the entire length of the highway. However, this data set was reduced to only include sections that were surveyed manually for calculation of PSR.

A summary of the distress data recorded within the asphalt section, concrete section, and a table identifying the labels used with the Pavement Management System is presented in Table 16, Table 17, and Table 18 respectively. The important information provided within these tables is the columns labeled PSI, SCI, ECI, RDI, JCI, and CSI. As explained in Chapter 2, CCI is recorded as the lowest of all other indices calculated for a section. PSI was the lowest calculated index for every section within the study. PSI is based solely on IRI which is a measure of surface roughness and cannot be determined via a manual surface distress survey. The remaining indices were calculated using the data collected from Section 490, Special Provision manual surveys and compared to the values provided by the Pavement Management System.

BEG_MP	END_MP	IRI_MEAN	PSI	SCI	ECI	RDI	CCI	FALLIG_L	FALLIG_M	FALLIG_H	FLONG_L	FLONG_M	FLONG_H	FTRANS_L	FTRANS_M	FTRANS_H	FBLOCK_L	FBLOCK_M	FBLOCK_H
12.60	12.70	146.800	2.996	5.000	5.000	4.777	2.996	0	0	0	0	0	0	0	0	0	0	0	0
13.20	13.30	53.800	4.012	5.000	5.000	4.874	4.012	0	0	0	0	0	0	0	0	0	0	0	0
13.80	13.90	57.400	3.955	5.000	5.000	4.874	3.955	0	0	0	0	0	0	0	0	0	0	0	0
14.40	14.50	65.200	3.833	5.000	5.000	4.741	3.833	0	0	0	0	0	0	0	0	0	0	0	0
14.60	14.70	58.600	3.932	5.000	5.000	4.704	3.932	0	0	0	0	0	0	0	0	0	0	0	0
15.20	15.30	102.300	3.327	5.000	5.000	4.777	3.327	0	0	0	0	0	0	0	0	0	0	0	0
15.40	15.50	81.300	3.615	5.000	5.000	4.741	3.615	0	0	0	0	0	0	0	0	0	0	0	0
16.00	16.10	59.900	3.914	5.000	5.000	4.665	3.914	0	0	0	0	0	0	0	0	0	0	0	0
16.40	16.50	115.800	3.239	4.790	5.000	4.005	3.239	1	0	0	0	0	0	0	0	0	0	0	0

Table 16: Summary of WVDOT PMS Distress Data for US 35 Northbound Slow Lane Asphalt Section

BEG_MP	END_MP	IRI_MEAN	PSI	JCI	CSI	JFAULT_L	JFAULT_M	JFAULT_H	JNT_DIST	BRSLBTR_L	BRSLBTR_M	BRSLBTR_H	BRSLBTRL_L	BRSLBTRL_M	BRSLBTRL_H
9.1	9.2	81.000	3.598	5.000	5.000	0	0	0	0	0	0	0	0	0	0
9.4	9.5	69.900	3.756	5.000	5.000	0	0	0	0	0	0	0	0	0	0
10.4	10.5	66.200	3.817	5.000	5.000	0	0	0	0	0	0	0	0	0	0
10.8	10.9	62.600	3.872	5.000	5.000	0	0	0	0	0	0	0	0	0	0
11.4	11.5	83.700	3.553	4.870	5.000	1	0	0	0	0	0	0	0	0	0
11.7	11.8	63.900	3.851	5.000	5.000	0	0	0	0	0	0	0	0	0	0
12.2	12.3	101.500	3.416	4.870	5.000	1	0	0	0	0	0	0	0	0	0

Table 17: Summary of WVDOT PMS Distress Data for US 35 Northbound Slow Lane Concrete Section

Starting Mile Point	BEG_MP	miles	WVDOT Beginning Mile point
Ending Mile Point	END_MP	miles	WVDOT Ending Mile point
Roughness Average	IRI_MEAN	inches/mile	Average of Left and Right IRI (-1 - invalid)
Present Serviceability Index	PSI	-	Present Serviceability Index ($PSI = 5 * E^{(-0.0041 * IRI)}$) (-1 - invalid)
Joint Faulting Low	JFAULT_L	%	Joint Faulting - Low Severity (% of slabs exhibiting faulting) +/- 0.1 to 0.2
Joint Faulting Moderate	JFAULT_M	%	Joint Faulting - Moderate Severity (% of slabs exhibiting faulting) +/- 0.3 to 0.4
Joint Faulting High	JFAULT_H	%	Joint Faulting - High Severity (% of slabs exhibiting faulting) +/- 0.41 to 1.2
Alligator Cracking Low	FALLIG_L		Alligator Cracking - Low Severity (Percentage of total wheelpath area)
Alligator Cracking Moderate	FALLIG_M		Alligator Cracking - Moderate Severity (Percentage of total wheelpath area)
Alligator Cracking High	FALLIG_H		Alligator Cracking - High Severity (Percentage of total wheelpath area)
Longitudinal Cracking Low	FLONG_L		Longitudinal cracking - Low severity (% wheelpath crack affected area)
Longitudinal Cracking Moderate	FLONG_M		Longitudinal cracking - Moderate severity (% wheelpath crack affected area)
Longitudinal Cracking High	FLONG_H		Longitudinal cracking - High severity (% wheelpath crack affected area)
Transverse Cracking Low	FTRANS_L		Transverse cracking - Low severity (% lane crack affected area)
Transverse Cracking Moderate	FTRANS_M		Transverse cracking - Moderate severity (% lane crack affected area)
Transverse Cracking High	FTRANS_H		Transverse cracking - High severity (% lane crack affected area)
Block Cracking Low	FBLOCK_L		Block cracking - Low severity (Percentage of the total lane area)
Block Cracking Moderate	FBLOCK_M		Block cracking - Moderate severity (Percentage of the total lane area)
Block Cracking High	FBLOCK_H		Block cracking - High severity (Percentage of the total lane area)
Joint Distress	JNT_DISTR		Joint Distress - One severity (% of slabs showing joint distress)
Broken Slab Trans Low	BRSLBTR_L		Broken Slabs - Transverse only low severity (% of slabs exhibiting condition)
Broken Slab Trans Moderate	BRSLBTR_M		Broken Slabs - Transverse only moderate severity (% of slabs exhibiting condition)
Broken Slab Trans High	BRSLBTR_H		Broken Slabs - Transverse only high severity (% of slabs exhibiting condition)
Broken Slab Trans & Long Low	BRSLBTRL_L		Broken Slabs - Transverse & Longitudinal low severity (% of slabs exhibiting condition)
Broken Slab Trans & Long Moderate	BRSLBTRL_M		Broken Slabs - Transverse & Longitudinal moderate severity (% of slabs exhibiting condition)
Broken Slab Trans & Long High	BRSLBTRL_H		Broken Slabs - Transverse & Longitudinal high severity (% of slabs exhibiting condition)
Structural Cracking Index	SCI		Structural cracking index $MAX(MIN(5-(0.21*(fallig_l^{0.67}))-(0.24*(fallig_m^{0.69}))-(0.40*(fallig_h^{0.80}))- (0.28*(flong_l^{0.73}))-(0.32*(flong_m^{0.75}))-(0.40*(fblock_h^{0.80})),5),0)$
Environmental Cracking Index	ECI		Environmental cracking index $MAX(MIN(5-(0.32*(ftrans_l^{0.75}))-(0.40*(ftrans_m^{0.80}))- (0.60*(ftrans_h^{0.89}))-(0.24*(fblock_l^{0.69}))-(0.28*(fblock_m^{0.73}))-(0.40*(fblock_h^{0.80})),5),0)$
Rut Depth Index	RDI		Rut depth index $MAX(MIN(5-(6.65*(frut_mean^{1.41})),5),0)$
Joint Condition Index	JCI		Joint condition index $MAX(MIN(5-(0.13*(jfault_l^{0.56}))-(0.16*(jfault_m^{0.60}))-(0.17*(jfault_h^{0.62}))- (0.13*(jnt_distr^{0.56})),5),0)$
Concrete Slab Index	CSI		Concrete slab index $(MIN(5-(0.13*(brslbtr_l^{0.56}))-(0.17*(brslbtr_m^{0.62}))-(0.20*(brslbtr_h^{0.65}))- (0.20*(brslbtrl_l^{0.65}))-(0.28*(brslbtrl_m^{0.73}))-(0.40*(brslbtrl_h^{0.80})),5),0)$

Table 18: WVDOT PMS Legend for Distress Data as provided with Distress Summary

Assumptions made during the comparison of ARAN and manual distress surveys on US 35 for the calculation of CCI and associated indices for asphalt section include:

- Data from Survey 1, 2, and 3 were used for comparison to WVDOH PMS data.
- Only data from the slow lane were used for comparison to WVDOH PMS data.
- The parameters for each severity of Alligator, Block, Transverse, and Longitudinal Cracking match identically between the two systems.
- The average of all the rut depth readings in BOTH wheel paths is RD.
- Only cracking within wheel paths is counted, i.e. joint cracking was counted in longitudinal cracking.
- The method for calculating percent of wheel path affected is the same as the method used to calculate percentage in Section 490, Special Provision.

Assumptions made during the comparison of ARAN and manual surveys on US 35 for the calculation of CCI and associated indices for concrete sections include:

- Data from Survey 1, 2, and 3 were used for comparison to WVDOH PMS data.
- Only data from the slow lane were used for comparison to WVDOH PMS data.
- The parameters for each severity of Faulting, Longitudinal Cracking, and Transverse Cracking match identically between the two systems.
- All transverse faults within the Section 490, Special Provision data were counted as + faults (there is no mention of direction of faults in surveys).
- General Joint Distress is the percentage of all transverse joints within the section that have any distresses (Faulting, Spalling, Cracking, etc. on transverse joints).
- Only Cracking within wheel paths is counted.
- The method for calculating percent of wheel path affected is the same as the method used to calculate percentage in Section 490, Special Provision.

Additional concerns regarding the comparison of WVDOH PMS data to PMS indices generated with the manual surface distress survey data include:

- Because the Section 490, Special Provision survey data does not include IRI data and there is no method of calculating IRI with the surveyed data, the Present Serviceability Index (PSI) cannot be determined.
- Because the PSI was the limiting factor in the determination of Composite Condition Index (CCI) in the WVDOH PMS data for both the HMA and PCC sections, comparing CCI values will be insignificant since PSI is not included in the Section 490, Special Provision data.
- In a few instances, if IRI within the PMS data were entered into the PSI equation, the resulting PSI slightly differed from the PSI provided by the PMS database. A summary of these differences

is provided within Table 19. In this table, “PSI from equation” represents PSI when calculated using IRI and the PSI equation. “PSI given” represents the PSI directly from the WVDOH PMS database.

- Although the assumption was made to consider distress definitions and severity levels comparable between WVDOH PMS and Section 490, Special Provision, there were slight variations between the two in terms of distress and severity identification. A summary of the discrepancies is presented in Table 19.
- All other concerns regarding accuracy and consistency in using manually surveyed distress data to calculate PSR are still applicable.

Mile Markers		PSI from equation	PSI Given
HMA	12.6 -12.7	2.74	3.00
	13.2 -13.3	4.01	4.01
	13.8 -13.9	3.95	3.96
	14.4 -14.5	3.83	3.83
	14.6 -14.7	3.93	3.93
	15.2 -15.3	3.29	3.33
	15.4 -15.5	3.58	3.62
	16.0 -16.1	3.91	3.91
	16.4 -16.5	3.11	3.24
PCC	9.1 - 9.2	3.59	3.60
	9.4 - 9.5	3.75	3.76
	10.4 - 10.5	3.81	3.82
	10.8 - 10.9	3.87	3.87
	11.4 - 11.5	3.55	3.55
	11.7 - 11.8	3.85	3.85
	12.2 - 12.3	3.30	3.42

Table 19: Variation between PSI calculated from IRI and PSI provided

In Table 20, parameters for distress identification for WVDOH PMS are abbreviated to PMS and for Section 490, Special Provision, the abbreviation S.P. is used. Indices pertaining to asphalt and concrete sections are in columns (a) and (b) respectively. Low, Medium, and High severities within distresses are labeled LS, MS, and HS respectively. Rows labeled “recording” indicated the method by which the distress is quantified. “% wheelpath” means the percentage of wheelpath affected by the distress. Length is a linear measurement of the distress. Millimeter ranges indicate the range of crack widths which qualify as the given severity. “+ faults” means faults across a crack or joint where there is an increase in elevation from the leave to approach slab or panel.

(a)

HMA:		
Structural Cracking Index (SCI)		
Allig. Cracks	PMS param.	SP param.
LS	0-10 mm	Severity not based on crack width
MS	10-18 mm	
HS	>18 mm	
recording	% wheelpath	length
Long. Cracks	PMS param.	SP param.
LS	0-10 mm	0-6 mm...
MS	10-18 mm	6-19 mm...
HS	>18 mm	>19 mm...
recording	% wheelpath	length
- PMS requires only distresses observed within the wheel paths which consist of 3-foot wide areas starting 2 feet from either edge of the lane. SP does not require differentiation		
Environmental Cracking Index (ECI)		
Block Cracks	PMS param.	SP param.
LS	0-10 mm	0-6 mm
MS	10-18 mm	6-19 mm...
HS	>18 mm	>19 mm...
recording	% wheelpath	length
Trans. Cracks	PMS param.	SP param.
LS	0-10 mm	0-6 mm...
MS	10-18 mm	6-19 mm...
HS	>18 mm	>19 mm...
recording	% wheelpath	length
Net Cracking Index (NCI)		
- still SCI + ECI - 5		
Rut Depth Index (RDI)		
Avg. Rut Depth	PMS param.	SP param.
recording	continuous average	average of 5 readings taken at 100 ft intervals

(b)

PCC:		
Joint Conditioning Index (JCI)		
Faulting	PMS param.	SP param.
LS	0-6 mm	No parameters given
MS	6-12 mm	
HS	>12 mm	
recording	only + faults	+/- faults
General Joint Distress		
- not defined in PMS		
- not included in SP		
Concrete Slab Index		
Trans. Cracks	PMS param.	SP param.
LS	0-12 mm	0-3 mm...
MS	12-25 mm	3-13 mm...
HS	>25 mm	>13 mm...
Long. Cracks	PMS param.	SP param.
LS	0-12 mm	0-3 mm...
MS	12-25 mm	3-6 mm...
HS	>25 mm	>6 mm...

Table 20: Inconsistencies between WVDOH PMS and Section 490, Special Provision distress definition and severities

4.3 Deflection Data Analysis

For asphalt deflection tests, estimating a SN_{eff} was the primary method of comparing estimation methods and judging the structural quality of the pavement. Table 21 displays averaged SN_{eff} values calculated by all described methods and programs. Table 22 displays the identification of SN_{eff} values which were calculated using M_{R^*} (highlighted values) as these estimated values consistently were higher than the WVDOH Design Directive's design structural number of approximately 6.7.

	SN _{eff} as a function of E _p as a function of M _R from a 3 layer MODULUS 6.1 backcalculation	SN _{eff} as a function of E _p as a function of M _R * from a 3 layer MODULUS 6.1 backcalculation	SN _{eff} as a function of E _p from a 2 layer MODULUS 6.1 backcalculation	SN _{eff} as a function of E _p and M _R from a 2 layer MODULUS 6.1 backcalculation	SN _{eff} as a function of E _p and M _R * from a 2 layer MODULUS 6.1 backcalculation
Program	MODULUS 6.1	MODULUS 6.1	MODULUS 6.1	MODULUS 6.1	MODULUS 6.1
Backcalc using:	3 Layer	3 Layer	2 Layer	2 Layer	2 Layer
E _p calculated with:	M _R	M _R *	(E _p provided)	M _R	M _R *
NB HMA Avg SN _{eff}	4.65	7.61	5.30	4.71	7.70
SB HMA Avg SN _{eff}	4.19	6.52	4.76	4.24	6.61
All HMA Avg SN _{eff}	4.42	7.07	5.03	4.48	7.15

	SN _{eff} as provided by 3 layer MODTAG backcalculation	SN _{eff} as a function of E _p and M _R from a 3 layer MODTAG backcalculation	SN _{eff} as a function of E _p and M _R * from a 3 layer MODTAG backcalculation	SN _{eff} as a function of E _p and M _R from a 3 layer BACKFAA backcalculation	SN _{eff} as a function of E _p and M _R * from a 3 layer BACKFAA backcalculation
Program	MODTAG	MODTAG	MODTAG	BACKFAA	BACKFAA
Backcalc using:	3 Layer	3 Layer	3 Layer	3 Layer	3 Layer
E _p calculated with:	not calculated	M _R	M _R *	M _R	M _R *
NB HMA Avg SN _{eff}	4.31	4.90	7.88	5.25	8.94
SB HMA Avg SN _{eff}	4.56	4.42	6.93	4.53	7.38
All HMA Avg SN _{eff}	4.44	4.66	7.41	4.89	8.16

Table 21: Estimated SN_{eff} Summary

	SN _{eff} as a function of E _p as a function of M _R from a 3 layer MODULUS 6.1 backcalculation	SN _{eff} as a function of E _p as a function of M _R * from a 3 layer MODULUS 6.1 backcalculation	SN _{eff} as a function of E _p from a 2 layer MODULUS 6.1 backcalculation	SN _{eff} as a function of E _p and M _R from a 2 layer MODULUS 6.1 backcalculation	SN _{eff} as a function of E _p and M _R * from a 2 layer MODULUS 6.1 backcalculation
Program	MODULUS 6.1	MODULUS 6.1	MODULUS 6.1	MODULUS 6.1	MODULUS 6.1
Backcalc using:	3 Layer	3 Layer	2 Layer	2 Layer	2 Layer
E _p calculated with:	M _R	M _R *	(E _p provided)	M _R	M _R *
NB HMA Avg SN _{eff}	4.65	7.61	5.30	4.71	7.70
SB HMA Avg SN _{eff}	4.19	6.52	4.76	4.24	6.61
All HMA Avg SN _{eff}	4.42	7.07	5.03	4.48	7.15

	SN _{eff} as provided by 3 layer MODTAG backcalculation	SN _{eff} as a function of E _p and M _R from a 3 layer MODTAG backcalculation	SN _{eff} as a function of E _p and M _R * from a 3 layer MODTAG backcalculation	SN _{eff} as a function of E _p and M _R from a 3 layer BACKFAA backcalculation	SN _{eff} as a function of E _p and M _R * from a 3 layer BACKFAA backcalculation
Program	MODTAG	MODTAG	MODTAG	BACKFAA	BACKFAA
Backcalc using:	3 Layer	3 Layer	3 Layer	3 Layer	3 Layer
E _p calculated with:	not calculated	M _R	M _R *	M _R	M _R *
NB HMA Avg SN _{eff}	4.31	4.90	7.88	5.25	8.94
SB HMA Avg SN _{eff}	4.56	4.42	6.93	4.53	7.38
All HMA Avg SN _{eff}	4.44	4.66	7.41	4.89	8.16

Table 22: Estimated SN_{eff} Identification of Values Generated using M_R*

Table 23 and Table 24 introduce the variable of pavements constructed on cuts and fills. Because US 35 is constructed in a location which required cut and fill construction, the potential of varying bedrock depths and subgrade conditions was identified as a possible factor in the variation of deflection data.

Dir. (North/ South)	Mile Post (mi)	CUT/ FILL	SN _{eff} as a function of E _p as a function of M _R from a 3 layer MODULUS 6.1 backcalculation (Avg of all drops)	SN _{eff} as a function of E _p from a 2 layer MODULUS 6.1 backcalculation (Avg of all drops)	SN _{eff} as a function of E _p and M _R from a 2 layer MODULUS 6.1 backcalculation (Avg of all drops)	SN _{eff} as provided by 3 layer MODTAG backcalculation (Avg of all drops)	SN _{eff} as a function of E _p and M _R from a 3 layer MODTAG backcalculation (Avg of all drops)	SN _{eff} as a function of E _p and M _R from a 3 layer BACKFAA backcalculation (12th drop only)
N	16.2	F	5.04	5.70	5.10	4.58	5.04	5.35
N	16.1	F	4.55	5.11	4.61	4.17	4.80	5.10
N	15.8	F	4.32	5.01	4.34	3.77	4.82	4.95
N	15.7	F	5.17	6.05	5.31	4.67	5.40	5.71
N	15.2	F	4.24	4.78	4.26	3.85	4.40	5.10
N	15.1	C	4.33	4.95	4.36	3.81	4.60	5.40
N	15.0	C	4.55	5.10	4.59	4.11	4.91	5.23
N	14.9	F	5.12	5.88	5.28	5.18	5.61	6.13
N	14.4	C	5.06	5.78	5.15	4.87	5.46	5.86
N	14.3	C	4.76	5.49	4.80	4.17	4.95	5.26
N	14.2	C	5.20	5.93	5.36	5.08	5.46	5.53
N	14.1	F	4.24	4.80	4.27	3.87	4.56	4.63
N	13.9	C	4.34	4.94	4.36	3.93	4.56	4.65
N	13.8	F	4.70	5.35	4.73	4.32	4.85	5.05
N	13.3	F	4.28	4.89	4.31	4.03	4.34	5.09
N	13.2	F	4.78	5.49	4.83	4.47	4.89	5.19
N	12.7	F	4.68	5.25	4.74	4.59	5.02	5.14
N	12.6	C	4.40	4.97	4.42	4.06	4.48	5.10
S	12.6	C	4.08	4.58	4.09	4.58	4.43	4.58
S	12.7	C	4.32	4.89	4.38	4.75	4.54	4.60
S	13.2	C	4.83	5.53	4.84	5.53	4.90	4.93
S	13.3	F	3.97	4.46	3.98	4.21	4.31	4.40
S	13.7	F	4.21	4.74	4.29	4.74	4.59	4.79
S	13.8	C	4.08	4.59	4.17	4.42	4.23	4.49
S	14.3	C	4.26	4.89	4.28	4.42	4.40	4.35
S	14.4	C	3.66	4.12	3.71	3.84	3.88	3.84
S	14.5	F	3.87	4.37	3.88	4.05	4.06	4.16
S	14.6	C	4.15	4.68	4.26	4.67	4.43	4.55
S	15.1	F	3.47	4.00	3.56	3.73	3.74	3.87
S	15.2	C	3.89	4.29	3.92	3.80	3.92	3.93
S	15.3	C	3.87	4.35	3.92	4.03	4.10	4.22
S	15.4	F	4.19	4.72	4.30	4.88	4.44	4.67
S	15.9	C	4.62	5.30	4.64	5.24	4.76	4.73
S	16.0	F	4.77	5.60	4.79	5.11	4.83	5.06
S	16.4	C	4.55	5.23	4.56	4.81	4.89	4.84
S	16.5	F	4.66	5.39	4.67	5.37	5.15	5.60
N Avg			4.65	5.30	4.71	4.31	4.90	5.25
S Avg			4.19	4.76	4.24	4.56	4.42	4.53
Avg			4.42	5.03	4.48	4.44	4.66	4.89

Table 23: Summary of Asphalt Section S_{Neff} Values at Each Test Location with Addition of Cut/Fill Information

Dir. (North/ South)	Mile Post (mi)	CUT/ FILL	SN _{eff} as a function of E _p as a function of M _R from a 3 layer MODULUS 6.1 backcalculation (Avg of all drops)	SN _{eff} as a function of E _p from a 2 layer MODULUS 6.1 backcalculation (Avg of all drops)	SN _{eff} as a function of E _p and M _R from a 2 layer MODULUS 6.1 backcalculation (Avg of all drops)	SN _{eff} as provided by 3 layer MODTAG backcalculation (Avg of all drops)	SN _{eff} as a function of E _p and M _R from a 3 layer MODTAG backcalculation (Avg of all drops)	SN _{eff} as a function of E _p and M _R from a 3 layer BACKFAA backcalculation (12th drop only)
N	15.1	C	4.33	4.95	4.36	3.81	4.60	5.40
N	15.0	C	4.55	5.10	4.59	4.11	4.91	5.23
N	14.4	C	5.06	5.78	5.15	4.87	5.46	5.86
N	14.3	C	4.76	5.49	4.80	4.17	4.95	5.26
N	14.2	C	5.20	5.93	5.36	5.08	5.46	5.53
N	13.9	C	4.34	4.94	4.36	3.93	4.56	4.65
N	12.6	C	4.40	4.97	4.42	4.06	4.48	5.10
S	12.6	C	4.08	4.58	4.09	4.58	4.43	4.58
S	12.7	C	4.32	4.89	4.38	4.75	4.54	4.60
S	13.2	C	4.83	5.53	4.84	5.53	4.90	4.93
S	13.8	C	4.08	4.59	4.17	4.42	4.23	4.49
S	14.3	C	4.26	4.89	4.28	4.42	4.40	4.35
S	14.4	C	3.66	4.12	3.71	3.84	3.88	3.84
S	14.6	C	4.15	4.68	4.26	4.67	4.43	4.55
S	15.2	C	3.89	4.29	3.92	3.80	3.92	3.93
S	15.3	C	3.87	4.35	3.92	4.03	4.10	4.22
S	15.9	C	4.62	5.30	4.64	5.24	4.76	4.73
S	16.4	C	4.55	5.23	4.56	4.81	4.89	4.84
N	16.2	F	5.04	5.70	5.10	4.58	5.04	5.35
N	16.1	F	4.55	5.11	4.61	4.17	4.80	5.10
N	15.8	F	4.32	5.01	4.34	3.77	4.82	4.95
N	15.7	F	5.17	6.05	5.31	4.67	5.40	5.71
N	15.2	F	4.24	4.78	4.26	3.85	4.40	5.10
N	14.9	F	5.12	5.88	5.28	5.18	5.61	6.13
N	14.1	F	4.24	4.80	4.27	3.87	4.56	4.63
N	13.8	F	4.70	5.35	4.73	4.32	4.85	5.05
N	13.3	F	4.28	4.89	4.31	4.03	4.34	5.09
N	13.2	F	4.78	5.49	4.83	4.47	4.89	5.19
N	12.7	F	4.68	5.25	4.74	4.59	5.02	5.14
S	13.3	F	3.97	4.46	3.98	4.21	4.31	4.40
S	13.7	F	4.21	4.74	4.29	4.74	4.59	4.79
S	14.5	F	3.87	4.37	3.88	4.05	4.06	4.16
S	15.1	F	3.47	4.00	3.56	3.73	3.74	3.87
S	15.4	F	4.19	4.72	4.30	4.88	4.44	4.67
S	16.0	F	4.77	5.60	4.79	5.11	4.83	5.06
S	16.5	F	4.66	5.39	4.67	5.37	5.15	5.60
Avg		CUT	4.39	4.98	4.43	4.45	4.61	4.78
Avg		FILL	4.46	5.09	4.52	4.42	4.71	5.00

Table 24: Reorganization of Table 23 by Cuts and Fills

Table 25 shows the BAKFAA backcalculated moduli values for the surface, base, and subgrade for all concrete section tests which were eligible for analysis. The subgrade modulus values will be compared to those backcalculated from asphalt section deflection data.

Dir. (North/ South)	Mile Post (mi)	Mile Post (ft)	Surface Modulus (ksi)	Base Modulus (ksi)	Subgrade Modulus (ksi)
N	10.9	57705	9491	217	29
N	10.9	57705	12339	255	26
N	10.9	57705	12384	255	26
N	10.8	57182	4853	234	28
N	10.8	57182	3999	147	33
N	10.5	55593	8741	130	13
N	10.5	55593	7429	149	16
N	10.4	55076	12458	258	26
N	10.4	55076	12736	263	26
N	10.4	55076	9256	293	32
N	9.5	50382	12948	268	27
N	9.5	50382	8791	276	33
N	9.5	50382	8656	269	31
S	9.2	48576	22110	349	28
S	9.2	48576	17073	359	35
S	9.2	48576	28114	365	25
S	9.5	50149	16089	338	33
S	9.5	50149	15407	321	32
S	9.5	50149	15952	334	33
S	11.4	60076	7545	111	19
S	11.4	60076	7537	111	19
S	11.4	60076	7051	165	18
S	11.7	61644	7125	251	28
S	11.7	61644	7012	203	28
S	11.7	61644	7048	193	27
S	11.8	62172	8711	217	25
S	11.8	62172	11572	240	24
S	11.8	62172	11135	230	24
S	12.2	64506	4165	68	26
S	12.2	64506	8781	179	19
S	12.2	64506	3814	101	26
S	12.3	65039	10434	230	19
S	12.3	65039	8921	182	19
S	12.3	65039	11804	236	18
N Avg			9545	232	26.6
S Avg			11305	228	25.0
Avg			10425	230	25.8

Table 25: BAKFAA Moduli Values for Eligible Concrete Drops

Chapter 5. Results

5.1 Pavement Surface Rating

5.1.1 US 35 PSR Original 2012 Spec. Calculation

Calculated PSR values for northbound asphalt and concrete sections following the initial analysis in July 2013 are summarized within Table 26 and Table 27 respectively. Calculated PSR values for southbound asphalt and concrete sections are summarized within Table 28 and Table 29 respectively. The 2012 Special Provision PSR calculation procedure was used for this analysis as it served as the starting point for this research.

Mile Marker	Slow Lane Survey 1	Slow Lane Survey 2	Slow Lane Survey 3	Fast Lane Survey 1	Fast Lane Survey 2	Fast Lane Survey 3
12.6 -12.7	86.46	86.46	69.75	91.37	91.37	91.37
13.2 -13.3	88.30	88.58	82.04	91.37	91.37	91.37
13.8 -13.9	90.99	90.99	88.97	91.37	91.37	91.37
14.4 -14.5	90.22	90.22	80.40	91.37	91.37	91.37
14.6 -14.7	91.37	91.37	91.37	91.37	91.37	91.37
15.2 -15.3	86.68	86.68	72.25	90.90	90.44	90.21
15.4 -15.5	89.56	87.57	78.69	89.75	89.29	89.06
16.0 -16.1	87.61	86.52	83.73	89.09	89.09	89.03
16.4 -16.5	88.61	88.61	86.90	91.37	91.37	91.37
Average	88.87	88.55	81.57	90.88	90.78	90.72

Table 26: Initial PSR Calculation for Northbound Asphalt Section

Mile Marker	Slow Lane Survey 1	Slow Lane Survey 2	Slow Lane Survey 3	Fast Lane Survey 1	Fast Lane Survey 2	Fast Lane Survey 3
9.1 - 9.2	85.35	79.01	78.30	99.97	99.97	98.06
9.4 - 9.5	99.97	66.68	64.99	99.97	59.39	59.39
10.4 - 10.5	90.78	76.32	68.41	98.06	89.62	69.75
10.8 - 10.9	95.57	65.40	57.88	98.69	60.94	62.13
11.4 - 11.5	99.97	98.06	92.55	98.04	94.33	89.03
11.7 - 11.8	98.06	90.20	92.55	96.19	82.44	79.32
12.2 - 12.3	93.15	91.37	91.37	94.96	93.15	89.62
Average	94.69	81.01	78.01	97.98	82.83	78.19

Table 27: Initial PSR Calculation for Northbound Concrete Section

Mile Marker	Slow Lane Survey 1	Slow Lane Survey 2	Slow Lane Survey 3	Fast Lane Survey 1	Fast Lane Survey 2	Fast Lane Survey 3
12.7 -12.6	81.06	76.76	76.76	91.37	79.10	79.10
13.3 -13.2	87.17	86.55	73.37	91.37	91.37	91.37
13.9 -13.8	87.84	87.84	87.84	69.75	69.75	69.75
14.5 -14.4	90.58	90.58	87.97	91.37	91.37	91.37
14.7 -14.6	99.97	99.97	83.33	83.50	83.50	83.50
15.3 -15.2	76.04	73.28	69.75	84.84	84.84	84.84
15.5 -15.4	84.27	84.27	84.27	91.37	91.37	91.37
16.1 -16.0	89.98	88.56	85.53	91.37	91.21	91.21
16.5 -16.4	91.37	90.51	78.51	91.37	91.37	91.37
Average	87.59	86.48	80.81	87.36	85.98	85.98

Table 28: Initial PSR Calculation for Southbound Asphalt Section

Mile Marker	Slow Lane Survey 1	Slow Lane Survey 2	Slow Lane Survey 3	Fast Lane Survey 1	Fast Lane Survey 2	Fast Lane Survey 3
9.3 - 9.2	53.93	51.10	47.67	90.08	75.73	62.29
9.5 - 9.4	62.29	53.59	51.56	59.55	55.69	55.69
10.5 - 10.4	79.32	75.83	75.83	91.60	81.59	81.59
10.9 - 10.8	77.70	77.30	75.83	86.67	81.59	77.01
11.5 - 11.4	81.38	80.34	80.34	85.13	78.81	78.81
11.8 - 11.7	81.41	76.45	75.67	92.25	88.64	83.34
12.35 - 12.25	77.30	74.19	73.81	83.29	75.34	73.81
Average	73.33	69.83	68.67	84.08	76.77	73.22

Table 29: Initial PSR Calculation for Southbound Concrete Section

5.1.2 Comparison and Correlation of PSR and PCI

The final version of the PSR calculation method was used to analyze the 77 asphalt and concrete surface distress scenarios. Figure 14 and Figure 15 present the comparisons. These plots are the end result of all included distresses and any changes to their definitions or weight factors. Both plots include a linear trendline, an equation for the trendline, an R^2 value, and a standard error of the data. Figure 16 contains all 77 scenarios as well as both trendlines plotted together. Figure 17 is the same graph as Figure 16, this time with a single trendline for all 77 data points. Individual asphalt and concrete data points still are represented by separate markers, but the trendline was generated by the combination of all points.

Figure 14: Final PCI vs. PSR Correlation for Asphalt Surfaces

Figure 15: Final PCI vs. PSR Correlation for Concrete Surfaces

Figure 16: Combination of PCI vs. PSR Correlations to Compare Asphalt and Concrete

Figure 17: Combined PCI vs. PSR Correlations for all Pavement Surfaces

5.1.3 Recommended PSR Procedure

A distress identification manual was developed for determining PSR. Previously, Section 490, Special Provision included a few distress definitions and severity identifications, but generally deferred definition to the LTPP Distress Identification Manual. Inconsistencies in definitions and severities existed between the two documents. The new identification manual is exclusive to the calculation of the WVDOH PSR. It includes a distress definition, severity level identification scheme, and method for determining extent for every distress necessary to calculate PSR. The manual is titled “WVDOH Distress Identification Manual (for PSR calculation)” and is included as Appendix A.

Figure 18 is a blank asphalt surface test segment PSR calculation sheet. It contains an input for test section length, which should be 528 for any warranty jobs, but can be changed in the event that a segment is not 1/10 mile so extents can be adjusted accordingly. Below that, a composite pavement identification input exists. A composite pavement is an asphalt overlay on an original concrete pavement. This has no effect on any calculation, but provides insight to anyone interpreting the distresses on diagrams or within the calculator.

Figure 19 is a blank concrete surface test segment PSR calculation sheet. It too contains an input for test section length for the same reason as the asphalt PSR calculator. Additionally an input for number of transverse joints within the test segment is included. This is used in conjunction with the Normalized Weight Factor Column. Any distresses dependent on the presence of a joint are normalized to a 35 joint per 1/10 miles basis. Previously, if a hypothetical concrete test section contained 80 foot slabs with six joints within a 1/10 mile section, one joint with low severity spalling would spike the extent calculation to 17%. Although technically in this situation 17% of the joints in that test section were experiencing low severity spalling, this would affect the TWD and PSR the same way five low severity spalls would affect a 30 slab test section. In reality, five low spalls would be far worse than one spall. So now applicable distress weight factors are multiplied by a ratio of number of slabs divided by 35, thus accounting for situations where there are non-uniform slab lengths, e.g. patched panels that create new joints within a section. This is actually an improvement on PCI's method which suggests only using test sections with 20 slabs to ensure the integrity of their deduct curves.

The weight factor is 0.0 for low severity transverse joint faults. This is because the definition for low severity faulting here is slightly more sensitive than that in the LTPP or PCI. The Special Provision warrant spec is to include a threshold for immediate corrective action for large amounts of faulting at any severity. For this reason, the low severity was left on the calculator spreadsheet to avoid changing the definition or removing a severity.

Compared to the 2012 PSR procedures, far more distresses on concrete segments are now measured by linear feet. This change accounts for non-uniform slab lengths. For most of these cases, the only difference is now instead of recording one slab affected by a distress, the length of the affected slab is recorded.

For both asphalt and concrete sections, the extent calculations are now based on the assumption that one transverse crack should affect a pavement the same amount that a distress at a joint of a concrete pavement would. Previously, extent was calculated by multiplying amount of transverse cracks by 2 to arrive at the extent percentage. This value is now 2.85 so that it too is normalized to a 35 joint per 1/10 mile basis ($2.85 * 35 = 100$). This means now a fault at a joint and a fault at a transverse crack in a concrete or asphalt surface pavement will have the same effect on PSR.

Asphalt Surface Segment PSR Calculator						
			Test Section Length (ft) =		528	
			Composite Pavement?		Y / N	
Distress	Severity	Weight Factor	Amount (#)	Length (ft)	Extent (%)	Weighted Distress
#1 Transverse Cracks	Low	0.020		-	0%	0.00
	Medium	0.110		-	0%	0.00
	High	0.200		-	0%	0.00
#2 Edge Cracking	Low	0.015	-		0%	0.00
	Medium	0.025	-		0%	0.00
	High	0.080	-		0%	0.00
#3 Alligator Cracking	Low	0.140	-		0%	0.00
	Medium	0.240	-		0%	0.00
	High	0.340	-		0%	0.00
#4 Block Cracking	Low	0.055	-		0%	0.00
	Medium	0.105	-		0%	0.00
	High	0.165	-		0%	0.00
#5 Longitudinal Cracking	Low	0.020	-		0%	0.00
	Medium	0.030	-		0%	0.00
	High	0.060	-		0%	0.00
#6 Longitudinal Joint Deterioration	Low	0.025	-		0%	0.00
	Medium	0.045	-		0%	0.00
	High	0.080	-		0%	0.00
#7 Lane Edge Cracking/ Deterioration	Low	0.010	-		0%	0.00
	Medium	0.020	-		0%	0.00
	High	0.040	-		0%	0.00
#8 Raveling/Weathering	-	0.040	-		0%	0.00
#9 Patching	-	0.030	-		0%	0.00
#10 Rutting	Low	0.065	-		0%	0.00
	High	0.150	-		0%	0.00
Segment TWD =					0.00	
Segment PSR =					100.0	

Figure 18: Blank Asphalt Surface Segment PSR Calculator

Concrete Surface Segment PSR Calculator							
				Test Section Length (ft) =		528	
				Joints in Segment (#) =		35	
Distress	Severity	Weight Factor	Amount/ Joints (#)	Length (ft)	Extent (%)	Normalized WF	Weighted Distress
#11 Transverse Cracks	Low	0.040		-	0%	0.040	0.00
	Medium	0.100		-	0%	0.100	0.00
	High	0.210		-	0%	0.210	0.00
#12 Transverse Joints Spalls	Low	0.020		-	0%	0.020	0.00
	Medium	0.075		-	0%	0.075	0.00
	High	0.150		-	0%	0.150	0.00
#13 Transverse Joint Faults	Low	0.000		-	0%	0.000	0.00
	Medium	0.110		-	0%	0.110	0.00
	High	0.210		-	0%	0.210	0.00
#14 Blowups	-	0.250		-	0%	0.250	0.00
#15 Longitudinal Cracking	Low	0.030	-		0%	0.030	0.00
	Medium	0.090	-		0%	0.090	0.00
	High	0.190	-		0%	0.190	0.00
#16 Longitudinal Joint Spalling	Low	0.020	-		0%	0.020	0.00
	Medium	0.060	-		0%	0.060	0.00
	High	0.150	-		0%	0.150	0.00
#17 Lane Edge Spalling	Low	0.010	-		0%	0.010	0.00
	Medium	0.050	-		0%	0.050	0.00
	High	0.150	-		0%	0.150	0.00
#18 D Cracking	-	0.100	-		0%	0.100	0.00
#19 Scaling	-	0.020	-		0%	0.020	0.00
#20 Patching	-	0.030	-		0%	0.030	0.00
#21 Popouts	-	0.035	-		0%	0.035	0.00
Segment TWD =						0.00	
Segment PSR =						100.0	

Figure 19: Blank Concrete Surface Segment PSR Calculator

5.1.4 US 35 PSR with Recommended Method

Table 30 and Table 31 contain a comprehensive summary of all final calculated PSR values for each of the five surveys at every test section observed. Figure 20 through Figure 35 graphically describe the data within these tables by analyzing the five surveys by lane, direction, and pavement type. For each combination of those three variables there is a figure which analyzes Pavement Age vs. PSR and a

figure which analyzes Mile Marker vs. PSR. Pavement Age vs. PSR plots the observed PSR values for all applicable test sections over the life of the pavement in months. Mile Marker vs. PSR plots observed PSR for each of the five surveys and is grouped by test section mile markers.

		Age (Months)	19	24	30	35	43
		Mile Marker	Survey 1	Survey 2	Survey 3	Survey 4	Survey 5
Concrete NB	Slow Lane	9.1 - 9.2 SL	97.94	95.74	95.74	95.47	95.23
		9.4 - 9.5 SL	99.97	97.68	97.68	97.18	96.44
		10.4 - 10.5 SL	99.34	98.48	97.95	97.04	94.22
		10.8 - 10.9 SL	99.96	98.14	97.13	96.88	95.65
		11.4 - 11.5 SL	99.97	99.71	99.46	97.37	97.37
		11.7 - 11.8 SL	99.97	99.94	99.94	99.67	99.67
		12.2 - 12.3 SL	99.33	99.33	99.32	99.01	98.73
	Fast Lane	9.1 - 9.2 FL	99.97	99.97	99.97	99.46	99.46
		9.4 - 9.5 FL	99.97	97.18	97.18	97.18	96.68
		10.4 - 10.5 FL	99.71	98.95	95.94	95.20	93.25
		10.8 - 10.9 FL	99.97	95.20	95.20	94.72	94.42
		11.4 - 11.5 FL	99.70	99.19	98.68	96.92	96.92
		11.7 - 11.8 FL	99.71	98.95	98.44	97.18	97.18
		12.2 - 12.3 FL	99.01	99.00	98.49	97.24	97.24
Concrete SB	Slow Lane	9.3 - 9.2 SL	94.23	94.23	93.75	93.75	93.27
		9.5 - 9.4 SL	96.18	94.94	94.46	91.82	91.59
		10.5 - 10.4 SL	99.71	99.71	99.71	97.68	97.68
		10.9 - 10.8 SL	99.44	99.44	98.93	95.92	95.92
		11.6 - 11.5 SL	99.87	99.87	99.87	97.82	97.82
		11.8 - 11.7 SL	99.61	99.37	99.37	99.33	99.33
		12.35 - 12.25 SL	99.66	99.65	99.65	99.65	99.65
	Fast Lane	9.3 - 9.2 FL	99.20	98.19	96.19	94.96	94.47
		9.5 - 9.4 FL	97.17	97.17	97.17	95.19	93.95
		10.5 - 10.4 FL	99.97	99.97	99.97	97.43	96.68
		10.9 - 10.8 FL	99.71	99.46	98.69	97.94	97.94
		11.6 - 11.5 FL	99.97	99.97	99.97	99.97	99.97
		11.8 - 11.7 FL	99.65	99.39	99.39	99.39	99.39
		12.35 - 12.25 FL	99.97	99.97	99.97	99.71	99.71
		PCC NB SL Avg	99.50	98.43	98.17	97.52	96.76
		PCC NB FL Avg	99.72	98.35	97.70	96.84	96.45
		PCC SB SL Avg	98.39	98.17	97.96	96.57	96.47
		PCC SB FL Avg	99.38	99.16	98.76	97.80	97.44
		PCC NB Avg	99.61	98.39	97.94	97.18	96.60
		PCC SB Avg	98.88	98.67	98.36	97.18	96.96
		PCC SL Avg	98.94	98.30	98.07	97.04	96.61
		PCC FL Avg	99.55	98.75	98.23	97.32	96.95
		PCC Avg	99.25	98.53	98.15	97.18	96.78

Table 30: Summary of US 35 Concrete Section PSR

		Age (Months)	19	24	30	35	43
		Mile Marker	Survey 1	Survey 2	Survey 3	Survey 4	Survey 5
Asphalt NB	Slow Lane	12.6 -12.7 SL	97.70	97.70	89.33	89.31	85.38
		13.2 -13.3 SL	97.86	98.05	93.46	91.41	91.41
		13.8 -13.9 SL	99.80	99.73	98.80	97.88	89.33
		14.4 -14.5 SL	98.81	98.81	96.00	96.00	95.25
		14.6 -14.7 SL	99.97	99.97	99.97	98.36	92.23
		15.2 -15.3 SL	98.51	98.30	91.53	86.24	86.24
		15.4 -15.5 SL	98.93	98.35	95.18	90.92	74.75
		16.0 -16.1 SL	98.89	97.86	95.86	95.50	83.66
		16.4 -16.5 SL	98.70	98.70	97.90	96.62	84.42
	Fast Lane	12.6 -12.7 FL	99.97	99.97	99.97	99.97	91.37
		13.2 -13.3 FL	99.97	99.97	99.97	99.97	92.33
		13.8 -13.9 FL	99.97	99.97	99.97	99.97	96.80
		14.4 -14.5 FL	99.97	99.97	99.97	99.97	99.97
		14.6 -14.7 FL	99.97	99.97	99.97	99.97	99.97
		15.2 -15.3 FL	99.97	99.97	99.97	99.97	88.58
		15.4 -15.5 FL	99.97	99.97	99.97	99.97	89.38
		16.0 -16.1 FL	99.97	99.97	99.97	99.97	88.82
		16.4 -16.5 FL	99.97	99.97	99.97	99.97	99.97
Asphalt SB	Slow Lane	12.7 -12.6 SL	98.00	98.00	98.00	93.59	88.42
		13.3 -13.2 SL	98.03	97.74	95.08	93.20	81.38
		13.9 -13.8 SL	99.29	99.29	98.34	92.37	90.19
		14.5 -14.4 SL	99.61	99.61	99.13	92.78	89.51
		14.7 -14.6 SL	99.97	99.97	98.08	94.91	94.91
		15.3 -15.2 SL	98.42	97.48	93.98	88.70	85.58
		15.5 -15.4 SL	98.63	98.63	98.63	96.36	85.80
		16.1 -16.0 SL	99.33	98.47	97.05	97.05	97.05
		16.5 -16.4 SL	99.97	99.27	93.68	93.68	89.47
	Fast Lane	12.7 -12.6 FL	99.97	97.60	97.60	97.60	97.60
		13.3 -13.2 FL	99.97	99.97	99.97	99.97	87.35
		13.9 -13.8 FL	95.57	95.57	95.57	95.57	83.50
		14.5 -14.4 FL	99.97	99.97	99.97	99.55	87.06
		14.7 -14.6 FL	99.97	99.97	99.97	99.97	99.97
		15.3 -15.2 FL	98.74	98.74	98.74	98.74	90.18
		15.5 -15.4 FL	99.97	99.97	99.97	99.97	95.33
		16.1 -16.0 FL	99.97	99.97	99.97	99.97	99.97
		16.5 -16.4 FL	99.97	99.97	99.97	99.97	99.97
		HMA NB SL Avg	98.80	98.61	95.34	93.58	86.96
		HMA NB FL Avg	99.97	99.97	99.97	99.97	94.13
		HMA SB SL Avg	99.03	98.72	96.89	93.63	89.15
		HMA SB FL Avg	99.35	99.08	99.08	99.03	93.44
		HMA NB Avg	99.38	99.29	97.65	96.78	90.55
		HMA SB Avg	99.19	98.90	97.98	96.33	91.29
		HMA SL Avg	98.91	98.66	96.11	93.61	88.06
		HMA FL Avg	99.66	99.53	99.53	99.50	93.78
		HMA Avg	99.29	99.09	97.82	96.55	90.92

Table 31: Summary of US 35 Asphalt Section PSR

Figure 20: US 35 Asphalt Northbound Slow Lane Pavement Age vs. PSR

Figure 21: US 35 Asphalt Northbound Slow Lane Mile Marker vs. PSR

Figure 22: US 35 Asphalt Northbound Fast Lane Pavement Age vs. PSR

Figure 23: US 35 Asphalt Northbound Fast Lane Mile Marker vs. PSR

Figure 24: US 35 Asphalt Southbound Slow Lane Pavement Age vs. PSR

Figure 25: US 35 Asphalt Southbound Slow Lane Mile Marker vs. PSR

Figure 26: US 35 Asphalt Southbound Fast Lane Pavement Age vs. PSR

Figure 27: US 35 Asphalt Southbound Fast Lane Mile Marker vs. PSR

Figure 28: US 35 Concrete Northbound Slow Lane Pavement Age vs. PSR

Figure 29: US 35 Concrete Northbound Slow Lane Mile Markers vs. PSR

Figure 30: US 35 Concrete Northbound Fast Lane Pavement Age vs. PSR

Figure 31: US 35 Concrete Northbound Fast Lane Mile Marker vs. PSR

Figure 32: US 35 Concrete Southbound Slow Lane Pavement Age vs. PSR

Figure 33: US 35 Concrete Southbound Slow Lane Mile Marker vs. PSR

Figure 34: US 35 Concrete Southbound Fast Lane Pavement Age vs. PSR

Figure 35: US 35 Concrete Southbound Fast Lane Mile Marker vs. PSR

5.1.5 US 35 PSR Final Calculation vs. Original 2012 Spec. Calculation

A comparison summary of PSR from survey 5 as calculated using the initial PSR calculation method and the final method is contained within Table 32 through Table 35 and Figure 36 through

Figure 43. “2012 PSR” refers to PSR calculated using the April 2012 version of “West Virginia Department of Transportation Division of Highways Special Provision, Section 490: Nine Year Pavement Performance Criteria”. “2015 PSR” refers to the final PSR calculation model described in the next section.

Mile Post	Slow Lane		Fast Lane	
	2012 Spec. PSR	2015 Spec. PSR	2012 Spec. PSR	2015 Spec. PSR
Average	67.3	87.0	87.4	94.1
12.6 -12.7	69.7	85.4	83.5	91.4
13.2 -13.3	79.2	91.4	90.9	92.3
13.8 -13.9	69.7	89.3	90.4	96.8
14.4 -14.5	69.7	95.3	91.4	100.0
14.6 -14.7	69.7	92.2	91.4	100.0
15.2 -15.3	69.7	86.2	83.2	88.6
15.4 -15.5	48.9	74.7	84.6	89.4
16.0 -16.1	59.0	83.7	80.0	88.8
16.4 -16.5	69.7	84.4	91.4	100.0

Table 32: Asphalt Northbound Survey 5 - 2012 Spec. vs 2015 Spec.

Mile Post	Slow Lane		Fast Lane	
	2012 Spec. PSR	2015 Spec. PSR	2012 Spec. PSR	2015 Spec. PSR
Average	69.78	89.1	78.04	93.4
12.7 -12.6	69.75	88.4	78.43	97.6
13.3 -13.2	55.77	81.4	45.95	87.3
13.9 -13.8	69.75	90.2	69.75	83.5
14.5 -14.4	69.99	89.5	82.09	87.1
14.7 -14.6	69.95	94.9	76.19	100.0
15.3 -15.2	67.18	85.6	78.98	90.2
15.5 -15.4	69.75	85.8	88.68	95.3
16.1 -16.0	85.53	97.1	90.90	100.0
16.5 -16.4	70.32	89.5	91.37	100.0

Table 33: Asphalt Southbound Survey 5 - 2012 Spec. vs 2015 Spec.

Figure 36: Asphalt Northbound Slow Lane Survey 5 – 2012 Spec. vs 2015 Spec.

Figure 37: Asphalt Northbound Fast Lane Survey 5 - 2012 Spec. vs 2015 Spec.

Figure 38: Asphalt Southbound Slow Lane Survey 5 - 2012 Spec. vs 2015 Spec.

Figure 39: Asphalt Southbound Fast Lane Survey 5 - 2012 Spec. vs 2015 Spec.

Mile Post	Slow Lane		Fast Lane	
	2012 Spec. PSR	2015 Spec. PSR	2012 Spec. PSR	2015 Spec. PSR
Average	79.23	96.76	84.50	96.45
9.1 - 9.2	79.32	95.23	94.96	99.46
9.4 - 9.5	75.53	96.44	80.14	96.68
10.4 - 10.5	65.74	94.22	77.10	93.25
10.8 - 10.9	64.74	95.65	75.34	94.42
11.4 - 11.5	84.37	97.37	86.33	96.92
11.7 - 11.8	96.19	99.67	87.91	97.18
12.2 - 12.3	88.70	98.73	89.74	97.24

Table 34: Concrete Northbound Survey 5 - 2012 Spec. vs 2015 Spec.

Mile Post	Slow Lane		Fast Lane	
	2012 Spec. PSR	2015 Spec. PSR	2012 Spec. PSR	2015 Spec. PSR
Average	82.67	96.47	89.85	97.44
9.3 - 9.2	71.20	93.27	83.72	94.47
9.5 - 9.4	75.73	91.59	77.90	93.95
10.5 - 10.4	70.47	97.68	87.91	96.68
10.9 - 10.8	85.02	95.92	91.84	97.94
11.5 - 11.4	89.91	97.82	97.68	99.97
11.8 - 11.7	92.71	99.33	96.62	99.39
12.35 - 12.25	93.63	99.65	93.27	99.71

Table 35: Concrete Southbound - Survey 5 - 2012 Spec. vs 2015 Spec.

Figure 40: Concrete Northbound Slow Lane Survey 5 - 2012 Spec. vs 2015 Spec.

Figure 41: Concrete Northbound Fast Lane Survey 5 - 2012 Spec. vs 2015 Spec.

Figure 42: Concrete Southbound Slow Lane Survey 5 - 2012 Spec. vs 2015 Spec.

Figure 43: Concrete Southbound Fast Lane Survey 5 - 2012 Spec. vs. 2015 Spec.

5.2 Comparison of ARAN and PSR Survey Surface Distress Data

The comparisons between indices provided and indices calculated for the first three surveys are shown in Figure 44 through Figure 49. Within the graph legends, “S.P.” stands for Special Provision which simply identifies the indices generated with the distress data manually collected for the calculation of Section 490, Special Provision PSR. “PMS data” is the index data provided by the previously mentioned ARAN, and dTIMS software. The “PMS data” were collected shortly after the second survey was completed.

SCI, ECI, NCI, and RDI comparisons were made for the northbound slow lane asphalt surface sections and JCI and CSI for northbound slow lane asphalt surface sections within US 35. The horizontal axis of each figure corresponds to the applicable test section stations for which comparisons could be made. A single index value is associated with each test section. The data points have been connected simply to make the identification of points easier as indices in many test sections overlap. It should not be assumed that index values between test sections are reflective of these lines.

Figure 44: Structural Cracking Index - Manual Survey Data vs. PMS Data Comparison

Figure 45: Environmental Cracking Index - Manual Survey Data vs. PMS Data Comparison

Figure 46: Net Cracking Index - Manual Survey Data vs. PMS Data Comparison

Figure 47: Rut Depth Index - Manual Survey Data vs. PMS Data Comparison

Figure 48: Joint Condition Index - Manual Survey Data vs. PMS Data Comparison

Figure 49: Concrete Slab Index - Manual Survey Data vs. PMS Data Comparison

5.3 Deflection Data Results and Summary

As was stated within Chapter 3 and Chapter 4, SN_{eff} was used for comparing analysis methods for asphalt pavements. After techniques were removed in which M_{R*} was used in calculations, the resulting final averaged asphalt SN_{eff} values are shown in Table 36 and Figure 50.

	SN_{eff} as a function of E_p as a function of M_R from a 3 layer MODULUS 6.1 backcalculation	SN_{eff} as a function of E_p from a 2 layer MODULUS 6.1 backcalculation	SN_{eff} as a function of E_p and M_R from a 2 layer MODULUS 6.1 backcalculation	SN_{eff} as provided by 3 layer MODTAG backcalculation	SN_{eff} as a function of E_p and M_R from a 3 layer MODTAG backcalculation	SN_{eff} as a function of E_p and M_R from a 3 layer BACKFAA backcalculation
Program	MODULUS 6.1	MODULUS 6.1	MODULUS 6.1	MODTAG	MODTAG	BACKFAA
Backcalc using:	3 Layer	2 Layer	2 Layer	3 Layer	3 Layer	3 Layer
E_p calculated with:	M_R	(E_p provided)	M_R	not calculated	M_R	M_R
NB HMA Avg SN_{eff}	4.65	5.30	4.71	4.31	4.90	5.25
SB HMA Avg SN_{eff}	4.19	4.76	4.24	4.56	4.42	4.53
All HMA Avg SN_{eff}	4.42	5.03	4.48	4.44	4.66	4.89

Table 36: Final Summary of Estimated Asphalt SN_{eff}

Figure 50: Asphalt SN_{eff} Comparison

One additional result which was observed pertained to the effect of temperature and temperature correction (or lack thereof). The BAKFAA backcalculation program included no input or correction for temperature so any effect of temperature on backcalculation should be most noticeable in this program. Figure 51 and Figure 52 show the resulting temperature vs. moduli graphs for surface and subgrade layers.

Figure 51: BAKFAA Temperature vs. Surface Modulus

Figure 52: BAKFAA Temperature vs. Subgrade Modulus

Table 37 shows all average subgrade moduli values backcalculated from asphalt and concrete deflection data. All three programs provided subgrade moduli values for the asphalt section tests. Due to the screening process and the limited number of eligible concrete tests only BAKFAA was able to perform backcalculations on the 34 concrete drops. Concrete section subgrade moduli backcalculated with BAKFAA were higher than asphalt section subgrade moduli from BAKFAA. Within the asphalt section, MODULUS 6.1 and MODTAG backcalculations produced subgrade moduli greater than BAKFAA in either section. All backcalculation programs determined that, on average, northbound subgrade moduli were greater than southbound subgrade moduli.

	Asphalt			Concrete
	MODULUS 6.1	MODTAG	BAKFAA	BAKFAA
North AVG	33.2	32.5	24.2	26.6
South AVG	30.7	25.7	23.6	25.0
AVG	32.0	29.1	23.9	25.8

Table 37: Asphalt and Concrete Average Subgrade Modulus Values

Chapter 6. Conclusions and Recommendations

6.1 Conclusions

6.1.1 Pavement Surface Rating

The initial and intermediate PSR calculations for US 35 are now obsolete and are only included to mark the progression of changes made. No conclusions about pavement performance or condition should be made based on 2012 PSR methodology.

Testing the accuracy of the surveyors was not within the scope of this research. It was the decision of WVDOH authorities to use the same survey form each time. Distresses recorded on previous surveys likely influenced subsequent survey recordings, but the integrity of the system was maintained. On a few occasions, distresses were noted and then either disappeared or decreased in extent or severity on a subsequent survey. This could be due to inaccurate judgments or measurements on either survey, erroneous documentation, or could be completely legitimate as some distresses such as cracks could increase or decrease in width with seasonal variability among other factors. In any case, analysis of distress was performed under the assumption that all distress surveys were accurate at the time of observance.

Figure 14, Figure 15, and Figure 17 indicate that there is a strong correlation between 2015 PSR and PCI. The comparison of trend lines and data points in Figure 16 verifies that the 2015 PSR method produces a distress based index that has a common scale for asphalt and concrete pavements. The linear relationship identified in Figure 17 can be used to adjust the thresholds for qualitative descriptors that are shown on Figure 7 as shown in Table 38 and Figure 53.

Qualitative Descriptor	PCI	PSR
Good	85 - 100	92 - 100
Satisfactory	70 - 85	80 - 92
Fair	55 - 70	68 - 80
Poor	40 - 55	56 - 68
Very Poor	25 - 40	44 - 56
Serious	10 - 25	34 - 44
Failed	0 - 10	0 - 34

Table 38: Comparison of PCI and 2015 PSR Ranges for Qualitative Descriptors

Figure 53: Graphical Comparison of PCI and 2015 PSR Ranges for Qualitative Descriptors

After the implementation of the proposed method for calculating PSR, a comparison of pavement types within US 35 was finally made. PSR was the only method of comparison used. Figure 54 shows the average asphalt and concrete PSR calculated for all test sections within US 35. This includes fast and slow lanes in northbound and southbound directions. The data shows that the condition of the asphalt and concrete was reasonably similar until the fifth survey where asphalt displayed a noticeably larger decrease in PSR than concrete. In the fifth survey, the average asphalt PSR is approximately 91 which is below the proposed Good/Satisfactory threshold discussed in the previous section. This threshold and the range for “Good” and “Satisfactory” are included in Figure 54 through Figure 58.

Figure 54: Average PSR Comparison: Asphalt vs. Concrete

Figure 55 and Figure 56 show fast lane and slow lane average PSR within the respective pavement type separately. For both pavement surface types, the slow lane was found to have a lower average PSR than the adjacent fast lane after each survey. However, there were instances of individual one-tenth mile test section fast lane average PSR values were found to be lower than the corresponding slow lane average PSR. The fact that slow lane PSR is on average consistently lower is to be expected due to the tendency of heavier and slower traffic in the lane. Interestingly, the difference between concrete fast and slow lane average PSR is much less drastic through all five surveys than in asphalt. The change in asphalt fast lane average PSR is unnoticeable through four surveys and displays a significant decrease at survey five.

Figure 57 and Figure 58 show asphalt and concrete average PSR as observed within the fast lane and slow lane separately. Interestingly, the fast lane asphalt average PSR is consistently higher than that of concrete for the first four surveys but falls below the fast lane average concrete PSR at survey five. Within both fast and slow lanes, concrete average PSR maintains relatively consistent decreases where asphalt average PSR drops most significantly (by numerical amount and percent change) between survey four and five. In Figure 54, we noted that the asphalt average PSR fell in the “Satisfactory” range. However, here, we notice that on average the fast lane asphalt PSR is within the “Good” range and the average slow lane average PSR is within the “Satisfactory” range.

Figure 55: Asphalt Average PSR Comparison: Fast Lane vs. Slow Lane

Figure 56: Concrete Average PSR Comparison: Fast Lane vs. Slow Lane

Figure 57: Fast Lane Average PSR Comparison: Asphalt vs. Concrete

Figure 58: Slow Lane Average PSR Comparison: Asphalt vs. Concrete

6.1.2 Comparison of ARAN and PSR Survey Surface Distress Data

The comparison of the PMS data to data surveyed manually was inconclusive. Because PMS data were generally used for network level analysis, it may have been too ambitious to apply it in this manner. The distress data provided by the PMS is obviously more simplified than the data collected with the intent of calculating PSR. The majority of sections are reported to have no distresses besides

roughness and minor rutting. In the case of CSI, ECI, and to some extent SCI, both data sets agree that there are no distresses within the section. In many instances where distress is observed in manual surveys, there are still none observed within the PMS data. Overall, there may not be enough distress on the road to really have a chance of making any comparison.

6.1.3 FWD Data Analysis

A large majority of data from the concrete section of this project was not useful because the importance of drop location on a slab was not fully understood. Although the primary use of an FWD on Jointed Plain Concrete Pavement, JPCP, is Joint Load Transfer, JLT; structural properties of pavement layers can be determined if proper drop locations are used. For the purpose of this project, it would have been necessary to perform all drops in the centers of each slab.

Within the relevant tests in the asphalt section, some evidence is available that FWD testing could provide information on pavement structural properties. The sets of SN_{eff} values generated with M_R were relatively consistent. The sets of SN_{eff} values generated with M_{R*} were also relatively consistent, however, the two sets differed significantly from each other. For this reason, it is impossible to call either set inaccurate. The set generated with M_R is more reasonable when considering the initial SN computed using the WVDOT Design Directive. Further investigation would be required to determine whether these computed M_R values are comparable to those which are generated through laboratory tests.

6.2 Recommendations

6.2.1 Pavement Surface Rating

If in the future, a more traditional and consistent range for PSR pavement condition qualitative descriptors is desired, a simple adjustment to the PSR equation could be made.

The consistency and accuracy of the distress observations made by surveyors across time should be evaluated. This will allow evaluation of the variance in PSR as a function of the quality of the surveys. The variability in PSR results should be considered when determining changes in PSR are due to changes in pavement distress or are the result of variance in the distress survey.

The procedure outlined within the “Final PSR Calculation Procedure” section of Chapter 5 should be adopted by the WVDOT and used within the newest version of the “Section 490: Nine Year Pavement

Performance Criteria.” This includes the addition of the “WVDOH Distress Identification Manual (for PSR calculation)” within Appendix A.

6.2.2 FWD Data and Analysis

In order to place more emphasis on FWD deflection data and the information provided by the analysis of such data, there should be more practice and organization in collecting data. The reasons for the challenges with the use of the backcalculation programs should be evaluated.

References

- AASHTO 1993. *AASHTO Guide for Design of Pavement Structures 1993*. Washington, DC: American Association of State Highway and Transportation Officials, 1993.
- Alavi, S., J.F. LeCates, and M.P. Tavares. *Falling Weight Deflectometer Usage*. Rep. no. NCHRP Synthesis 381. Washington, DC: TRB, 2008.
- AlNouri, I. *Effect of Temperature on the Elastic Response of Asphalt Treated Base Material*. Rep. no. R-816. Lansing, MI, 1972.
- ASTM D6433-11. *Standard Practice for Roads and Parking Lots Pavement Condition Index Surveys*. Vol. ASTM Standard D6433-11. West Conshohocken, PA, 2014.
- Clark, T. *Conversation about Application of FWD Data*. Telephone interview. Nov. 2014.
- Cornell University. *Digital image*. Cornell Local Roads Program. Cornell University, 2005
- Fugro Roadware Inc. *Fugro Roadware Inc*. Mississauga, ON, CA: Fugro Roadware, 2012.
- Gucunski, N., N. Vitillo, and S. Zaghloul. *Development of FWD Procedures Manual*. Rep. no. FHWA-NJ-2009-005. Piscataway, NJ: NJDOT, 2009.
- Killingsworth, B., and H. Von Quintus, *Backcalculation of Layer Moduli of LTPP General Pavement Study (GPS) Sites*. Rep. no. FHWA-RD-97-086. McLean, VA, 1997.
- Jackson, N. *Development of Revised Pavement Condition Indices for Portland Cement Concrete Pavement for the WSDOT Pavement Management System*. Rep. no. WA-RD 682.3. Seattle, WA, 2008.
- Lukanen, E.O., R. Stubstab, and R. Briggs. *Temperature Predictions and Adjustment Factors for Asphalt Pavements*. Rep. no. FHWA-RD-98-085. Mclean, VA: Federal Highway Administration, 2000.
- Lytton, R. L., and F. P. Germann. "General Procedure for Backcalculating Layer Moduli." Ed. A. J. Bush and G. Y. Baladi. *Nondestructive Testing of Pavements and Backcalculation of Moduli*. By J. Uzan. Philadelphia, PA: American Society for Testing and Materials, 1989.
- MnDOT, Office of Materials and Road Research Pavement Management Unit. *Mn/DOT Distress Identification Manual*. Maplewood, MN, 2003.
- Norouzi, M. *Performance Evaluation of Flexible Pavements in Alberta Using Falling Weight Deflectometer Data*. Thesis. University of Alberta, 2013. Ottawa, Canada: Library and Archives Canada, 2013.
- Pologruto, M. *Procedure for Use of Falling Weight Deflectometer to Determine AASHTO Layer Coefficients*. Rep. Vol. 1764. Washington, DC: Transportation Research Board, 2007.

- PCS/Law Engineering. *Layer Moduli Backcalculation procedure: Software Selection*. Rep. no. SHRP-P-651. Washington, DC: Transportation Research Board, 1993.
- Sami, N. *Composite Condition Index for West Virginia DOT: Final CCI Model*. IMS Infrastructure Management Services, 1997.
- Schmalzer, P. N. Long-Term Pavement Performance Program Manual for Falling Weight Deflectometer Measurements. Rep. no. FHWA-HRT-06-132. Vol. Version 4.1. McLean, VA: FHWA, 2006.
- Shahin, M. Y. *Pavement Management for Airports, Roads, and Parking Lots*. 2nd ed. Boston, MA: Springer, 2005.
- Section 490 Nine Year Pavement Performance Criteria, West Virginia Department of Transportation Division of Highways Special Provision. April 19, 2012.
- Shoukry, S., and G. William. Performance Evaluation of Backcalculation Algorithms Through Three-Dimensional Finite-Element Modeling of Pavement Structures. Rep. no. 99-1277. Washington, DC: Transportation Research Board, 1999.
- William, G., and S. Shoukry. *Mechanistic Evaluation of the Depth to Bedrock and Its Effect on the Response of 3D FE Pavement Models*. [Http://ascelibrary.org/doi/abs/10.1061/40509\(286\)5](http://ascelibrary.org/doi/abs/10.1061/40509(286)5). 1999.
- WVDOH. *Design Directives*. Charleston WV: WVDOT, 2006.

Appendix A. WVDOT Distress Identification Manual (for PSR calculation)

A.1 Asphalt Surfaces

These distress definitions, severity levels, and calculations are specific to asphalt surfaced roads manually surveyed for the calculation of PSR on 1/10th mile long test sections as part of WVDOT Special Provision Section 490: Nine Year Pavement Performance Criteria. This may also include composite pavements (concrete pavements with asphalt overlays).

A.1.1 Transverse Cracks – #1

Definition

Transverse cracks are any cracks within the travel lane predominantly perpendicular to the pavement centerline. This may include reflection cracking in composite pavements. In the case of full width patching that produces transverse construction joints, evaluate distresses in these joints as transverse cracks using the severity levels described in Longitudinal Joint Deterioration.

Severity Level Identification

Rate entire crack at highest level present for 10% or more of total crack length.

Low

- unsealed cracks 0 – ¼ inch wide, less than ¼ inch faulting, no blowups, no adjacent random cracking, and no loss of material
- sealed cracks with sealant material in good condition, no faulting, no blowups, no adjacent random cracking, and no loss of material

Medium

- any crack ¼ – ¾ inch wide, less than ¼ inch faulting, no blowups, no adjacent random cracking, and no loss of material
- any crack less than ¾ inch wide with adjacent low severity cracking, less than ¼ inch faulting, no blowups, and no loss of material

High

- any crack greater than ¾ inch wide
- any crack with adjacent medium or high severity random cracking
- any crack with greater than ¼ inch faulting
- any crack with a noticeable blowup
- any crack with noticeable loss of material

Extent Calculation

Percentage is calculated by multiplying amount of cracks at each distress level by 2.86. The sum of all three severities cannot exceed 100%. If this happens, disregard cracks of the lowest severity present until the sum of percentages equals 100%.

A.1.2 Edge Cracking – #2

Definition

Edge cracking refers to any crescent shaped or predominantly longitudinal cracks in the travel lane (including the paint stripe) that are within 2 feet of the pavements edge. This can occur only where there is an unpaved shoulder. Edge cracking may include longitudinal reflection cracking in composite pavements.

Severity Level Identification

Rate entire crack at highest level present for 10% or more of total crack length.

Low

- unsealed cracks 0 – ¼ inch wide and no loss of material
- sealed cracks with sealant material in good condition

Medium

- any crack ¼ – ¾ inch wide and no loss of material

High

- any crack greater than ¾ inch wide
- any crack with noticeable loss of material or loose pieces of pavement

Extent Calculation

For each severity, the total length of edge cracking measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected. In the unlikely event of a one lane road with unpaved shoulders on both sides of the travel lane surveyed, the calculation will remain the same however now there will be the potential for a maximum of 200%

A.1.3 Alligator Cracking – #3

Definition

Alligator cracking occurs only in areas subjected to repeated traffic loadings (wheelpaths). The exact location of the wheelpath is based on the inspector's judgment but will usually occur approximately 1.5 feet from paint stripes and extend about 2.5 feet from that point. Alligator cracks appear as interconnected cracks in early stages and may develop into many sided, sharp angled pieces, usually less than 1 foot in any dimension, characteristically with a chicken wire/alligator pattern. Meandering longitudinal cracking with adjacent random cracking can be considered alligator cracking if it is within the wheelpath. In this case it cannot also be counted as longitudinal cracking.

Severity Level Identification

Severity of alligator cracking can change between each linear foot of pavement. Rate cracks at highest level present for 10% or more within each linear foot where appropriate. If severity changes frequently, inspector's judgment should be applied.

Low

- an area with only a few connecting cracks and no noticeable loss of material

Medium

- an area of interconnecting cracks that forms a complete pattern but no considerable loss of material

High

- an area of interconnecting cracks with noticeable loss of material or loose pieces

Extent Calculation

For each severity, the total length of alligator cracking measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected. If alligator cracking is present in both wheelpaths, consider only the higher severity within each linear foot. For example, if a ten foot section of pavement exhibits low severity alligator cracking in the left wheelpath and high severity alligator cracking in the right wheelpath, only 10 feet of high severity alligator cracking should be recorded. If that same section exhibit low severity alligator cracking in both wheelpaths, only 10 feet of low severity alligator cracking should be recorded.

A.1.4 Block Cracking – #4**Definition**

Block cracking is a pattern of cracks that divides the pavement into approximately rectangular pieces greater than 1 foot and less than 10 feet in any dimension. This can occur anywhere within the lane. If a series of cracks is identified as block cracking, it should not also be counted as any other distress.

Severity Level Identification

Severity of block cracking can change between each linear foot of pavement. Rate cracks at highest level present for 10% or more of each section within the block cracking pattern. If severity changes frequently, inspector's judgment should be applied.

Low

- unsealed cracks 0 – ¼ inch wide, no adjacent random cracking, and no loss of material
- sealed cracks with sealant material in good condition

Medium

- any crack ¼ – ¾ inch wide, no adjacent random cracking, and no loss of material
- any crack less than ¾ inch wide with adjacent low severity cracking, and no loss of material

High

- any crack greater than ¾ inch wide
- any crack with adjacent medium or high severity random cracking
- any crack with noticeable loss of material

Extent Calculation

For each severity, the total length of block cracking measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected.

A.1.5 Longitudinal Cracking – #5

Definition

Longitudinal cracks are any cracks within the travel lane predominantly parallel with the pavement centerline. This may include reflection cracking in composite pavements. If a crack has been identified as longitudinal cracking, it should not be counted as any other distress.

Severity Level Identification

Severity of longitudinal cracking can change between each linear foot of pavement. Rate cracks at highest level present for 10% or more within each linear foot where appropriate. If severity changes frequently, inspector's judgment should be applied.

Low

- unsealed cracks 0 – ¼ inch wide, no adjacent random cracking, and no loss of material
- sealed cracks with sealant material in good condition, no adjacent random cracking, and no loss of material

Medium

- any crack ¼ – ¾ inch wide, no adjacent random cracking, and no loss of material
- any crack less than ¾ inch wide with adjacent low severity cracking, and no loss of material

High

- any crack greater than ¾ inch wide
- any crack with adjacent medium or high severity random cracking
- any crack with noticeable loss of material

Extent Calculation

For each severity, the total length of longitudinal cracking measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected. If multiple longitudinal cracks are present in any linear foot of the lane, record only the highest severity within each linear foot.

A.1.6 Longitudinal Joint Deterioration – #6

Definition

Longitudinal joint deterioration refers to any distresses affecting the deterioration of longitudinal construction joints found entirely within travel lanes. Any distress occurring exclusively within six inches of a longitudinal joint should be counted only as joint deterioration. Any longitudinal joint located within (or 6 inches from) the paint line separating a lane from a shoulder should be evaluated with the lane edge cracking distress. Otherwise count

deterioration in whichever lane the joint is located. If a longitudinal joint is found within the divider line between travel lanes, consider that joint a part of the slower (right) lane.

Severity Level Identification

Severity of longitudinal joint deterioration can change between each linear foot of pavement. Rate cracks at highest level present for 10% or more within each linear foot where appropriate. If severity changes frequently, inspector's judgment should be applied.

Low

- unsealed crack 0 – ¼ inch wide propagating from the joint into the pavement, no adjacent random cracking
- minor loss of material on either side of a construction joint and no adjacent random cracking within 6 inches of the joint
- any other low severity distress located within 6 inches of a joint

Medium

- a crack ¼ – ¾ inch wide propagating from the joint into the pavement, no adjacent random cracking
- a crack less than ¾ inch wide propagating from the joint into the pavement, adjacent random cracking less than ¼ inch wide
- minor loss of material on either side of a construction joint and adjacent random cracking less than ¼ inch wide
- any other medium severity distress located within 6 inches of a joint

High

- a crack greater than ¾ inch wide propagating from the joint into the pavement
- a crack propagating from the joint into the pavement with adjacent random cracking greater than ¼ inch wide
- major loss of material on either side of a construction joint
- minor loss of material on either side of a construction joint and adjacent random cracking greater than ¼ inch wide

Extent Calculation

For each severity, the total length of longitudinal joint deterioration measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected. In the unlikely event that multiple longitudinal joints are found within a single lane, percent affected could exceed 100%.

A.1.7 Lane Edge Cracking/Deterioration – #7

Definition

Lane edge cracking/deterioration refers longitudinal joint deterioration specifically between a travel lane and a paved shoulder. A paved shoulder here is defined by at least two feet of pavement past the paint stripe. Lane edge cracking/deteriorations includes any distress which occurs or stretches into the paint stripe or first 6 inches of lane. All definitions of longitudinal

joint deterioration apply no to this location. Additionally lane edge cracking will include cracking in the paint stripe which propagates into the pavement and is caused by the paint itself.

Severity Level Identification

Severity of lane edge cracking/deterioration can change between each linear foot of pavement. Rate cracks or deterioration at highest level present for 10% or more within each linear foot where appropriate. If severity changes frequently, inspector's judgment should be applied.

Low

- unsealed crack 0 – $\frac{1}{4}$ inch wide propagating from the paint into the pavement, no adjacent random cracking
- unsealed crack 0 – $\frac{1}{4}$ inch wide propagating from the joint into the pavement, no adjacent random cracking
- minor loss of material on either side of a construction joint and no adjacent random cracking within 6 inches of the joint
- any other low severity distress located within 6 inches of a joint

Medium

- a crack $\frac{1}{4}$ – $\frac{3}{4}$ inch wide propagating from the paint into the pavement, no adjacent random cracking
- a crack less than $\frac{3}{4}$ inch wide propagating from the paint into the pavement, adjacent random cracking less than $\frac{1}{4}$ inch wide
- a crack $\frac{1}{4}$ – $\frac{3}{4}$ inch wide propagating from the joint into the pavement, no adjacent random cracking
- a crack less than $\frac{3}{4}$ inch wide propagating from the joint into the pavement, adjacent random cracking less than $\frac{1}{4}$ inch wide
- minor loss of material on either side of a construction joint and adjacent random cracking less than $\frac{1}{4}$ inch wide
- any other medium severity distress located within 6 inches of a joint

High

- a crack greater than $\frac{3}{4}$ inch wide propagating from the paint into the pavement
- a crack propagating from the paint into the pavement with adjacent random cracking greater than $\frac{1}{4}$ inch wide
- a crack greater than $\frac{3}{4}$ inch wide propagating from the joint into the pavement
- a crack propagating from the joint into the pavement with adjacent random cracking greater than $\frac{1}{4}$ inch wide
- major loss of material on either side of a construction joint
- minor loss of material on either side of a construction joint and adjacent random cracking greater than $\frac{1}{4}$ inch wide

Extent Calculation

For each severity, the total length of lane edge cracking/deterioration measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected.

A.1.8 Raveling/Weathering – #8

Definition

Raveling and weathering refer to the wearing of pavement surface characterized by the dislodging of aggregate particles and loss of asphalt binder. It may range from loss of fines and binder between coarse aggregate to very rough and pitted surface with obvious loose aggregate.

Severity Level Identification

No severity levels

Extent Calculation

Raveling/weathering is recorded in linear feet. If any of the pavement within a linear foot of the lane appears to be raveled/weathered then it should be recorded. The total length of raveling/weathering measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected.

A.1.9 Patching – #9

Definition

Patching refers to any portion of pavement surface that has been replaced or added to after the original construction. This should include full depth repairs. All other distresses found within the patch should still be recorded.

Severity Level Identification

No severity levels

Extent Calculation

Patching of any type, width, depth, etc. within the lane is recorded in linear feet. The total length of patching measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected.

A.1.10 Rutting – #10

Definition

Rutting refers to pavement surface depression due to repeated loading, within the wheelpath, and occurring in the longitudinal direction.

Severity Level Identification

Rutting severity is based on the average rut depth of 5 measurements in each wheelpath. These measurements should be taken approximately at the 64th, 164th, 264th, 364th, and 464th foot of the test section. These rut measurements will be taken using a 5 foot long straight edge, placed perpendicular to the pavement centerline. Rut depth is measured at the point of greatest distance from the bottom of the straightedge to the pavement surface. Measurements must be

accurate to the closest 1/16th inch. If the average rut depth for the five measurements in either wheelpath rut depth qualify for a severity, then that entire test section is recorded at that severity. Also if both wheelpaths qualify, the higher severity should be recorded.

Low

- average rut depth ¼ – ½ inch

High

- average rut depth greater than ½ inch

Extent Calculation

If the average rut depth qualifies for a severity, then 100% of that section is recorded at that severity.

A.2 Concrete Surfaces

These distress definitions, severity levels, and calculations are specific to all concrete surfaced roads manually surveyed for the calculation of PSR on 1/10th mile long test sections as part of WVDOT Division of Highways Special Provision Section 490: Nine Year Pavement Performance Criteria. This may include jointed reinforced concrete pavements, jointed plain concrete pavements, and continuously reinforced concrete pavements. Surveys on pavements with concrete surfaces require an input for number of joints within the 1/10th mile segment as some extent calculations are dependent on this.

A.2.1 Transverse Cracks – #11

Definition

Transverse cracks are cracks predominantly perpendicular to the pavement centerline and propagate through the width of the slab. This may count a linear crack that separates a corner of a slab. This is sometimes referred to as a corner break but should be recorded as a transverse crack if it is predominantly perpendicular to the pavement centerline.

Severity Level Identification

Rate entire crack at highest level present for 10% or more of total crack length.

Low

- unsealed cracks 0 – 1/8 inch wide, no faulting, no spalling
- sealed cracks with sealant material in good condition, no faulting, no spalling

Medium

- any crack 1/8 – ¼ inch wide, no faulting, no spalling
- any crack less than ¼ inch wide with faulting up to ¼ inch
- any crack less than ¼ inch wide with spalling up to 3 inches wide
- any crack that would otherwise be considered Low Severity but is accompanied by additional Low Severity cracks that fragment the slab

High

- any crack greater than ¼ inch wide
- any crack with greater than ¼ inch faulting
- any crack with greater than 3 inch wide spalling
- any crack that would otherwise be considered Medium Severity but is accompanied by additional Low or Medium Severity cracks that fragment the slab

Extent Calculation

Percentage is calculated by multiplying amount of cracks at each distress level by 2.86. The sum of all three severities cannot exceed 100%. If this happens, disregard cracks of the lowest severity present until the sum of percentages equals 100%.

A.2.2 Transverse Joint Spalls – #12

Definition

Transverse joint spalling refers to cracking, breaking, chipping, or fraying of slab edges at transverse joints. Spalling includes any cracking within 1 foot of the face of the joint. Spalling is counted on a per joint basis so it does not matter if the spalling occurs on the leave or approach slab. Spall width is based on the distance from the face of the joint to the end of displaced material on either side of the joint. If no material is displaced but cracking is still present, the spall width is zero but it is still considered spalled.

Severity Level Identification

Rate a joints spalling as the highest severity present for at least 10% of the joint length. Spalling is recorded on a per joint basis so the entire joint is considered spalled at that severity.

Low

- spall widths up to 2 inches
- joints with low severity cracking in crescent shaped patterns or parallel to the joint within 1 foot of the joint

Medium

- spall widths 2 – 4 inches

High

- spall widths greater than 4 inches

Extent Calculation

Record the number of transverse joints with spalling at each severity level. Divide the amount of affected joints at each severity level by the total number of joints in the segment. Multiply by 100 to determine the percentage of segment affected.

A.2.3 Transverse Joint Faults – #13

Definition

Transverse joint faulting refers to the difference in elevation across a transverse joint. This can be an increase or decrease in elevation from the leave to the approach slab. It is recorded on a per joint basis.

Severity Level Identification

Rate a joints faulting as the highest severity present for at least 10% of the joint length. Faulting is recorded on a per joint basis so the entire joint is considered faulted at that severity.

Low

- measurable faulting to a maximum of 1/8 inch

Medium

- faulting greater than 1/8th inch but less than ½ inch

High

- faulting ½ inch or greater

Extent Calculation

Record the number of transverse joints with faulting at each severity level. Divide the amount of affected joints at each severity level by the total number of joints in the segment. Multiply by 100 to determine the percentage of segment affected.

A.2.4 Blowups – #14

Definition

Blowups refer to localized upward movement of pavement surface at transverse joints, possible accompanied by shattering of concrete in the area on either side of the joint. Blowups can occur mid-slab at a transverse crack but these should will not be counted in this distress. If a joint is experiencing a blowup, there is no need to also record faulting or spalling at that joint

Severity Level Identification

No severity levels

Extent Calculation

Record the number of transverse joints with a blowup. Divide the amount of affected joints at by the total number of joints in the segment. Multiply by 100 to determine the percentage of segment affected.

A.2.5 Longitudinal Cracking – #15

Definition

Longitudinal cracks are cracks predominantly parallel to the pavement centerline and propagate through the length of the slab. This may count a linear crack that separates a corner of a slab. This is sometimes referred to as a corner break but should be recorded as a longitudinal crack if it is predominantly parallel to the pavement centerline.

Severity Level Identification

Rate the entire crack within a single slab at the highest level present for 10% or more of total crack length. Longitudinal cracks are recorded on a linear foot basis so if multiple longitudinal cracks are present on a single slab, record it as a single crack and increase the severity.

Low

- unsealed cracks 0 – 1/8 inch wide, no faulting, no spalling
- sealed cracks with sealant material in good condition, no faulting, no spalling

Medium

- any crack 1/8 – ¼ inch wide, no faulting, no spalling
- any crack less than ¼ inch wide with faulting up to ¼ inch
- any crack less than ¼ inch wide with spalling up to 3 inches wide
- any crack that would otherwise be considered Low Severity but is accompanied by additional Low Severity cracks that fragment the slab

High

- any crack greater than ¼ inch wide
- any crack with greater than ¼ inch faulting
- any crack with greater than 3 inch wide spalling
- any crack that would otherwise be considered Medium Severity but is accompanied by additional Low or Medium Severity cracks that fragment the slab

Extent Calculation

For each severity, the total length of longitudinal cracking measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected.

A.2.6 Longitudinal Joint Spalling – #16

Definition

Longitudinal joint spalling refers to any cracking, breaking, chipping, or fraying of slab edges at longitudinal construction joints found entirely within travel lanes. Spalling includes any cracking within 1 foot of the face of the joint. Any longitudinal joint located within (or 1 foot from) the paint line separating a lane from a shoulder should be evaluated with the lane edge spalling distress. Otherwise count spalling in whichever lane the joint is located. If a longitudinal joint is found within the divider line between travel lanes, consider that joint a part of the slower (right) lane. Spalling is counted as a distress to the joint so it does not matter which side of the joint

experiences spalling. Spall width is based on the distance from the face of the joint to the end of displaced material on either side of the joint. If no material is displaced but cracking is still present, the spall width is zero but it is still considered spalled.

Severity Level Identification

Severity of longitudinal joint spalling can change between each linear foot of pavement. Rate spalls at highest level present for 10% or more within each linear foot where appropriate. If severity changes frequently, inspector's judgment should be applied.

Low

- spall widths up to 2 inches
- joints with low severity cracking in crescent shaped patterns or parallel to the joint within 1 foot of the joint

Medium

- spall widths 2 – 4 inches

High

- spall widths greater than 4 inches

Extent Calculation

For each severity, the total length of longitudinal joint spalling measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected. If multiple longitudinal joints are found within a single lane, percent affected could exceed 100%. This is relevant when slab widths are smaller than lane widths.

A.2.7 Lane Edge Spalling – #17

Definition

Lane edge spalling refers longitudinal joint spalling specifically between a travel lane and a shoulder. This includes both paved and unpaved shoulders. Spall width is based on the distance from the face of the joint to the end of displaced material on either side of the joint. If no material is displaced but cracking is still present, the spall width is zero but it is still considered spalled. In the case of unpaved shoulders, where there is technically no joint, spalling still can be experienced on the edge of the slab.

Severity Level Identification

Severity of lane edge spalling can change between each linear foot of pavement. Rate spalls at highest level present for 10% or more within each linear foot where appropriate. If severity changes frequently, inspector's judgment should be applied.

Low

- spall widths up to 3 inches
- joints with low severity cracking in crescent shaped patterns or parallel to the joint within 1 foot of the joint

Medium

- spall widths 3 – 6 inches

High

- spall widths greater than 6 inches

Extent Calculation

For each severity, the total length of lane edge spalling measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected. In the unlikely event of a one lane road with shoulders (paved or unpaved) on either side, lane edge spalling could be present on both sides, therefore, percent affected could exceed 100%.

A.2.8 D Cracking – #18

Definition

D cracking, sometimes known as durability cracking, refers to closely spaced hairline cracking crescent shaped patterns that follow the edge of a slab near all joints. This is a very distinct distress that is usually caused by un-ideal properties of aggregate in concrete. It can increase in severity to entire slabs showing this patterned crack with significant loss of material across the surface. It is not to be confused with spalling which generally leads to loss of material specifically at the joint, or scaling which is usually a more random cracking pattern in the surface of the concrete.

Severity Level Identification

No severity levels

Extent Calculation

The total length of D cracking measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected.

A.2.9 Scaling – #19

Definition

Scaling, also known as map cracking, refers to a series of interconnected cracks in the surface of concrete. This can range in severity from noticeable interconnected hairline cracks, to sections with significant loss of material across the surface. Generally, scaling will not result in displaced material deeper than ½ inch from the original pavement surface.

Severity Level Identification

No severity levels

Extent Calculation

The total length of scaling measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected.

A.2.10 Patching – #20

Definition

Patching refers to any portion of pavement surface that has been replaced or added to after the original construction. Full depth, full width repairs will not be considered patches. However, it should be noted that full depth repairs could change the amount of joints and slabs within test sections for future surveys. All other distresses found within the patch should still be recorded.

Severity Level Identification

No severity levels

Extent Calculation

Patching of any type, width, depth, etc. within the lane is recorded in linear feet. The total length of patching measured in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected.

A.2.11 Popouts – #21

Definition

Popouts are small pieces of pavement broken loose from the surface, normally ranging in diameter from 1 – 4 inches and depth from ½ - 2 inches.

Severity Level Identification

No severity levels

Extent Calculation

Sections of pavement with, on average, more than 3 popouts per square yard should be recorded as experiencing excessive popouts. This is not to say that one square yard with 3 popouts must be noted, but rather take note if significant sections of pavement or entire slabs appear to exceed this average popout density. This will require the inspector's judgment. Popouts are measured on a linear foot basis, so record the length of sections, or the length of slabs exhibiting excessive popouts. The total length in linear feet will be divided by 528 and then multiplied by 100 to determine the percent of test section affected.

Appendix B. Deduct Curve Comparison

The comparison of deduct curves for each severity of every distress which led to the final weight factors within the respective PSR calculation model is included here. The final weight factor for each severity of every distress as well as the rationale for it is noted. Within each figure's legend, "ASTM Deduct Value" refers to the deduct values read directly from the curves within PCI's ASTM. "PSR Deduct Value" refers to the adaption of weight factors to deduct curve by applying the array of extents to the isolated distress and calculating TWD as in PSR's calculation model.

Deduct Curve Ratio (DCR) will be used exclusively here as a quick description of the theoretical difference between curves in PCI and PSR for asphalt surface distresses. It is defined as the ratio of PCI to PSR deduct value at any given extent percentage. This is necessitated by the difference in recording extent in either method. For instance, a 528 foot long longitudinal crack would be recorded as having an extent of 8.33% in PCI (for a 12 foot wide lane) and 100% in PSR. In this case, a DCR of approximately 12:1 would be justifiable. Additionally this difference is the reason many PCI Deduct curves do not exist beyond 20-30%. By definition, some distresses within PCI are impossible to exist on 100% of the pavement surface. PSR uses an extent calculation system which could be more closely defined as the percent of area exhibiting distress symptoms of all the area that could be affected by that distress. After comparing definitions of severity levels this was usually the first modification made to the PSR deduct curves. It is impossible to perfectly match curves based on DCR alone because often the curves will have a different curvature so this was used as a tool to establish an approximate theoretical match. This was not a factor within concrete surface distresses as those are calculated for PCI on a joint or slab basis.

After this, a reduction of PSR curves was usually made as PCI includes a built in correction within its procedure where PSR does not. This again was an approximation because the PCI deduct correction is dependent on the total amount of distress in a section. From experience, in normal situations where 2 or 3 different distresses are recorded, this correction may reduce the deduct value to about 70-80% of the original. As distresses mount, the reduction factor is increased to the point where the final deduct value could be 40% of the original value if 7 or 8 different distresses are recorded. For most distresses, the PSR deduct curve was reduced to about 60% of the curve set by DCR. Without a dynamic correction factor, PSR when compared to PCI could theoretically be underestimating pavement distress in situations where few are present and overestimate when many are present. For the purpose of maintaining simplicity this was deemed acceptable as a starting point for comparisons.

In a few situations slight changes in distress definitions and naming necessitated the modifications of curves where intuition and experience would be required to establish reasoning. Also, in a few select cases senior engineer judgment and input was factored. A few requests were made based on the preferences of the DOH office to slightly increase or reduce weight factors to address their own concerns.

PSR final weight factors are listed from Low to High in the first bullet of each distress for as many weight factors defined for each distress. This is followed by brief descriptions to the reasoning for any or all modifications. Then last, the deduct comparison curves used are included.

B.1 Deduct Comparison for Asphalt Surfaces

Transverse Cracks:

- 0.020, 0.110, 0.200
- Severity definitions are similar with the exception of crack width thresholds which are more lenient within the PCI definition, especially at High Severity.
- Initial DCR of approximately 3:1
- Additional decrease to Low Severity because perceived distress is minimal at this level.
- Inclusion of Faulting and especially the potential for Blowups within composite pavements resulted in the increase of Medium and High Severity curves.

Figure 59: Transverse Cracks Low Severity Deduct Curve Comparison

Figure 60: Transverse Cracks Medium Severity Deduct Curve Comparison

Figure 61: Transverse Cracks High Severity Deduct Curve Comparison

Edge Cracking

- 0.015, 0.025, 0.080
- Severity definitions match closely.
- Initial DCR of 12:1

Figure 62: Edge Cracking Low Severity Deduct Curve Comparison

Figure 63: Edge Cracking Medium Severity Deduct Curve Comparison

Figure 64: Edge Cracking High Severity Deduct Curve Comparison

Alligator Cracking

- 0.014, 0.024, 0.034
- Severity definitions closely match.
- Initial DCR of approximately 2:1
- At high extents this ratio is surpassed and deemed acceptable due to the extreme nature of perceived distress associated with Alligator Cracking.

Figure 65: Alligator Cracking Low Severity Deduct Curve Comparison

Figure 66: Alligator Cracking Medium Severity Deduct Curve Comparison

Figure 67: Alligator Cracking High Severity Deduct Curve Comparison

Block Cracking

- 0.055, 0.105, 0.165
- Severity definitions are similar with the exception of crack width thresholds which are more lenient within the PCI definition, especially at High Severity. This necessitated a slight lowering of curves, especially in Medium and High Severity.
- Initial DCR of 1:1

- A slight increase in all curves was also factored because several other distresses are included in Block Cracking and cannot be recorded if Block Cracking exists.

Figure 68: Block Cracking Low Severity Deduct Curve Comparison

Figure 69: Block Cracking Medium Severity Deduct Curve Comparison

Figure 70: Block Cracking High Severity Deduct Curve Comparison

Longitudinal Cracking

- 0.020, 0.030, 0.060
- Severity definitions are similar with the exception of crack width thresholds which are more lenient within the PCI definition, especially at High Severity. This necessitates a lowering of Medium and High Severity Curves
- Initial DCR of approximately 12:1

Figure 71: Longitudinal Cracking Low Severity Deduct Curve Comparison

Figure 72: Longitudinal Cracking Medium Severity Deduct Curve Comparison

Figure 73: Longitudinal Cracking High Severity Deduct Curve Comparison

Longitudinal Joint Deterioration

- 0.025, 0.045, 0.080
- For PCI, Longitudinal Joint Deterioration would be contained within the definitions of Longitudinal Cracking and Raveling to some degree.
- Weight factors are based on Longitudinal Cracking with a minor increase due to the nature of a paving joints, their susceptibility to deterioration, and potential affect on multiple lanes.

Lane Edge Cracking/Deterioration

- 0.010, 0.020, 0.040
- For PCI, Lane Edge Cracking/Deterioration would be contained within the definitions of Longitudinal Cracking and Raveling to some degree.
- Weight factors are based on Longitudinal Cracking with a minor decrease this time due to the fact that Lane Edges are driven across far less often than cracking present within or between travel lanes.

Raveling/Weathering

- 0.040
- PCI includes Weathering at Low, Medium, and High Severities. PSR Raveling/Weathering matches the definition of Medium Severity Weathering most closely so this was the comparison made.
- Initial DCR of 1:1
- The curve was decreased because Weathering generally occurs in older pavements and is accompanied by other distresses.

Figure 74: Raveling/Weathering Deduct Curve Comparison

Patching

- 0.030
- PSR definition matches PCI Low Severity Patching definition so it was used for comparison. PCI also includes Medium and High Severity Patching which are related to distress found within patching. PSR allows for the recording of distresses within patching so this would be redundant.
- Initial DCR of 1:1
- Curve was reduced because well maintained Patching should have a minimal effect on perceived distress. Additionally, distresses within Patches are already counted separately.

Figure 75: Patching Deduct Curve Comparison

Rutting

- 0.065, 0.150
- PCI includes Low, Medium, and High Severities. PSR Low and High Severity definitions closely match PCI Low and Medium Severities respectively so these were used for comparison.
- Rutting is either recorded as 0 or 100 percent in PSR so those points are the only that matter when matching curves.
- Initial DCR of 2:1
- At high extents of High Severity Rutting this ratio is surpassed and deemed acceptable due to the extreme nature of perceived distress associated with Rutting.

Figure 76: Rutting Low Severity Deduct Curve Comparison

Figure 77: Rutting High Severity Deduct Curve Comparison

B.2 Deduct Comparison for Concrete Surfaces

Transverse Cracks

- 0.040, 0.100, 0.210
- PSR Transverse Cracks were compared to PCI Linear Cracking. Definitions are generally similar in crack identification.

- Large reduction was made because PCI combines Transverse and Longitudinal Cracking in Linear Cracking.
- PCI counts Linear Cracking extent on an affected slab basis which through experience severely overestimates distress associated with Transverse Cracks on relatively long slabs which necessitated the separation.
- Due to a change in PSR Transverse Crack extent calculation which was consistent with asphalt surface pavements, a significant increase was necessitated.

Figure 78: Transverse Cracks Low Severity Deduct Curve Comparison

Figure 79: Transverse Cracks Medium Severity Deduct Curve Comparison

Figure 80: Transverse Cracks High Severity Deduct Curve Comparison

Transverse Joint Spalls

- 0.020, 0.075, 0.150
- Transverse Joint Spalls closely match the definition for PCI Joint Spalls so these curves were used for comparison.
- Slight Reduction made to all Severity Transverse Joint Spalls because Transverse and Longitudinal Spalling are separated now. This was a small reduction because from experience most spalling will occur in transverse joints.
- At the request of WVDOH, Low and Medium Severity were increased to the initial curve location because from experience, small spalls in transverse joints deteriorate quickly toward High Severity. When compared to PCI this could mean that PSR will slightly overestimate distress associated with Low or Medium Transverse Joint Spalls but in this case it is necessary as an indicator of imminent future distress.

Figure 81: Transverse Joint Spalls Low Severity Deduct Curve Comparison

Figure 82: Transverse Joint Spalls Medium Severity Deduct Curve Comparison

Figure 83: Transverse Joint Spalls High Severity Deduct Curve Comparison

Transverse Joint Faults

- 0.000, 0.110, 0.210
- PSR Transverse Joint Faults generally matches the PCI Faulting definitions so this was the comparison made.
- The Low Severity Faulting weight factor was reduced to zero at the request of WVDOH because the minimum threshold for recording a Fault was so small that a severe overestimation of distress appeared to be made on test sections with large amounts of nearly insignificant faults present. These faults are still recorded for warranty purposes.

Figure 84: Faulting Low Severity Deduct Curve Comparison

Figure 85: Faulting Medium Severity Deduct Curve Comparison

Figure 86: Faulting High Severity Deduct Curve Comparison

Blowups

- 0.250
- PSR Blowups definition most closely matched PCI Medium Severity Blowups so this was the comparison made.
- Because Blowups recorded in PSR are counted at this weight factor, when compared to distress associated with PCI defined Blowups, PSR will overestimate small Blowups and underestimate large Blowups. To maintain simplicity, this was deemed acceptable for PCI defined Low Severity

Blowups based on the extreme nature of perceived distress associated with Blowups. PCI High Severity Blowups are so devastating that this difference was of little effect.

Figure 87: Blowups Deduct Curve Comparison

Longitudinal Cracking

- 0.030, 0.090, 0.190
- PSR Longitudinal Cracking was compared to PCI Linear Cracking. Definitions are generally similar in crack identification.
- Large reduction was made because PCI combines Transverse and Longitudinal Cracking in Linear Cracking.
- PCI counts Linear Cracking extent on an affected slab basis which through experience severely overestimates distress associated with Longitudinal Cracks which affect less than a full slab length on relatively long slabs which necessitated the separation.
- Due to a change in PSR Longitudinal Crack extent calculation which was consistent with asphalt surface pavements, a significant increase was necessitated.

Figure 88: Longitudinal Cracking Low Severity Deduct Curve Comparison

Figure 89: Longitudinal Cracking Medium Severity Deduct Curve Comparison

Figure 90: Longitudinal Cracking High Severity Deduct Curve Comparison

Longitudinal Joint Spalling

- 0.020, 0.060, 0.150
- Longitudinal Joint Spalling is based on PCI Joint Spalling where severity definitions generally match.
- The graphs of the PCI Deduct Curves are from Transverse Joint Spalling Deduct Curve Comparisons.
- A small reduction to Medium Severity was made because joints between travel lanes are driven across far less than transverse joints.
- No reduction was made to Low Severity because the deduct value is so insignificant that a proportional reduction was not noticeable.
- No reduction was made to High Severity because of the potential for loss of material included within the definition which could affect perceived distress in the travel lane.

Lane Edge Spalling

- 0.010, 0.050, 0.150
- Lane Edge Spalling is based on PCI Joint Spalling where severity definitions generally match.
- The graphs of the PCI Deduct Curves are from Transverse Joint Spalling Deduct Curve Comparisons.
- An additional reduction to Low and Medium Severity curves was made due to the fact that Lane Edges are driven across far less often than cracking present within or between travel lanes.
- This reduction was not made for High Severity because the definition includes the potential for loss of material into the lane that could affect perceived distress in the travel lane.

D-Cracking

- 0.100
- PSR D-Cracking definition most closely matched PCI Medium Severity D-Cracking so this was the comparison made.
- Because D-Cracking recorded in PSR are counted at this weight factor, when compared to distress associated with PCI defined D-Cracking, PSR will overestimate Low D-Cracking and underestimate High D-Cracking. To maintain simplicity, this was deemed acceptable for PCI defined Low Severity D-Cracking based on the extreme nature of perceived distress associated with D-Cracking. PCI High Severity D-Cracking is devastating enough that this difference was of little effect.

Figure 91: D-Cracking Deduct Curve Comparison

Scaling

- .020
- PCI defines Low, Medium, and High Severity Scaling. PSR minimum definition of Scaling most closely matches PCI Low Severity Scaling so this was used for comparison.
- Little reduction was made to the curve to account for the potential of a surface with no other distresses where no correction factor would be used in PCI.
- Without Medium and High Severity Scaling the potential for Scaling exceeding the Low Severity threshold necessitated no additional reduction of the curve.

Figure 92: Scaling Deduct Curve Comparison

Patching

- 0.030
- PSR definition matches PCI Low Severity Patching definition so it was used for comparison. PCI also includes a High Severity Patching which is related to distress found within patching. PSR allows for the recording of distresses within patching so this would be redundant.
- Curve was reduced because well maintained Patching should have a minimal effect on perceived distress. Additionally, distresses within Patches are counted separately.

Figure 93: Patching Deduct Curve Comparison

Popouts

- 0.035
- Definition matches.
- At the request of the WVDOH, no reduction was made to the curve. This is to account for the potential of a road with no distress other than excessive popouts which would require no correction factor in PCI.

Figure 94: Popouts Deduct Curve Comparison

Appendix C. FWD text files

C.1 US 35 All Northbound Drops .FWD (.R80) File Format

```
R80    20140709route35n36F20
70    18002-146 80355 00 60 .
150   0 203 305 457 610 9141219 5.91 0.00 12.01 17.99 24.02 35.98 47.99 60.00
C:\Users\dynfieldid\Document.FWD
us 35
S
S
99076 86231-01 49859 85536
7.920.0 3.510.0 3.030.0 3.010.0
Ld 0202 0.997 88.1 .
D1 2241 0.999 1.003 .
D2 2242 0.999 1.031 .
D3 2243 0.997 1.018 .
D4 2244 0.998 0.993 .
D5 2245 0.994 0.986 .
D6 2246 0.998 0.985 .
D7 2247 0.999 0.984 .
D0 2248 0.997 1.035 .
D0 2249 0.995 1.000 .
D* NO 1.000 1.000 .
Administrator
11 5 1110 1 1 .
5 2.0 2 0.0
*mason co
DtCty PxNnnnS 000+0.0 000+0.0 St
Cty P Nnnn
000+0.0 000+0.0 St ...
300 0 0 0 0 0 0 0 11.81 0.00 0.00 0.00 0.00 0.00 0.00
36 432 1882 19578
ABCD111222333444.....
ABCD111222333444.....
.
.... ***** .....
.
.

Dynatest
*mason co
S 85536 29 26 50914 83 79
412 66 70 65 58 52 43 37 6540 4.03 2.54 2.30 2.06 1.69 1.46 1.22
414 66 70 65 59 52 43 38 6584 4.13 2.55 2.31 2.05 1.71 1.51 1.25
410 67 71 65 59 53 43 38 6518 4.07 2.55 2.31 2.07 1.69 1.48 1.24
576 95 100 92 84 74 57 46 9158 5.44 3.62 3.30 2.92 2.25 1.83 1.64
574 94 99 92 84 74 57 46 9114 5.38 3.62 3.29 2.91 2.24 1.80 1.65
```

577 94 99 92 84 74 57 47 9169 5.43 3.61 3.29 2.91 2.24 1.85 1.70
787 130 137 128 116 103 80 60 12510 7.45 5.03 4.56 4.04 3.15 2.37 1.83
799 131 138 128 117 104 81 61 12696 7.48 5.05 4.59 4.08 3.18 2.40 1.82
792 131 137 127 116 103 80 60 12576 7.43 5.00 4.56 4.06 3.15 2.37 1.80
1038 174 182 169 153 137 106 81 16497 10.00 6.65 6.04 5.39 4.19 3.17 2.31
1033 174 182 168 153 136 106 80 16410 9.91 6.63 6.02 5.37 4.17 3.16 2.31
970 174 183 169 153 137 106 81 15413 9.90 6.65 6.04 5.40 4.19 3.17 2.33
S 85013 29 26 50916 84 78
401 76 81 75 66 57 46 39 6375 5.73 2.96 2.59 2.26 1.83 1.54 1.24
402 75 81 74 65 57 45 39 6386 5.35 2.93 2.56 2.24 1.78 1.54 1.20
403 76 81 75 66 57 45 39 6397 5.41 2.94 2.59 2.26 1.76 1.52 1.23
573 109 117 108 96 84 62 45 9103 6.23 4.25 3.78 3.30 2.44 1.78 1.58
576 110 117 108 96 84 62 44 9147 6.25 4.26 3.78 3.31 2.44 1.75 1.58
575 110 117 108 96 84 62 46 9136 6.26 4.27 3.78 3.30 2.44 1.81 1.63
776 152 162 150 134 117 87 63 12324 8.62 5.90 5.26 4.61 3.43 2.49 1.82
784 152 163 150 134 117 88 63 12455 8.66 5.91 5.28 4.61 3.45 2.49 1.78
778 152 163 149 133 117 87 63 12357 8.67 5.88 5.25 4.59 3.43 2.48 1.80
1036 205 216 199 178 156 117 85 16454 11.42 7.85 6.99 6.14 4.61 3.35 2.34
997 205 216 199 178 156 117 85 15840 11.39 7.85 6.99 6.14 4.61 3.35 2.34
983 204 217 200 178 156 118 85 15621 11.28 7.87 7.00 6.15 4.64 3.36 2.36
S 83450 29 26 50920 85 79
399 59 62 56 49 44 41 36 6343 7.87 2.20 1.93 1.75 1.63 1.43 1.05
397 58 61 55 49 44 41 34 6310 7.63 2.18 1.92 1.73 1.62 1.33 1.08
401 60 61 56 48 43 40 36 6365 8.47 2.19 1.88 1.70 1.59 1.42 1.02
570 84 87 79 70 62 49 43 9048 6.06 3.11 2.74 2.44 1.94 1.71 1.57
573 85 87 79 70 62 49 45 9103 5.80 3.11 2.74 2.43 1.94 1.78 1.54
572 84 87 79 69 61 47 43 9092 5.85 3.10 2.72 2.42 1.87 1.68 1.41
777 115 121 110 98 87 67 52 12346 7.15 4.34 3.87 3.41 2.65 2.03 1.77
770 115 121 110 98 87 68 51 12236 7.11 4.35 3.85 3.43 2.67 2.02 1.72
781 115 121 110 98 87 68 51 12411 7.17 4.34 3.87 3.44 2.66 2.02 1.73
1029 153 161 147 131 116 91 69 16344 10.04 5.78 5.17 4.58 3.57 2.72 1.99
1018 153 160 147 131 116 90 69 16169 9.91 5.77 5.15 4.57 3.56 2.71 1.99
1006 153 161 147 131 117 91 69 15982 9.83 5.78 5.17 4.59 3.57 2.70 1.99
S 82928 29 26 50922 85 80
394 48 49 47 45 44 38 33 6255 4.33 1.85 1.78 1.73 1.50 1.30 0.78
399 48 49 47 45 43 38 33 6343 4.20 1.84 1.76 1.70 1.48 1.28 0.74
399 50 49 47 45 44 39 33 6332 4.13 1.87 1.79 1.74 1.52 1.29 0.80
569 67 71 66 58 53 47 44 9037 4.08 2.58 2.30 2.10 1.87 1.73 1.40
570 68 71 66 58 53 47 44 9059 4.01 2.60 2.30 2.07 1.87 1.72 1.43
571 68 71 66 58 52 47 43 9070 4.06 2.59 2.30 2.04 1.84 1.68 1.39
776 93 98 90 80 70 53 48 12324 5.41 3.56 3.16 2.76 2.07 1.89 1.69
779 94 99 91 81 71 53 48 12378 5.37 3.59 3.18 2.78 2.10 1.88 1.68
769 94 99 91 81 71 53 49 12225 5.40 3.59 3.19 2.80 2.10 1.91 1.72
987 127 133 122 108 95 72 54 15687 7.42 4.80 4.26 3.74 2.83 2.13 1.84
978 126 133 122 108 95 72 54 15533 7.42 4.79 4.27 3.74 2.84 2.12 1.83
1017 126 132 121 108 95 72 54 16158 7.41 4.78 4.26 3.74 2.83 2.12 1.83
S 80325 30 27 50927 86 81
388 80 86 76 66 55 45 41 6156 5.76 2.99 2.58 2.18 1.79 1.61 1.31

390 79 85 75 65 55 44 39 6189 5.77 2.97 2.56 2.17 1.74 1.54 1.22
 388 79 84 75 65 54 44 40 6156 5.74 2.95 2.54 2.13 1.75 1.57 1.23
 561 113 122 108 94 81 59 54 8917 6.79 4.26 3.71 3.18 2.33 2.14 1.93
 563 113 121 108 94 80 59 53 8950 6.76 4.24 3.70 3.16 2.31 2.07 1.86
 563 113 121 107 93 80 58 55 8950 6.77 4.22 3.67 3.14 2.30 2.15 1.92
 772 156 168 150 132 114 84 62 12269 9.77 5.92 5.18 4.47 3.32 2.45 2.32
 765 156 168 151 132 114 85 64 12148 9.78 5.93 5.19 4.48 3.34 2.52 2.36
 772 156 168 150 132 114 85 62 12269 9.76 5.92 5.19 4.49 3.33 2.43 2.30
 960 209 224 201 177 153 114 83 15249 12.72 7.92 6.96 6.03 4.50 3.26 2.66
 984 210 225 202 177 154 115 83 15632 12.71 7.94 6.98 6.06 4.51 3.26 2.61
 960 210 225 202 177 154 115 83 15249 12.69 7.94 6.98 6.06 4.52 3.26 2.62
 S 79797 30 27 50930 86 81
 377 61 68 58 50 46 42 36 5992 5.31 2.29 1.96 1.80 1.66 1.40 1.18
 370 60 66 58 49 44 41 35 5883 5.15 2.27 1.94 1.74 1.61 1.39 1.13
 379 60 66 58 49 45 40 36 6014 5.30 2.27 1.94 1.78 1.59 1.41 1.17
 550 88 97 85 74 64 56 50 8731 5.93 3.35 2.90 2.50 2.22 1.98 1.71
 550 87 97 86 74 64 57 51 8742 5.93 3.37 2.90 2.50 2.25 2.01 1.73
 552 87 96 84 73 63 55 49 8774 5.87 3.31 2.88 2.47 2.17 1.93 1.70
 763 123 136 119 104 90 66 60 12127 8.42 4.70 4.09 3.53 2.61 2.35 2.19
 764 123 135 119 104 89 66 59 12137 8.45 4.70 4.08 3.52 2.59 2.33 2.13
 754 123 135 119 104 90 67 61 11984 8.40 4.69 4.08 3.53 2.64 2.39 2.16
 959 167 181 161 140 121 90 69 15238 10.71 6.34 5.53 4.78 3.53 2.72 2.53
 989 168 182 161 140 122 90 68 15709 10.73 6.35 5.52 4.79 3.55 2.68 2.52
 987 168 182 161 141 122 90 68 15687 10.69 6.35 5.54 4.80 3.56 2.67 2.56
 S 79263 30 27 50933 85 81
 382 72 78 70 62 53 43 34 6069 6.16 2.76 2.43 2.09 1.69 1.35 1.23
 383 72 77 69 61 53 43 36 6091 6.39 2.73 2.39 2.08 1.68 1.43 1.27
 383 71 77 69 61 53 42 35 6080 6.40 2.70 2.39 2.07 1.66 1.38 1.22
 553 101 110 99 88 76 57 48 8785 6.01 3.91 3.45 3.00 2.24 1.89 1.71
 550 101 109 99 87 75 57 51 8731 5.81 3.89 3.42 2.97 2.25 2.00 1.74
 555 101 110 100 88 76 58 50 8818 5.94 3.92 3.47 3.01 2.28 1.97 1.74
 760 137 149 135 119 104 80 63 12072 7.81 5.30 4.69 4.10 3.14 2.49 2.09
 754 137 150 135 120 105 80 62 11984 7.65 5.32 4.72 4.12 3.15 2.46 2.13
 759 137 149 135 119 104 80 62 12061 7.80 5.31 4.69 4.11 3.14 2.46 2.11
 965 181 196 177 158 138 106 82 15325 10.10 6.98 6.21 5.43 4.17 3.21 2.39
 981 182 196 177 158 138 106 81 15588 10.33 6.98 6.21 5.44 4.17 3.19 2.41
 1000 183 197 178 158 138 106 82 15884 10.31 6.99 6.21 5.44 4.18 3.22 2.41
 S 78735 31 27 50935 88 81
 379 77 82 76 68 61 49 42 6025 4.64 3.00 2.69 2.41 1.92 1.64 1.46
 379 77 82 75 68 61 49 41 6025 4.61 2.97 2.68 2.42 1.93 1.63 1.44
 380 77 81 75 67 61 49 40 6036 4.59 2.94 2.65 2.39 1.91 1.59 1.41
 547 112 118 110 99 90 72 57 8687 5.61 4.33 3.91 3.53 2.82 2.23 1.93
 547 112 118 110 99 90 72 57 8687 5.56 4.33 3.91 3.53 2.83 2.24 1.96
 547 112 117 109 99 89 71 57 8698 5.47 4.30 3.89 3.50 2.80 2.23 1.92
 756 155 163 153 139 125 101 80 12017 7.73 6.02 5.46 4.93 3.97 3.15 2.46
 744 155 164 153 139 125 101 80 11820 7.75 6.02 5.46 4.94 3.98 3.15 2.48
 754 156 164 153 139 126 102 80 11973 7.79 6.03 5.48 4.95 4.00 3.16 2.47
 992 208 217 203 185 167 135 107 15752 10.20 8.01 7.28 6.59 5.32 4.21 3.31

970 208 218 204 185 168 135 107 15413 10.24 8.03 7.30 6.60 5.33 4.23 3.32
 994 208 218 204 186 168 136 108 15796 10.25 8.04 7.32 6.61 5.35 4.24 3.31
 S 76074 30 27 50939 86 81
 387 71 76 71 65 56 47 44 6145 4.64 2.81 2.55 2.22 1.84 1.74 1.61
 393 72 76 72 65 57 46 46 6244 4.49 2.82 2.55 2.24 1.82 1.81 1.65
 392 72 76 71 65 57 47 45 6233 4.47 2.81 2.55 2.24 1.84 1.78 1.62
 566 105 111 104 95 83 70 55 8994 5.90 4.11 3.75 3.28 2.77 2.15 1.94
 563 107 110 104 95 83 71 56 8950 5.92 4.08 3.73 3.25 2.78 2.21 2.00
 561 108 110 104 94 82 71 56 8906 5.90 4.09 3.72 3.22 2.81 2.19 2.01
 761 148 155 146 134 117 99 77 12094 7.71 5.76 5.26 4.59 3.89 3.02 2.31
 765 147 155 146 133 116 99 77 12159 7.67 5.73 5.24 4.58 3.89 3.04 2.34
 764 148 156 146 134 118 99 77 12137 7.69 5.75 5.26 4.65 3.88 3.02 2.30
 998 200 210 197 180 161 134 104 15851 10.57 7.74 7.10 6.35 5.29 4.09 3.13
 981 200 210 197 180 162 134 105 15588 10.63 7.74 7.10 6.36 5.28 4.12 3.14
 1005 201 210 197 181 162 134 105 15972 10.63 7.74 7.11 6.39 5.28 4.12 3.15
 S 75552 30 27 50941 86 81
 392 53 57 51 47 45 41 36 6233 4.45 2.02 1.84 1.79 1.62 1.40 1.11
 392 54 57 51 47 45 41 37 6233 4.19 2.01 1.85 1.79 1.61 1.44 1.15
 394 56 56 51 46 45 41 38 6266 4.40 1.99 1.82 1.78 1.61 1.48 1.15
 565 81 80 72 62 55 51 49 8983 5.50 2.85 2.46 2.16 2.00 1.91 1.56
 564 78 82 73 64 58 52 48 8961 5.56 2.89 2.52 2.29 2.06 1.88 1.63
 563 79 81 73 63 56 50 46 8939 5.31 2.87 2.48 2.22 1.97 1.83 1.58
 765 108 111 101 88 76 57 53 12148 6.23 3.96 3.45 2.99 2.25 2.08 1.90
 760 106 111 101 88 76 57 52 12072 6.21 3.96 3.45 2.99 2.25 2.05 1.90
 763 108 111 101 88 76 57 52 12116 6.24 3.98 3.45 2.98 2.25 2.05 1.89
 991 144 148 134 117 101 76 56 15741 8.71 5.29 4.60 3.99 3.00 2.21 2.10
 942 144 148 134 117 101 76 57 14964 8.67 5.28 4.59 3.98 3.01 2.24 2.10
 980 144 148 134 117 102 76 57 15577 8.70 5.29 4.60 4.00 3.01 2.24 2.12
 S 75024 32 27 50944 89 81
 388 63 69 62 56 49 44 38 6167 3.54 2.46 2.19 1.91 1.74 1.49 1.17
 392 63 69 63 56 49 44 39 6233 3.57 2.48 2.19 1.91 1.73 1.52 1.19
 393 63 69 63 56 49 44 38 6244 3.49 2.49 2.20 1.93 1.74 1.51 1.19
 565 92 99 91 81 71 53 45 8983 5.16 3.59 3.19 2.81 2.09 1.78 1.56
 565 92 99 91 81 71 53 45 8972 5.17 3.58 3.19 2.81 2.10 1.76 1.55
 564 92 99 91 81 71 53 45 8961 5.17 3.58 3.19 2.80 2.09 1.78 1.55
 772 128 138 127 113 100 75 54 12269 6.69 5.00 4.44 3.93 2.96 2.13 1.71
 772 129 138 127 113 100 75 54 12269 6.65 5.00 4.44 3.93 2.96 2.13 1.68
 769 129 138 127 113 100 75 54 12225 6.63 4.99 4.44 3.93 2.97 2.13 1.70
 994 173 185 171 153 135 102 74 15796 9.09 6.72 6.02 5.31 4.03 2.91 2.00
 958 173 185 171 153 135 102 74 15227 9.09 6.73 6.01 5.31 4.03 2.91 2.00
 936 174 185 171 153 135 103 74 14876 9.11 6.74 6.02 5.31 4.04 2.91 2.01
 S 74496 32 27 50946 89 81
 382 60 63 57 49 46 40 35 6069 5.68 2.24 1.94 1.82 1.59 1.39 0.99
 388 62 65 58 50 47 41 36 6167 6.65 2.29 1.98 1.84 1.61 1.43 1.02
 388 62 65 58 50 47 41 36 6167 6.52 2.28 1.98 1.85 1.62 1.40 1.02
 556 87 94 84 72 62 49 44 8829 5.80 3.31 2.85 2.44 1.93 1.75 1.51
 554 88 93 84 73 62 49 44 8807 5.74 3.31 2.86 2.44 1.94 1.74 1.46
 558 88 94 85 73 62 50 43 8862 5.62 3.33 2.87 2.44 1.95 1.71 1.45

758 122 130 118 103 87 62 47 12039 7.94 4.64 4.05 3.43 2.45 1.87 1.71
759 122 130 118 102 87 62 47 12061 8.01 4.63 4.02 3.43 2.44 1.87 1.70
760 123 130 117 102 87 62 48 12072 8.05 4.62 4.02 3.44 2.43 1.88 1.72
985 166 176 159 139 118 85 58 15643 10.83 6.27 5.49 4.66 3.33 2.29 1.81
987 166 176 160 139 118 85 58 15676 10.82 6.28 5.47 4.65 3.34 2.30 1.83
1005 167 176 159 139 118 85 58 15972 10.81 6.27 5.46 4.66 3.34 2.29 1.81
S 73392 32 27 50953 90 81
382 58 60 55 48 43 38 33 6069 4.54 2.15 1.89 1.71 1.48 1.30 0.83
384 58 61 55 48 43 39 33 6102 4.43 2.17 1.90 1.71 1.55 1.28 0.81
383 57 60 55 48 44 39 33 6080 4.38 2.16 1.89 1.74 1.55 1.31 0.85
551 83 88 80 70 60 43 43 8753 6.17 3.15 2.77 2.37 1.71 1.70 1.39
550 83 88 80 71 60 44 43 8731 6.16 3.15 2.78 2.38 1.72 1.68 1.37
550 83 88 80 71 60 46 43 8731 6.09 3.16 2.78 2.38 1.80 1.70 1.41
752 117 123 113 99 85 61 48 11951 7.93 4.44 3.91 3.36 2.41 1.88 1.67
749 116 123 113 99 85 61 47 11907 7.94 4.43 3.90 3.35 2.42 1.85 1.67
749 117 123 113 99 85 61 46 11896 8.02 4.43 3.90 3.35 2.40 1.81 1.61
960 159 168 154 135 117 84 58 15260 10.62 6.05 5.33 4.59 3.31 2.27 1.95
947 159 168 153 135 117 84 58 15040 10.56 6.04 5.33 4.59 3.31 2.27 1.94
985 159 168 153 135 117 84 58 15654 10.52 6.04 5.32 4.59 3.30 2.27 1.91
S 72832 33 27 50956 91 81
376 58 62 56 49 45 40 36 5981 4.26 2.21 1.94 1.76 1.57 1.40 0.97
372 57 62 57 50 46 41 36 5915 4.38 2.24 1.98 1.81 1.61 1.41 1.00
381 59 62 56 50 45 39 34 6047 4.38 2.22 1.96 1.76 1.53 1.35 0.94
546 84 89 82 72 62 49 45 8676 5.31 3.21 2.82 2.44 1.94 1.76 1.49
550 83 89 82 72 62 49 45 8731 5.26 3.22 2.83 2.44 1.94 1.78 1.50
548 84 89 82 72 63 50 46 8709 5.24 3.22 2.83 2.47 1.96 1.81 1.53
757 115 123 113 100 86 64 52 12028 7.12 4.46 3.93 3.39 2.53 2.05 1.83
755 115 123 113 100 86 65 52 11995 7.08 4.45 3.94 3.39 2.54 2.03 1.85
758 115 123 113 100 86 64 52 12039 7.09 4.46 3.94 3.38 2.53 2.06 1.84
995 154 164 150 132 115 86 63 15807 9.70 5.91 5.21 4.53 3.37 2.47 1.99
978 155 164 150 132 115 86 62 15533 9.67 5.91 5.21 4.54 3.38 2.46 1.97
1002 154 164 150 133 115 86 63 15917 9.61 5.92 5.22 4.54 3.38 2.47 1.97
S 70229 33 27 51000 92 81
376 67 71 65 59 53 44 40 5981 4.85 2.57 2.34 2.07 1.73 1.59 1.31
376 66 70 65 59 52 44 40 5981 4.82 2.57 2.33 2.06 1.74 1.58 1.31
376 66 70 65 59 53 42 40 5981 4.80 2.57 2.33 2.07 1.67 1.56 1.30
545 99 103 97 87 78 59 48 8654 7.27 3.81 3.43 3.06 2.34 1.89 1.68
545 99 104 97 87 78 60 48 8654 7.22 3.82 3.44 3.06 2.35 1.89 1.67
545 99 104 98 88 78 60 48 8665 7.27 3.84 3.47 3.08 2.36 1.89 1.67
752 138 145 136 123 110 85 64 11940 9.03 5.34 4.86 4.33 3.34 2.51 1.98
745 138 146 136 124 110 85 64 11842 8.95 5.36 4.87 4.34 3.34 2.51 2.02
748 138 145 136 124 110 85 64 11886 8.93 5.35 4.87 4.34 3.34 2.51 2.01
907 189 197 185 168 150 117 87 14416 12.59 7.29 6.63 5.91 4.59 3.44 2.52
903 189 198 185 169 150 117 88 14339 12.46 7.30 6.64 5.92 4.60 3.45 2.53
932 189 198 185 168 150 116 87 14799 12.34 7.28 6.63 5.92 4.57 3.44 2.52
S 69696 33 27 51003 92 81
371 60 63 59 53 48 46 38 5893 4.43 2.31 2.08 1.89 1.80 1.50 1.24
373 60 63 59 53 47 44 37 5926 4.31 2.31 2.08 1.86 1.74 1.47 1.20

374 60 63 59 53 48 45 38 5948 4.26 2.31 2.09 1.89 1.77 1.51 1.20
 549 87 91 85 77 69 57 50 8720 5.60 3.36 3.04 2.73 2.26 1.98 1.81
 547 86 91 85 77 69 57 50 8687 5.51 3.36 3.05 2.73 2.23 1.98 1.81
 548 87 92 86 78 70 59 53 8709 5.54 3.39 3.07 2.76 2.34 2.09 1.86
 752 123 128 119 108 97 76 59 11940 7.47 4.69 4.26 3.82 2.98 2.32 2.12
 755 122 128 119 108 97 75 60 11995 7.43 4.69 4.24 3.81 2.97 2.37 2.19
 750 122 127 119 108 97 75 60 11918 7.41 4.69 4.25 3.80 2.97 2.35 2.17
 984 163 171 160 145 130 101 76 15632 9.96 6.30 5.70 5.10 3.97 3.01 2.50
 944 163 170 160 144 129 101 76 14997 9.91 6.28 5.68 5.09 3.96 3.00 2.58
 987 163 170 160 145 129 101 76 15687 9.90 6.29 5.69 5.09 3.96 3.00 2.50
 S 67088 33 28 51008 91 82
 383 72 75 70 62 55 42 37 6080 5.09 2.76 2.46 2.18 1.64 1.44 1.22
 384 73 75 70 63 55 43 37 6102 5.10 2.76 2.47 2.17 1.68 1.46 1.28
 383 73 75 70 63 55 41 37 6091 5.15 2.76 2.48 2.17 1.60 1.46 1.26
 553 103 108 101 91 79 60 46 8785 5.50 3.97 3.57 3.11 2.35 1.80 1.59
 554 105 108 101 91 80 60 46 8807 5.47 3.98 3.58 3.14 2.36 1.81 1.59
 552 104 109 102 91 80 60 48 8764 5.48 4.00 3.59 3.15 2.37 1.89 1.65
 759 144 151 141 126 111 85 63 12061 8.26 5.55 4.98 4.37 3.33 2.48 1.97
 749 143 150 140 126 110 84 62 11896 8.27 5.51 4.95 4.35 3.30 2.46 1.96
 751 144 150 141 126 110 84 63 11929 8.29 5.54 4.97 4.35 3.31 2.48 1.93
 985 193 201 188 169 148 113 84 15643 10.61 7.40 6.67 5.83 4.43 3.31 2.43
 920 193 201 188 169 148 113 85 14613 10.59 7.40 6.67 5.83 4.43 3.33 2.43
 886 192 201 188 169 148 113 84 14076 10.58 7.40 6.66 5.84 4.43 3.30 2.44
 S 66560 32 27 51011 90 80
 374 69 74 67 58 51 44 39 5948 4.91 2.65 2.30 2.00 1.73 1.55 1.41
 376 69 74 67 58 49 44 39 5981 4.76 2.63 2.27 1.93 1.72 1.55 1.36
 379 68 74 66 57 50 44 40 6025 4.70 2.60 2.26 1.95 1.72 1.56 1.34
 544 102 109 99 87 75 56 48 8643 6.43 3.91 3.41 2.96 2.19 1.89 1.69
 543 102 109 99 87 75 55 48 8632 6.44 3.89 3.41 2.97 2.18 1.89 1.70
 545 102 109 99 87 76 55 47 8654 6.43 3.89 3.41 3.00 2.18 1.87 1.74
 754 143 155 141 125 109 82 59 11973 8.81 5.54 4.91 4.30 3.21 2.33 2.03
 752 144 155 141 125 109 82 59 11940 8.82 5.55 4.91 4.31 3.21 2.32 2.05
 747 144 155 141 125 110 82 59 11864 8.81 5.56 4.92 4.33 3.21 2.33 2.05
 969 198 210 191 170 150 112 82 15391 12.15 7.53 6.69 5.89 4.42 3.23 2.32
 980 198 210 192 170 151 113 82 15566 12.12 7.54 6.71 5.93 4.43 3.24 2.35
 911 198 210 191 170 150 112 82 14471 12.04 7.53 6.69 5.91 4.42 3.23 2.35
 S 65261 30 26 51017 87 79
 380 60 53 50 49 47 46 41 6036 2.57 1.98 1.93 1.86 1.83 1.63 1.54
 376 64 60 58 55 54 50 44 5981 2.73 2.29 2.15 2.13 1.98 1.72 1.57
 378 60 52 50 48 46 44 42 6003 2.56 1.96 1.88 1.80 1.75 1.64 1.49
 548 86 75 71 66 60 58 56 8709 3.09 2.80 2.60 2.38 2.29 2.20 1.98
 548 86 75 70 65 61 59 58 8709 3.06 2.76 2.57 2.39 2.33 2.27 2.00
 545 86 74 69 65 61 56 56 8665 3.13 2.73 2.54 2.42 2.21 2.20 1.92
 756 120 101 94 87 85 68 64 12017 4.33 3.70 3.44 3.34 2.68 2.53 2.26
 756 118 103 98 90 83 70 63 12006 4.33 3.85 3.56 3.28 2.76 2.48 2.34
 747 118 103 98 90 83 70 64 11864 4.32 3.85 3.56 3.26 2.75 2.52 2.37
 978 161 137 128 119 113 92 79 15544 5.82 5.02 4.68 4.44 3.63 3.10 2.60
 949 161 138 130 121 111 93 78 15084 5.82 5.13 4.76 4.37 3.68 3.06 2.65

966 161 138 130 121 112 93 78 15347 5.83 5.12 4.75 4.39 3.67 3.07 2.65
 S 64749 32 27 51022 89 80
 374 42 44 43 41 44 40 37 5948 4.81 1.68 1.60 1.74 1.56 1.44 1.26
 376 43 44 43 41 44 40 36 5981 5.20 1.68 1.63 1.72 1.56 1.43 1.21
 376 46 44 41 41 44 39 38 5981 5.03 1.63 1.62 1.72 1.55 1.48 1.24
 543 59 56 55 54 54 51 48 8621 2.18 2.17 2.12 2.14 2.02 1.88 1.74
 552 59 58 57 56 54 52 47 8774 2.25 2.23 2.19 2.11 2.04 1.85 1.71
 550 59 57 56 54 55 52 49 8731 2.28 2.20 2.13 2.17 2.03 1.91 1.74
 754 81 76 74 69 65 60 56 11984 2.94 2.90 2.70 2.56 2.36 2.22 2.07
 751 81 76 74 69 65 60 56 11929 2.89 2.90 2.71 2.54 2.36 2.20 2.05
 752 81 76 74 69 65 59 56 11940 2.81 2.90 2.72 2.54 2.34 2.22 2.08
 968 107 101 97 91 85 73 62 15380 4.22 3.83 3.60 3.36 2.89 2.46 2.36
 987 108 101 97 91 85 73 62 15687 4.22 3.83 3.59 3.36 2.88 2.44 2.33
 978 108 101 98 92 86 73 62 15544 4.25 3.85 3.61 3.37 2.89 2.44 2.37
 S 62336 32 27 51029 90 81
 368 43 41 43 41 34 31 20 5839 5.52 1.71 1.61 1.32 1.22 0.80 0.97
 371 40 40 42 41 33 31 21 5893 5.93 1.65 1.62 1.31 1.22 0.81 0.92
 368 40 40 40 40 32 30 20 5839 6.48 1.59 1.58 1.26 1.17 0.78 0.88
 539 51 48 49 50 47 44 38 8555 2.06 1.91 1.96 1.84 1.74 1.51 1.32
 540 51 48 48 50 46 44 38 8577 1.95 1.89 1.96 1.82 1.72 1.49 1.45
 544 52 49 49 51 45 45 38 8643 1.90 1.92 2.01 1.78 1.77 1.49 1.33
 740 53 54 51 55 52 52 48 11754 2.73 2.02 2.15 2.06 2.03 1.89 1.51
 742 52 53 51 53 52 50 47 11787 1.73 2.02 2.07 2.04 1.98 1.84 1.53
 750 52 52 51 53 53 49 47 11918 1.67 2.02 2.09 2.07 1.93 1.85 1.75
 910 69 71 68 63 57 49 44 14460 3.04 2.66 2.48 2.26 1.92 1.72 1.68
 994 70 71 67 63 57 48 44 15796 3.00 2.65 2.47 2.24 1.89 1.72 1.72
 967 70 71 67 63 58 49 44 15369 2.89 2.65 2.48 2.27 1.93 1.73 1.74
 S 61818 33 28 51033 91 82
 368 46 42 45 41 41 39 30 5839 5.92 1.78 1.63 1.63 1.52 1.18 0.90
 367 47 40 43 41 40 37 28 5828 7.06 1.69 1.63 1.58 1.47 1.10 0.77
 371 46 41 43 40 41 38 28 5893 6.83 1.68 1.59 1.61 1.48 1.11 0.84
 533 55 50 49 48 52 50 41 8468 2.38 1.92 1.90 2.06 1.96 1.63 1.40
 533 55 50 50 48 52 51 40 8468 2.37 1.95 1.89 2.03 2.00 1.57 1.46
 535 56 49 50 48 52 50 41 8501 2.35 1.96 1.88 2.03 1.98 1.61 1.41
 740 59 59 56 54 54 54 48 11754 1.87 2.20 2.11 2.13 2.11 1.89 1.72
 729 58 58 55 52 54 52 45 11579 1.89 2.17 2.06 2.11 2.03 1.79 1.84
 728 59 59 55 53 54 53 46 11568 2.06 2.18 2.07 2.13 2.09 1.83 1.86
 913 79 80 76 72 68 57 48 14504 3.16 3.00 2.82 2.66 2.23 1.89 1.83
 940 79 80 76 72 68 57 49 14931 3.18 3.00 2.84 2.67 2.23 1.91 1.87
 932 79 80 76 72 68 57 49 14810 3.15 3.00 2.84 2.67 2.23 1.92 1.86
 S 60783 36 28 51039 96 83
 370 44 51 52 52 45 49 37 5872 3.42 2.04 2.06 1.76 1.94 1.45 1.45
 370 36 53 58 56 43 55 38 5872 3.81 2.27 2.21 1.68 2.15 1.50 1.02
 370 38 49 53 52 44 49 39 5872 3.66 2.07 2.05 1.72 1.94 1.54 1.43
 529 61 61 59 57 58 55 49 8402 2.33 2.33 2.26 2.27 2.16 1.94 2.03
 530 60 61 60 58 57 54 51 8424 2.39 2.35 2.29 2.23 2.13 2.02 2.17
 527 61 60 59 58 53 56 48 8380 2.36 2.31 2.29 2.09 2.22 1.90 1.81
 716 88 83 81 77 75 65 56 11371 3.52 3.20 3.05 2.97 2.57 2.19 2.06

725 87 84 82 77 75 66 55 11513 3.35 3.22 3.05 2.96 2.58 2.18 1.93
 709 87 84 82 77 75 66 55 11261 3.36 3.21 3.05 2.97 2.58 2.16 1.88
 967 113 113 109 104 100 86 75 15358 4.57 4.29 4.09 3.93 3.39 2.94 2.46
 958 114 113 110 105 100 86 75 15216 4.58 4.32 4.12 3.95 3.39 2.95 2.47
 905 114 113 110 104 100 86 75 14383 4.56 4.33 4.10 3.94 3.38 2.94 2.47
 S 60276 37 28 51041 98 82
 364 44 45 44 42 35 35 25 5784 1.77 1.74 1.66 1.39 1.36 0.98 0.61
 361 43 49 45 44 37 38 23 5740 1.56 1.79 1.72 1.46 1.51 0.91 0.60
 356 39 40 40 38 36 34 25 5652 2.00 1.56 1.50 1.43 1.34 0.98 0.58
 533 47 61 55 53 50 50 40 8468 2.49 2.15 2.09 1.96 1.98 1.57 1.27
 535 48 57 53 52 48 45 38 8501 2.26 2.09 2.06 1.88 1.79 1.49 1.15
 536 46 60 56 54 51 52 40 8512 2.13 2.19 2.12 1.99 2.03 1.57 1.24
 734 58 60 58 55 52 53 46 11666 2.46 2.28 2.15 2.06 2.08 1.82 1.59
 721 58 60 58 55 54 53 47 11447 2.48 2.28 2.15 2.11 2.09 1.84 1.61
 727 58 60 58 55 53 53 46 11557 2.50 2.28 2.15 2.10 2.07 1.83 1.63
 978 80 81 78 74 69 60 51 15533 3.52 3.09 2.93 2.72 2.36 2.00 1.75
 949 80 82 79 75 70 61 51 15073 3.49 3.11 2.94 2.76 2.39 1.99 1.80
 936 80 82 79 75 70 60 51 14865 3.50 3.11 2.94 2.74 2.37 1.99 1.76
 S 57705 34 29 51047 93 84
 376 40 40 37 37 36 31 23 5970 4.91 1.44 1.47 1.42 1.23 0.90 0.46
 377 44 44 42 40 40 34 27 5992 5.42 1.67 1.57 1.56 1.35 1.07 0.63
 381 44 44 41 40 40 35 27 6047 5.32 1.61 1.59 1.57 1.39 1.07 0.57
 550 52 53 49 51 51 50 47 8742 2.71 1.92 2.00 2.00 1.95 1.84 1.66
 553 53 53 50 51 51 50 46 8785 2.56 1.95 2.01 2.01 1.96 1.83 1.69
 552 52 53 50 51 51 49 44 8774 2.65 1.95 1.99 1.99 1.92 1.74 1.58
 756 64 65 61 57 55 53 49 12006 1.78 2.40 2.26 2.18 2.07 1.91 1.61
 755 63 65 61 57 54 52 46 11995 1.79 2.39 2.25 2.13 2.04 1.83 1.58
 749 63 64 61 57 55 52 48 11896 1.80 2.39 2.25 2.15 2.06 1.90 1.70
 978 86 85 81 76 70 59 53 15533 3.91 3.20 2.98 2.77 2.34 2.07 2.01
 993 86 85 82 76 71 59 52 15774 3.94 3.21 2.99 2.78 2.34 2.05 1.99
 995 85 85 81 76 71 60 53 15807 3.93 3.20 2.99 2.78 2.35 2.07 1.97
 S 57182 34 29 51048 93 83
 375 48 46 46 45 44 40 39 5959 1.88 1.83 1.78 1.74 1.57 1.53 1.22
 370 47 45 45 44 43 41 39 5883 1.98 1.76 1.73 1.70 1.62 1.52 1.16
 372 48 44 45 45 44 40 38 5904 1.98 1.78 1.76 1.74 1.58 1.50 1.17
 541 54 52 51 51 51 48 49 8588 3.26 2.00 2.02 2.02 1.89 1.93 1.64
 543 54 53 51 51 51 47 49 8621 3.25 2.02 2.01 2.02 1.87 1.92 1.63
 541 54 52 51 51 51 48 49 8588 3.05 2.01 2.02 2.02 1.90 1.93 1.63
 741 74 74 71 67 62 54 54 11776 4.04 2.78 2.62 2.43 2.12 2.13 1.97
 741 73 73 71 66 61 55 54 11765 3.89 2.78 2.60 2.42 2.15 2.11 1.96
 746 74 74 71 66 62 55 54 11853 3.99 2.81 2.61 2.44 2.15 2.13 1.98
 1005 97 98 94 88 82 69 56 15972 3.78 3.71 3.48 3.23 2.70 2.22 2.07
 928 97 98 94 88 82 68 57 14745 4.83 3.71 3.46 3.23 2.69 2.24 2.07
 977 97 96 94 86 81 68 57 15522 5.39 3.69 3.39 3.19 2.66 2.24 2.04
 S 55593 35 29 51052 95 84
 381 53 53 52 50 47 45 42 6047 2.22 2.04 1.96 1.85 1.78 1.67 1.50
 381 53 54 52 50 47 44 42 6058 2.39 2.04 1.97 1.87 1.75 1.67 1.51
 381 53 54 53 50 48 46 43 6058 2.19 2.08 1.98 1.90 1.80 1.70 1.50

528 73 74 72 69 65 58 53 8391 3.69 2.84 2.73 2.57 2.30 2.07 1.94
534 74 75 72 70 65 58 52 8479 4.53 2.84 2.74 2.57 2.30 2.05 1.90
532 73 74 72 69 65 58 52 8457 4.69 2.84 2.72 2.57 2.30 2.04 1.92
731 101 102 99 94 89 79 69 11612 4.73 3.89 3.70 3.51 3.11 2.70 2.30
734 102 102 99 94 89 80 69 11655 4.66 3.90 3.72 3.52 3.13 2.72 2.31
734 101 102 99 94 90 81 72 11666 4.62 3.89 3.72 3.54 3.18 2.83 2.70
924 135 134 131 125 118 104 90 14679 5.32 5.16 4.91 4.63 4.09 3.54 3.00
901 136 135 131 125 118 104 90 14317 5.37 5.17 4.92 4.64 4.11 3.56 3.02
983 135 135 131 124 118 104 90 15621 5.38 5.15 4.90 4.63 4.08 3.55 3.01
S 55076 34 29 51055 94 84
375 44 45 45 45 37 37 33 5959 1.60 1.77 1.76 1.44 1.46 1.28 0.69
374 46 46 45 44 41 38 29 5937 1.94 1.79 1.72 1.62 1.49 1.16 0.76
371 44 43 46 44 41 40 29 5893 1.69 1.82 1.74 1.62 1.56 1.16 0.72
549 51 50 46 48 46 44 41 8720 1.85 1.83 1.88 1.83 1.72 1.61 1.30
549 51 49 47 49 46 44 41 8720 1.88 1.85 1.91 1.82 1.74 1.61 1.28
550 51 49 46 48 46 44 40 8742 1.84 1.81 1.89 1.81 1.73 1.57 1.26
758 61 62 58 54 51 50 47 12050 2.33 2.30 2.12 2.02 1.96 1.84 1.64
753 61 62 58 54 52 50 48 11962 2.33 2.30 2.12 2.05 1.96 1.89 1.66
756 62 61 58 53 52 48 49 12017 2.35 2.29 2.10 2.06 1.90 1.92 1.61
952 84 84 81 74 68 56 49 15128 3.50 3.17 2.93 2.69 2.20 1.93 1.78
971 85 84 81 74 68 56 48 15424 3.49 3.18 2.92 2.69 2.21 1.89 1.81
1003 85 84 81 74 69 56 48 15939 3.52 3.18 2.92 2.70 2.21 1.88 1.81
S 50382 37 28 51101 99 83
375 41 40 42 42 38 32 26 5959 3.64 1.65 1.64 1.50 1.27 1.04 0.53
373 41 40 42 40 37 33 26 5926 3.67 1.65 1.59 1.47 1.30 1.04 0.52
376 43 41 43 41 38 34 27 5970 3.70 1.69 1.63 1.50 1.35 1.07 0.55
550 50 50 50 50 49 44 41 8742 1.60 1.95 1.96 1.92 1.75 1.60 1.30
549 50 49 49 48 49 43 41 8720 1.69 1.92 1.89 1.92 1.71 1.63 1.30
548 51 49 49 49 48 44 40 8709 1.61 1.93 1.91 1.90 1.72 1.56 1.27
752 59 59 57 53 51 48 45 11940 2.33 2.25 2.10 1.99 1.89 1.78 1.65
749 59 60 57 53 50 49 46 11907 2.31 2.25 2.09 1.96 1.92 1.80 1.61
750 59 60 57 53 51 47 46 11918 2.31 2.26 2.10 2.00 1.87 1.83 1.65
975 84 83 80 74 68 56 47 15490 3.46 3.14 2.92 2.67 2.22 1.85 1.67
992 84 83 80 75 69 57 46 15763 3.41 3.15 2.94 2.70 2.25 1.80 1.64
953 85 84 80 75 69 58 46 15139 3.42 3.16 2.95 2.71 2.27 1.81 1.69
S 49859 37 28 51106 98 83
379 47 44 46 46 46 41 40 6014 2.56 1.80 1.81 1.81 1.62 1.57 1.41
376 49 46 44 43 46 40 39 5970 2.51 1.74 1.70 1.80 1.57 1.53 1.35
379 54 50 46 46 47 43 41 6014 2.33 1.81 1.83 1.87 1.68 1.63 1.42
543 63 65 64 61 57 51 49 8632 2.34 2.52 2.39 2.26 2.02 1.93 1.81
542 64 65 64 61 57 50 49 8610 2.42 2.52 2.39 2.26 1.98 1.93 1.85
543 63 65 64 60 57 51 49 8632 2.39 2.52 2.38 2.24 2.01 1.91 1.81
743 87 88 86 82 77 68 59 11798 4.00 3.37 3.22 3.03 2.69 2.34 2.30
735 87 88 86 82 77 68 60 11677 4.02 3.40 3.22 3.03 2.67 2.37 2.36
738 88 89 87 83 78 70 64 11721 4.09 3.44 3.28 3.09 2.76 2.50 2.46
948 115 116 114 108 102 91 78 15062 4.50 4.47 4.24 4.01 3.57 3.08 2.61
983 117 117 115 108 103 92 80 15610 4.58 4.51 4.27 4.06 3.61 3.15 2.70
977 116 117 114 108 102 91 78 15522 4.59 4.50 4.26 4.02 3.59 3.08 2.61

S 48576 40 29 51120 104 84
 384 51 51 48 46 43 38 33 6102 5.30 1.90 1.80 1.68 1.48 1.31 1.02
 381 48 47 45 44 43 39 30 6058 5.54 1.79 1.72 1.71 1.55 1.19 0.93
 381 49 48 46 45 45 39 31 6047 5.12 1.80 1.76 1.77 1.55 1.21 0.87
 547 54 51 53 53 51 45 38 8698 2.35 2.09 2.09 1.99 1.78 1.51 1.33
 545 54 52 52 52 50 46 41 8654 2.09 2.06 2.03 1.97 1.83 1.62 1.42
 550 54 52 52 52 52 46 40 8731 2.12 2.06 2.04 2.03 1.82 1.57 1.41
 754 71 68 66 60 56 53 50 11973 2.65 2.59 2.36 2.19 2.08 1.97 1.74
 758 72 68 65 60 54 52 49 12039 2.75 2.57 2.36 2.13 2.04 1.92 1.72
 747 71 68 65 59 54 50 49 11864 2.78 2.56 2.34 2.12 1.98 1.94 1.69
 950 98 93 88 81 74 59 51 15095 3.72 3.45 3.20 2.91 2.31 2.01 2.11
 942 98 92 88 81 74 59 51 14964 3.74 3.47 3.19 2.91 2.32 2.02 1.89
 987 98 93 88 81 74 59 49 15687 3.67 3.46 3.20 2.90 2.33 1.91 1.92
 S 48048 39 29 51124 101 84
 375 52 49 49 44 48 41 37 5959 2.15 1.91 1.74 1.89 1.63 1.46 1.02
 370 53 47 49 47 48 41 37 5872 2.45 1.92 1.84 1.88 1.63 1.47 1.06
 376 52 48 48 41 46 42 36 5981 2.32 1.89 1.63 1.83 1.67 1.41 1.02
 536 54 57 52 51 52 50 44 8512 1.80 2.03 2.02 2.04 1.96 1.72 1.49
 539 55 56 53 49 52 52 46 8566 1.77 2.10 1.94 2.05 2.05 1.81 1.44
 541 56 57 54 50 52 53 47 8588 1.95 2.11 1.96 2.06 2.07 1.85 1.51
 738 75 74 70 67 61 62 59 11732 3.56 2.76 2.62 2.40 2.43 2.32 1.98
 742 74 74 70 66 61 60 55 11787 3.56 2.74 2.60 2.39 2.37 2.18 2.07
 730 75 74 70 66 61 62 57 11601 3.45 2.74 2.60 2.40 2.44 2.24 1.87
 912 99 99 94 89 82 71 61 14493 3.82 3.69 3.51 3.22 2.78 2.41 2.19
 978 99 99 94 89 82 70 60 15533 3.89 3.70 3.52 3.22 2.76 2.38 2.07
 963 100 99 94 90 82 70 60 15303 3.91 3.71 3.54 3.23 2.77 2.35 2.08
 EOF

C.2 US 35 All Southbound Drops .FWD (.R80) File Format

```
R80 20140709route35s36F20
70 18002-146 80355 00 60 .
  150 0 203 305 457 610 9141219 5.91 0.00 12.01 17.99 24.02 35.98 47.99 60.00
C:\Users\dynfieldid\Document.FWD
us 35
S
S
99076 86231-01 48576 84554
  7.920.0 3.510.0 3.030.0 3.010.0
Ld 0202 0.997 88.1 .
D1 2241 0.999 1.003 .
D2 2242 0.999 1.031 .
D3 2243 0.997 1.018 .
D4 2244 0.998 0.993 .
D5 2245 0.994 0.986 .
D6 2246 0.998 0.985 .
D7 2247 0.999 0.984 .
D0 2248 0.997 1.035 .
D0 2249 0.995 1.000 .
D* NO 1.000 1.000 .

11 5 1110 1 1 .
  5 2.0 2 0.0
*mason co
DtCty PxNnnnS 000+0.0 000+0.0 St
  Cty P Nnnn
000+0.0 000+0.0 St ...
  300 0 0 0 0 0 0 0 11.81 0.00 0.00 0.00 0.00 0.00 0.00 0.00
  30 360 1915 20094
ABCD111222333444.....
ABCD111222333444.....
.
.... ***** .....
.
.
Dynatest
*mason co
S 48576      38 32 51243  101 90
390 46 40 41 41 39 33 23 6189 2.43 1.60 1.63 1.55 1.30 0.92 0.56
394 44 37 37 38 37 29 23 6255 2.61 1.44 1.50 1.47 1.15 0.89 0.54
395 46 40 40 40 39 31 24 6277 2.09 1.56 1.56 1.52 1.23 0.93 0.54
565 52 49 47 46 46 42 38 8972 1.54 1.87 1.80 1.82 1.67 1.48 1.15
567 52 48 46 45 46 41 37 9005 1.47 1.83 1.78 1.81 1.63 1.45 1.12
567 52 49 49 43 46 41 37 9005 1.41 1.92 1.71 1.80 1.63 1.46 1.10
774 55 57 54 52 53 49 45 12302 2.66 2.11 2.04 2.07 1.94 1.76 1.54
774 56 59 55 52 52 50 45 12302 2.46 2.18 2.06 2.06 1.96 1.78 1.58
```

776 55 55 54 50 50 49 44 12335 2.08 2.11 1.96 1.97 1.94 1.72 1.54
998 65 67 64 58 54 49 46 15862 2.78 2.50 2.27 2.11 1.93 1.83 1.67
1020 65 66 63 57 53 50 46 16213 2.65 2.47 2.26 2.08 1.95 1.80 1.70
983 65 67 63 57 52 50 46 15610 2.67 2.47 2.24 2.06 1.95 1.81 1.76
S 49093 39 32 51246 102 90
379 56 53 51 50 48 44 42 6014 2.98 2.00 1.96 1.89 1.75 1.66 1.50
381 56 53 51 49 49 45 42 6058 2.66 2.02 1.93 1.92 1.77 1.66 1.50
382 56 53 51 49 48 45 42 6069 2.67 2.02 1.91 1.89 1.79 1.65 1.46
544 81 76 74 69 64 53 47 8643 3.24 2.90 2.70 2.51 2.07 1.87 1.80
547 81 76 73 68 64 53 48 8698 3.01 2.89 2.69 2.52 2.07 1.90 1.82
545 81 76 73 68 64 53 48 8654 3.00 2.89 2.69 2.50 2.07 1.89 1.83
752 113 106 102 95 89 74 61 11940 4.42 4.03 3.74 3.49 2.91 2.40 1.93
753 113 106 102 94 88 74 61 11962 4.39 4.02 3.72 3.48 2.91 2.40 1.92
750 112 106 102 94 88 74 61 11918 4.38 4.03 3.70 3.46 2.90 2.40 1.92
1014 154 143 137 128 119 100 83 16103 5.94 5.41 5.02 4.68 3.95 3.27 2.62
977 155 144 137 128 119 101 83 15522 5.82 5.40 5.03 4.69 3.96 3.27 2.61
999 153 142 137 127 119 100 83 15873 5.80 5.41 5.01 4.69 3.95 3.27 2.60
S 49632 39 32 51249 101 90
386 50 48 46 41 41 38 39 6134 3.33 1.82 1.60 1.63 1.50 1.55 1.33
388 51 49 48 43 43 40 40 6167 4.09 1.90 1.68 1.68 1.57 1.56 1.38
382 50 48 47 42 43 41 39 6069 3.59 1.87 1.66 1.70 1.62 1.52 1.37
558 71 69 68 62 60 52 46 8873 2.80 2.66 2.44 2.36 2.06 1.83 1.61
558 72 70 68 64 61 53 46 8862 2.92 2.68 2.50 2.39 2.09 1.81 1.59
558 72 71 68 64 61 53 46 8862 2.73 2.69 2.52 2.40 2.09 1.81 1.60
760 101 99 95 90 85 74 64 12072 3.93 3.74 3.53 3.35 2.93 2.51 2.09
762 101 98 95 89 85 74 64 12105 3.86 3.74 3.49 3.35 2.91 2.51 2.11
754 99 97 93 87 83 72 62 11973 3.74 3.67 3.43 3.28 2.84 2.43 2.02
1017 135 132 127 119 114 100 86 16158 5.27 5.01 4.69 4.49 3.92 3.38 2.84
1017 135 132 127 118 114 100 87 16158 5.31 5.01 4.66 4.50 3.92 3.41 2.90
981 135 132 128 120 114 100 86 15588 5.20 5.02 4.71 4.50 3.93 3.37 2.83
S 50149 37 32 51251 99 90
385 37 36 36 33 31 24 15 6124 2.85 1.41 1.28 1.24 0.94 0.58 0.35
381 40 36 38 34 31 24 15 6058 2.79 1.49 1.35 1.22 0.95 0.58 0.37
386 39 36 38 35 33 24 15 6134 2.81 1.50 1.38 1.29 0.96 0.58 0.41
551 50 50 49 50 48 37 34 8753 1.42 1.93 1.98 1.90 1.45 1.35 0.79
552 52 51 50 52 50 38 35 8764 1.41 1.97 2.03 1.97 1.49 1.36 0.83
552 51 50 50 50 50 39 34 8764 1.39 1.95 1.98 1.96 1.54 1.35 0.83
757 56 52 54 54 52 50 39 12028 2.16 2.11 2.14 2.06 1.97 1.55 1.28
756 57 52 54 54 52 50 40 12017 2.16 2.11 2.11 2.05 1.96 1.57 1.33
761 57 53 55 54 54 52 40 12083 2.32 2.18 2.13 2.13 2.06 1.59 1.33
977 66 66 64 58 54 48 45 15522 2.80 2.50 2.30 2.11 1.90 1.76 1.57
939 66 66 63 58 54 48 45 14920 2.80 2.49 2.29 2.11 1.89 1.78 1.58
973 67 66 63 58 54 47 45 15457 2.80 2.49 2.29 2.11 1.87 1.77 1.59
S 54886 37 31 51256 98 88
399 50 50 48 46 49 45 35 6332 4.32 1.90 1.83 1.91 1.77 1.39 1.36
396 50 51 48 45 49 45 37 6299 4.85 1.89 1.79 1.93 1.78 1.45 1.34
390 50 50 45 45 48 44 36 6200 3.63 1.78 1.78 1.89 1.75 1.41 1.28
528 61 61 57 56 53 52 45 8391 2.22 2.25 2.19 2.07 2.03 1.77 1.61

532 61 60 57 56 52 51 46 8457 2.11 2.26 2.19 2.04 2.01 1.82 1.64
531 60 61 57 56 52 51 44 8435 2.17 2.25 2.20 2.05 2.02 1.73 1.63
730 85 83 81 77 71 61 51 11601 3.48 3.18 3.03 2.80 2.41 2.00 1.96
747 85 84 81 77 72 61 52 11864 3.19 3.17 3.03 2.82 2.40 2.03 1.91
726 84 83 80 76 71 60 51 11535 3.21 3.15 3.01 2.78 2.38 2.02 1.94
961 115 113 108 103 96 81 67 15270 4.51 4.26 4.07 3.78 3.17 2.65 2.13
971 116 113 108 103 95 81 67 15424 4.48 4.27 4.07 3.74 3.20 2.64 2.12
932 116 113 108 104 96 81 67 14799 4.43 4.27 4.09 3.77 3.20 2.65 2.13
S 55392 38 31 51258 100 88
382 56 51 51 53 50 42 40 6069 3.66 2.00 2.07 1.96 1.67 1.57 1.29
382 55 50 50 52 50 42 42 6069 3.37 1.96 2.05 1.97 1.66 1.66 1.38
376 54 50 50 52 51 42 39 5981 3.57 1.98 2.04 2.00 1.64 1.54 1.41
543 63 58 57 60 59 56 54 8621 2.34 2.25 2.38 2.31 2.19 2.11 1.83
543 65 60 58 61 59 57 54 8632 3.09 2.28 2.41 2.33 2.24 2.11 1.78
547 62 58 57 60 60 56 53 8698 3.18 2.24 2.37 2.35 2.19 2.09 1.87
735 86 81 75 71 68 61 59 11677 6.44 2.97 2.80 2.66 2.41 2.31 2.13
741 87 81 76 71 68 61 59 11776 6.27 2.99 2.81 2.68 2.41 2.31 2.07
734 86 81 76 71 68 61 59 11666 6.64 2.98 2.80 2.68 2.39 2.31 2.13
927 116 108 102 95 90 73 59 14723 3.94 4.03 3.75 3.54 2.89 2.33 2.24
968 115 108 103 96 90 73 61 15380 3.80 4.04 3.76 3.53 2.89 2.40 2.27
984 116 108 102 95 89 73 60 15632 3.93 4.01 3.73 3.52 2.87 2.38 2.23
S 56955 39 32 51301 101 89
382 65 58 56 52 55 48 46 6069 2.60 2.19 2.06 2.16 1.89 1.83 1.51
374 64 57 54 50 52 47 45 5937 2.61 2.14 1.98 2.05 1.85 1.79 1.38
374 64 58 55 52 54 46 45 5948 2.64 2.16 2.03 2.13 1.83 1.76 1.51
543 91 83 78 72 65 56 53 8632 3.36 3.09 2.82 2.54 2.20 2.10 1.85
544 91 83 79 72 65 54 53 8643 3.31 3.10 2.84 2.56 2.12 2.08 1.88
543 91 82 78 72 65 54 53 8632 3.31 3.07 2.83 2.54 2.12 2.07 1.94
743 126 113 106 98 87 72 57 11809 5.01 4.19 3.87 3.44 2.82 2.25 2.00
745 128 114 108 99 89 72 57 11831 5.04 4.24 3.90 3.51 2.84 2.26 2.13
737 126 114 107 99 88 72 58 11710 5.04 4.22 3.89 3.45 2.83 2.28 2.12
960 170 150 143 130 119 96 74 15249 6.38 5.63 5.11 4.67 3.78 2.93 2.21
960 170 151 143 131 117 97 76 15249 6.39 5.63 5.15 4.59 3.80 2.98 2.23
974 167 150 142 130 114 96 76 15468 6.33 5.59 5.13 4.50 3.77 3.00 2.25
S 57489 39 32 51303 102 90
370 50 50 49 49 44 45 34 5883 2.05 1.91 1.91 1.74 1.76 1.32 0.87
370 47 52 47 50 45 44 34 5883 2.57 1.84 1.96 1.76 1.72 1.33 0.80
372 46 48 46 48 43 43 32 5915 2.40 1.80 1.90 1.68 1.69 1.26 0.78
545 54 56 55 55 53 51 44 8665 1.81 2.15 2.17 2.07 2.00 1.74 1.42
546 62 61 61 60 60 56 48 8676 1.88 2.39 2.38 2.35 2.19 1.89 1.56
547 58 58 56 57 55 53 46 8687 1.87 2.20 2.25 2.16 2.09 1.83 1.47
749 74 73 70 67 66 56 53 11907 3.56 2.75 2.64 2.61 2.20 2.07 1.85
753 73 73 70 67 62 55 50 11962 3.59 2.74 2.64 2.45 2.15 1.98 1.80
749 73 73 70 67 64 55 50 11896 3.70 2.75 2.65 2.50 2.16 1.95 1.83
1005 99 97 93 88 78 67 55 15972 3.90 3.67 3.48 3.06 2.64 2.17 1.91
968 100 97 92 87 79 67 55 15380 3.89 3.64 3.44 3.11 2.64 2.16 1.94
970 99 97 92 88 78 67 55 15413 3.86 3.64 3.45 3.08 2.64 2.17 1.96
S 60076 40 32 51307 105 90

373 47 46 44 44 46 41 36 5926 2.31 1.75 1.72 1.81 1.62 1.43 1.24
376 46 46 46 45 46 42 36 5981 2.26 1.81 1.79 1.81 1.67 1.43 1.24
377 47 46 45 46 46 44 36 5992 2.14 1.79 1.80 1.81 1.72 1.43 1.26
546 68 66 64 61 57 50 47 8676 2.69 2.53 2.39 2.23 1.95 1.87 1.78
551 68 66 64 61 57 50 49 8753 2.71 2.53 2.40 2.25 1.97 1.92 1.80
550 67 67 65 61 58 50 49 8731 2.68 2.54 2.40 2.27 1.95 1.93 1.82
754 94 93 90 85 80 69 58 11973 3.96 3.54 3.36 3.15 2.72 2.28 1.80
747 94 93 90 85 80 69 58 11875 3.96 3.54 3.36 3.14 2.70 2.30 1.81
745 94 93 90 85 80 69 58 11831 3.94 3.54 3.36 3.15 2.70 2.28 1.80
996 127 126 122 116 110 94 80 15818 5.23 4.82 4.57 4.33 3.70 3.15 2.51
994 126 126 122 116 110 94 80 15785 5.22 4.82 4.57 4.32 3.70 3.14 2.51
956 127 126 123 116 110 94 80 15194 5.22 4.83 4.58 4.33 3.71 3.14 2.52
S 60604 41 32 51309 105 90
374 62 51 49 48 53 44 40 5948 1.97 1.94 1.90 2.07 1.74 1.59 1.40
375 59 50 48 49 49 46 41 5959 2.05 1.90 1.92 1.94 1.80 1.62 1.49
377 58 53 49 49 50 47 41 5992 1.96 1.94 1.94 1.98 1.87 1.63 1.49
541 79 69 64 63 63 58 55 8599 3.28 2.52 2.49 2.49 2.28 2.17 2.06
539 78 69 65 64 65 60 56 8566 3.40 2.56 2.51 2.54 2.35 2.21 2.07
539 78 69 65 64 61 60 57 8566 3.43 2.54 2.50 2.42 2.36 2.24 2.12
754 104 94 91 87 82 70 65 11973 4.88 3.57 3.44 3.22 2.77 2.54 2.45
741 104 94 91 87 81 72 67 11776 4.85 3.58 3.44 3.20 2.84 2.62 2.53
743 103 94 92 88 82 73 67 11798 4.63 3.61 3.45 3.22 2.87 2.63 2.54
936 135 126 121 115 109 92 81 14865 5.06 4.78 4.54 4.28 3.63 3.20 2.94
926 137 126 120 115 109 91 82 14712 5.06 4.73 4.52 4.30 3.60 3.24 2.85
955 138 125 120 115 109 91 83 15172 5.00 4.71 4.52 4.30 3.58 3.27 2.86
S 61644 41 33 51312 105 91
370 46 48 46 43 47 41 34 5872 2.25 1.81 1.70 1.84 1.60 1.32 1.00
368 46 50 45 45 49 41 35 5839 1.29 1.76 1.79 1.91 1.61 1.38 1.19
372 46 48 45 44 49 40 36 5915 1.33 1.78 1.72 1.91 1.58 1.43 1.22
541 52 51 49 51 52 50 44 8588 2.31 1.93 2.02 2.03 1.98 1.72 1.54
539 55 53 52 53 52 51 46 8566 2.43 2.05 2.10 2.03 2.00 1.81 1.57
539 54 52 50 52 54 50 44 8566 2.15 1.97 2.04 2.12 1.98 1.72 1.59
742 71 72 70 66 61 55 52 11787 2.82 2.74 2.58 2.39 2.15 2.04 1.89
733 71 72 70 65 61 54 51 11645 2.76 2.74 2.56 2.39 2.13 1.99 1.91
738 70 72 69 65 61 55 50 11732 2.81 2.72 2.55 2.39 2.16 1.97 1.91
970 97 97 93 87 82 69 56 15413 4.07 3.67 3.44 3.22 2.73 2.22 1.75
971 97 97 94 88 82 70 56 15424 4.19 3.70 3.46 3.22 2.74 2.22 1.81
947 97 97 94 88 82 70 56 15040 4.13 3.70 3.46 3.23 2.74 2.22 1.80
S 62172 41 33 51314 106 91
376 45 42 41 40 40 39 36 5970 1.60 1.60 1.59 1.56 1.53 1.41 1.12
376 46 43 43 41 41 40 36 5970 1.70 1.68 1.63 1.60 1.57 1.40 1.15
373 44 41 41 41 40 39 36 5926 1.70 1.63 1.60 1.58 1.53 1.42 1.12
538 51 50 48 47 47 45 43 8544 3.16 1.90 1.87 1.87 1.79 1.70 1.55
543 51 50 49 49 49 46 43 8621 3.26 1.91 1.92 1.94 1.81 1.70 1.54
543 51 50 49 47 48 45 43 8621 3.16 1.91 1.85 1.90 1.78 1.70 1.54
746 71 70 67 63 58 50 47 11853 3.43 2.64 2.47 2.29 1.95 1.87 1.69
744 71 70 67 62 58 50 46 11820 3.54 2.64 2.46 2.30 1.95 1.83 1.68
738 71 70 67 62 58 50 47 11732 3.78 2.64 2.45 2.30 1.97 1.85 1.69

932 96 94 90 84 78 67 56 14799 3.81 3.53 3.32 3.09 2.63 2.21 1.88
 1003 96 94 90 85 78 67 56 15939 3.86 3.54 3.33 3.09 2.63 2.20 1.84
 980 97 95 90 85 79 67 56 15566 4.01 3.56 3.34 3.11 2.64 2.21 1.84
 S 64506 42 33 51317 107 92
 366 50 44 40 45 42 42 37 5817 1.08 1.57 1.79 1.67 1.64 1.44 1.24
 354 46 43 43 44 42 41 36 5620 1.46 1.68 1.74 1.67 1.62 1.42 1.15
 354 42 45 43 46 40 42 38 5620 1.38 1.68 1.80 1.59 1.65 1.48 1.20
 521 55 57 60 55 51 54 49 8282 5.40 2.36 2.15 2.01 2.13 1.93 1.72
 523 55 56 55 54 49 53 47 8303 5.13 2.15 2.11 1.94 2.07 1.85 1.63
 524 56 56 58 53 50 54 47 8325 5.45 2.27 2.09 1.95 2.11 1.86 1.66
 718 78 77 75 71 67 62 57 11415 3.17 2.96 2.78 2.63 2.43 2.25 2.16
 732 78 77 75 71 67 61 56 11623 3.08 2.96 2.78 2.63 2.39 2.22 2.17
 732 78 77 75 70 67 61 55 11623 3.04 2.94 2.77 2.63 2.39 2.17 2.10
 917 103 103 100 95 90 78 66 14569 5.96 3.95 3.74 3.54 3.07 2.61 2.20
 963 104 103 100 95 90 79 66 15292 6.35 3.95 3.74 3.53 3.10 2.61 2.18
 906 103 103 101 95 89 78 66 14394 6.01 3.96 3.74 3.51 3.09 2.61 2.22
 S 65039 42 33 51319 108 91
 373 56 58 48 52 52 52 45 5926 5.71 1.90 2.04 2.06 2.06 1.77 1.78
 369 53 58 50 51 53 51 45 5861 5.81 1.96 2.02 2.08 1.99 1.78 1.78
 376 54 56 51 52 53 50 45 5981 6.60 1.99 2.04 2.07 1.96 1.77 1.85
 537 62 64 61 58 62 59 53 8533 2.50 2.40 2.28 2.43 2.32 2.10 2.22
 538 62 64 62 59 63 59 55 8544 2.65 2.46 2.33 2.47 2.34 2.15 2.09
 539 60 64 64 59 63 58 52 8566 2.62 2.53 2.31 2.49 2.28 2.06 1.94
 746 81 84 82 75 73 66 56 11853 3.48 3.22 2.95 2.89 2.58 2.20 2.25
 737 81 85 83 75 74 66 57 11710 3.35 3.25 2.96 2.91 2.60 2.26 2.18
 745 81 85 82 75 74 65 57 11842 3.31 3.22 2.97 2.91 2.57 2.24 2.22
 989 108 111 109 101 99 85 73 15709 4.43 4.31 3.97 3.88 3.35 2.87 2.37
 947 108 111 110 101 98 86 73 15040 4.36 4.33 3.98 3.87 3.37 2.88 2.38
 992 108 112 110 101 99 86 73 15752 4.30 4.32 3.98 3.89 3.39 2.88 2.45
 S 66338 44 33 51322 111 91
 374 92 95 90 81 71 51 44 5948 6.46 3.56 3.18 2.79 2.01 1.75 1.46
 381 93 95 90 81 71 51 45 6047 6.47 3.56 3.19 2.80 2.02 1.77 1.49
 379 93 95 90 81 71 51 45 6014 6.47 3.56 3.19 2.81 2.02 1.77 1.46
 539 135 139 133 119 106 78 56 8566 8.44 5.22 4.69 4.18 3.09 2.22 2.04
 534 135 139 132 119 106 78 56 8479 8.33 5.21 4.68 4.17 3.09 2.21 2.02
 536 135 139 132 119 106 78 56 8523 8.30 5.21 4.69 4.17 3.09 2.21 2.08
 741 189 195 185 167 149 111 81 11765 11.32 7.30 6.58 5.87 4.37 3.17 2.17
 739 190 194 185 167 149 111 81 11743 11.30 7.29 6.58 5.87 4.36 3.17 2.18
 734 190 195 185 167 149 111 80 11666 11.27 7.30 6.58 5.87 4.37 3.16 2.26
 929 258 263 250 227 203 152 111 14767 15.13 9.86 8.92 7.98 5.97 4.36 3.03
 960 258 263 251 227 203 152 111 15249 15.06 9.88 8.94 8.01 5.98 4.37 3.03
 972 258 263 251 227 203 152 111 15435 14.97 9.88 8.94 8.00 5.99 4.37 3.04
 S 66861 44 33 51324 111 91
 372 75 76 70 61 53 43 38 5915 4.83 2.76 2.41 2.07 1.70 1.50 1.18
 370 75 76 70 61 53 44 38 5872 4.79 2.77 2.41 2.07 1.72 1.50 1.21
 375 74 76 70 61 53 44 38 5959 4.80 2.77 2.41 2.07 1.74 1.48 1.11
 529 109 110 102 89 77 54 45 8402 6.45 4.00 3.50 3.04 2.11 1.78 1.58
 532 109 110 103 89 78 54 47 8457 6.49 4.04 3.52 3.06 2.14 1.84 1.63

531 108 110 102 89 77 54 45 8435 6.47 4.02 3.50 3.04 2.13 1.77 1.61
736 151 153 141 124 108 75 52 11688 8.66 5.57 4.89 4.24 2.96 2.06 1.76
737 150 153 142 124 108 76 52 11710 8.60 5.58 4.90 4.25 2.98 2.03 1.74
735 151 153 142 124 108 76 52 11677 8.57 5.58 4.90 4.26 3.00 2.03 1.72
965 205 206 191 168 146 103 71 15325 12.00 7.53 6.60 5.74 4.05 2.81 1.91
911 204 207 192 168 146 103 71 14471 11.91 7.55 6.63 5.76 4.07 2.80 1.93
949 204 207 192 168 146 103 71 15084 11.91 7.56 6.63 5.76 4.07 2.79 1.88
S 69469 43 33 51327 110 91
374 66 66 64 57 50 44 38 5948 3.61 2.50 2.23 1.97 1.74 1.51 1.24
370 65 66 63 56 50 43 39 5872 3.69 2.48 2.22 1.96 1.71 1.54 1.25
372 65 66 63 56 50 44 39 5915 3.70 2.49 2.22 1.96 1.74 1.52 1.29
541 94 96 91 82 72 56 50 8588 5.81 3.60 3.22 2.85 2.20 1.98 1.72
541 93 95 91 82 72 57 51 8588 5.82 3.59 3.22 2.85 2.24 2.02 1.78
537 93 95 91 81 72 55 50 8533 5.81 3.58 3.20 2.83 2.18 1.98 1.72
741 130 132 127 113 100 75 60 11765 7.71 5.00 4.45 3.95 2.94 2.37 2.11
728 130 133 127 113 100 75 61 11568 7.69 5.00 4.46 3.95 2.95 2.40 2.15
736 130 133 127 113 100 75 59 11688 7.69 5.00 4.46 3.95 2.95 2.33 2.12
973 176 178 171 153 136 102 75 15457 10.54 6.73 6.02 5.34 4.00 2.96 2.40
928 176 178 170 152 135 101 75 14745 10.44 6.71 6.00 5.32 3.98 2.94 2.44
901 176 178 170 152 135 101 75 14317 10.40 6.71 6.00 5.32 3.98 2.94 2.45
S 69992 42 33 51330 107 91
368 82 86 80 72 62 45 41 5850 6.26 3.15 2.82 2.44 1.78 1.60 1.24
370 83 87 81 72 62 45 40 5883 6.25 3.17 2.84 2.45 1.78 1.58 1.24
368 83 86 80 72 62 46 41 5839 6.22 3.16 2.83 2.44 1.83 1.62 1.29
532 121 127 118 106 93 66 49 8446 7.83 4.65 4.17 3.65 2.61 1.94 1.70
530 121 127 118 106 93 67 49 8413 7.78 4.65 4.18 3.66 2.63 1.93 1.70
530 121 127 118 106 93 67 49 8413 7.73 4.65 4.17 3.67 2.63 1.92 1.70
732 171 178 166 149 131 94 66 11623 11.24 6.53 5.88 5.14 3.72 2.61 1.94
731 170 178 166 149 131 94 66 11612 11.21 6.54 5.88 5.15 3.72 2.60 1.93
725 171 178 166 149 131 94 66 11513 11.20 6.54 5.88 5.14 3.72 2.60 1.96
862 233 243 226 203 179 130 91 13693 14.46 8.89 8.01 7.04 5.11 3.57 2.45
974 234 243 226 204 179 130 91 15479 14.40 8.91 8.03 7.06 5.13 3.59 2.46
954 234 243 226 204 179 130 91 15150 14.34 8.91 8.03 7.05 5.13 3.59 2.45
S 72574 41 33 51333 105 91
368 106 113 103 90 78 56 44 5850 6.48 4.07 3.55 3.09 2.19 1.74 1.47
370 106 113 104 90 79 56 43 5883 6.41 4.08 3.56 3.10 2.20 1.69 1.46
369 105 112 103 90 78 56 44 5861 6.42 4.06 3.55 3.09 2.19 1.72 1.47
543 152 163 149 132 115 82 57 8621 7.62 5.87 5.19 4.54 3.24 2.23 1.73
536 153 163 150 132 116 82 57 8523 7.59 5.89 5.20 4.55 3.24 2.25 1.72
538 153 163 150 132 116 83 57 8544 7.61 5.89 5.20 4.56 3.26 2.26 1.77
735 210 224 206 183 161 116 81 11677 10.87 8.11 7.20 6.34 4.56 3.17 2.20
728 211 225 207 183 161 116 81 11568 10.94 8.13 7.20 6.34 4.57 3.17 2.19
736 210 224 206 182 160 116 80 11688 10.85 8.10 7.18 6.31 4.55 3.16 2.18
964 282 298 274 244 215 156 109 15314 14.55 10.80 9.59 8.47 6.16 4.31 2.99
963 283 299 275 245 216 157 109 15303 14.51 10.83 9.63 8.50 6.18 4.31 2.99
931 282 298 274 244 215 156 109 14788 14.43 10.80 9.59 8.47 6.15 4.30 2.98
S 73117 41 33 51335 106 91
370 89 93 84 71 59 42 38 5872 4.67 3.30 2.79 2.33 1.66 1.48 1.10

370 90 94 84 71 59 43 37 5883 4.63 3.32 2.80 2.34 1.71 1.45 1.10
 370 89 93 84 71 59 43 37 5872 4.58 3.30 2.78 2.33 1.69 1.45 1.08
 533 128 134 122 103 88 58 46 8468 8.35 4.79 4.06 3.45 2.30 1.80 1.56
 529 127 135 122 103 88 58 44 8402 8.35 4.80 4.07 3.47 2.29 1.74 1.51
 529 127 134 121 103 88 58 45 8402 8.31 4.77 4.06 3.45 2.28 1.76 1.57
 726 176 182 166 142 121 81 53 11535 9.81 6.52 5.58 4.76 3.20 2.07 1.80
 727 175 183 166 142 121 81 53 11557 9.71 6.52 5.58 4.76 3.19 2.08 1.77
 732 175 182 165 141 120 81 53 11634 9.71 6.49 5.56 4.74 3.20 2.08 1.80
 954 233 242 219 188 161 109 72 15150 13.65 8.63 7.41 6.34 4.30 2.83 2.04
 867 233 242 220 188 161 109 72 13781 13.53 8.65 7.42 6.35 4.30 2.84 2.07
 970 233 242 220 188 162 109 72 15413 13.50 8.65 7.42 6.36 4.28 2.84 2.02
 S 75705 42 33 51338 108 91
 378 56 58 55 49 47 42 34 6003 4.31 2.17 1.91 1.87 1.66 1.33 0.76
 376 57 58 55 49 48 42 35 5970 4.27 2.17 1.93 1.88 1.64 1.37 0.77
 375 58 58 55 49 48 42 35 5959 4.29 2.17 1.93 1.88 1.66 1.36 0.80
 532 84 86 81 72 63 52 44 8457 6.50 3.20 2.83 2.47 2.03 1.73 1.46
 530 85 86 82 72 63 52 45 8424 6.48 3.21 2.85 2.47 2.04 1.77 1.46
 532 85 86 81 71 62 51 45 8446 6.41 3.19 2.81 2.44 2.00 1.78 1.43
 732 117 120 114 101 88 61 51 11634 8.56 4.47 3.97 3.46 2.40 2.02 1.81
 738 116 120 113 101 88 61 51 11721 8.55 4.46 3.96 3.45 2.39 2.00 1.76
 737 117 120 113 101 88 61 51 11710 8.50 4.46 3.96 3.46 2.39 2.00 1.77
 976 163 165 155 138 120 84 57 15511 11.47 6.12 5.43 4.74 3.30 2.24 2.02
 972 162 166 156 138 121 84 57 15435 11.37 6.13 5.44 4.75 3.31 2.25 2.00
 949 163 166 156 139 121 84 57 15084 11.35 6.15 5.46 4.76 3.31 2.26 2.04
 S 76233 43 33 51340 109 91
 373 85 91 80 67 56 47 36 5926 6.09 3.14 2.63 2.22 1.87 1.41 0.69
 372 84 90 80 66 57 48 36 5915 6.05 3.13 2.60 2.23 1.88 1.42 0.70
 374 84 89 79 66 56 46 36 5937 5.99 3.10 2.59 2.21 1.83 1.41 0.68
 535 121 129 114 96 81 54 46 8501 8.86 4.49 3.78 3.17 2.12 1.82 1.34
 533 121 129 114 96 80 54 45 8468 8.83 4.49 3.78 3.16 2.12 1.79 1.33
 534 121 129 114 96 81 54 46 8479 8.84 4.50 3.79 3.17 2.13 1.81 1.36
 726 170 182 162 137 116 75 50 11535 11.81 6.36 5.41 4.56 2.95 1.97 1.66
 732 170 182 162 137 116 75 49 11634 11.74 6.36 5.41 4.56 2.94 1.94 1.64
 730 170 182 162 138 116 75 49 11601 11.72 6.37 5.43 4.56 2.96 1.94 1.65
 947 233 247 220 188 159 104 65 15040 15.74 8.67 7.39 6.26 4.09 2.55 1.78
 919 233 247 220 187 158 104 65 14602 15.61 8.65 7.37 6.24 4.10 2.54 1.78
 934 233 248 220 188 159 104 65 14843 15.57 8.67 7.39 6.26 4.09 2.54 1.77
 S 76740 42 32 51342 107 90
 375 86 91 84 75 65 48 39 5959 6.39 3.30 2.94 2.57 1.88 1.53 1.33
 376 85 90 84 74 65 48 39 5981 6.36 3.29 2.93 2.56 1.89 1.52 1.34
 372 84 89 82 74 65 48 41 5904 6.20 3.24 2.92 2.55 1.88 1.60 1.34
 534 120 129 118 106 94 68 52 8490 8.56 4.66 4.18 3.69 2.69 2.05 1.59
 539 120 129 119 106 94 69 51 8555 8.70 4.67 4.19 3.70 2.70 2.01 1.55
 537 120 129 118 106 94 69 49 8533 8.65 4.66 4.18 3.69 2.70 1.94 1.59
 734 167 177 163 147 130 95 69 11655 11.47 6.43 5.78 5.11 3.75 2.73 1.88
 734 166 177 163 146 129 95 70 11655 11.43 6.41 5.76 5.09 3.73 2.74 1.89
 729 166 177 163 147 130 96 69 11579 11.37 6.42 5.77 5.10 3.76 2.73 1.88
 914 224 238 219 197 174 128 93 14515 15.26 8.63 7.77 6.87 5.04 3.66 2.62

963 224 239 219 198 175 129 94 15292 15.21 8.63 7.78 6.89 5.06 3.69 2.64
 964 224 239 219 198 175 129 94 15314 15.17 8.64 7.79 6.89 5.07 3.70 2.66
 S 77273 42 32 51345 107 90
 364 97 105 95 82 70 50 41 5784 5.23 3.73 3.24 2.76 1.95 1.63 1.18
 367 98 104 94 82 69 50 41 5828 5.18 3.70 3.23 2.73 1.98 1.63 1.09
 368 97 104 94 82 69 53 39 5839 5.16 3.71 3.23 2.72 2.07 1.55 1.17
 529 138 149 136 119 102 71 53 8402 7.91 5.34 4.67 4.03 2.79 2.07 1.79
 534 139 149 136 119 102 72 53 8479 8.03 5.37 4.69 4.02 2.85 2.09 1.74
 533 138 149 136 119 101 73 51 8468 7.92 5.35 4.68 3.99 2.87 2.02 1.80
 729 190 203 186 164 141 101 70 11590 10.76 7.32 6.45 5.57 3.96 2.74 1.92
 727 191 204 186 164 142 100 70 11557 10.83 7.31 6.45 5.60 3.93 2.74 1.89
 723 191 204 186 164 142 100 70 11491 10.80 7.33 6.46 5.61 3.95 2.76 1.85
 983 254 272 248 220 192 135 96 15610 14.41 9.76 8.66 7.57 5.33 3.76 2.54
 937 254 271 247 219 191 135 96 14887 14.29 9.74 8.63 7.53 5.33 3.76 2.48
 972 254 272 247 219 192 135 96 15435 14.26 9.73 8.63 7.56 5.33 3.76 2.48
 S 79855 42 33 51347 107 91
 366 123 132 116 98 82 55 41 5817 7.90 4.56 3.84 3.22 2.18 1.60 1.41
 368 122 131 115 98 81 55 40 5839 7.85 4.54 3.85 3.20 2.18 1.56 1.31
 368 123 132 116 99 83 57 42 5839 7.87 4.58 3.89 3.27 2.25 1.65 1.45
 527 177 189 167 142 120 82 56 8380 11.09 6.57 5.59 4.74 3.24 2.20 1.68
 527 177 188 166 141 119 82 55 8369 11.01 6.54 5.57 4.70 3.23 2.17 1.56
 526 177 188 166 142 120 82 55 8358 10.99 6.55 5.58 4.71 3.24 2.17 1.59
 719 245 258 230 197 166 115 79 11425 14.70 9.05 7.75 6.54 4.52 3.11 2.09
 718 246 259 230 197 167 115 78 11404 14.70 9.06 7.76 6.57 4.52 3.09 2.10
 723 245 259 230 197 167 116 78 11491 14.68 9.06 7.77 6.59 4.55 3.09 2.09
 912 332 348 310 266 226 157 107 14493 19.54 12.20 10.47 8.91 6.19 4.21 2.83
 951 333 348 310 266 227 157 106 15106 19.44 12.21 10.48 8.93 6.18 4.19 2.81
 937 333 349 310 266 227 157 106 14887 19.35 12.22 10.49 8.92 6.18 4.18 2.82
 S 80388 42 33 51349 107 92
 364 51 49 47 45 40 21 9 5784 4.24 1.86 1.76 1.56 0.82 0.34 0.14
 369 48 49 47 45 39 21 7 5861 4.21 1.87 1.76 1.55 0.84 0.27 0.13
 370 49 50 48 45 39 22 7 5883 4.22 1.90 1.78 1.55 0.88 0.27 0.13
 527 62 68 58 56 52 37 22 8380 6.47 2.30 2.19 2.03 1.46 0.87 0.33
 527 62 69 58 55 51 36 21 8380 6.43 2.30 2.15 2.00 1.43 0.81 0.28
 527 62 69 59 55 50 37 21 8380 6.45 2.31 2.15 1.97 1.44 0.83 0.30
 721 85 93 80 63 55 45 34 11447 8.07 3.14 2.48 2.17 1.76 1.34 0.75
 728 85 94 80 64 55 45 34 11568 8.04 3.16 2.50 2.15 1.79 1.35 0.78
 734 85 94 80 64 54 44 34 11655 8.03 3.16 2.50 2.11 1.74 1.35 0.77
 894 115 126 108 86 68 50 40 14208 10.73 4.26 3.40 2.69 1.96 1.57 1.24
 933 116 127 108 86 68 49 39 14821 10.70 4.26 3.39 2.69 1.94 1.54 1.18
 888 115 127 108 86 68 53 40 14109 10.67 4.26 3.40 2.69 2.08 1.57 1.22
 S 80895 42 33 51352 108 92
 365 86 89 78 64 49 43 35 5806 5.29 3.09 2.52 1.94 1.69 1.39 1.02
 370 85 90 78 64 51 43 35 5872 5.26 3.08 2.52 2.00 1.70 1.39 1.00
 370 86 89 78 64 49 44 36 5872 5.22 3.08 2.53 1.94 1.72 1.40 0.99
 527 119 128 113 93 76 53 48 8380 8.12 4.43 3.66 3.00 2.10 1.88 1.55
 523 119 127 112 93 76 53 47 8314 8.10 4.41 3.65 2.98 2.09 1.85 1.54
 525 119 128 112 93 76 54 48 8347 8.08 4.41 3.66 2.99 2.14 1.89 1.54

723 165 176 156 130 107 67 52 11491 10.43 6.13 5.11 4.20 2.65 2.06 1.83
 729 165 176 156 130 106 67 51 11579 10.36 6.13 5.11 4.19 2.64 2.02 1.81
 725 165 176 156 130 107 67 52 11513 10.38 6.13 5.11 4.20 2.65 2.03 1.83
 979 224 236 210 176 145 92 59 15555 13.79 8.28 6.93 5.70 3.64 2.33 1.95
 912 224 236 211 176 145 93 59 14493 13.80 8.29 6.94 5.72 3.65 2.33 1.96
 949 226 236 210 176 145 92 59 15073 13.72 8.28 6.94 5.69 3.64 2.33 2.02
 S 81423 44 33 51354 110 92
 362 103 108 99 83 70 51 39 5751 5.06 3.88 3.28 2.77 2.00 1.55 1.24
 363 102 107 98 83 70 51 38 5762 5.04 3.85 3.25 2.75 1.99 1.50 1.38
 367 103 108 98 83 71 51 39 5828 5.02 3.87 3.28 2.78 2.02 1.53 1.58
 526 149 156 142 122 104 75 51 8358 8.22 5.60 4.79 4.10 2.97 2.02 1.95
 524 148 155 142 121 104 75 51 8325 8.13 5.58 4.77 4.08 2.96 2.02 1.91
 525 148 155 141 121 104 75 51 8336 8.14 5.56 4.77 4.09 2.96 2.01 1.99
 724 205 214 196 169 146 106 73 11502 10.35 7.71 6.67 5.75 4.16 2.87 2.44
 734 205 214 196 170 146 106 73 11666 10.36 7.73 6.68 5.76 4.16 2.86 2.46
 724 204 213 196 169 146 105 73 11502 10.32 7.70 6.67 5.74 4.15 2.86 2.45
 958 276 288 264 230 199 144 100 15227 14.66 10.39 9.04 7.83 5.68 3.93 2.86
 931 277 289 265 230 200 145 100 14788 14.63 10.42 9.07 7.87 5.69 3.95 2.89
 973 277 289 265 231 200 145 100 15457 14.59 10.43 9.08 7.87 5.72 3.95 2.89
 S 84036 43 33 51357 110 92
 372 60 62 58 52 49 44 38 5904 3.82 2.28 2.03 1.94 1.73 1.49 1.17
 373 60 62 57 51 48 43 37 5926 3.82 2.26 2.02 1.90 1.70 1.45 1.14
 370 59 62 58 51 48 44 38 5872 3.84 2.27 2.02 1.88 1.74 1.48 1.19
 536 85 89 84 75 66 50 45 8523 5.99 3.31 2.96 2.60 1.95 1.76 1.54
 537 85 88 84 75 66 50 45 8533 5.93 3.30 2.96 2.59 1.96 1.76 1.54
 535 85 88 84 75 66 50 45 8501 5.88 3.29 2.95 2.58 1.95 1.77 1.54
 734 121 126 120 108 95 70 51 11666 7.79 4.71 4.24 3.73 2.74 1.99 1.76
 736 122 126 120 108 95 70 51 11688 7.70 4.71 4.25 3.74 2.76 2.00 1.77
 725 121 126 120 108 95 70 50 11524 7.67 4.71 4.25 3.74 2.75 1.98 1.82
 972 167 174 165 149 132 97 71 15435 10.78 6.48 5.85 5.18 3.83 2.78 2.02
 900 167 173 165 149 132 98 71 14296 10.67 6.50 5.86 5.19 3.85 2.78 2.06
 903 167 173 165 149 132 98 71 14350 10.65 6.50 5.87 5.20 3.84 2.79 2.01
 S 84554 42 33 51400 107 91
 376 55 52 53 52 50 43 34 5970 3.88 2.07 2.04 1.95 1.68 1.35 0.81
 375 54 52 53 51 48 42 35 5959 3.78 2.10 2.02 1.90 1.66 1.39 0.86
 375 53 53 54 52 50 43 35 5959 3.79 2.12 2.05 1.96 1.69 1.39 0.85
 539 67 69 66 60 60 53 46 8566 5.18 2.61 2.38 2.36 2.07 1.83 1.46
 539 67 69 66 61 60 53 47 8566 5.08 2.61 2.39 2.35 2.08 1.84 1.51
 536 67 69 66 60 59 52 46 8512 5.04 2.61 2.36 2.33 2.06 1.81 1.47
 732 94 96 93 84 74 61 55 11623 7.00 3.65 3.30 2.92 2.41 2.17 1.88
 729 94 96 93 83 74 61 55 11579 6.92 3.65 3.28 2.92 2.39 2.16 1.85
 715 94 96 93 84 74 60 56 11360 6.86 3.65 3.30 2.92 2.38 2.21 1.92
 950 129 131 126 114 101 74 60 15095 8.99 4.97 4.48 3.98 2.93 2.37 2.12
 915 129 131 126 114 101 74 61 14537 8.92 4.97 4.49 3.99 2.93 2.39 2.17
 965 129 131 126 114 101 74 60 15336 8.85 4.97 4.49 3.99 2.93 2.38 2.17
 S 86592 39 34 51416 102 93
 373 64 67 63 58 52 44 40 5926 4.26 2.48 2.27 2.03 1.74 1.59 1.34
 376 64 67 63 57 51 44 41 5970 4.23 2.47 2.26 2.02 1.74 1.61 1.36

374 64 67 63 58 52 44 41 5937 4.23 2.48 2.27 2.03 1.73 1.62 1.37
 530 94 97 91 84 75 57 48 8413 6.33 3.60 3.30 2.97 2.26 1.89 1.65
 530 94 98 92 84 76 57 47 8413 6.42 3.61 3.31 2.98 2.26 1.84 1.63
 528 94 97 92 84 76 58 48 8391 6.35 3.61 3.30 2.98 2.27 1.90 1.62
 736 131 135 127 117 105 81 60 11688 8.56 5.00 4.59 4.13 3.19 2.36 1.83
 743 131 135 127 117 105 81 60 11798 8.56 5.00 4.59 4.15 3.20 2.37 1.83
 736 131 135 127 117 105 81 60 11688 8.57 5.01 4.60 4.14 3.20 2.37 1.86
 973 178 183 172 157 142 110 82 15457 11.13 6.76 6.20 5.59 4.34 3.22 2.33
 970 178 183 172 158 143 110 82 15413 11.06 6.79 6.22 5.62 4.33 3.23 2.34
 940 179 183 172 158 143 110 82 14931 11.12 6.78 6.22 5.62 4.33 3.23 2.34
 S 87115 44 34 51418 111 93
 370 60 61 59 55 50 42 38 5872 4.75 2.31 2.16 1.98 1.67 1.50 1.20
 368 59 61 59 55 51 41 37 5839 4.71 2.33 2.17 2.00 1.63 1.46 1.19
 370 60 61 59 55 51 42 38 5872 4.69 2.34 2.18 1.99 1.66 1.48 1.22
 532 87 89 86 80 73 58 49 8457 5.66 3.39 3.14 2.89 2.30 1.91 1.64
 528 87 89 86 80 73 58 49 8391 5.55 3.38 3.13 2.88 2.28 1.92 1.68
 529 87 89 86 80 73 58 49 8402 5.52 3.39 3.14 2.88 2.28 1.91 1.67
 731 120 123 119 110 101 81 63 11612 7.84 4.67 4.33 3.98 3.18 2.49 1.93
 732 120 123 119 110 102 81 63 11634 7.82 4.67 4.34 4.00 3.19 2.49 1.93
 730 120 123 119 110 101 81 63 11601 7.79 4.67 4.32 3.98 3.18 2.49 1.89
 927 162 166 160 148 136 109 85 14723 10.18 6.30 5.83 5.36 4.28 3.33 2.52
 931 162 166 160 149 136 109 85 14788 10.13 6.30 5.85 5.37 4.30 3.35 2.54
 976 161 165 160 148 136 108 85 15500 10.04 6.28 5.83 5.35 4.27 3.33 2.52
 EOF